MIL-A-9962A
AMENDMENT 4
5 April 1977
SUPERSEDING
AMENDMENT 3
21 JULY 1972

MILITARY SPECIFICATION

ABRASIVE MATS, NON-WOVEN, NON-METALLIC

This amendment forms a part of Military Specification MIL-A-9962A, dated 1 December 1966, and is approved for use by all Departments and Agencies of the Department of Defense.

Page 3

Paragraph 3.3.1.2, line 1: After "size 500" add "and finer".

Paragraph 3.3.1.3: Delete in its entirety and substitute: "Grade A. The very fine particles shall be grit size 280 to 600 for Type I and 240 to 320 for Type III (see 4.6)."

Paragraph 3.3.2.1: Delete in its entirety and substitute: "Grade B. The fine particles shall be grit size 180 to 240 for Types I and III, and 180 to 360 for Type II (see 4.6)."

Page 8

Paragraph 4.5.3: Between the third and fourth sentences add the following: "Rinse the exposed pad with a gentle stream of tap water to remove the chemical residues. Drain the bulk of the water. Place the pad between several thicknesses of absorbent paper towels and press to remove the balance of the water. Do not distort the pad in a way that would affect its structural integrity. Dry in a forced draft oven at $105 \pm 2^{\circ}C$ until dry, approximately 30 minutes.

Custodians:
Army - MR
Navy - AS
Air Force - 99

Review Activities
Army - MR
Navy - AS
Air Force - 99

Preparing Activity:
Air Force - 99

Project Nr:
5350-0057

FSC 5350

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:16Z
Check the source to verify that this is the current version before use.