MILITARY SPECIFICATION

LIGHT, WARNING, VEHICULAR, RED, FLASHING

This amendment forms a part of Military Specification MIL-L-9965A(USAF) dated 13 September 1978.

PAGE 2

2.1, Under "STANDARDS" add the following:

"Federal

FED-STD-141	- Paint, Varnish, Lacquer and Related Materials: Methods of Inspection, Sampling and Testing"
FED-STD-595	- Colors"

PAGE 3

Add the following new paragraph:

"3.2.1, Reclaimed materials. The use of reclaimed materials shall be encouraged to the maximum extent possible."

3.3.2, line 1. Between the words "metal" and "suitable" add "or plastic".
line 4. Delete the words "and metal content".
line 4. Add the following two sentences after the word "contours":

"Plastic material must withstand a simulated weathering and impact test (see 4.3.7). Exposed test specimens shall show no more than 10 percent loss in impact strength compared with unexposed specimens."

PAGE 4

3.9, add the following:

"When plastic material is used, the exterior appearance shall be of a lustered color comparable to a color ranging from Color Chip 16187 (Gray) to Color Chip 16473 (Gray) of FED-STD-595. Color of the plastic may be added by coating or by dispersion throughout the meterial. At the option of the manufacturer, a chromed finish visually equivalent to polished chrome plated metal may be supplied to plastic material skirts."

4.1, line 4. Delete the word "his".

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T13:17Z
Check the source to verify that this is the current version before use.

PAGE 5

4.1 line 1. Change "inspection" to " inspections".
line 2. Change "preceived" to prescribed".

PAGE 6

Section 4, add the following paragraphs:

"4.3.7 Simulated weathering resistance. To determine conformance to 3.3.2, specimen measuring 3 inches X 9 inches X 1/8 inch shall be subjected to 168 hours exposure in a twin-arc weatherometer in accordance with method 6152 of FED-STD-141. After exposure, the exposed specimen and also unexposed specimens shall be impact tested. Impact equipment shall be Gardner Heavy Duty Impact Tester, Model 1G 1120, or equivalent, equipped with a 0.625 inch diameter dart and an 0.640 inch die. The falling weight shall be 6 pounds."

"4.3.7.1 Frequency of test. This test shall be performed on each lot of material prior to its use in production and on the lot of material to be used for the preproduction sample when one is required."

"4.3.7.2 Failure. Failure of the test constitutes rejection of the entire lot of material from which the sample was selected."

PAGE 8

Section 6, Delete paragraph 6.3

Custodians:
Air Force - 99

Review Activity:
DLA - GS

Preparing Activity:
Air Force - 99

Project No. 6220-F277

Source: https://assist.dla.mil - Downloaded: 2026-10-17T13:17Z
Check the source to verify that this is the current version before use.