MIL-A-37837(DLA-DM)
24 April 1978

MILITARY SPECIFICATION

ALUMINUM OXIDE SCRUB CLEANSER

This specification is approved for use by the Defense Personnel Support Center, Defense Logistics Agency, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers Aluminum Oxide Scrub Cleanser (see 6.2).

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents, of the issue in effect on date of invitation for bids or request for proposals, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

PPP-C-186 - Containers, Packaging and Packing for Drugs, Chemicals Pharmaceuticals.

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Directorate of Medical Materiel, DPSC-ATT, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 6505

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:35Z
Check the source to verify that this is the current version before use.

(Copies of specifications and standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply.

U. S. DEPARTMENT OF HEALTH, EDUCATION, AND WELFARE,
FOOD AND DRUG ADMINISTRATION (FDA)

Federal Food, Drug, and Cosmetic Act and Regulations Promulgated Thereunder.

(Application for copies should be addressed to the Food and Drug Administration, Washington, DC 20204.)

U. S. PHARMACOPEIAL CONVENTION, INC.

The United States Pharmacopeia (USP).

(Application for copies should be addressed to the Mack Publishing Company, Easton, PA 18042.)

The National Formulary (NF).

(Application for copies should be addressed to the Mack Publishing Company, Easton, PA 18042.)

3. REQUIREMENTS

3.1 Material. Shall be a scrub cleanser containing aluminum oxide microsized particles, 52 percent W/W in a suitable surfactant cleansing base.

3.2 Assay for aluminum oxide. Shall assay to contain not less than 90.0 percent and not more than 130.0 percent of the required amount of aluminum oxide when determined as specified in 4.7.1.

3.3 Identity test for aluminum oxide. The presence of aluminum oxide in the finished product shall be determined as specified in 4.7.2.

3.4 Ingredients. All ingredients used in the manufacture of the product shall be in accordance with the tests, standards, and requirements of the USP or NF, including any supplements or revisions thereto; or, if not included in either of these compendia, the ingredients shall be of the highest pharmaceutical grade.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:35Z
Check the source to verify that this is the current version before use.

3.5 Expiration dating period. The expiration dating period shall be not less than 24 months.

3.5.1 Delivery. Not more than 3 months of the expiration dating period shall have elapsed at the time of delivery to the Government.

3.6 Workmanship. The material and its containers shall be free from defects which detract from their appearance or impair their serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Supplier responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and, (i) as to any expiration dated item, for the expiration dating period specified by the contractor for such item, or such longer period as may be required by regulation of any federal agency; or (ii) as to non-dated items, for not less than 3 years after delivery of the item to the Government.

4.1.2 No company supplying any ingredient(s) to the contractor will be considered an acceptable facility for the performance of the inspection requirements specified herein.

4.2 Lot. For purposes of this specification, a lot, batch, or control is that single, uniform, and homogeneous quantity of product produced from one formulation, subjected to the same compounding and manufacturing operation, and filled into final containers.

4.3 Sampling. Sampling shall be conducted in accordance with MIL-STD-105.

TABLE I. Sampling.

For visual examination	Inspection level	AQL (percent defective)	Unit of product
Major	S-2	1.0	Filled jar
Minor	II	2.5	Filled jar

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:35Z
Check the source to verify that this is the current version before use.

4.3.1 End item testing. Noncompliance with any of the following is cause for rejection. The acceptance number for each test shall be zero (0).

TABLE II. Criteria for end item testing.

Characteristic	Requirement paragraph	Inspection level 1/	Minimum sample
Assay for Aluminum Oxide	3.2.	S-2	5 Composite
Identity for Aluminum Oxide	3.3.		5

1/ Where possible, the sample shall be used for two or more tests.

4.4 Examination. The finished product shall be examined to determine compliance with all requirements of this specification. Nonconformance will be permitted to the extent indicated in 4.3 and 4.3.1.

4.4.1 Classification of defects. Examination will be conducted in accordance with the following classification of defects:

TABLE III. Classification of defects.

Categories	Defects 1/
Major	
101	Product not essentially free from foreign matter.
102	Product not homogeneous.
Minor	
201	Exterior of immediate container is not free from contents or foreign matter.
202	Label not free from defacing marks or tears.

1/ Inspection is not restricted to the classified possible defects listed above.

4.5 Packaging inspection. The inspection of the intermediate package, packing and marking for shipment and storage shall be in accordance with quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:35Z
Check the source to verify that this is the current version before use.

4.6 Labeling inspection. Sampling shall be in accordance with MIL-STD-105 and the unit of product shall be the unit of issue. The inspection lot shall be the number of units of issue of each batch, lot, control number, etc., offered for inspection at one time. The inspection level for labeling shall be S-2 and the acceptance number shall be zero.

4.7 Tests.

4.7.1 Assay for aluminum oxide. Either of the following procedures may be used in the assay for aluminum oxide.

Method A.

1. Accurately weigh about 10 grams of sample and place into a 200 ml beaker.

2. Fill to about two-thirds full with hot purified water and place on a steam bath to dissolve.

3. Allow the aluminum oxide grits to settle to the bottom.

4. Any grits floating on the top should be decanted into a tared filter paper. Any remaining water should be decanted from the residue.

Repeat steps 2 to 4 two more times; then transfer all the grits from the beaker to the tared filter paper by washing out the beaker with a wash bottle filled with hot purified water. After all the purified water has been passed through the filter paper, wash the wet filter with isopropyl alcohol. Place the filter paper in an oven and dry to constant weight at 105°C. Cool to room temperature in a desiccator; then weigh the dried paper and grits and calculate the percentage of aluminum oxide. (Save the residue for identity test.)

Method B.

Accurately weigh about 2 grams of sample and transfer to a beaker containing 30 ml of alcohol. Heat to boiling on a steam bath and let stand for several minutes, and carefully decant the supernatant. Wash the residue with two 20 ml portions of hot alcohol, decanting each wash. Add 65 ml of hot purified water to the residue, place on a magnetic stirrer to dissolve any base and allow to settle. Decant the excess water and quantitatively transfer the aluminum oxide residue to a tared sintered glass filter of medium porosity, with the aid of five 25 ml portions of hot purified

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:35Z
Check the source to verify that this is the current version before use.

water. Wash the residue with 25 ml of isopropyl alcohol and dry to constant weight at 105°C. Calculate the percentage of aluminum oxide. (Save the residue for identity test.)

4.7.2 Identity. Mix 1.0 gram of the residue collected from the assay procedure for aluminum oxide with 200 mg of anhydrous sodium carbonate and 2.0 grams of anhydrous potassium carbonate. Place the mixture in a platinum crucible and heat the mixture in a muffle furnace at 800°C until fusion is complete. Cool and transfer the fused mixture to a beaker and then add hydrochloric acid until effervescence ceases. Evaporate the mixture to dryness, cool, and add 10 ml of purified water. Heat to boiling and filter. The clear filtered solution responds to the tests for aluminum in the USP Identification Tests - General.

5. PACKAGING

5.1 Packaging requirements. The requirements for packaging shall be in accordance with all applicable requirements of PPP-C-186, and as specified herein.

5.2 Packaging. Packaging shall be level A or C, as specified (see 6.1).

5.2.1 Unit of issue. One jar containing 6 oz (170.1 gram), as specified, constitutes one unit of issue.

5.2.2 Level A.

5.2.2.1 Immediate container. The immediate container shall be a commercially available jar considered acceptable by the Food and Drug Administration (FDA) for the product contained therein and shall be of such compatibility that neither the contents nor the container are altered in any way by each other.

5.2.2.2 Unit package. At the option of the contractor, each unit may be packaged as specified in 5.2.5 of PPP-C-186.

5.2.2.3 Intermediate package. Twelve (12) units of issue shall be packaged as specified in 5.2.8 of PPP-C-186.

5.2.3 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.3 Packing. Packing shall be level A, B or C, as specified (see 6.1).

5.3.1 Level A. Forty-eight (48) units of issue shall be packed as specified in 5.4.4 of PPP-C-186.

5.3.2 Level B. Forty-eight (48) units of issue shall be packed as specified in 5.4.3.2 of PPP-C-186.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:35Z
Check the source to verify that this is the current version before use.

5.3.3 Level C. The packaged commodity shall be packed in shipping containers that will afford adequate protection against damage during direct shipment from the supply source to the first receiving activity. These packs shall conform to the applicable carrier's rules and regulations.

5.4 Marking.

5.4.1 Labeling. Labeling shall be in accordance with the requirements of the Federal Food, Drug and Cosmetic Act and shall include the information required below:

5.4.1.1 Immediate container. Each immediate container label shall bear the following information:

(a) label information in accordance with commercial practice.
(b) the expiration date.

5.4.1.2 Unit package. Each unit package label shall bear the following information:

(a) label information in accordance with commercial practice.
(b) the National Stock Number.

NOTES: (1) The National Stock Number need not be preceded by any prefix.
(2) Strip labeling may be used.
(3) Label adhesion test shall not apply.
(4) If a unit package is not supplied, the National Stock Number shall appear on the immediate container label.

5.4.2 Intermediate package. Intermediate package shall be marked as specified in 5.5.3 of PPP-C-186. Type I shelf life markings as specified in MIL-STD-129 shall be shown. Marking shall include the legend:

"STORE AT CONTROLLED ROOM TEMPERATURE 15° - 30°C (59° - 86°F)".

5.4.3 Exterior container. Exterior container shall be marked as specified in 5.5.4 of PPP-C-186. Type I shelf life marking as specified in MIL-STD-129 shall be shown. Marking shall include the legend:

"STORE AT CONTROLLED ROOM TEMPERATURE 15° - 30°C (59° - 86°F)".

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:35Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) National Stock Number.
(c) Selection of applicable levels of packaging and packing (see 5.2 and 5.3).

6.2 This specification covers the following item:

National Stock Number	Item Identification
6505-01-049-3034	ALUMINUM OXIDE SCRUB CLEANSER, MEDIUM GRIT, 6 oz (170.1 Gram)

Preparing activity:
DLA - DM

Project No. 6505-1985

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:35Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.

NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE
MIL-A-37837(DLA-DM) ALUMINUM OXIDE SCRUB CLEANSER

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1 OCT 76 1426 EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T11:35Z
Check the source to verify that this is the current version before use.