MILITARY SPECIFICATION

GENERATOR, PULSE: 10526464

This amendment forms a part of Military Specification MIL-G-60186(MU), dated 23 February 1965

Paragraph 4.5.1.3.2: Delete in its entirety and substitute:

"4.5.1.3.2 Operating. - This test shall be conducted in accordance with the humidity test defined in Procedure III of MIL-F-13926, except that the humidity shall be maintained at 92 to 97 percent for the 24-hour period, and the test shall cease at the end of that period (Method 106 of MIL-STD-202 shall be excluded). Throughout the test period, the board shall be capable of performing the tests of 4.5.2.2.2. In order to demonstrate this capability, the tests of 4.5.2.2.2. shall be performed a minimum of once each 6 hours of the 24-hour period. The final test shall be conducted during the final portion of the 24-hour period. Between tests, the board shall be electrically energized as described in 4.5.2."

Paragraph 4.5.1.4 Delete in its entirety and substitute:

"4.5.1.4 Salt spray. - This test shall be conducted in accordance with the salt spray test defined in Method 101, Condition B of MIL-STD-202 using a 5 percent salt solution. At the end of the exposure period, salt deposits shall be removed from the board by a gentle wash, not exceeding 30 minutes, in running water not warmer than 100°F, using a soft-hair brush or plastic-bristle brush. The board shall then be air dried in a controlled environment at 72°F ± 5°F and a relative humidity of 30 to 50 percent for a period of 24 hours. The board shall be inspected visually for any physical damage, then tested in accordance with 4.5.2.1 to 5.4.2.2.1 for compliance with 3.3.6".

TABLE VII, Column B, Line 3: Delete "Pin 36A" and substitute "Pin 35B"
Column C, Line 3: Delete "Plus 1.2±0.3" and substitute "0.4±0.15".

Custodian:

Army - MU

Preparing activity:

Army - MU

Project No. 1220-A046

FSC 1270

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T00:15Z
Check the source to verify that this is the current version before use.