FED. SUP CLASS
6640

USER ACTIVITIES: ARMY - MD, DM
NAVY - MS

REVIEWER ACTIVITIES: ARMY - ME
NAVY - OS
AIR FORCE - 82



PART NUMBER	DIMENSIONS (mm) DIAMETER	HEIGHT
MS36081-1	25	76
MS36081-2	38	75
MS36081-3	40	90
MS36081-4	52	100
MS36081-5	76	127
MS36081-6	79	177
MS36081-7	100	280

MATERIAL: Cup shall be made of porous ceramic with the following properties:

Pore diameter 0.5 micron;
Bubble pressure 80 PSI;
Apparent porosity 35.9%;
Absorption 21.1%.

DESIGN: The cup shall be cylindrical in shape with a flat bottom and uniform wall thickness.

NOTE: Items differing from this Military Standard by minor variations in design or dimensions are considered standard under this document, provided such variations do not affect performance and are not in conflict with the material requirements specified herein.

APPROVED 30 JUN 1983 REVISED

This military standard is approved for use by all Departments and Agencies of the Department of Defense. Selection for all new engineering and design applications and for repetitive use shall be made from this document.

P.A. EA	INTERNATIONAL INTEREST	TITLE	MILITARY STANDARD
Other Cust MS 99		CUP, POROUS	MS36081
Procurement Specifications NONE	SUPERSEDES:		SHEET 1 OF 1

PROJECT NUMBER 6640-1181

DD FORM 1 MAY 73 672 (COORDINATED) PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T17:34Z
Check the source to verify that this is the current version before use.