AA-H-00600b(GSA-FSS)
Revision 3
August 15, 1959
SUPERSEDING
Int.Fed.Spec.AA-H-00600a(GSA-FSS)
July 30, 1957, and
Int.Fed.Spec.AA-H-00600(GSA-FSS)
August 6, 1956

# INTERIM FEDERAL SPECIFICATION

## HOUSEHOLD FURNITURE, WOOD, CASEGOODS AND CHAIRS

This Interim Federal Specification has been prepared by the Federal Supply Service, General Services Administration, based upon currently available technical information, and has not been approved as a Federal Specification. It is subject to modification, and pending its promulgation as a regular Federal Specification, may be used in procurement.

### 1. SCOPE AND CLASSIFICATION

1.1 Scope. - This specification covers minimum general requirements for wood household furniture items of commercial design, and is of a quality required by the Government for use in Federal installations and institutions such as homes and quarters provided certain Government personnel.

1.2 Classification.

1.2.1 Items, types, classes and sizes. - Unless otherwise specified, the furniture shall be of the following items, types and classes as specified in the invitation for bids;

All dimensions are overall and are minimum (see 3.2.1.1).

Item I Bedstead

Type I - Bookcase headboard with bed frame.

| | | | | |
|---|---|---|---|---|
| Class 1 | Double | - Traditional | width 56 inches, | height 37 inches |
| | | Modern | width 56 inches, | height 36 inches |
| Class 2 | Single | - Traditional | width 41 inches, | height 37 inches |
| | | Modern | width 41 inches, | height 36 inches |

Type II - Headboard, footboard and side rails.

| | | | | |
|---|---|---|---|---|
| Class 1 | Double | - Traditional | width 56 inches, | height 35 inches |
| | | Modern | width 56 inches, | height 32 inches |
| Class 2 | Single | - Traditional | width 41 inches, | height 35 inches |
| | | Modern | width 41 inches, | height 32 inches |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:40Z
Check the source to verify that this is the current version before use.

Height of footboards shall be in proportion to headboard design.

Type III - Headboard with bed frame.

| | | | |
|---|---|---|---|
| Class 1 | Double - Traditional | width 54-1/2 inches, | height 35 inches |
| | Modern | width 54-1/2 inches, | height 32 inches |
| Class 2 | Single - Traditional | width 39-1/2 inches, | height 35 inches |
| | Modern | width 39-1/2 inches, | height 32 inches |

Item II Bench, Dressing Table.

Length 19 inches, width 16 inches, height 17 inches

(Item VI, Class 2, Chair; may be furnished in lieu of Item II with Colonial or Early American designs unless otherwise specified.)

Item III Book shelves.

Width 29-1/2 inches, depth 12 inches at deepest point and not less than 9 inches at any point, height 32 inches

Item IV Buffet.

Type I - Chippendale, Hepplewhite, French Provincial, Early American or Colonial.

Class 1 - Width 56 inches, depth 19 inches, height 31 inches
Class 2 - Width 42 inches, depth 16 inches, height 31 inches

Type II - Modern.

Class 1 - Width 56 inches, depth 19 inches, height 31 inches
Class 2 - Width 48 inches, depth 16 inches, height 30 inches

Item V Cabinet China

Type I - Open hutch, 10 inches deep.

Class 1 - Early American or Colonial
Size 1 - Width 52 inches, depth 19 inches, height 62 inches
Size 2 - Width 35 inches, depth 16 inches, height 68 inches
Class 2 - Modern
Size 1 - Width 48 inches, depth 16 inches, height 62 inches
Size 2 - Width 34 inches, depth 16 inches, height 58 inches

Type II - With glass doors hutch, 10 inches deep.

Class 1 - Chippendale, Heppelwhite, Early American or Colonial
Size 1 - Width 42 inches, depth 16 inches, height 68 inches
Size 2 - Width 35 inches, depth 15 inches, height 68 inches

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the current version before use.

Class 2 - Modern
Size 1 - Width 48 inches, depth 18 inches, height 62 inches
Size 2 - Width 34 inches, depth 16 inches, height 58 inches
Class 3 - French Provincial
Size 1 - Width 60 inches, depth 16 inches, height 72 inches
Size 2 - Width 53 inches, depth 16 inches, height 72 inches

Item VI Chairs, Straight.

Type I - Ship seat.

Class 1 - With arms, seat size width 20 inches, depth 17 inches, height of back or back post 30 inches
Class 2 - Without arms, seat size width 18 inches, depth 17 inches, height of back or back post 30 inches

Type II - Wood seat.

Class 1 - With arms, seat size width 20 inches, depth 17 inches, height of back or back post 30 inches
Class 2 - Without arms, seat size width 17 inches, depth 17 inches, height of back or back post 30 inches

Item VII Chest of Drawers,

Type I - 4 drawer minimum - width 40 inches, depth 19 inches, height 39 inches

Type II - 5 drawer minimum - width 34 inches, depth 19 inches, height 45 inches

Type III - 3 drawer minimum - width 28 inches, depth 19 inches, height 30 inches

Type IV - 3 drawer chest desk, 1 pedestal - width 52 inches, depth 19 inches, height 30 inches

Item VIII Desk, Flat-top.

Type I - 1 pedestal - width 39 inches, depth 19 inches, height 29 inches

Type II - 2 pedestal - width 44 inches, depth 20 inches, height 29 inches

Item IX Dressers and Mirrors (with provision for attaching and hanging).

Type I - Double - Modern - width 50 inches, depth 19 inches, height 31 inches, mirror plate size 30 x 42 inches

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the currentversion before use.

| | | |
|---|---|---|
| | Traditional | width 54 inches, depth 20 inches, height 32 inches, mirror plate size 28 x 40 inches |
| Type II - Single - | Modern | width 40 inches, depth 19 inches, height 31 inches, mirror plate size 30 x 32 inches |
| | Traditional | width 44 inches, depth 19 inches, height 32 inches, mirror plate size 28 x 20 inches |
| Type III - Triple - | Modern | width 62 inches, depth 19 inches, height 31 inches, mirror plate size 28 x 40 inches |
| | Traditional | width 58 inches, depth 20 inches, height 32 inches, mirror plate size 30 x 44 inches |

Item X Server, Dining Room.

Type I - Cabinet style.

| | |
|---|---|
| Traditional | - width 35 inches, depth 18 inches, height 30 inches |
| Modern | - width 30 inches, depth 19 inches, height 30 inches |

Type II - Cart style.

| | |
|---|---|
| Traditional | - width 30 inches, depth 18 inches, height 28 inches |
| Modern | - width 30 inches, depth 19 inches, height 28 inches |

Item XI Tables.

Type I - Tables, dining.

| | |
|---|---|
| Class 1 - Drop-leaf | - width 36 inches; length, closed 24 inches, open 53 inches; height 29 inches; no leaf |
| Class 2 - Drop-leaf | - width 40 inches; length, closed 24 inches, open 53 inches; height 29 inches; no leaf |
| Class 3 - Drop-leaf extension | - width 40 inches; length, closed 26 inches, open 72 inches; height 29 inches; 1-12 inch leaf |
| Class 4 - Extension | - width 36 inches; length, closed 54 inches, open 78 inches; height 29 inches; 2-12 inch leaves |
| Class 5 - Extension | - width 40 inches; length, closed 60 inches, open 96 inches; height 29 inches; 3-12 inch leaves |

Type II - Tables, occasional.

| | | |
|---|---|---|
| Class 1 - Coffee | - Modern | width 20 inches, length 48 inches, height 14 inches |

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:40Z
Check the source to verify that this is the current version before use.

| | | | |
|---|---|---|---|
| Class 2 - Coffee | - Traditional | width 19 inches, length 36 inches, height 17 inches |
| Class 3 - Round | - Modern | width 36 inches, length 36 inches, height 14 inches |
| Class 4 - Round | - Traditional | width 36 inches, length 36 inches, height 17 inches |
| Class 5 - Corner | - without step | width 29 inches, length 29 inches, height 25 inches |
| Class 6 - Corner | - with step | width 29 inches, length 29 inches, height 25 inches |
| Class 7 - End | - without step | width 18 inches, length 26 inches, height 22 inches |
| Class 8 - End | - with step | width 18 inches, length 26 inches, height 22 inches |
| Class 9 - Lamp | - | width 19 inches, length 19 inches, height 24 inches |
| Class 10 - Night | - Modern | width 18 inches, length *14 inches, height 24 inches |
| Class 11 - Night | - Traditional | width 18 inches, length *16 inches, height 26 inches |

*Length becomes depth

Type III - Dressing table (vanity) and mirror (with provision for attaching to permit tilting).

| | |
|---|---|
| Class 1 - Traditional | width 44 inches, depth 19 inches, height 29 inches, mirror plate size 28 x 20 inches |
| Class 2 - Modern | width 52 inches, depth 19 inches, height 31 inches, mirror plate size 30 x 32 inches |

1.2.2 Design. - The items offered by the bidder shall conform to the design or style specified in the invitation for bids. The furniture shall meet or exceed the minimum dimensions and construction requirements of this specification (as to wood, adhesives, hardware, plastic laminates, finish and workmanship).

1.2.3 Color or finish. - The color of finish shall be as specified in the invitation for bids. Sample finish panels will be supplied to bidder by the procuring officer. Bidder shall furnish three panels with their bid. These panels shall represent the bidder's match to the color and finish to be furnished and the two extremes within which production will be maintained and delivered. Unless otherwise specified, the successful bidder will be required to furnish three additional identical sets of panels to be used by the Quality Control Division for inspection.

2. APPLICABLE SPECIFICATIONS, STANDARDS AND OTHER PUBLICATIONS

2.1 The following specifications and standards of the issues in effect on date of invitation for bids, form a part of this specification:

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the current version before use.

Federal Specifications:

| | |
|---|---|
| L-P-00386 | - Plastic Material, Cellular, Urethane. |
| L-P-00508a | - Plastic Sheets, Laminated, Decorative and Non-Decorative. |
| L-T-00411c | - Table Top and Furniture Assemblies. |
| P-P-554 | - Polish, Furniture, Wax. |
| P-W-158 | - Wax, General-Purpose, Solvent-Type, Liquid and Paste (for floors, furniture, etc.) |
| AA-B-250 | - Bedsprings (Platform-Top Type). |
| DD-G-451 | - Glass, Flat and Corrugated for Glazing, Mirrors and Other Use. |
| DD-M-411 | - Mirrors; Plate Glass, Framed. |
| TT-F-336 | - Filler, Wood Paste. |
| TT-L-57 | - Lacquer, Rubbing, Clear (for Wood Furniture). |
| TT-L-58 | - Lacquer; Spraying, Clear and Pigmented. |
| TT-S-00180 | - Sealer and Lubricant for Wood Furniture. |
| TT-S-190 | - Sealer, Sanding, Lacquer Type (for Wood Furniture). |
| CCC-A-700 | - Artificial Leather, Upholstery (Synthetic Resin Coated Cloth). |
| CCC-F-206 | - Fabrics, Upholstery. |
| CCC-P-91 | - Padding, Rubberized Curled Hair or Vegetable Fiber. |
| LLL-H-35 | - Hardboard, Fibrous-Felted (Fiberboard). |
| MMM-A-100 | - Adhesive, Animal Gelatine. |
| MMM-A-125 | - Adhesive, Casein-Type, Water and Mold Resistant. |
| MMM-A-188 | - Adhesive, Urea-Resin-Type (Liquid and Powder). |
| PPP-B-601 | - Boxes, Wood, Cleated-Plywood. |
| PPP-B-621 | - Boxes, Wood, Nailed and Lock-Corner. |
| PPP-B-636 | - Boxes, Fiber. |
| PPP-C-843 | - Cushioning Material, Cellulosic. |

Federal Standards:

| | |
|---|---|
| Fed. Std. No. 102 | - Preservation, Packaging, and Packing Levels. |
| Fed. Std. No. 123 | - Marking for Domestic Shipment (Civil Agencies). |

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards and Handbooks from established distribution points in their agencies.)

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the currentversion before use.

Military Specifications:

JAN-P-125 - Packaging and Packing for Overseas Shipment - Barrier Material, Waterproof, Flexible.
MIL-A-140 - Adhesive, Water-Resistant, Waterproof Barrier-Material.
MIL-R-5001 - Rubber, Latex Foam Sponge.
MIL-W-6110 - Wood, Determination of Moisture Content.
MIL-S-10617 - Stain; Wood, Non-Grain-Raising, Solvent-Dye-Type.
MIL-R-17252 - Rubber, Cellular (Bonded Shredded).

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. - The following publications and standards of the issues in effect ondate of invitation for bids, form a part of this specification:

American Society for Testing Materials:

ASTM Specification - D-1055 - Latex Foam Rubber.

(Copies of ASTM Specifications may be obtained from the American Society for Testing Materials, 1916 Race Street, Philadelphia 3, Pennsylvania.)

Department of Commerce Publications:

Commercial Standard CS-35-56 - Hardwood, Plywood.
CS-45-55 - Douglas Fir Plywood.
Simplified Practice Recommendation R2-57, Beadsteads, Springs, and Mattresses.

(Copies of the Commercial Standards and the Simplified Practice Recommendation referenced above, which are Department of Commerce Publications, may be obtained upon application, accompanied by money order, coupon, or cash, to the Superintendent of Documents, Government Printing Office, Washington 25, D. C. Prices may be obtained from the Superintendent of Documents.)

3. REQUIREMENTS

3.1 Preproduction sample. - Unless otherwise specified, before production is commenced a sample of the finished commodity and each component part shall be submitted or made available for approval to the contracting officer or his authorized representative for design, construction, workmanship, and appearance. The approval of the preproduction sample does not relieve the contractor of responsibility from compliance with all other applicable provisions of this specification. When the preproduction sample is approved, it shall be used as a guide throughout production of the contract.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the currentversion before use.

3.1.1 Materials. - The materials, construction and finish requirements of the items covered by this specification shall be not less than is specified in 3.1, 3.2, 3.3 and subparagraphs thereunder.

3.1.1.1 Adhesives. - Adhesives used in the construction of the furniture and their permitted application shall be as shown in table I.

I. - Adhesives

| Application | Kind of Adhesive |
|---|---|
| All assembly joints, glue blocks, glued laminated stock, and edge joining of lumber core panels, and built-up solid panels. | Any adhesive that will conform to or exceed the block shear test requirements of the following:<br>Animal, Fed. Spec. MMM-A-100, grade J-2, or<br>Casein, Fed. Spec. MMM-A-125, or<br>Urea-Resin, Fed. Spec. MMM-A-188 |
| All plywood gluing edge joining of veneer and edge banding. | Any adhesive that will conform to the test requirements of type II bond or better, as described in Commercial Standard CS-35-58 when specified in the invitation for bids Type I bond shall be supplied. |

3.1.2 Dowels. - Dowels shall be of maple, birch, oak, or beech dried to a moisture content of from 3 to 5 percent. They shall be longitudinally or spirally grooved and shall have beveled ends. Diameter and length shall be as large as practicable to insure maximum serviceability of joining members.

3.1.3 Fabrics. - The upholstery fabric for chairs and dressing table benches shall be as specified in the invitation to bid, and when specified, shall meet the requirements of Federal Specification CCC-F-66.

3.1.4 Artificial leather. - The quality and weight of artificial leather shall be in accordance with Federal Specification CCC-A-700. The treatment, if any, the class, the grain and the color required shall be as specified in the invitation to bid.

3.1.5 Padding.

3.1.5.1 Cotton felting. - Cotton felting shall be at least equal in quality to felt made of 90 percent cotton linters not lower in grade and staple than the official Cotton Linters Standard of the United States for Grade 4 and Staple 4, and 10 percent not lower in grade and staple length than the official Cotton Standard of the United States for Low Middling Spotted and 7/8 inch staple length. The felting shall weight not less than 14 ounces per yard, 27 inch basis.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the currentversion before use.

3.1.5.2 Fiber padding. - Padding for chairs and vanity benches shall conform to class 2 of either type I or type II, and either grade A or grade B of Federal Specification CCC-P-91 for Padding; Rubberized Curled Fibres (Hair or Vegetable). The thickness shall be not less than 1 inch.

3.1.5.3 Latex foam. - The latex foam shall be all natural rubber or a suitable blend of natural and synthetic rubber, and shall conform to the test methods as shown in ASTM Specification designation D-1055, latest issue as they apply to latex foam. The latex foam sheets shall be solid stock not less than 1 inch thick and of a compression resistance of ASTM, Grade R-32H. The molded latex foam cushions shall be of cored stock, ASTM Grade R-22H.

3.1.5.4 Bonded shredded foam. - The bonded shredded foam shall be made of synthetic or natural rubber foam that is dry, free from coagulation, excessive flash and other foreign materials, and shall conform to type II, class 2, condition medium, as specified in MIL-R-17252, thickness shall be according to design requirements, but for seat and back cushions shall be not less than 1 inch thick. Bonded shredded foam shall not be used on loose cushions.

3.1.5.5 Plastic material, cellular urethane. - The plastic cellular urethane used for padding of slip seats or backs of chairs or benches shall conform to the requirements of type II, class 2, of Interim Federal Specification L-P-00386 (GSA-FSS).

3.1.6 Hardware. - All finishing hardware shall be brass plated, chromium plated or nickel plated steel or solid brass, bronze, or corrosion-resisting alloy, unless otherwise specified, according to design requirements. The surface of brass, bronze, and corrosion-resisting alloy hardware shall be polished and shall have one coat of baked-on clear, synthetic enamel or lacquer.

3.1.6.1 Glides. - Glides for furniture shall be of the nail type, or the three prong type, made of corrosion-resisting steel or steel case-hardened after forming and nickel or chromium plated. Glides shall be as large as the leg or base permits (to within not more than 1/8 inch of outside edges of leg or base). When specified, adjustable glides shall be furnished.

3.1.6.2 Hinges. - Fully mortised butt hinges shall have not less than five knuckles and material thickness shall be not less than 0.072 inch. Semi-invisible knife hinges shall be not less than 0.089 inch thick and shall be secured by not less than four number 6 flat head screws. Table leaf hinges shall have not less than three knuckles and be not less than 1-1/8 inches long at the joint and not less than 2-3/4 inches wide when open. material thickness shall be not less than 0.072 inch. Ornamental hinges shall have not less than three knuckles and material thickness shall be not less than 0.036 if embossed, or less than 0.072 inch if flat. Exposed parts of hinges shall be of the finish specified in 3.1.6 unexposed hinges shall be cadmium, zinc or brass plated to resist rust.

3.1.6.3 Shelf brackets and support strips. - The adjustable brackets and support strips for shelves shall be made of brass or nickel or chromium plated cold rolled steel. The brackets shall be of a type to lock into the perforations in the steel support strips. The steel support strips shall be perforated to

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:40Z
Check the source to verify that this is the current version before use.

receive the shelf brackets on center not greater than 1/2 inch. The shelf support strips shall be secured to the case ends by screws not farther apart than one every 6 inches. Support strips shall not be let into end panels.

3.1.6.4 Leg plates. - When legs over 7 inches long are not a part of the case, they shall be attached so that they can be replaced, and shall have die stamped steel leg plates which shall be secured to the leg by not less than 5/16 inch diameter rail bolt or lag screw and to the case by not less than four screws. The center part of the plate shall be offset to give additional strength to the plate and for clearance for the head of the lag screw or nut of rail bolt. The rail bolt nut shall be welded or swaged to the plate.

3.1.6.5 Leg ferrules. - Leg ferrules shall be wrought, spun or cast brass, bronze, aluminum, or chrome finished die casting, tapered to fit the contour of the leg. Leg ferrules shall be secured by not less than one escutcheon nail or screw.

3.1.6.6 Drop-leaf support. - The drop-leaf supports shall be of the folding type and shall have spring tension to hold the drop-leaf rigidly in place in the raised position. The leaf support shall be secured to the frame and leaf by not less than four No. 8 screws. Support shall be of plain wrought steel, cadmium, zinc or brass plated.

3.1.6.7 Pneumatically driven staples. - Staples, if used to secure case backs, shall be size .050 x .030, of 1010 to 1012 steel, cold drawn, work hardened, and copper lacquer coated.

3.1.6.8 Drawer guides. - The drawer guides may be all wood, all steel, or metal and wood consisting of a drawer guide channel and drawer slide. The drawer guide channel shall be secured to the drawer bottom or to the drawer front and drawer back by glue and screws. The drawer slide shall be secured to the parting rails at the front and back of the case. If metal or combination metal wood guides are used, metal parts shall be channel formed from not less than 16 gage (nominal thickness 0.0598 inch) steel. The steel guide channel shall interlock with the drawer runner in such manner as to prevent the drawer from dropping excessively when opened. Drawer guides and slides, when of wood, shall be made of any of the wood in table II except alder, magnolia or yellow poplar.

3.1.6.9 Table extension slides. - Each section of the table extension slide shall be not less than 1/2 the length of the table top. In the fully open position each section of the slide shall overlap the adjacent section by not less than 1/2 the length of the section. The complete set of slides shall withstand the test specified in 4.4.2 with not more than 1/8 inch permanent deflection, loosening of parts or impairment of operating efficiency after the test is complete. Steel slides shall be secured to the table top with sheetmetal screws.

3.1.7 Lacquer. - Lacquer shall conform to the test requirements specified in 4.4.1.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the currentversion before use.

3.1.8 Glass. - The types and quality shall conform to Federal Specification DD-G-451.

3.1.8.1 Sliding glass doors. - Sliding glass doors shall be of plate glass, type I, glazing quality, nominal thickness 3/16 inch.

3.1.8.2 Framed glass doors. - Glass for framed doors shall be type II, clear sheet glass, AA quality, double strength.

3.1.8.3 Mirrors. - Mirror glass shall conform to grade 1 of Federal Specification DD-M-411, and shall have a copper backing as specified therein, or other suitable backing that will withstand the same tests. Wood frames shall be constructed as described in 3.2.1 of the specification. The size, design, and whether framed or frameless mirrors are desired, shall be as specified in the invitation for bids. The mirror backs shall be 3-ply hardwood, not less than 3/20 inch thick, the face and back veneers conforming to paragraph 3.1.9.4 or hard-pressed wood fiberboard not less than 3/16 inch thick as specified in 3.1.11. The mirror backs shall be closely fitted and tightly secured. Frameless mirrors shall have hardwood blocks of a size to accomodate the hanging device attached to the back. Each block shall be secured by not less than two screws and glue. The screw heads on the inside of the mirror backs shall be covered with gummed tape to prevent marring of the mirror plating. When wood frames are specified, the wood and finish shall conform to the requirements of this specification and be styled in accordance with design requirements. When mirrors without frames are specified, the edges of the glass shall be polished and corners eased. All dresser mirrors shall be equipped with provision for attaching to the case and for hanging. Attaching means may include tilting device for dressers, but shall have tilting type for dressing tables.

3.1.9 Wood varieties and parts. - Wood parts including solid wood and veneers in any one item for the color of finish specified, shall be of the kind of wood listed in table II and of the quality hereinafter specified. It is to be noted by manufacturers that the wide range of species indicated for each kind of wood listed is in no way to be construed as all such species being acceptable in any one piece of furniture, but rather all species that will conform to a uniform finish color and to the wood quality specified hereinafter. Exposed parts include all parts and surfaces of each item of furniture which are exposed to view when the item is placed in the generally accepted positions of use.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the currentversion before use.

TABLE II. - Varieties of Wood

| Color of Finish 1/ | Face Veneer | Exposed Solid Parts | Unexposed Solid Parts |
|---|---|---|---|
| Mahogany or Walnut | Mahogany 2/ or Walnut | Beech<br>Birch<br>Cherry<br>Elm<br>Hickory<br>Mahogany 2/<br>Maple<br>Pecan<br>Gum, except Tupelo<br>Walnut | Alder<br>Ash<br>Beech<br>Birch<br>Cherry<br>Elm<br>Hackberry<br>Hickory<br>Holly<br>Magnolia<br>Mahogany<br>Maple<br>Oak<br>Pecan<br>Sweetgum<br>Sycamore<br>Walnut<br>Yel. Poplar |
| Maple, Cherry or Fruitwood | Beech<br>Birch<br>Cherry<br>Maple | Beech<br>Birch<br>Cherry<br>Maple | |
| Limed Oak Finish | Oak | Oak<br>White Ash | |
| Pigmented Finish | Mahogany<br>Walnut<br>Oak<br>Elm | Elm<br>Mahogany<br>Oak<br>Walnut | |

1/ Decorative plastic laminate color and finish shall simulate the color and general appearance of other wood parts.

2/ American, African, or Philippine Mahogany except the species "almon" of Philippine mahogany is not permitte for exposed parts.

3.1.9.1 Seasoning. - All wood shall be uniformly kiln-dried to moisture content of from 5 to 8 percent as determined by Military Specification MIL-W-6110 dependent upon the manufacturer's best commercial practice and after kiln-drying shall be held in properly controlled warm dry storage for sufficient period of time to insure a uniform distribution of moisture among the individual pieces. After gluing, built-up solid panels, including built-up legs and lumber cors, shall be permitted to cure out or condition by one of the following suggested methods or other comparable methods to insure a uniform distribution of glue joint moisture and the elimination of sunken joints, spring back and stresses that impair serviceability or finished appearance, before planing and sanding for crossbanding:

(a) 7 days at 80°F. and 30% relative humidity.
(b) 4 days at 120°F. and 35% relative humidity.
(c) 24 hours at 160°F. and 44% relative humidity.
(d) 16 hours at 200°F. and 55% relative humidity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:40Z
Check the source to verify that this is the current version before use.

3.1.9.2 Solid exterior parts. - All solid exposed parts, of any single item, shall be of the same kind of wood. Parts shall be free of defects which impair appearance or which might impair serviceability except as follows:

a. Sound, tight knots of not over 1/8 inch in average diamete. provided they are not in clusters.

b. Figured grain or discoloration provided the wood is such as to permit a uniform color when finished.

3.1.9.3 Solid interior parts. - Wood shall be free from defects which might impair serviceability or appearance except as follows:

a. Sound, tight knots of not over 1/2 inch in average diameter provided they are not in clusters, except not over 1/4 inch for drawer sides.

b. Holes not over 1/16 inch in diameter, except drawer sides and backs.

c. Surface checks with barely perceptable opening not over 4 inches long.

d. Bark, gum or pitch pockets not over 1/8 inch wide and 2 inches long, except drawer parts exposed when open.

3.1.9.4 Plywood.

3.1.9.4.1 Hardwood plywood. - The hardwood plywood shall be constructed according to the requirements of Commercial Standard CS-35-56 and as specified herein. Bondage shall be type II or better, face and back veneers shall be not less than 1/28 inch thick before sanding and when face and back veneers are not of the same species, the two veneers shall be of the same density and thickness. Face veneers shall be of the wood specified in table II and shall be grade 1 (good), either plain sliced, flat cut, quarted or half round cut except oak which shall be rift cut, and maple or birch which may be rotary cut grade 1 (good) select white. All face veneers in one panel shall be matched for color and grain to present uniform appearance. The above requirements shall apply to all paneled surfaces viewed in normal position of use and in addition, the backs of kneehole desks, swinging doors, and drop leaves, top side of shelves, the interior of bookcases and china cabinets and various other visible compartments and surfaces. Face side of drawer bottoms or mirror backs and various other unexposed surfaces, shall be grade 2 or better and may be rotary cut veneer. Both sides of dust panels and back of drawer bottoms shall be grade 3 rotary cut or better veneer. Crossbands shall be not less than 1/24 inch thick and shall be grade 2 or better under grade 1 veneers and grade 3 or better crossbands shall be used under grade 2 veneers. Veneer cores shall be grade 3 or better and any voids at panel edges shall be filled. The entire exposed edge of veneer core 5, 7, or 9 ply plywood shall be banded with same kind of wood as other exposed parts. Lumber core panels shall be regular grade except that no butt joints or knots in excess of 1/2 inch diameter, will be permitted. Crossbands, veneer cores and lumber cores shall be of medium or low density wood as defined in Cs-35-56. At time of assembly, the moisture content shall be from 5 to 9 percent determined in conformance with Military Specification MIL-W-6110.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:40Z
Check the source to verify that this is the current version before use.

Business Service Center of the nearest GSA ... wide and centered between the sides, depth-

3.1.9.4.2 Douglas Fir plywood. - Douglas Fir plywood if used for chair seats or backs, shall comply with the requirements of Commercial Standard CS-45-55 Douglas Fir plywood, interior type, grade A-D-INT.

3.1.9.5 Built-up solid panels. - All built-up exposed panels shall be of full length solid wood strips, not greater than 6 inches or less than 1-1/4 inches wide, except one edge strip may be not less than 1/2 inch wide. The solid wood strips shall be carefully selected for similar grain and color and shall be edge joined with either continuous tongue and groove construction or with matched square edge joints. Finish thickness of flush panels shall be not less than 3/4 inch and framed in raised panels shall be not less than 5/16 inch thick at the edges or less than 1/2 inch thick in the raised portion.

= 3.1.10 Plastic thermosetting resin laminate assemblies. - The plastic thermosetting resin laminate assemblies shall be either type II or type III assemblies conforming to Federal Specification L-T-0041c and as specified herein.

3.1.10.1 Type II decorative laminate assemblies. - When specified in the invitation for bids, the decorative laminate assemblies shall be Style D, type I, grade HP, class 1, finish B, nominal thickness 1/16 inch as specified in Federal Specification L-P-00508. The decorative laminate shall simulate the general appearance of other exposed wood parts.

3.1.10.1.1 Backing sheet. - Type II assemblies shall have Style ND, type V, grade HP, nominal thickness 0.030 inch as specified in Federal Specification L-P-00508.

3.1.10.2 Type III decorative laminate assemblies. - When specified in the invitation for bids, the type III laminate assemblies shall conform to Federal Specification L-T-0041c and in addition surface requirements shall be type I, grade HP, class 1, finish B as specified in Federal Specification L-P-00508b. The color and finish shall simulate other exposed wood parts.

3.1.11 Hardboard. - Hardboard which may be used for case backs, mirror backs and dust panels shall be hard-pressed wood-fiber hardboard, smooth one exposed side and shall be not less than 3/16 inch thick and comply with Federal Specification LLL-H-35 for type I, class 2 hardboard.

3.1.12 Finishing materials.

3.1.12.1 Stain. - Stain shall conform to Military Specification MIL-S-10617, except that in the fading test, a small color change will be permissible.

3.1.12.2 Filler, wood paste. - The filler shall conform to Federal Specification TT-F-336.

3.1.12.3 Lacquer, spray, clear. - The lacquer shall conform to type I or II, Federal Specification TT-L-57.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the currentversion before use.

3.1.12.4 Sealer. - The sealer shall conform to Federal Specification TT-S-190.

3.1.12.5 Wax. - The wax or polish shall conform to Federal Specification P-P-554 or type I or II, Federal Specification P-W-158.

3.2 Construction.

3.2.1 Framing. - The framing shall be mortise and tenon, tenon and groove, or dowel joints. In mirror frame construction, the use of splines, wood or metal to secure miter joint is permissible. Miter joints of aprons, bases or other similar joints may be secured by clampnails after glueing and shall be reinforced by full length triangular glue blocks not less than 1 inch along the right angular sides. The mortises for rails and panels shall be not less than 1/2 inch deep except for dust partitions and drawer bottoms which shall be not less than 3/16 inch deep. Tenons shall be not less than 1/3 the thickness of the rails or panels or less than 1/4 inch. All joints shall be true and all wood parts shall be accurately, neatly and smoothly milled. Dowel joints shall be as specified herein. All parts of construction subject to stress shall be strengthened by hardwood glue blocks, which shall be accurately fitted and secured by glue. Corner braces shall be not less than 3/4 inch thick and shall be accurately fitted into the corner or around posts or legs where applicable.

3.2.1.1 Tolerances. - Where tolerances are not specified for components, the following tolerance will be permitted:

Overall dimension, may have a minus tolerance of 1/4 inch and may excede dimensions to include furniture in this range of sizes
Dimension of any solid wood part - plus or minus 1/16 inch.
Dimension of plywood parts - plus 1/16 inch minus 1/32 inch on plywood 3/16 inch thick or thicker.
Mirror glass size as specified in Federal Specification DD-M-411.

3.2.1.2 Gluing. - All joints shall be milled true and even and all structural joints shall be thoroughly glued and held under proper pressure until the glue has set sufficient to handle. Nails, brads or staples will not be permitted on outside frames, or drawer sides to drawer fronts or backs. A 6d barbed or cement coated nail through the tenon into the case frame or post will be permitted, provided the head does not show when the furniture is in its used position. Dust bottom frames on solid built-up furniture need not be glued at the joints of end rails to the back rail to allow for expansion of the end panel. Excess glue shall be neatly cleaned from exposed surfaces.

3.2.2 Legs and posts. - Legs and posts shall be made of one piece solid wood or may be built-up of full length strips. Where a particular design requires turned legs, posts, or pedestals with member or ornamentations larger in dimensions than the square stock from which they are produced, such members may be built-up. Legs of Duncan Phyfe or similar styles shall be glued up using not less than three pieces and the natural grain of the wood shall follow the line of the leg as close as possible. Multi-leg pedestals shall have a metal webb plate secured by screws to the under part of the pedestal and to the legs. When

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the currentversion before use.

legs are over 7 inches long and are not a part of the item or base construction (posts or base to the floor) they shall be applied by plates as specified in 3.1.6.4. Detachable tapered legs shall be not less than 1-1/4 inch diameter at the bottom and shall have leg ferrules as specified in 3.1.6.5 and the wood leg shall continue to the end of ferrule. Detachable dining table legs shall be equipped for securing to the table apron with metal or wood corner braces with a hanger bolt. All wood used for built-up parts, shall be carefully matched for grain and color. All legs or base support members shall have glides as specified in 3.1.6.1.

3.2.3 Drawers. - Plywood drawer fronts shall be 5-ply lumber core plywood as specified in 3.1.9.4. Solid wood fronts shall be as specified in 3.1.9.5. Shaped drawer fronts or drawer fronts having the grain run vertical, may be 7-ply laminate with cross-ply under face and back veneer. Drawer sides and backs shall be not less than 3/8 inch thick solid built-up wood or 7/16 inch 5-ply plywood and shall be not more than 1/4 inch less in height than the drawer opening for the full height of the drawer, to prevent the drawer from dropping excessively when opened. The drawer sides shall be dovetailed and glued to the drawer front and back. The dovetails shall be milled true and even, and any open, poorly milled or poorly glued, or uneveness of assembled dovetails will be considered as not meeting the requirements of this specification. Drawer bottoms shall be not less than 3/20 inch thick not less than 3-ply plywood as specified in 3.1.9.4. The drawer sides, front and back, shall be milled not less than 3/16 inch deep to receive the drawer bottoms. Drawer bottoms and guide channel shall be reinforced with not less than 6 rubbed-in-place glue blocks. Space between back of drawer and case back shall not exceed 3 inches. Drawer stops shall be provided to prevent the drawer from hitting the back of the case. The top edge and ends of flush drawer fronts or drawer fronts not overlapping the case, shall be slightly beveled or offset to prevent sticking and to allow free sliding of the drawer as soon as the drawer is opened. Clearance of 1/16 (plus or minus 1/32) inch shall be allowed on each end, top and bottom edges of drawers. All drawers shall have a center guide channel as specified in 3.1.6.8. The guide channel shall be accurately milled, neatly fitted, glued, or glue blocked to the center of the underside of the drawer bottom. Novelty drawers, or drawers with shaped fronts shall be made and glue blocked in accordance with the design and dimensions of similar items used in regular commercial furniture.

3.2.3.1 Drawer pulls. - Metal or wood drawer pulls shall be in accordance with design requirements. Wood pulls may be an integral part of drawer or case and may be of flush construction. All attached wood pulls shall be glued and secured by screws. The screws used for wood pulls shall penetrate not less than 3/4 of the thickness of the pull. All flat head screws used to secure either type pull shall be fully countersunk on the inside of the drawer front, or screws having non-slip, self-centering, recessed, round-heads may be used.

3.2.4 Drawer bearers and dust bottom sections. - The drawer bearer frame and top frame shall consist of a rail at the front (forming either an exposed or concealed drawer partitioning rail), and a rail at the back of the case, and not less than two joining rails which shall form a frame to support the drawers. The rails shall be 3/4 inch thick by not less than 1-1/2 inches wide, minus 1/16

Source: https://assist.dla.mil -- Downloaded: 202640-26T11:40Z
Check the source to verify that this is the currentversion before use.

inch, plus 1/8 inch for front, back and intermediate rails. The end rails and intermediate rails (for drawers 34 inches wide or more, or for double drawers) shall be joined to the front and back rails by mortise and tenon, or tenon and groove, or by not less than two dowels at each joint. The frame sections shall be dadoed into the ends, or may be secured by not less than four dowels at each end or by housing into panels or posts and for solid built-up end panels, the section shall be of floating construction to permit expansion of the end panel. All drawer bearer sections (except knee-hole desks) shall have a dust bottom housed into the rails on all four sides. The dust bottom shall be not less than 3/20 inch thick or less than 3-ply plywood as specified in 3.1.9.4, or may be of hardboard as specified in 3.1.11 and shall completely close off the section. Drawer guide channel shall be accurately fitted and shall be in perfect alignment with the drawer slide. The function of the slide and guide channel specified in 3.1.6.8 shall give a maximum of efficiency to drawer movement.

3.2.5 Tops. - Case and table tops shall be of either of the following constructions as specified in the invitation for bids:

3/4 inch thick built-up, solid wood strips as specified in 3.1.9.5,

5-ply 3/4 inch thick lumber core plywood as specified in 3.1.9.4 or

5 or more ply 3/4 inch thick plywood with plastic decorative laminate as specified in 3.1.10, either self-edged or wood banded matching the other wood parts. Molded or shaped edges of lumber core plywood need not be edge banded. Table tops and case tops shall be secured to table aprons, case top frame rails, or case ends by wood screws or metal fasteners. Solid built-up wood tops over 12 inches wide shall be of floating construction secured by metal fasteners designed for the purpose or by other equally secure manner.

3.2.5.1 Tables, extension, dropleaf and gateleg. - The extension tables shall be equipped with extension slides as specified in 3.1.6.9. The leaves and top sections shall have dowels and matching holes to assure accurate alignment of the leaves and top sections. Securing points shall be not more than 16 inches apart. Leaf joints shall fit flush on top and edges. Dropleaf tables shall have leaf supports as specified in 3.1.6.6 and not less than three hinges as specified in 3.1.6.2. Leaves of gateleg tables shall have not less than three hinges as specified in 3.1.6.2 and shall be supported in the raised position by the extended gateleg.

3.2.6 Case ends. - The case ends shall be either built-up solid wood as specified in 3.1.9.5 or 3/4 inch thick 5-ply lumber core plywood, or panels fully framed in on all four edges shall be not less than 3/16 inch thick nor less than 3-ply plywood as specified in 3.1.9.4 with face veneer as shown in table II.

3.2.7 Aprons and rails. - The aprons and rails shall be solid wood 3/4 inch thick or 5-ply lumber core plywood not less than 3/4 inch thick and of the woods specified in table II for the color of finish specified. The aprons and top rails shall be milled to receive metal top fasteners when tops are secured by this method.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:40Z
Check the source to verify that this is the current version before use.

3.2.8 Case backs. - The case backs shall be not less than 3/20 inch thick and shall be either 3-ply plywood as specified in 3.1.9.4 or hardboard as specified in 3.1.11 may be used on backs of dressers or chest of drawers. The ends of all cases shall be rabbeted to receive the backs, tops shall be rabbeted or extend over the back panel to cover the top edge of the back panel. The back panel shall be secured to the case, including drawer sections, by means of round headed screws or 3-D cement coated box nails. The spacing of screws shall be not greater than one every 8 inches, and of nails not greater than one every 6 inches including one at each corner. Alternatively staples as specified in 3.1.6.7 spaced not over 3 inches apart, pneumatically driven flush may be used.

3.2.9 Shelves. - Unless otherwise specified in the invitation for bids, shelves shall be constructed by any one of the materials of tops specified in 3.2.5. Fixed shelves in open or glassed in areas shall be joined to the case by dadoing and gluing into the end, or by not less than four dowels at each end of the shelf. Shelves shall be provided for compartments of servers and buffets. The shelf may rest on cleats secured by screws to the panels forming the compartment. Adjustable shelves shall be supported on shelf supports and perforated support strips as specified in 3.1.6.3, and shall be routed or dadoed not less than 1/8 inch deep where the shelf rests on the shelf bracket to prevent movement.

3.2.10 Beds. - All bedsteads, rails and bed frame dollies shall be constructed to accommodate standard size bed springs as specified in Federal Specification AA-B-250 and shall be in accordance with Simplified Practice Recommendation R2-57.

3.2.10.1 Head and foot boards. - Head and foot boards shall be of such width that there will be not less than 54 inches between wood bed side rails of double beds or less than 39 inches between wood rails of single beds. Head and foot rails and panels shall be mortised or doweled, with not less than two dowels at each joint. Fully framed in panels shall be not less than 1/4 inch thick, 5-ply plywood as specified in 3.1.9.4 and table II. Open panels or spindles shall be not less than 3/4 inch thick as specified in 3.1.9.2 and table II. The open panels shall be secured by mortise and tenon or by dowels. Spindles shall be doweled or chucked into the rails or posts. Modern head and foot board panels shall be not less than 3/4 inch thick plywood as specified in 3.1.9.4 or built-up solid wood as specified in 3.1.9.2 and shall be secured by glue and not less than two screws to each post. The head and foot boards shall be of the wood shown in table II for the color of finish specified.

3.2.10.1.1 Bed rails. - Bed rails shall be either solid wood, 5-ply lumber core plywood, 9-ply laminate 4-1/2 (plus or minus 1/4 inch) inches high, 3/4 inch thick and reinforced with a slat rest of not more than three wood strips 3/4 inch by 1-1/4 (plus or minus 1/8 inch) inches glued to each rail and secured on the end and in center by not less than three number 8 wood screws, not less than 1-1/4 inches long or the strips may be nailed to the rails with an auto nailer using barbed nails. There shall be not less than 18 nails when the strip is in two pieces and not less than 22 nails when a three piece strip is used. The nails shall be not less than 15 gage, or less than 1-3/8 inches long. Three

Source: https://assist.dla.mil -- Downloaded: 20260-26T11:40Z
Check the source to verify that this is the current version before use.

slats shall be supplied with each bed. Slats shall be of sound, clear stock 3/4 inch thick by 3-5/8 (plus or minus 1/8 inch) inches if of alder, elm, sweetgum, poplar, Douglas fir or sitka spruce. Slats made of other acceptable hard woods listed in table II shall be a minimum of 3/4 inch thick and 2-1/2 inches in width. The metal fittings for attaching the bed rails to the posts shall be of an approved commercial type having at least 2 hooks each.

3.2.10.2 Bookcase head boards. - Bookcase head boards shall be not less than the overall width of the bed of which it is a part. Compartments shall be 9 (plus or minus 1/4) inches from front to back at the bottom of the compartment, and there shall be not less than three compartments for double beds or less than two compartments for single beds. Inside compartments and outside faces of sliding doors shall be finished the same as the exposed parts. There shall be provision made near the bottom for securing the headboard to the bed frame dolly and a stretcher to hold the bookcase ends in alignment. Tops, ends, shelves, partitions and doors shall be as specified herein, except edge banding of doors is not required. Sliding doors shall operate easily and efficiently, and be easily removable. Alternatively, a low foot board and wood rails, specified in 3.1.10.1.1, may be furnished in lieu of the metal bed frame dolly when specified in the invitation for bids.

3.2.10.2.1 Dolly. - The dolly shall consist of a frame or base, four legs or risers equipped with not less than 2 inch diameter top-bearing, soft rubber tread or plastic casters and means for securing the dolly to the headboard. The caster stem shall be not less than 3/8 inch diameter except where it is decreased for retaining purpose, the stem may be inserted into a molded nylon socket. The frame shall be constructed of not less than 1-1/2 inches by 1-1/2 inches by 1/8 11 gage (.1196 inch nominal) inch thick steel angles and be braced and welded or riveted to give firm support and to accommodate the springs specified in Federal Specification AA-B-250 and Simplified Practice Recommendation R2-57. These dollies may be furnished, and shall be easily adjustable to fit either single or double bed springs. The lateral members of either construction shall not interfere with proper seating of bed spring construction having drop cross-slats. Attaching brackets and hardware shall be furnished. Bed frame shall be cleaned and finished with baked enamel, or aluminum paint. All rough edges and surfaces shall be eliminated. Alternatively, a frame otherwise meeting all requirements listed above may be constructed of channels, the cross rails of which shall be not less than 16 gage (0.0598 inch) steel with a vertical web no less than 1-1/8 inches and flanges no less than 1 inch, and the side rails of which shall be no less than 14 gage (0.0747 inch) steel with a vertical web no less than 1-1/2 inches and flanges no less than 1 inch; the side rails shall be equipped with suitable flanges or angles to retain the box springs.

3.2.11 Chairs, dining room, bedroom and desk. - Front legs of chairs with rails shall carry through to the top of seat rails. Back posts shall carry beyond the top of seat rails to a height to meet requirements of the design specified. Front, back, and side rails shall be either double-doweled, or mortised and tenoned to front legs and back posts, and chairs shall have corner blocks of hardwood, properly fitted, glued, and secured with screws to the inside of the seat rails. The inner side of rails and membering ends of corner blocks may be

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the current version before use.

tongue and grooved to interlock to facilitate placing and gluing of the blocks. Chairs without seat rails shall have the legs chucked at least 1 inch into the seat and back posts shall be fully chucked through the seats and be wedged from underneath the seat. Both constructions shall produce rigid back and leg assemblies. Number and type of stretchers, back splats, and top rails, spindles, etc., shall be in accordance with design requirements and shall be doweled, chucked, doweled or mortised and tenoned and glued. Wood arms shall be secured with screws or doweled and glued to back posts. Arm stumps shall be secured by glue and two screws to seat or rails and doweled or chuck dowels to the arm. Screw holes shall be flush or button wood-plugged on sides or front of chairs.

3.2.11.1 Pad backs. - When specified, pad backs on plywood shall not be considered a part of the chair back structure but a refinement. Top and intermediate rails between chair back posts shall be as required. A 1-inch layer of padding as specified in 3.1.5.2 and covered with a layer of cotton as specified in 3.1.5.1 or 1 inch of rubber as specified in 3.1.5.3 or 3.1.5.4, or 1 inch of plastic cellular urethane as specified in 3.1.5.5 shall be secured to a 3/8-inch thick plywood base as specified in 3.1.9.4.1 or 3.1.9.4.2. The pad back shall be secured to the back rails and posts of the chair by concealed screws.

3.2.11.2 Rush seats. - When specified, rush seats shall be made of broad leaved flag Typha latifola, carefully handwoven over a hardwood seat frame. Seat frame shall follow design requirements and shall have all edges rounded. The rush shall be of a grade and type used on similarly designed chairs for commercial trade.

3.2.11.3 Slip seats and upholstered spring seats. - When specified, slip seats shall have a plywood base as specified in 3.1.9.4.1 or 3.1.9.4.2 not less than 3/8 inch thick or a hardwood frame in accordance with design requirements. When a plywood seat is specified, the plywood shall be finished both sides as specified in 3.3.7, method 2 and covered with a layer of not less than 1-inch thick rubber as specified in 3.1.5.3 or 3.1.5.4 or 1 inch of plastic cellular urethane as specified in 3.1.5.5 or the plywood seat padded with a layer of fibre padding as specified in 3.1.5.2 of not less than 1 inch thickness and a layer of cotton batting as specified in 3.1.5.1. When a frame seat is specified, it shall consist of four hardwood members, 1-3/4 (plus or minus 1/4) inches wide by not less than 3/4 inch thick, securely doweled and glued together with top outside edge and corners eased. Each seat frame shall have not less than four sinuous type springs anchored at each end by metal clips secured with not less than three nails. Sinuous type springs shall be held in alignment from side to side by helical springs. A layer of wire reinforced burlap or equivalent shall be tacked over the springs and stitched to the springs to prevent the springs from turning or twisting. The burlap shall be covered by a 1 inch layer of hair or fibre padding as specified in 3.1.5.2, or rubber as specified in 3.1.5.3 or 3.1.5.4 or plastic cellular urethane specified in 3.1.5.5 of not less than 1 inch thickness. A layer of cotton batting as specified in 3.1.5.1 shall then be placed over the fibre pad before applying the upholstery cover. Slip-seats shall be securely fastened to the rails but made easily removable by releasing concealed metal fasteners or screws.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:40Z
Check the source to verify that this is the current version before use.

3.2.11.4 Solid wood seats. - When specified, solid wood seats shall be of hardwood strips, 2 inches minimum to 6 inches maximum in width, and not less than 3/4 inch thick for chairs with rails and not less than 1-1/8 inches thick for chairs without rails. The wood shall be carefully selected and dowel joined with not less than three dowels at each joint or with a continuous tongue and groove construction and glued together or, if an electronic gluing machine or a clamp carrier is used, the strips, except hard maple, may be butt edge joined. The grain of the wood shall run from front to back of the seats. Saddle or ball-shaped seats shall have character, depth and workmanship in accordance with the design of the chairs.

3.3 Methods of finishing. - All surfaces normally exposed to view shall be finish sanded smooth and all corners and edges eased, and thoroughly cleaned, and finished as herein specified.

3.3.1 Procedure for clear wood finish on open pore wood:

1. Sap stain to equalize wood color.
2. Apply selected colorant to wood to produce color specified. Stain and colorant shall conform to tests specified in 4.4.1.7.
3. Wash coat with adhesive sealer. Sealer shall withstand toughness and adhesion test specified in 4.4.1.8.
4. Scuff sand, using fineness of sandpaper grit needed to produce proper surface.
5. Fill to degree necessary to match sample. The filler shall conform to the test specified in 4.4.1.7.
6. Seal with adhesive type sealer. Sealer shall withstand toughness and adhesion test specified in 4.4.1.8.
7. Sand, using fineness of sandpaper grit needed to give proper surface.
8. Shade to tie in color variation, if necessary. Shading shall conform to the test specified in 4.4.1.7.
9. Top coat with lacquer.
10. Top coat with lacquer. The lacquer and finish shall be of a quality to meet the requirements specified in 4.4.1 and subparagraphs thereunder.
11. Rub, steel wool, wax or polish, if required.

NOTE: Operation number 8 may be performed where shown or after operation number 5.

3.3.2. Procedure for clear wood finish of close grain wood: The finish shall be as specified in 3.3.1 except operations 3, 4, and 5 are omitted.

3.3.3 Procedure for open pore woods in close-to-the-wood, clear wood finishes: The finish shall be as specified in 3.3.1 except wood shall be slush filled for semi-filled pore, or omit filling for complete open pore to match sample panel of finish. Operation number 9 is omitted.

3.3.4 Procedure for glazed clear wood finish: The finish shall be as specified in 3.3.1 and in addition the glazing operation shall follow operation

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the currentversion before use.

number 7 and prior to operation number 8. Glazing material shall, when incorporated into the complete finish, meet the test for ultra-violet light resistance specified in 4.4.1.7 and test of toughness and adhesion specified in 4.4.1.8.

3.3.5 Bleached clear wood finish on open pore wood:

1. Bleach to required degree of absence of color. - The bleach, when incorporated into the complete finish shall be of a quality to meet the requirements specified in 4.4.1 and subparagraphs thereunder.
2. Wash thoroughly.
3. Dry thoroughly.
4. Sand thoroughly.
5. Then follow the finishing procedure specified in 3.3.1, 3.3.3 or 3.3.4 as applicable to match sample finish panel.

3.3.6 Procedure for limed oak and pigmented finishes:

1. Apply pigmented lacquer sealer. The pigmented lacquer sealer, when incorporated into the complete finish shall be of a quality to meet the requirements of 4.4.1.7 and 4.4.1.8.
2. Apply wash coat of adhesive type sealer.
3. Sand, using fineness of sandpaper grit to provide proper smoothness of surface.
4. Fill with filler of required color to produce properly filled pores.
5. Apply water white top coat of desired sheen.
6. Rub, steel wool, wax or polish, if necessary to match sample panel of finish.

The complete finish shall meet the requirements of 4.4.1 and subparagraphs thereunder.

3.3.7 Unexposed parts and surfaces. - All unexposed interior parts and surfaces including the underside of the top, inside of bed rails, drawer interior and exterior surfaces, drawer bearer sections, and drawer guides shall be machined smooth and cleaned. After the furniture has been finished as specified in 3.3, the above parts shall be treated by either method 1 or method 2 as specified below:

Method 1, chemical treatment. - These entire surfaces shall be given a moisture-retarding and lubricating treatment. The liquid used shall conform to the requirements of composition B as specified in Interim Federal Specification TT-S-00180(GSA-FSS). The entire surfaces of the unexposed parts of the drawers shall be submerged in the moisture retarding solution for not less than 3 minutes. The drawers shall be allowed to drain before insertion into the furniture cases and all surplus of the solution shall be thoroughly wiped from finished surfaces to insure a clean smooth finish, and free sliding drawer operation.

Alternatively, the solution may be applied by spraying a heavy wet coat, then oven dried for not less than 30 minutes at a temperature of not less than 120 degrees.

Source: https://assist.dla.mil -- Downloaded: 2026l0-26T11:40Z
Check the source to verify that this is the currentversion before use.

Method 2, sealer and lacquer. - The above parts shall receive one coat of lacquer sealer and one coat of clear lacquer. The sealer and lacquer shall be as specified in 3.1.7. The outside of drawers, drawer bears, shall then be rubbed with wax. The drawer guides shall be rubbed with paraffin.

3.4 Identification marking. - Each item shall be permanently and clearly marked in an inconspicuous place, with the Federal Stock Number, this specification number, the year of manufacture, and the contractor's or manufacturer's name or trademark so that the source of manufacture may be readily determined.

3.5 Workmanship. - The methods of construction, veneering, joining, assembly, and finishing shall be in strict accordance with the minimum requirements of this specification. Each item shall be free from any defects that affect the appearance or that might affect the serviceability for the lifetime of the furniture.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Sampling for inspection. - Representative random samples shall be selected from the lot in accordance with Military Standard MIL-STD-105.

4.2 Inspection. - The items shall be inspected to determine compliance with this specification as to workmanship, materials, design, details of construction, hardware, finish, marking and packing. Each item shall be subject to inspection and tests at all times and places, to determine compliance with all requirements of this specification, and when practicable, during manufacture. When inspection is made at the place of manufacture, all reasonable facilities and assistance required by the inspectors in the performance of their duty for safe and convient inspection and tests shall be provided by the contractor without cost to the Government. All inspections and tests by the Government shall be performed in such a manner as not to delay the work unduly.

4.3 Supplier's inspection. - Unless otherwise specified herein, the supplier is responsible for the performance of all inspection requirements prior to the submission of supplies for Government inspection and acceptance. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. Inspection records of the examinations and tests shall be maintained by the supplier and made available to the Government for a period of not less than one year after completion of contract or delivery of order.

4.4 Tests.

4.4.1 Test of finish system. - The following tests shall be made on panels produced in accordance with the production procedures used in producing the furniture:

4.4.1.1 Working properties. - Working properties shall conform to the requirements of 4.2.3.1 of Federal Specification TT-L-57.

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the current version before use.

4.4.1.2 Spot test. - Spot test shall conform to 4.2.3.3 of Federal Specification TT-L-57.

4.4.1.3 Alcohol. - Alcohol test shall conform to 4.2.3.3.1 of Federal Specification TT-L-57.

4.4.1.4 Print resistant test. - Print resistant test shall conform to the requirements of 4.2.3.4, 4.2.3.4.1, 4.2.3.4.2 and 4.2.3.4.3 of Federal Specification TT-L-57.

4.4.1.5 Cold check resistance. - Cold check resistance shall conform to the requirements of 4.2.3.5, 4.2.3.5.1, 4.2.3.5.2 and 4.2.3.5.3 of Federal Specification TT-L-57.

4.4.1.6 Boiling water. - The boiling water test shall conform to the requirements of 4.2.3.6 of Federal Specification TT-L-57.

4.4.1.7 Ultra-violet light resistance. - Ultra-violet light resistance shall be as specified in 4.2.3.7 of Federal Specification TT-L-57 except that panel preparation as specified shall be disregarded, and tests shall be made on complete finished wood panel of the same wood as used in production. The finish shall be produced in accordance with production procedures used in producing the furniture.

4.4.1.8 Toughness and adhesion. - The test for toughness and adhesion shall be made using a Bell Laboratories adhesion tester with setting at 2-1/2, in accordance with instructions for using the tester, as provided by Bell Laboratories. The panel shall be marred both parallel and perpendicular to the grain. The resulting indentation shall show no whitening which is evidence of film separation. The film shall conform to the contour of the indentation and shall not crack in a brittle manner in or along the indentation. The test shall be made on completely finished wood panels of the same wood as used in production. The finish shall be produced in accordance with production procedures used in producing the furniture.

4.4.2 Test of extension table. - The sample to be tested shall be one complete table of each size in the lot being offered.

4.4.2.1 Procedure. - The assembled table with the leaf or leaves in place shall be placed upright with all legs resting firmly on a flat surface. Then, still load 50 pounds on the center of the extended part; establish vertical check points and take accurate measurements. The check points shall be midway of the extended part of the table, and between the table top and the flat surface on which the table rests. The load shall be increased to a total of 150 pounds (plus or minus 1 pound) and remain on the table for 30 minutes (plus or minus 1 minute). Remove the weight and check for requirements specified in 3.1.6.9.

5. PREPARATION FOR DELIVERY

(Levels of preservation, packaging and packing protection used are defined in Federal Standard No. 102 (for civil agencies only).)

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the current version before use.

5.1 Levels of protection. - Subject commodity shall be packaged and packed for (a) overseas shipment - military, (b) domestic shipment - storage, (c) domestic shipment - immediate use, and (d) overseas shipment - commercial.

5.2 Level A (Navy) when specified.

5.2.1 Packaging. - Each item shall be wrapped and padded sufficiently to insure against scratching, rubbing, or marring of the finish or materials using cellulosic cushioning material conforming to Federal Specification PPP-C-843. The cushion wraps, pads, and blankets shall be securely fastened to the item by means of tape or twine. Removable cushions shall be secured in place by a strip of 2-inch cotton tape drawn snugly over the center of each cushion and tack-fastened to the underside frame members. Drawers shall be securely fastened in the closed position so that they will not come open during shipment and handling. All items shall be wrapped or shrouded with waterproof paper, or shall be placed in waterproof bags, all constructed of material conforming to Military Specification JAN-P-125. The waterproof wraps or bags shall be sealed with adhesive conforming to Military Specification MIL-A-140, except that for upholstered furniture the waterproof wrap or bag shall not be sealed. Head, foot, and rails of beds shall be packaged as follows: Head and foot shall be placed together with padding between them, then wrapped and tied. Rails shall be placed together, finished sides in, with padding between them, then completely wrapped and tied. Mirrors shall be placed in fiberboard boxes conforming to Federal Specification PPP-B-636. The mirror shall be protected within the fiberboard box with cellulosic cushioning material conforming to Federal Specification PPP-C-843, and with double faced corrugated fiberboard sheets scored to form cell spacers and spring pads to provide an air space on all sides of the mirror.

5.2.2 Packing. - The items shall be packed in overseas type cleated plywood boxes conforming to Federal Specification PPP-B-601 or nailed wood boxes conforming to Federal Specification PPP-B-621. The items shall be packed individually except in instances where two or more like items may be packed together to effect a reduction in cubage without loss of physical protection for the items and where the resultant gross weight does not exceed approximately 200 pounds. Contents of boxes shall be blocked, braced, and anchored to prevent movement within the boxes. Cushioning shall be provided as necessary to prevent chafing and rupture of waterproof wraps, shrouds, or bags. Davenports, sofas, and chairs shall be suspended in the boxes by means of three or more cleats, attached to the item by means of wood screws and securely nailed to the box and braced so that the legs or feet have a clearance of not less than 1 inch. A clearance of not less than 2 inches shall be maintained on the sides adjacent to the arms. A horizontal longitudinal brace shall be placed just above the arms in the best position to afford protection to the arms and to further stabilize the item within the box. The brace shall be nailed to the box and cushioned in the area of the arms.

5.3 Level B (for domestic shipment - storage). - When specified, packaging and packing shall be in accordance with instructions contained in the invitation for bids.

Source: https://assist.dla.mil -- Downloaded: 2026l0-26T11:40Z
Check the source to verify that this is the current version before use.

5.4 Level C (for domestic shipment - immediate use). - Unless otherwise specified, subject commodity shall be packed in containers which, together with packaging, wrapping and inner packing, are acceptable by common or other carriers for safe transportation to point of destination specified in shipping instructions at the lowest transportation rate of such supplies. Shipping containers shall comply with the carrier rules and regulations applicable to mode of transportation.

5.5 Level D (for overseas shipment - commercial export). - When specified, subject commodity shall be packed in containers which, together with packaging, wrapping and inner packing, are acceptable by ocean-going vessels for safe transportation to the points of destination specified in the shipping instructions at the lowest transportation rate for such supplies.

5.6 Marking. - Unless otherwise specified, shipping containers shall be marked according to Federal Standard No. 123. When specified, shipments for the military departments shall be marked in accordance with Military Standard MIL-STD-129, and the following additional requirements: Arrows or prominent marks shall be placed on the sides of the container to indicate the position in which the container shall be handled during shipment. The word "UP" shall be placed at the point of the arrows in letters at least 2 inches in height.

The front panel of each shipping container shall be plainly marked as follows:

UP FURNITURE UP
FRAGILE, HANDLE WITH CARE

Top panels shall be plainly marked as follows:

FURNITURE
FRAGILE, HANDLE WITH CARE
TOP
THIS SIDE UP

6. NOTES

6.1 Ordering data. - Procurement documents should specify the following:

a. The item, the type and the class of furniture required (see 1.2.1).
b. The design and size of the item required or furnish drawings (see 1.2.2).
c. The color and type of finish required and if additional samples of finish are not required of successful bidder (see 1.2.3).
d. The fabric type, number, pattern and color required (see 3.1.3).
e. The color and grain of artificial leather required (see 3.1.4).
f. Whether specific kind of padding is required (see 3.1.5).
g. If specific kind of hardware is required (see 3.1.6).
h. Whether wood framed or frameless mirrors are required (see 3.1.8.3).
i. If built-up solid wood or plywood tops or plastic laminate tops are required for casegoods and tables (see 3.2.5).
j. The kind of chair seat required (see 3.2.11 and subparagraphs).

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the current version before use.

k. Whether packaging and packing for other than domestic shipment immediate use is required (see 5.6).
l. Whether special marking is required (see 5.6).
m. Whether a preproduction sample is required for each item (see 3.1 and 6.3).
n. Whether one or two piece cabinet, china, is required.
o. Whether or not a particular item will be used as a room divider or may be situated any place in a room, as might be the case with a desk.

6.2 Federal specifications do not include all the types, classes, grades, sizes, etc., of the commodities indicated by the titles of the specifications or which are commercially available, but are intended to cover the types, etc., which are suitable for Federal Government requirements.

6.3 Preproduction sample. - When specified in invitation for bids, and before production is commenced, sample of each complete unit under contract shall be made available to the Contracting Officer or his representative for approval, either at the contractor's plant or at such other place as designated. When the preproduction sample is approved, it shall be retained by the inspector as a control guide for subsequent production on the contract. The approved sample may be included as a part of the last shipment.

6.4 Definitions (see section 5). - Federal Standard No. 102 should be referred to for definitions and applications of the various levels of packaging protection for supplies and equipment.

6.5 Transportation description.

6.5.1 Transportation description and minimum weight applicable to this commodity are:

Rail:

Item I
Bed ends, not otherwise indexed by name, wooden.

Item II
Benches, wooden, not otherwise indexed by name. (Specify SU or KD)

Item III
Shelving, with open backs and fronts, finished. (Specify SU or KD)

Item IV
Buffets, wooden. (Specify SU or KD)

Item V
China cabinets (closets) other than kitchen cabinets, wooden.

Item VI
Chairs, wooden, finished, not otherwise indexed by name. (Specify SU or KD)

Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the current version before use.

Item VII
Chests of drawers, wooden. (Specify SU or KD)

Item VIII
Desks, wooden, with one or more enclosed pedestals on either side or both sides of an open knee space. (Specify SU or KD)

Item IX
Dressers, wooden. (Specify SU or KD)

Item IX
Mirrors.

Item X
Buffet servers, wooden. (Specify SU or KD)

Item XI
Tables, not otherwise indexed by name, wooden. (Specify SU or KD)

Carload minimum weights on above items:

In cars 40' 9" or less in length, inside measurements - 10,000; 12,000; 15,000; 18,000; 22,000 and 30,000 pounds.

In cars exceeding 40' 9" in length, inside measurements - 16,000; 18,000; 21,000; 24,000; 30,000 and 40,000 pounds.

Motor:

Item I
Bed ends, not otherwise indexed, wooden.

Item II
Benches, wooden, not otherwise indexed. (Specify SU or KD)

Item III
Shelving, wooden, with open backs and fronts, finished. (Specify SU or KD)

Item IV
Buffets, wooden. (Specify SU or KD)

Item V
China cabinets (closets), wooden. (Specify SU or KD)

Item VI
Chairs, wooden, not otherwise indexed, finished. (Specify SU or KD)

Item VII
Chests of drawers, wooden. (Specify SU or KD)

Source: https://assist.dla.mil -- Downloaded: 20261O-26T11:40Z
Check the source to verify that this is the current version before use.

Item VIII
Desks, with one or more enclosed pedestals on either side or both sides of an open knee space, wooden. (Specify SU or KD)

Item IX
Dressers, wooden. (Specify SU or KD)

Item IX
Mirrors, not otherwise indexed, not bent (specify size).

Truckload minimum weight 12,000 pounds, subject to Rule 34, National Motor Freight Classification.

Item X
Buffet servers, wooden. (Specify SU or KD)

Item XI
Tables, not otherwise indexed, wooden. (Specify SU or KD)

Truckload minimum weights subject to Rule 34, National Motor Freight Classification, on all items except "Mirrors - Item IX": 10,000; 12,000; 15,000; 18,000; 22,000 and 30,000 pounds.

Notice. - When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise, as in any manner licensing the holder, or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.



Source: https://assist.dla.mil -- Downloaded: 202610-26T11:40Z
Check the source to verify that this is the currentversion before use.