CCC-A-680a
May 1966

SUPERSEDING
Int. Fed. Spec. CCC-A-00680 (GSA-FSS)
April 13, 1964

FEDERAL SPECIFICATION

ARTIFICIAL LEATHER (CLOTH COATED), VINYL RESIN, EXPANDED LAYER, (UPHOLSTERY)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers requirements for artificial leather, untreated and treated for fire, mildew, and oil resistance, composed of knitted cotton cloth with a vinyl wear layer and secondary expanded layer of vinyl foam, primarily intended for use as upholstering material.

1.2 Classification.

1.2.1 *Classes and treatments.* Artificial leather covered by this specification shall be of the following classes and treatments, as specified (see 6.1):

Class 1—Untreated.
Class 2—Treated.
Treatments:
(a) Fire resistant:
1—Regular.
2—Special.
(b) Mildew resistant.
(c) Oil resistant.

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:
TT-S-735—Standard Test Fluids; Hydrocarbon.
CCC-T-191—Textile Test Methods.
PPP-B-636—Box, Fiberboard.
PPP-P-51—Packaging, Packing, and Marking of Textile Fabrics (Woolens, Worsteds, Cottons, Silks, and Synthetics).

Federal Standards:
Fed. Test Method Std. No. 406—Plastics: Methods of Testing.
Fed. Test Method Std. No. 601—Rubber: Sampling and Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standard:
MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publication. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

Department of Commerce Publication:
Commercial Standard CS 273-65—Expanded Vinyl Fabrics for Upholstery.

(Application for copies should be addressed to the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C., 20204. Price 10 cents each.)

3. REQUIREMENTS

3.1 Preproduction sample. When specified, before production is commenced, a five-yard sample of the treated or untreated coated cloth specified in the contract or order shall be submitted to the contracting officer for approval. Approval of the preproduction sample authorizes production. Such authorization does not relieve the contractor of the responsibility for compliance with all provisions of this specification.

3.2 Materials.

3.2.1 *Base cloth.* The base cloth shall be of a plain (jersey) knit cotton cloth weighing not less than 3.6 ounces per square yard (6.0 ounces per linear yard base on 60-inch width), in gray state.

3.2.2 *Coating compound.* The coating compound (wear layer and expanded layer) shall be formulated from virgin vinyl-chloride polymer or copolymer thereof suitably plasticized and pigmented to meet the specified color (see 3.4). Materials containing mercurial compounds or water soluble ingredients shall not be used.

3.3 Coated cloth. The coated cloth shall consist of a base cloth, 3.2.1, coated on one side with the coating compound specified in 3.2.2. The coated cloth shall be untreated or treated, 3.3.1, as required. The coated cloth shall meet the requirements as specified in table I when tested as specified in table IV.

3.3.1 *Treated coated cloth.* Coated cloth with treatments "a", "b", or "c", or any combination thereof, 1.2.1, shall conform to the requirements specified in tables I and II. The reverse side of the special treated fire-resistant coated cloth "a" "2" may be flash coated with the same coating compound used on the face side.

TABLE I. *Requirements of untreated coated cloth*

Characteristic	Requirement
Width—inches (min.)	53-1/2
Gage (thickness)—inch (min.)	0.046
Total weight (ozs. per sq. yd.) (min.)	21.3
Breaking strength:	
Wales (pounds) (min.)	60.0
Courses (pounds) (min.)	60.0
Tearing strength:	
Wales (pounds) (min.)	10.0
Courses (pounds) (min.)	10.0
Abrasion resistance (500 double rubs)[1]	Pass
Adhesion of coating (pounds—2-inch width) (min.)	6.0
Accelerated weathering (120 hours)[2]	Pass
Hydrostatic resistance (pounds per sq. in.)	50.0
Volatility, percent (max.)	10.0
Plasticizer loss, percent (max.):	
Activated carbon extraction	10.0
Cold resistance at −20° ± 2°F.[3]	Pass
Flexing[4]	Pass
Stitch-tear resistance:	
Wales (pounds) (min.)	25.0
Courses (pounds) (min.)	20.0
Blocking scale rating (max.)	No. 3
Colorfastness to crocking (min.)	Good
Elongation:	
Wales (percent) (min.)	5.0
Courses (percent) (min.)	25.0

[1] No wear-through to the vinyl foam.
[2] There shall be no appreciable fading of the color, discoloration, exudation, development of tackiness or stiffness. "Appreciable" means a change that is noticeable on first glance in comparing the tested specimen with the original.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

[3] The coating shall not crack through to the base cloth.

[4] There shall be no separation of the vinyl foam from the vinyl wear layer or base cloth after 15,000 cycles.

TABLE II. *Requirements of treated coated cloth*

Treatment	Characteristic	Requirements
(a) 1. Regular fire resistance	Flame resistance:	
	After flame-seconds (max.)	2.0
	Char length-inches (max.)	3.0
	Breaking and tearing strength	Note 1
	Breaking strength:	
	After accelerated aging	Note 2
(a) 2. Special fire resistance	Flame resistance after leaching resistance:	
	After flame-seconds (max.)	2.0
	Char length-inches (max.)	3.0
	Breaking and tearing strength	Note 1
	Breaking strength:	
	After leaching resistance and after accelerated aging	Note 2
(b) Mildew resistance	Breaking strength:	
	After mildew resistance test	Note 3
(c) Oil resistance	Oil resistance	Note 4

Note 1. The breaking strength and tearing strength of the fire-resistant treated coated cloth shall be not less than 80 percent of the applicable minimum values shown (see table I).

Note 2. The breaking strength of the treated coated cloth after accelerated aging or after leaching resistance and accelerated aging, as applicable, shall be not less than 75 percent of initial breaking strength of the treated coated cloth (see table II).

Note 3. The breaking strength of the treated coated cloth after the soil burial test shall be not less than 90 percent of the initial breaking strength of the treated coated cloth. If both fire- and mildew-resistance treatments are specified, the retained strength of the cloth shall be not less than 75 percent of the treated coated cloth (see table II).

Note 4. There shall be no indication that the oil has permeated the coated cloth.

3.4 Color, shade, grain, and finish. Color, shade, grain, and finish shall be as specified (see 6.1).

3.4.1 The color, shade, grain, and finish shall approximate standard samples when standard samples are available. When standard samples are not available, color, shade, grain, and finish shall approximate the preaward samples which have been approved by the contracting officer as conforming to the desired color, shade, grain, and finish (see 6.3).

3.5 Length. Coated cloth shall be put up in rolls as specified in PPP-P-51, except that roll length shall be not less than 30 linear yards and not more than 40 linear yards. An individual roll shall contain no more than 3 pieces of which no piece shall be less than 6 yards in length.

3.6 Marking. For identification purposes, the coated cloth shall be permanently and legibly marked on the back with a nontransferable marking material indicating the manufacturer's name or trademark and the month and year of manufacture. The marking shall be positioned 8 inches in from both selvages and shall be repeated at intervals of not more than 24 inches. The size of the letters and numerals shall be 1/2 inch.

As an alternative, the above required markings indicating the manufacturer's name or trademark, and the month and year of manufacture may be contained on each invoice to a purchaser and conform to like markings on shipping tickets which shall be attached to each roll covered by that invoice.

3.7 Workmanship. The finished coated cloth shall conform to the quality of product established by this specification. The occurrence of defects shall not exceed the acceptable quality levels (AQLs) specified in section 4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Contractor inspection responsibility. Unless otherwise specified in the contract or order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government. The Government reserves the right to perform any inspection where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Preacceptance inspection.

4.2.1 *Preproduction sample inspection.* The preproduction sample submitted in accordance with 3.1 shall be visually inspected for appearance, color, shade, grain, and finish. The samples shall be tested for physical and chemical properties in accordance with the methods shown in table IV and in 4.4.

4.3 Inspection for acceptance.

4.3.1 *Sampling for inspection and acceptance.* Sampling for inspection and acceptance shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated. For purposes of sampling, an inspection lot shall consist of all end items made with the same components and submitted for acceptance and delivery at one time.

4.3.2 *Inspection of materials and components.* In accordance with 4.1, the supplier is responsible for insuring that materials and components used in the end item were manufactured, tested, and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified, or, if none, in accordance with this specification. In the event of conflict, this specification shall govern.

4.3.2.1 *Inspection of components.* In addition to the quality assurance provisions of the subsidiary specifications, components and materials listed in 3.2.1 and 3.2.2 will be accepted on the basis of a contractor's certificate of compliance with the requirements specified for such characteristics.

4.3.3 *Inspection of the end item.*

4.3.3.1 *Examination of the end item.* The end item shall be examined for the defects listed in 4.3.3.1.1 through 4.3.3.1.4.

4.3.3.1.1 *Yard-by-yard examination.* The required yardage of each roll shall be inspected on the coated side for the defects listed herein. All defects shall be counted regardless of their proximity, one to another, except where two or more defects represent a single local condition of the cloth, in which case only one defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The sample unit for this examination shall be 1 linear yard. The sample size shall be in accordance with inspection level II of MIL-STD-105. The AQL shall be 1.5 defects per 100 units (yards). The lot size shall be expressed in units of one yard each and shall be not larger than 22,000 units. An approximate equal number of yards shall be examined from each roll selected. The number of rolls over which the sample yardage shall be distributed shall be in accordance with table III.

Defects
Any uncoated area.
Any thinly coated area evidenced by light area or window.
Any separation of coating from expanded layer or expanded layer from base cloth.
Tacky coating.
Cracked or checked coating.
Any blister or lump.
Nonuniform coating.
Any wrinkle or crease on coated surface.
Any cut, hole, tear, or coated surface scratch or abrasion.
Curled, folded, doubled, or rolled selvage.
Dirt, spot, or stain.
Width less than minimum specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

4.3.3.1.2 *Overall examination.* Each defect listed as follows shall be counted not more than once in each roll examined. The sample unit for this examination shall be one roll. The sample size (number of rolls selected as sample) for this examination and the acceptance number shall be as shown in table III.

Defects
Color not as specified.
Shade, grain, and finish do not approximate standard sample (established standard sample or approved preaward sample).
Color not uniform, i.e., mottled, blotchy, or spotted.
Shade not uniform.
Objectionable odor.
Tackiness (coating adheres to opposite surface upon unrolling).
Dimensional distortions and waviness (coated cloth does not lie uniformly flat along its entire width when no tension is applied).

TABLE III

Lot size in yards	Sample size in rolls	Acceptance No.
Up to 1,300[1]	5	0
1,301 to 3,200	7	0
3,201 to 8,000	10	0
8,001 to 22,000	15	1

[1] If a lot contains fewer than 5 rolls, each roll shall be examined.

4.3.3.1.3 *Examination for length and identification marking.* Each individual roll in the sample shall be examined for the following defects listed. The sample unit for this examination shall be one roll. The sample size and acceptance number shall be as shown in table III.

Examine	Defect
Roll for length	Length of roll more or less than specified (see 3.5).
	Length of roll less than length indicated on roll ticket.
Roll for number and length of pieces	Roll contains more pieces than permitted, and pieces are of less length than required.
Roll for gross length	Actual gross length of rolls less than the total gross yards marked on piece ticket.
Roll for identification marking	Marking not as specified.
	Marking illegible or incomplete.
Roll for identification marking (cont'd)	Marking not positioned as specified or does not appear at specified intervals.
	Size of letters and numerals varies from size specified by more than plus or minus 1/4 inch.

4.3.3.1.4 *Examination of preparation for delivery.* An examination shall be made to determine that packaging, packing, and marking requirements of section 5 are complied with. Defects shall be scored in accordance with the following list. The sample unit shall be one shipping container fully packed, selected just prior to the closing operation. Closed shipping containers shall be examined for closure defects. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL 4.0 defects per 100 units.

Examination	Defect
Marking (exterior and interior)	Omitted, incorrect, illegible, or improper size, location, sequence, or method of application.
Materials	Any nonconforming component, component missing or seriously damaged.
Workmanship	Inadequate application of components, such as: Incomplete closure of case liners, container flaps, loose strapping, inadequate stapling.
	Bulged or distorted containers.
Weight	Gross weight exceeds requirements.

4.3.3.2 *Testing of the end item.* Whenever applicable, the methods of testing specified in CCC-T-191, and those listed in table IV herein shall be followed. The requirements specified in section 3, except those for abrasion resistance and blocking apply to the average of the determinations made on a sample unit for test purposes as specified in applicable test method. For the characteristics "abrasion resistance" and "blocking" the requirement shall apply to each determination separately. The AQL for each char- The sample size shall be in accordance with acteristic shall be 4.0 defects per 100 units. inspection level S-1 of MIL-STD-105. The

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

lot size shall be expressed in units of 1 linear yard and shall not be larger than 22,000 units. The sample unit for test purposes shall be 3 yards, full width of finished coated cloth.

TABLE IV. *Instructions for testing*

Characteristic	Requirement	Test method	Number of determinations per sample unit	Results reported as numerically to nearest
Width	Table I	5020	5	1/2 inch
Gage (thickness)	Table I	Comm'l. Std. CS 273-65	—	0.001 inch
Total weight	Table I	5041	5	0.1 ounce
Breaking strength:				
Initial				
Wales	Table I	5100	5	1.0 pound
Courses	Table I	5100	5	1.0 pound
Tearing strength:				
Initial				
Wales	Table I	[1]5136	5	0.1 pound
Courses	Table I	[1]5136	5	0.1 pound
Abrasion resistance	Table I	Par. 4.4.1	3	Pass or fail
Adhesion of coating	Table I	Comm'l. Std. CS 273-65	—	0.1 pound
Resistance to accelerated weathering	Table I	Par. 4.4.2	1	Pass or fail
Hydrostatic resistance	Table I	[2]5512	5	1.0 p.s.i.
Volatility	Table I	Par. 4.4.3	2	0.1 percent
Plasticizer test:				
Activated carbon extraction	Table I	Par. 4.4.4	2	0.1 percent
Flexing	Table I	Comm'l. Std. CS 273-65[7]	—	Pass or fail
Stitch test resistance:				
Initial				
Wales	Table I	Comm'l. Std.	—	1.0 pound
Courses	Table I	CS 273-65	—	1.0 pound
Blocking	Table I	5872	3	Scale rating
Colorfastness to crocking	Table I	5651	1	Excellent, good, fair, or poor
Elongation:				
Initial				
Wales	Table I	Par. 4.4.5	1	0.1 percent
Courses	Table I	Par. 4.4.5	1	0.1 percent
Additional tests for treated coated cloth:				
Treatment (a)[1]				
Flame resistance:				
Flame time	Table II	5903T	5	1/5 sec.
Char length	Table II	5903T	5	0.1 inch
Breaking strength:				
Wales	Table II	5100	5	1.0 pound
Courses	Table II	5100	5	1.0 pound
Tearing strength:				
Wales	Table II	[1]5136	5	0.1 pound
Courses	Table II	[1]5136	5	0.1 pound
Breaking strength after accelerated aging:				
Wales	Table II	[4]5100 and 5850	5	Percent
Courses	Table II	[4]5100 and 5850	5	Percent
Cold resistance	Table I	[3]5874	1	Pass or fail

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

TABLE IV. *Instructions for testing (continued)*

Characteristic	Requirement	Test method	Number of determinations per sample unit	Results reported as numerically to nearest
Treatment (a) [2]				
Flame resistance after leaching resistance:				
Flame time	Table II	5830 and 5903T	5	1/5 sec.
Char length	Table II	5830 and 5903T	5	0.1 inch
Breaking strength:				
Wales	Table II	5100	5	1.0 pound
Courses	Table II	5100	5	1.0 pound
Tearing strength:				
Wales	Table II	[1]5136	5	0.1 pound
Courses	Table II	[1]5136	5	0.1 pound
Breaking strength after leaching resistance and accelerated aging[5]				
Wales	Table II	[4]5830 and 5850	5	Percent
Courses	Table II	[4]5830 and 5850	5	Percent
Treatment (b)				
Breaking strength after mildew resistance test:				
Wales	Table II	[6]5100 and 5762	5	Percent
Courses	Table II	[6]5100 and 5762	5	Percent
Treatment (c)				
Oil resistance	Table II	Par. 4.4.6	1	Pass or fail

[1] A 5/8-inch slit shall be used instead of 3/8 inch.
[2] The water pressure shall be applied to the coated side.
[3] Except that a 5-pound roller shall be used and the specimens shall be exposed at −20° ± 2°F. for a period of 2 hours.
[4] Except that the test shall be for a period of 7 days at 158° ± 2°F.
[5] This shall be interpreted to mean that the sample shall be leached first, then subjected to accelerated aging, and finally tested for breaking strength. The percent of change in breaking strength is the only result that need be reported.
[6] The exposure period shall be 14 days.
[7] The weight on the tension arm shall be adjusted to produce an 8-pound load on the sample.

4.4 Test methods. Results of physical tests obtained under testing conditions defined in Fed. Test Method Std. No. 601, Fed. Test Method Std. No. 406, or CCC-T-191 will be acceptable except in case of dispute. In dispute cases, tests shall be conducted with both the specimen and test apparatus under standard conditions as defined in CCC-T-191.

4.4.1 *Abrasion.* The resistance to abrasion shall be determined as specified in method 5304 of CCC-T-191, with the following exceptions:

(a) The long dimension of the specimen shall be parallel to the warp direction of the sample.
(b) The tension on the specimen shall be 6 pounds.
(c) The abrader shall be silicon-carbide cloth 240 grit.
(d) The coated cloth shall be subject to 500 double rubs; however, the abradant shall be changed after 250 double rubs.
(e) Three specimens shall be tested from each sample unit.
(f) Results of this test shall be reported as pass or fail as indicated in table I, using the criteria specified in footnote[1] of table I.

Note: Prior to the test, the uncoated side of all test specimens (underside) shall be examined and discarded if base cloth defects which may affect test results are discovered.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

4.4.2 *Accelerated weathering.* The test shall be performed with filters for a period of 120 hours on a coated cloth specimen 3 by 6 inches minimum with the coated side exposed as specified in method 5804 of CCC-T-191 except as follows:

(a) Delete from title "(National Weathering Unit)."

(b) Water spray nozzles shall be mounted horizontally (the water spray assembled vertically) in the test chamber inside the specimen rack and so spaced that the water shall strike the specimen evenly over its entire length in the form of a fine spray in sufficient volume to cover the specimen immediately on impact. The apparatus shall be so operated that the specimen is exposed to successive cycles of 102 minutes of light without spray, and 18 minutes of light with spray.

(c) The rack shall rotate about the arc at a uniform speed of one revolution per minute.

(d) The pressure of the water entering the spray shall be 12-18 p.s.i., inclusive.

(e) The black panel thermometer shall be mounted on the test panel rack and readings taken at a point where maximum heat is developed and where water spray is not striking the panel. The black panel temperature at the exposure plane of the specimen rack shall be 155° ± 10°F. when filters are in place and 175° ± 10°F. when filters are removed.

(f) Note: Attention is called to manufacturers who own equipment which operates at one cycle in two hours. This equipment may continue to be used. However, the one cycle per minute shall be the standard procedure in the event of dispute, and the laboratory reports shall state the procedure used.

4.4.3 *Volatility.* The coated cloth shall be conditioned for at least 24 hours and a 2- by 8-inch specimen cut out and weighed. The specimen shall be placed in a ventilated circulating hot air oven and held for 48 hours at 220° ± 2°F., cooled, conditioned for at least 24 hours, and again weighed. The loss in weight shall be calculated.

4.4.4 *Plasticizer test.*

4.4.4.1 *Activated carbon extraction.* Place 120 milliliters (ml.) of 6- to 14-mesh activated carbon in bottom of 1-pint wide-mouth jar. Duplicate 2- by 2-inch preconditioned specimens shall be placed in the jar, one on top of a second layer of 120 ml. of activated carbon which is covered by a third layer of 120 ml. of activated carbon. Cap jar and place in a convection oven at 220° ± 5°F. for 24 hours. Allow jar to cool 15 minutes at 78°F. Remove specimens and brush free of carbon, recondition, weigh, and compute percentage loss in weight based on the total weight of coated cloth.

4.4.5 *Elongation.* The elongation test shall be conducted in the following manner:

(a) Cut a 3- by 9-inch specimen from the center section of the coated cloth and mark off a 3-inch section across the center of the sample.

(b) Clamp a 27-lb. weight to one end of the 9-inch dimension and suspend vertically for 10 minutes.

(c) Measure the increase in length of the 3-inch section and calculate as percent of elongation.

Note: If the first specimen tested does not fall within the specification limits, three additional specimens from the sample unit shall be tested. The percent elongation of a sample unit shall then be computed as the average value obtained from testing the four specimens.

4.4.6 *Oil resistance.* An 8- by 8-inch specimen shall be placed on a wood frame. The inside dimension of the wood frame shall be 6 by 6 by 1 inch. The coated cloth shall be inserted with the coated side up. The specimen shall be forced into the frame by a wooden block 5-3/4 by 5-3/4 by 3/4 inch with

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

rounded corners to form a basin of uniform depth. The edges of the specimen shall be tacked to the frame and the block removed. Oil conforming to type IV of TT-S-735 shall be poured into the basin for four hours, the bottom of the specimen forming the basin shall feel dry and there shall be no indication that the oil has permeated the coated cloth.

5. PREPARATION FOR DELIVERY

(Applicable only when purchased by the Government.)

5.1 Packaging. Packaging shall be level A, B, or C, as specified (see 6.1 and 6.4).

5.1.1 *Levels A, B, and C.* The coated cloth shall be put up in rolls only and packaged in accordance with the applicable requirements for class 3 fabrics of PPP-P-51. The coated cloth shall be rolled with the minimum tension practicable to produce a "soft" roll. Each roll shall be secured from unwinding with pressure-sensitive tape.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.1 and 6.4).

5.2.1 *Levels A, B, and C.* The coated cloth shall be packed in accordance with the applicable requirements of PPP-P-51, except that packing in bias-sewn tubing or presewn bags shall not be permitted. When two rolls are packed per container, the rolls shall be placed two in width and one in depth. When four rolls are packed, an A-flute double-faced corrugated fiberboard separator pad having a minimum bursting strength of 200 p.s.i. conforming to type CF, class domestic of PPP-B-636 and measuring 1/4 inch less than the inside length and width dimensions of the shipping container shall be placed between each layer of rolls.

5.3 Marking. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with PPP-P-51.

5.3.1 *Precautionary marking.* In addition to the marking specified, the following precautionary marking, in letters not less than 3/4 inch in height, shall appear at least on one side and wherever practicable on two sides of each shipping container.

KEEP COOL AND DRY
DO NOT STAND ON END

6. NOTES

6.1 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(*a*) Title, number, and date of this specification.
(*b*) Class and treatment (see 1.2.1).
(*c*) Whether preproduction sample is required (see 3.1).
(*d*) Color, shade, grain, and finish (see 3.4).
(*e*) Contractor inspection responsibility (see 4.1).
(*f*) Preaward sample requirements (6.3.1).
(*g*) Selection of applicable levels of packaging and packing (5.1 and 5.2).

6.2 Treatments. Fire-resistant, mildew-resistant, and oil-resistant treated coated cloths are intended for use in special installations, in unusually damp climates, or where exposed to solvents and oil, respectively.

6.3 Samples. For access to standard shade samples, address the procuring office issuing the invitation for bids (see 3.4).

6.3.1 *Preaward samples.* The procuring activity should require the submission of preaward samples with invitations to bid when standard samples are not available for use in determining conformance with shade, grain, and finish requirements. The contracting officer should arrange for the evaluation of the preaward samples, which upon approval by the contracting officer, should be used as standards for shade, grain, and finish.

6.4 In the preparation of contracts or orders, it must be noted that various options,

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.

choices, and alternatives as indicated in PPP-P-51 may be exercised in the preparation for delivery of coated cloth.

6.5 Any questions raised regarding toxicity should be referred by the procuring agency, through channels, to the departmental medical authority. In the case of Army procurement, the Surgeon General will act as advisor to the procuring agency.

6.6 **Transportation descriptions.** Transportation descriptions and minimum weights applicable to this commodity are:

Rail:
Leather, artificial, not otherwise indexed by name.
Carload minimum weight 30,000 pounds.

Motor:
Cloth, cotton, coated with plastic.
Truckload minimum weight 30,000 pounds subject to Rule 115, National Motor Freight Classification.

6.7 Level B packaging and packing should be used by ordering agencies only when shipment is known to be made to a holding supply depot or warehouse from which partial shipments will be made to ultimate consumers.

MILITARY CUSTODIANS:

Review activities:
Army—None
Navy—SA
Air Force—None

User activities:
Army—None
Navy—SH
Air Force—None

Review and user information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current Federal Supply Classification Listing of DOD Standardization Documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:31Z
Check the source to verify that this is the current version before use.