CCC-B-606
May 27, 1966

SUPERSEDING
Fed. Spec. CCC-C-606
May 23, 1941

FEDERAL SPECIFICATION

BATTING, COTTON; NONABSORBENT, UNBLEACHED

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the requirements for unbleached, nonabsorbent cotton batting.

1.2 Classification.

1.2.1 The cotton batting shall be of one type and of the following grades (see 6.2):

Grade A—50-percent	3/4-inch fibers
Grade B—50-percent	1/2-inch fibers

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

CCC-T-191—Textile Test Methods.
PPP-B-636—Box, Fiberboard.

Federal Standard:

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL-B-43291—Boxes; Fiberboard; Corrugated, Double-Wall, Weather Resistant.

Military Standards:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publication. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

Rules and Regulations Under the Textile Fiber Products Identification Act.

(Copies may be obtained without charge from the Federal Trade Commission, Washington, D. C., 20580.)

3. REQUIREMENTS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

3.1 Materials.

3.1.1 *Grade A.* Shall be unbleached, made from new cotton.

3.1.2 *Grade B.* Shall be unbleached, made from new or reworked cotton.

3.1.3 *Staple length.*

3.1.3.1 Grade A shall contain fibers, of which at least 50 percent shall have a staple length of not less than 3/4 inch (see 4.2.1).

3.1.3.2 Grade B shall contain fibers, of which at least 50 percent shall have a staple length of not less than 1/2 inch (see 4.2.1).

3.1.4 *Color.* The color shall be white or cream. Definite yellow, brown, or other colors are not acceptable.

3.1.5 *Absorbency.* The cotton shall be non-absorbent and the cotton batting specimen, when tested as specified in 4.3, shall not submerge within 15 minutes.

3.1.6 *Ash.* The ash residue shall be not more than 2 percent when tested as specified in 4.3.

3.2 Size and weight. Unless otherwise specified (see 6.2), the batting shall be furnished in a continuous layer 12 ± 1/2 inch wide and 9 to 12 feet long. The net weight of the layer of batting, exclusive of wrapping materials, shall be not less than 15 ounces (see 4.2.2 and 4.2.3).

3.3 Batting. The batting shall be cleaned and garnetted so as to produce unbroken sheets that have an even thickness throughout the batt.

3.4 Put-up. Each layer of batting shall be furnished in rolls. A blue or white lightweight paper shall run the entire length of the layer and to within 1 inch of each side. The batting and paper shall be rolled together tightly and evenly and put up as specified in 5.1 and 5.2.

3.5 Workmanship. The finished batting shall conform to the quality established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels (AQLs).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Inspection. Sampling for inspection shall be in accordance with MIL-STD-105, except where otherwise indicated.

4.2.1 *Component and material inspection.* In accordance with 4.1, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase documents. In addition, the supplier shall furnish a certificate of compliance for the material requirements of 3.1.1, 3.1.2, and 3.1.3.

4.2.2 *Examination of the end item.* The sample unit for this examination shall be one roll. The sample shall be unrolled and inspected on both sides. The inspection level for determining sample size shall be level I and the number of containers from which the sample is to be selected shall be in accordance with table I. An approximate equal number of rolls shall be examined from each container. The AQL shall be 4 percent defective. The lot size shall be expressed in units of one roll each. The required number of rolls shall be inspected for visual defects listed as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

Hole, cut, or tear over 1/2 inch in any dimension.
Overall uncleanliness: (appreciably dirty, spotted, stained, embedded foreign matter, mildewed, etc.).
Excessive lumps, nibs, shell, unshredded yarn.
Excessive loose fibers or lint.
Color of cotton other than white or cream.
Not uniform thickness or not tightly or evenly rolled.
Not a continuous layer.
Width or length not as specified.
Not marked in accordance with the Textile Fiber Products Identification Act.

TABLE I. *Sample size distribution*

Lot size in rolls	Number of containers
280 or less	2
281 up to and including 1200	3
1201 up to and including 3200	5
3201 up to and including 10,000	8
10,001 up to and including 35,000	13
35,001 and over	20

4.2.3 *Examination for weight.* The sample unit for this examination shall be 5 rolls and the sample size shall be one sample unit regardless of lot size. The wrappings shall be removed from each roll. Each layer of batting shall be allowed to reach equilibrium under Standard Conditions as defined in section 4 of CCC-T-191. After reaching equilibrium, each layer shall be individually weighed, the results averaged, and reported to the nearest 1/4 ounce. The lot shall be unacceptable if the average is less than the minimum specified.

4.3 Testing of the end item. The methods of testing specified in CCC-T-191, wherever applicable, and as listed in table II shall be followed. The physical and chemical values specified in section 3, except where otherwise specified, apply to the results of the determinations made on the sample unit for test methods. The sample unit for testing shall be one roll. The sample size (number of sample units) shall be in accordance with the following:

Lot size	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

The lot shall be unacceptable if one or more sample units fail to meet any requirement specified.

TABLE II. *Tests*

Characteristics	Requirement paragraph	Test method
Absorbency	3.1.5	4.3.1
Ash	3.1.6	2611

4.3.1 *Absorbency.* The specimen for testing shall be a 10 gram portion of the cotton folded into a square approximately 4 inches on a side. The specimen shall be held parallel to, and almost in contact with, the surface of distilled water at 25° ± 2°C., then dropped lightly upon the water. One specimen shall be taken, and the time required for the specimen to completely submerge shall be recorded to the nearest whole second. Five determinations shall be made.

4.3.2 *Examination of preparation for delivery requirements.* Unless otherwise specified, an examination shall be made to determine that packaging, packing, and marking requirements of section 5 are complied with. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery. The lot shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per 100 units.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; improper size, location, sequence, or method of application.
Materials	Any component missing. Any component damaged, affecting serviceability.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, improper taping, loose strapping, or inadequate stapling. Bulging or distortion of containers.
Weight	Weight of contents of shipping container is more or less than required.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, or C, as specified (see 6.2).

5.1.1 *Level A.* Batting, put up as specified, shall be completely and securely wrapped in minimum 30 pound basis weight blue or white paper. Each wrapped roll shall be secured with adhesive, label, sticker, or gummed or pressure-sensitive tape (see 6.2.1).

5.1.2 *Level C.* Batting shall be packaged to afford adequate protection against damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets this requirement.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 *Level A.* Batting, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, V3c or V3s of PPP-B-636. Alternatively, shipping containers shall conform to style RSC, V15c of MIL-B-43291. Each fiberboard shipping container shall be waterproofed in accordance with the appendix of PPP-B-636. Each shipping container shall be closed and reinforced with flat steel strapping or tape banding, in accordance with the appendix of the applicable container specification. Net weight of the contents of each shipping container shall not exceed 65 pounds.

5.2.2 *Level B.* Batting, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF or SF, class domestic, variety SW, grade 275 of PPP-B-636. Each shipping container shall be closed in accordance with method II of the appendix of the container specification. Net weight of the contents of each shipping container shall not exceed 65 pounds.

5.2.2.1 When specified, shipping containers shall be fabricated from V3c or V3s fiberboard of PPP-B-636 (see 6.2).

5.2.3 *Level C.* Batting, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with rules or regulations of carriers applicable to the mode of transportation

5.3 Marking.

5.3.1 *Civil agencies.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 *Military requirements.* In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The nonabsorbent cotton batting covered herein is to be used for wadding.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(*a*) Title, number, and date of this specification.
(*b*) Grade (see 1.2.1).
(*c*) Size and weight if other than specified (see 3.2).
(*d*) Packaging examination if other than specified (see 4.3.2).
(*e*) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(*f*) Whether V-board shipping containers are required for level B shipments (see 5.2.2.1).

6.2.1 The method of packaging referred to in 5.1.1 is similar to method III of MIL-P-116.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

MILITARY CUSTODIANS:

Army—GL
Air Force—67

Review activities:

Army—MD
Air Force—67

User activity:

Air Force—26

Preparing activity:

Army—GL

Review and user information is current as of the date of this document. For future coordination of changes to this document draft circulation should be based on the information in the current Federal Supply Classification Listing of DOD Standardization Documents.

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 5 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

"to detach this form, cut along this line"

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity.

SPECIFICATION

Batting, Cotton; Nonabsorbent, Unbleached - CCC-B-606a

ORGANIZATION	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT
		$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

DD FORM 1 OCT 64 1426

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01762

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRE-SS
Natick, Massachusetts 01762

FOLD

"to detach this form, cut along this line"

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.