CCC-C-448a
MAY 26, 1959
SUPERSEDING
Int. Fed. Spec. CCC–C–00448
April 27, 1959
(See Section 6.)

FEDERAL SPECIFICATION

# CLOTH, COTTON, SEERSUCKER

*This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.*

## 1. SCOPE AND CLASSIFICATION

**1.1 Scope.**—This specification covers the requirements for cloth, cotton, seersucker.

**1.2 Classification.**

**1.2.1** *Types and classes.*—The cloth, cotton, seersucker covered by this specification shall be of the following types and classes (see 6.2):

Type I.—Narrow stripe.

Class 1.—82 by 86 texture.

Type II.—Medium stripe.

Class 1.—112 by 80 texture.

Class 2.—80 by 80 texture.

Type III.—Stripe pattern effect.

Class 1.—280[1] by 72 texture.

[1] Per repeat (approx. 2⅝ inches).

## 2. APPLICABLE SPECIFICATIONS AND STANDARDS

**2.1** The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification:

*Federal Specifications:*

CCC–T–191—Textile Test Methods.

PPP–P–51 — Packaging, Packing, and Marking of Textile Fabrics (Woolens, Worsteds, Cottons, Silks, and Synthetics).

*Federal Standards:*

Fed. Std. No. 4—Glossary of Fabric Imperfections.

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.

Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

481469/59/315



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

*Military Standard:*

MIL–STD–105 — Sampling Procedures and Tables for Inspection by Attributes and Appendix.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

## 3. REQUIREMENTS

**3.1 Standard sample.** — Unless otherwise specified, the cloth shall be equal to the standard sample in all respects not specifically covered by this specification (see 6.3).

**3.2 Material**

3.2.1 *Cotton.*—The cotton shall be of suitable length of staple and grade to meet the requirements of this specification.

3.2.2 *Yarn.*—The cotton used in the manufacture of the yarn shall be thoroughly cleaned, carded, combed, drawn, and evenly spun into singles yarns except that the slack beam warp yarn for the type I, class 1 cloth and tight beam warp yarn for the type II, class 2 cloth shall be two-ply.

**3.3 Color.**—The color shall be as specified and shall match an approved standard shade (see 6.2). The use of sulfur dyes or dyes containing sulfur compounds capable of oxidation to sulfuric acid are prohibited (see 4.4.1).

3.3.1 *Matching.*—The color shall match the approved standard shade under natural (north sky) daylight or artificial daylight having a color temperature of 7500° Kelvin and shall be a good approximation to the standard shade under incandescent lamplight at 2800° Kelvin.

3.3.2 *Colorfastness.*

3.3.2.1 *Rating per standard sample.*—The finished cloth shall show colorfastness to laundering, bleaching, perspiration, crocking, and light equal to or better than the standard sample when tested as specified in 4.4.

3.3.2.2 *Rating per no standard sample.*—The finished cloth shall show good colorfastness to laundering, bleaching, perspiration, crocking, and light when tested as specified in 4.4 (see 6.2).

**3.4 Physical requirements.**—The finished fabric shall conform to the requirements shown in table I, when tested as specified in 4.4.

3.4.1 *Weave.*

3.4.1.1 *Types I and III.*—The weave shall be plain.

TABLE I.—*Physical requirements*

| Type | Class | Weight (ounces per square yard) minimum | Texture (yarns per inch) minimum | | Breaking strength (grab method) minimum | |
|---|---|---|---|---|---|---|
| | | | Warp | Filling | Warp | Filling |
| I | 1 | 4.0 | 82 | 86 | 24 | 45 |
| II | 1 | 4.0 | 112 | 80 | 30 | 40 |
| II | 2 | 4.0 | 80 | 80 | 30 | 40 |
| III | 1 | 4.0 | 280[1] | 72 | 25 | 30 |

[1] Per repeat (see 3.4.3.3).



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

3.4.1.2 *Type II.*—The weave shall be plain with the slack beam warp weaving two ends as one.

3.4.2 *Slack beam take-up.*—The minimum slack beam take-up for all types and classes shall be 40 percent, when tested as specified in 4.4.

3.4.3 *Stripes or pattern effect.*

3.4.3.1 *Type I, class 1.*—The stripe effect of the type I cloth shall be produced by using two warp beams, one tight and one slack. The color of the tight beam warp yarn shall be as specified. The slack beam warp yarns shall be natural or bleached. The two warps shall alternate in sections of tight and slack ends and each color pattern repeat shall be as follows:

Tight – 6
Slack – 4

3.4.3.2 *Type II, classes 1 and 2.*—The stripe effect of the type II cloth shall be produced by using two warp beams, one tight and one slack. The color of the tight beam warp yarn shall be as specified. The slack beam warp yarn shall be natural or bleached. The two warps shall alternate in sections of tight and slack ends and each color pattern repeat shall be as follows:

Tight – 10
Slack – 12

The reading plan shall produce a concentration of slack beam warp ends double that of the tight beam ends.

3.4.3.3 *Type III, class 1.*—The pattern effect of the type III, class 1 cloth shall be produced by using two warp beams, one tight and one slack. The color of the slack beam warp yarn shall be as specified (see 6.2). The tight beam warp yarn shall be natural or bleached. The two warps shall alternate in sections of tight and slack ends and each color pattern repeat shall be as follows:

| | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|
| Tight beam | 16 | 16 | 16 | 16 | 16 | 8 | 8 | 8 | 8 |
| Slack beam | 12 | 12 | 12 | 12 | 24 | 24 | 24 | 24 | 24 |

The warp reeding plans shall produce finished stripes of the following widths:

Colored yarn 24 ends — $\frac{3}{16} \pm \frac{1}{32}$ inch
Colored yarn 12 ends — $\frac{3}{32} \pm \frac{1}{32}$ inch
Bleached yarn 8 ends — $\frac{3}{32} \pm \frac{1}{32}$ inch
Bleached yarn 16 ends — $\frac{3}{16} \pm \frac{1}{32}$ inch

The total width of each 280 end repeat shall be $2\frac{5}{8} \pm \frac{1}{8}$ inch. The repeats of the patterns shall be balanced between the selvages.

3.5 **Width.**—The width shall be as specified and shall be the minimum width exclusive of selvage (see 6.2).

3.6 **Finish.**—The cloth shall be closely singed, desized, and bleached. When bleached warp and filling yarns are used for the undyed yarns, piece bleaching is not required. Residual size, finishing, or other nonfibrous material shall not exceed 2 percent when tested as specified in 4.4.

3.7 **Shrinkage.**—The cloth shall be preshrunk and shall not shrink more than 4 percent in the direction of the warp nor more than 2 percent in the direction of the filling when tested as specified in 4.4. The preshrinking process shall not be identified on the cloth, the ticket or on the package.

3.8 **Length.** — Unless otherwise specified, the cloth shall be in one continuous piece of not less than 50 yards (see 6.2).

3.9 **Ticket.**—Each piece or roll shall have an identification ticket conforming to the requirements of Federal Specification PPP–P–51 attached to the selvage at the inner end of the cloth.

3.10 **Workmanship.**—The cloth shall conform to the quality and grade of product established by this specification, and the occurrence of defects shall not exceed the levels



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

TABLE II.—*Sampling for inspection*

| Number of yards in lot | Number of rolls or bolts in the inspection sample | Number of yards in the inspection sample[1] | Acceptance number—total, defects | Rejection number—total, defects | Acceptance number—major, defects | Rejection number—major, defectives |
|---|---|---|---|---|---|---|
| 300 and under | 2 | 35 | 5 | 6 | 2 | 3 |
| 301 to 500 | 3 | 50 | 6 | 7 | 3 | 4 |
| 501 to 800 | 5 | 75 | 9 | 10 | 4 | 5 |
| 801 to 1,300 | 7 | 110 | 12 | 13 | 6 | 7 |
| 1,301 to 3,200 | 10 | 150 | 17 | 18 | 8 | 9 |
| 3,201 to 8,000 | 15 | 225 | 24 | 25 | 11 | 12 |
| 8,001 to 22,000 | 20 | 300 | 32 | 33 | 14 | 15 |
| 22,001 to 110,000 | 30 | 450 | 43 | 44 | 20 | 21 |
| 110,001 to 550,000 | 40 | 750 | 68 | 69 | 31 | 32 |
| 550,001 and over | 60 | 1500 | 124 | 125 | 56 | 57 |

[1] Yards in the inspection sample shall be divided equally among sample rolls of cloth and that number of yards shall be examined from each sample roll.

set by the applicable acceptable quality levels (see 4.3.1.1.1).

## 4. SAMPLING, INSPECTION, AND TEST PROCEDURES

**4.1 General.**—The quality assurance provisions contained in this section are applicable to inspection. Quality assurance provisions for components or materials described shall be in accordance with this specification and with subsidiary specifications referred to herein to the extent applicable, except that this specification shall govern in the event of conflict.

4.1.1 *Contractor's inspection responsibility.*—Unless otherwise specified herein, the supplier is responsible for the performance of all inspection requirements prior to submission for Government inspection and acceptance. Except as otherwise specified, the supplier may utilize his own facilities or any other commercial laboratory acceptable to the Government. Inspection records of the examination and tests shall be kept complete and made available to the Government as specified in the contract or order.

**4.2 Civil agencies.**—Civil agencies may use sampling, inspection, and test procedures outlined under 4.2 when desirable. When procedures outlined under 4.2 are not deemed suitable, the procedures specified under civil agencies paragraphs shall be followed.

4.2.1 *Sampling.*

4.2.1.1 *Inspection lot.*—Unless otherwise specified in the invitation for bids, all cloth of one type submitted at one time shall be considered a lot for purposes of inspection and tests.

4.2.1.2 *Sampling for inspection.*—A random sample of cloth shall be taken from each lot in accordance with table II.

4.2.1.3 *Sampling for tests.*—Random samples for tests shall be taken from each inspection lot in accordance with table III.

4.2.2 *Yard-by-yard inspection.*—Each of the samples selected in accordance with table II, shall be visually inspected and defects classified in accordance with 4.3.1.1. The maximum number of defects acceptable shall be as specified in table II.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

TABLE III.—*Sampling for tests*

| Number of rolls or bolts in lot | Number of rolls or bolts in test sample[1] | Acceptance number (defects) | Rejection number (defects) |
|---|---|---|---|
| 8 and under | 2 | 0 | 1 |
| 9 to 15 | 3 | 0 | 1 |
| 16 to 40 | 4 | 0 | 1 |
| 41 and over | 5 | 0 | 1 |

[1] One unit of product (test sample) at least 2 yards long and the full width of the cloth shall be taken from each sample roll.

4.2.3 *Overall inspection and inspection for length.* — Overall inspection and inspection for length shall be as specified in 4.3.1.2 and 4.3.1.3, respectively. Sample size and the maximum number of defects acceptable shall be as specified in table IV.

4.2.4 *Tests.*—Samples selected for tests in accordance with table III shall be tested in accordance with the applicable methods of Federal Specification CCC–T–191 as listed in table V of this specification. The physical and chemical values specified in section 3 of this specification apply to the average of the determinations made on a unit of product for test purposes as specified in applicable test methods. The unit of product shall be 2 continuous yards, full width of finished cloth. The number of defects acceptable shall be as specified in table III.

4.2.5 *Compliance criteria.*

4.2.5.1 *Inspection.*—Any piece in the sample for inspection, failing to conform to the requirements for which the inspection was made shall be considered defective. If the number of defective pieces in the sample exceeds the acceptance number for that sample, the entire lot from which the sample was taken shall be considered to have failed to meet the requirements of this specification.

4.2.5.2 *Tests.*—Any piece in the sample for tests, failing to conform to the requirements for which tests were made shall be considered defective. If the number of defective pieces in the sample exceeds the acceptance number for that sample, the entire lot from which the sample was taken shall be considered to have failed to meet the requirements of this specification.

**4.3 Military inspection for acceptance.**—Inspection shall be in accordance with Military Standard MIL–STD–105 and Appendix except where otherwise indicated.

4.3.1 *Inspection of the end item.*

4.3.1.1 *Examination of the end item.*—The cloth shall be examined to determine conformance with the requirements of this specification. Defects found during this examination shall be classified in accordance with 4.3.1.1.1, 4.3.1.2 and 4.3.1.3.

4.3.1.1.1 *Yard-by-yard examination.*—The required yardage of each piece shall be inspected on the face and visual defects classified as listed below. All defects found shall be counted regardless of their proximity one to another, except where two or more defects represent a single local condition of the cloth, in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warp-wise yard or fraction thereof in which it occurs. The unit of product for this examination shall be one linear yard. The inspection level shall be level II, table III of Military Standard MIL–STD–105. The acceptable quality levels (AQL's) shall be 2.5 major and 6.5 total defects (major and minor combined) per 100 units (yards). The lot size shall be expressed in units of 1 yard each. The number of pieces from which the sample is to be selected shall be in accordance with table IV. An approximate equal number of yards shall be examined from each piece in the sample.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

| Glossary No. of Fed. Std. No. 4 | Defects | Classification | |
|---|---|---|---|
| | | Major | Minor |
| 79 | Abrasion mark: | | |
| | Resulting in a thin or weak place | X | |
| | Clearly visible* but not resulting in a weak place | | X |
| 11, 33 | Broken or missing yarns: | | |
| | Three or more contiguous regardless of length, two contiguous 2 inches or more in length | X | |
| | Two contiguous less than 2 inches in length, or single more than 4 inches missing | | X |
| 1, 2 | Coarse or heavy filling bar—clearly visible* | X | |
| 55, 56, 90, 91, 92 | Cut, hole or tear (Including selvage)—Any | X | |
| 9 | Fine or light filling bar, light place—Clearly visible* | X | |
| 13, 34 | Floats or Skips: | | |
| | Multiple ½ inch or more in combined warp and filling directions | X | |
| | Multiple less than ½ inch in combined directions, or single 2 inches or more in length | X | |
| 35 | Hitchback: | | |
| | Resulting in thin area or weak spot ½ inch or more in combined directions | X | |
| | Clearly visible* but not resulting in a weak spot | | X |
| 3, 5 | Jerked-in or sloughed-off filling: | | |
| | Two or more extra yarns in the shed | | X |
| 10 | Mispick: | | |
| | Resulting in clearly visible double pick or harness skips | | X |
| 14 | Mixed filling or shade bar— | | |
| | Clearly visible* | X | |
| 41 | Reed Mark: | | |
| | Resulting in clearly visible* warp-wise separation 9 in. or longer, and distinctly wider than normal | | X |
| 37 | Tight end: | | |
| | Occurring in the slack warp and clearly noticeable or any slack section having noticeable less take-up than other unaffected slack sections | | X |
| 5, 27, 77 | Slub, slug or gout: | | |
| | More than three times the thickness of normal yarn, 1 inch or more in length | X | |
| | Less than 1 inch in length and clearly visible* | | X |
| 78 | Smash—Any | X | |
| 69, 70, 74, 75, 76 | Spot, stain or streak: | | |
| | Clearly visible* extending 1 inch or more in combined directions | X | |
| | Clearly visible* but extending less than 1 inch in combined directions | | X |
| | Width less than specified | | X |
| | Either selvage missing | | X |

* Clearly visible at normal inspection distance (approx. 3 feet)

4.3.1.2 *Overall examination.*—Each defect listed shall be counted not more than once in each piece examined. The unit of product for this examination shall be one piece. The sample size (number of pieces selected as sample) for this examination and the number of defects acceptable shall be as shown in table IV.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

*Defects*

Overall uncleanness.
Finish not equal to standard sample.
Incorrect pattern, i.e., color arrangement or width of stripes not as specified.
Off shade, not within established tolerances.
Uneven weaving throughout.
Creped seersucker stripes not pronounced, not equal to standard sample.
Shaded end to end, side to side, side to center, or throughout piece.
Cloudy, streaky or mottled throughout piece.
Pattern not centered against both selvages as specified.
Selvage beaded, rolled, folded or slack, continuously or intermittently for more than half the length of the piece.

TABLE IV.—*Sample size and acceptable defects*

| Lot sizes in yards | Sample size in pieces | Acceptance number |
|---|---|---|
| Up to 1300[1] | 3 | 0 |
| 1301 to 3200 | 5 | 0 |
| 3201 to 8000 | 7 | 0 |
| 8001 to 22,000 | 10 | 0 |
| 22,001 to 110,000 | 15 | 1 |
| 110,001 to 550,000 | 25 | 2 |

[1] If lot contains fewer than 3 pieces, each piece in the lot shall be examined.

4.3.1.3 *Examination for length.*

4.3.1.3.1 *Examination for length of individual pieces.*—The pieces shall be examined for gross length. Any gross length found to be less than the specified minimum length or more than 2 yards below the gross length marked on the piece ticket shall be considered as a defect with respect to length. The unit of product for this examination shall be one piece. The number of pieces selected as sample (sample size) for this examination and the number of defects acceptable shall be in accordance with table IV.

4.3.1.3.2 *Total yardage in sample.*—The lot shall be unacceptable if the total of the actual gross length of pieces in the sample is less than the total of the gross lengths marked on the piece tickets. The pieces examined shall be those selected for examination for length of individual pieces.

**4.4 Testing of the end item.**—The methods of testing specified in Federal Specification CCC–T–191, wherever applicable, and as listed in table V and 4.1.1, shall be followed. The physical and chemical values specified in section 3 apply to the average of the determinations made on a unit of product for test purposes as specified in the applicable test method. The unit of product shall be 3 continuous yards, full width of the finished cloth. For each characteristic the acceptable quality level shall be 4.0 test failures per 100 units (yards), and the inspection level shall be level L–1, table VII, of Appendix to Military Standard MIL–STD–105. The lot size shall be expressed in terms of 1 yard each.

4.4.1 *Test for sulfur dyes.*—Sulfur dyes are determined by tests for available sulfur.

4.4.1.1 *Procedure.*—Dissolve 100 grams of stannous chloride crystals in 100 ml. of hydrochloric acid (35 percent concentration) and add 50 ml. of distilled water. To preclude interference in dye identification, sample first shall be boiled in distilled water to remove any trace of chemical used in the dyeing process. One to 1.5 grams of the finished material, cut into small pieces, shall be used for the test. Place the sample in a test tube of suitable size and cover with the stannous chloride solution. Place a filter paper which has been moistened with one drop of lead acetate solution (made by dissolving 5 grams of reagent grade lead acetate to 100 cc. of distilled water; add a drop of glacial acetic acid to clear up if cloudy), over the mouth of the test tube. Heat slowly over a low flame until the solution is boiling. Solution shall not be boiled for more than 10 to 15 seconds as prolonged boiling will reduce the sensitivity of the test. A brown to black stain appearing on the paper indicates the presence of sulfur.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

TABLE V.—*Test methods*

| Characteristic | Requirement reference | Test method |
|---|---|---|
| Weave | 3.4.1 | Visual |
| Yarn ply | 3.2.2 | Visual |
| Yarns per inch | Table I | 5050 |
| Weight, oz. / sq. yd. | Table I | 5041 |
| Breaking strength | Table I | 5100 |
| Colorfastness to: | | |
| Light[1] | 3.3.2 | 5660 |
| Laundering | 3.3.2 | 5610 |
| Bleaching | 3.3.2 | 5600 |
| Perspiration[2] | 3.3.2 | 5680 or 5682 |
| Crocking | 3.3.2 | 5650 |
| Take-up (percent) | 3.4.2 | 4110[3] |
| Warp pattern | 3.4.3.1 | Visual |
| | 3.4.3.2 | Visual |
| | 3.4.3.3 | Visual |
| Shrinkage in laundering | 3.7 | 5550 |
| Nonfibrous materials | 3.6 | 2611 |
| Presence of sulfur dyes | 3.3 | Par. 4.4.1 |

[1] In the event of a dispute resulting from the test method 5660, or as a result of suspected anomalous behavior of certain dye type or formulations, the contracting officer may authorize the exposure to natural light in accordance with method 5662.

[2] The transfer cloth shall consist of a warp of Orlon 81 and a 6-fiber filling of equal bars of wool, spun nylon, spun rayon, spun silk, spun acetate and bleached cotton. Each 6-fiber repeat shall measure approximately 2 inches and shall be separated by a waste filling stripe.

[3] The following changes shall be incorporated in the test method:

*a.* Substitute the word "take-up" wherever the word "crimp" appears.

*b.* The test specimen shall be a puckered warp yarn removed from a 14-inch length of cloth.

*c.* Delete the formula for percent take-up and substitute as follows:

$$\text{Take up (percent)} = \frac{L - 10}{L} \times 100$$

L = Total distance between marks under tension.

## 5. PREPARATION FOR DELIVERY

Federal Standard No. 102 shall be referred to for definitions and applications of the various levels of packaging protection for supplies and equipment (for civil agencies only).

**5.1 Packaging.**—Packaging shall be level A, B, or C as specified (see 6.2 and 6.2.1).

5.1.1 *Level A, B, and C.*—The cloth shall be packaged in accordance with the applicable requirements for class 3 fabrics of Federal Specification PPP–P–51.

**5.2 Packing.**—Packing shall be level A, B, or C as specified (see 6.2 and 6.2.1).

5.2.1 *Levels A, B, and C.*—The cloth shall be packed in accordance with the applicable requirements of Federal Specification PPP–P–51.

**5.3 Marking.**

5.3.1 *Civil agencies.*—In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with the requirements of Federal Standard No. 123.

5.3.2 *Military agencies.*—In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the requirements of Federal Specification PPP–P–51.

## 6. NOTES

**6.1 Intended use.**—The cloth covered by this specification is intended for use in clothing items.

**6.2 Ordering data.** — Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

*a.* Title, number, and date of this specification.

*b.* Type and class of cloth required (see 1.2).

*c.* Color of cloth required (see 3.3).

*d.* Colorfastness, requirement and evaluation if other than specified. (See 3.3.2.)



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

*e.* Width of cloth required (see 3.5).

*f.* Length of roll if other than 50 yds. minimum (see 3.8).

*g.* Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.2.1 In the preparation of contracts or orders, it must be noted that various options, choices, and alternatives, as indicated in Federal Specification PPP–P–51, may be exercised in the preparation for delivery of cloth.

**6.3 Standard sample.**—For access to standard sample, address the procuring office issuing the invitation for bids.

6.4 This specification includes the requirements of Military Specification MIL–C–343A, dated 31 July 1951. Comparison of types and classes as pertains to Military Specification MIL–C–343A and this specification is as follows:

| *CCC–C–448* | *MIL–C–343A* |
|---|---|
| Type I, class 1 | Type III, classes 1 and 2 |
| Type II, class 1 | Type I, classes 1 and 2 |
| Type II, class 2 | Type I, class 3 |
| Type III, class 1 | Type II, class 1 |

6.5 This specification replaces GSA Specification No. 405, Seersucker, Woven, dated May 16, 1941.

**6.6 Transportation description.**—Transportation description applicable to this item is:

Cotton piece goods in the original piece.
Carload minimum weight, any quantity.
Cotton piece goods, not otherwise indexed.
Motor volume minimum weight, any quantity.

**Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.**

**MILITARY INTEREST:**
**Army—MQ**
**Navy—S**
**Air Force.**



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.