CCC-C-467
DECEMBER 30, 1957
SUPERSEDING
Fed. Spec. CCC–B–811
June 28, 1932

FEDERAL SPECIFICATION

CLOTH, JUTE (OR KENAF), BURLAP

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—This specification covers requirements for burlap made from jute or kenaf. (See 6.1.)

1.2 Classification.—The burlap shall be of one type and four classes (weight based a 40-inch width), as specified. (See 6.2.)

Class 1.—7.5 ounces
Class 2.— 8 ounces
Class 3.— 10 ounces
Class 4.— 12 ounces

2. APPLICABLE SPECIFICATIONS AND STANDARDS

2.1 The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification:

Federal Specifications:

UU–P–268—Paper, Kraft, Wrapping.
UU–P–271 — Paper, Wrapping, Waterproofed, Kraft.
CCC–T–191—Textile Test Methods.
PPP–P–31 — Preservation, Packaging, Packing and Marking of Material; and Shipping Instructions (Domestic Shipment and Storage).

Federal Standards:

Fed. Std. No. 4—Glossary of Fabric Imperfections.
Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.

(Activities outside the Federal Government may obtain copies of Federal Specifications and Standards as outlined under General Information in the index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications and Standards and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Specification:

MIL–A–140 — Adhesive, Water-Resistant, Waterproof Barrier Material.

Military Standards:

MIL–STD–105 — Sampling Procedures and Tables for Inspection by Attributes.

MIL–STD–129 — Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by the contractor in connection with specific procurement functions, should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Material.

3.1.1 *Jute or kenaf.*—The cloth shall be made of jute or kenaf (see 6.3) at the option of the contractor.

3.2 Physical requirements. — The burlap shall conform to the physical requirements specified in table I.

3.2.1 *Width.*—Unless otherwise specified, the burlap shall have a minimum width of 40-inches inclusive of selvage. (See 6.2.)

3.2.2 *Weave.*—The weave shall be plain.

3.2.3 *Selvages.*—The selvages shall be firm and straight, and may contain cotton yarn.

3.3 Length. — Unless otherwise specified, the cloth shall be in one continuous piece of not less than 25 yards.

3.4 Tickets.—Each roll shall have a ticket attached to the selvage at the inner end of the cloth with not finer than 5-ply cotton string doubled to not less than 8 inches long. The tickets shall be made of paper stock not less than 0.020 inch in thickness and the color shall be white or light in intensity to permit easy reading of printed or penciled markings. The ticket shall have a reinforced eyelet for attaching the tying cord and shall be legibly printed with water insoluble ink with the following information. In addition, the ticket shall have sufficient blank space for the inspector's stamp.

Nomenclature
Class_____ Width_____
Stock number
Contractor's name
Contract number and date
Specification number and date
Name of contracting office
Gross yards
Net yards
Inspector

3.5 Workmanship. — The burlap shall be clean, evenly woven, and shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Nonmilitary.

4.1.1 *Sampling.*

4.1.1.1 *Lot.* — Unless otherwise specified, cloth of the same class presented at one time shall be considered a lot for purposes of inspection and tests.

4.1.1.2 *Sampling for visual and dimensional inspection.* — Unless otherwise specified, a random sample of cloth shall be taken from each lot in accordance with table II, for inspection for visual and dimensional characteristics.

TABLE I.—*Physical requirements*

Class	Weight per linear yard (40 inch basis)	Yarns per inch of warp	Yarns per inch of filling	Weight per square yard (Min.)
	ounces			*ounces*
1	7½	8 to 11, inclusive	8 to 11, inclusive	6.7
2	8	9 to 12, inclusive	8 to 11, inclusive	7.2
3	10	11 to 13, inclusive	10 to 12, inclusive	9.0
4	12	11 to 13, inclusive	11 to 13, inclusive	10.8

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

TABLE II.—*Sampling for visual and dimensional inspection*

Number of yards in lot	Number of rolls in sample	Number of yards in sample piece*	Acceptance number (defective)	Rejection number (defective)
300 and under	2	15	0	1
301 to 500	3	25	1	2
501 to 800	5	35	1	2
801 to 1300	7	50	2	3
1301 to 3200	10	75	3	4
3201 to 8000	15	110	4	5
8001 and over	25	150	5	6

*Yards in the sample piece shall be divided equally among sample rolls of cloth and that number of yards shall be unrolled from each sample roll.

4.1.1.3 *Sampling for tests.*—Unless otherwise specified, random samples of cloth shall be taken from each inspection lot in accordance with the following table:

TABLE III.—*Sampling for tests*

Number of rolls in lot	Number of rolls in sample*	Acceptance number (defective)	Rejection number (defective)
8 and under	2	0	1
9 to 15	3	0	1
16 to 40	4	0	1
41 and over	5	0	1

*One unit of product at least 1 yard long and the full width of the cloth shall be taken from each sample roll.

4.1.2 *Inspection.*—Each of the samples selected in accordance with table II, or as specified, shall be visually and dimensionally inspected in accordance with the requirements of paragraphs 4.2.2.1.1.1, 4.2.2.1.1.2, 4.2.2.1.1.3, and 4.2.2.1.1.4. (See 6.5.)

4.1.3 *Tests.*—Samples selected for tests in accordance with table III or as otherwise specified, shall be tested in accordance with applicable methods of Federal Specification CCC–T–191, as listed in table V of this specification.

4.1.4 *Compliance criteria.*

4.1.4.1 *Inspection.*—Any piece in the sample for inspection failing to conform to the requirements for which inspection was made, (4.1.2), shall be considered defective. If the number of defective pieces in the sample exceeds the acceptance number of that sample specified in table II, the entire lot from which the sample was taken shall be considered as having failed to meet the requirements of this specification.

4.1.4.2 *Tests.*—Any unit of product in the sample for test failing to conform to the requirements for which tests were made, (4.1.3), shall be considered defective. If the number of defective units of products in the sample for test exceeds the acceptance number for that sample specified in table III, the entire lot of cloth from which the sample was taken shall be considered as having failed to meet the requirements of this specification.

4.2 Military.

4.2.1 *General.*—The quality assurance provisions contained in this section are applicable to inspection. Quality assurance provisions for components or materials described shall be in accordance with this specification and with subsidiary specifications referenced herein to the extent applicable, except that this specification shall govern in the event of conflict.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

4.2.2 *Inspection for acceptance.* — Inspection shall be in accordance with Military Standard MIL–STD–105 and Appendix, except where otherwise indicated.

4.2.2.1 *Inspection of the end item.*

4.2.2.1.1 *Examination of the end item.*— Defects found during the examination shall be classified in accordance with list shown in 4.2.2.1.1.1, 4.2.2.1.1.2, 4.2.2.1.1.3.

4.2.2.1.1.1 *Yard-by-yard examination.* — The required yardage of each piece shall be inspected and visual defects classified as listed. All defects found shall be counted regardless of their proximity to each other, except where two or more defects represent a single local condition of the cloth in which case only the more serious defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The unit of product for this examination shall be 1 linear yard. The acceptable quality levels for this examination shall be 1.5 major defects and 6.5 total defects (major and minor combined) per 100 units (yards). The sample size expressed in units of yards shall be based upon inspection level II, table III of Military Standard MIL–STD–105. The lot size shall be expressed in units of 1 yard each. The number of rolls from which the sample is to be selected shall be in accordance with the table in 4.2.2.1.1.2. An approximately equal number of yards shall be examined from each roll.

Glossary No. Fed. Std. No. 4	*Defects*	Classification	
		Major	*Minor*
90, 91, 92	Hole, cut, tear — Two or more yarns ruptured at adjoining points in body of cloth	X	
78	Smash	X	
11, 33	Broken or missing yarns:		
	Two or more contiguous	X	
	Single end		X
	Single pick		X
10, 34	Float (harness), mispicks—Multiple affecting serviceability	X	
9, 12, 79	Fine filling, fine filling bar, thin place, open place, weak or chafed place—affecting serviceability	X	
5	Slough-off—Snarled or bunched, affecting serviceability	X	
49, 50	Selvage slack or tight		X
55, 56	Selvage cut, torn, or broken, extending into body of cloth	X	
74, 75	Spots, or stains—Heavy grease spots or stains, badly water stained		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

4.2.2.1.1.2 *Overall examination.*—Each defect listed shall be counted no more than once in each piece examined. The unit of product for this examination shall be one roll. The sample size (number of pieces selected as sample) for this examination and the number of defects acceptable shall be as shown in table IV.

Defects

Rancid or otherwise objectionable odor

Overall uncleanness

Width less than specified

Selvage defects which are continuous or intermittent throughout the piece

Uneven weaving

TABLE IV.

Lot size in yards	Sample size in rolls	Maximum No. or defects acceptable
Up to 1300[1]	3	0
1301 to 3000	5	0
3001 to 8000	7	0
8001 to 22,000	10	0
22,001 to 110,000	15	0
110,001 and over	25	1

[1] If lot contains fewer than 3 rolls, each roll in the lot shall be examined.

4.2.2.1.1.3 *Examination for length of individual rolls.*—The roll shall be examined for gross length. Any gross length found to be less than specified minimum length or any gross length found to be more than 1 yard below the gross length marked on the ticket, shall be considered as a defect with respect to length. The unit of product for this examination shall be 1 roll. The number of rolls selected as sample (sample size) for this examination and the number of defects acceptable shall be in accordance with table IV.

4.2.2.1.1.4 *Examination for total yardage in sample.*—The lot shall be unacceptable if the total of the actual gross lengths of rolls in the sample is less than the total of the gross lengths marked on roll tickets. The rolls examined shall be those selected for examination of individual rolls.

4.2.3 *Tests.*—The methods of testing specified in Federal Specification CCC–T–191 wherever applicable, and as listed in table V, shall be followed. The physical values specified in section 3 apply to the average of the determinations made on a unit of product for test purposes as specified in the applicable test methods. For each characteristic, the acceptable quality level shall be 4.0 test failures per 100 units. The unit of product shall be 1½ continuous yards full width of finished cloth. The sample size expressed in units of rolls shall be in accordance with level L–2, table VII of Appendix to Military Standard MIL–STD–105. The lot size shall be expressed in units of 1 yard each.

TABLE V.—*Test methods*

Test	Requirement reference	Method
Weight, ozs/linear yard	Par. 3.2	5041
Yarns per inch	Par. 3.2	5050
Weave	Par. 3.2.2	visual

5. PREPARATION FOR DELIVERY

(For definitions and levels, see 5.4).

5.1 Packaging.

5.1.1 *Level A.*—The burlap cloth shall be wound open width on a chipboard tube with ends flush with each side of the roll. The cloth shall be in one continuous piece of not less than 25 yards and each roll shall not exceed 200 pounds in weight. Each roll shall be completely inclosed in a wrap of 60-pound kraft paper conforming to grade B, of Federal Specification UU–P–268. The paper shall be folded over the ends of the roll. Paper wrapping shall be secured by means of gummed paper tape, twine, or cloth tape.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

5.1.2 *Level C.*—The burlap cloth shall be packaged in accordance with the contractor's normal practice, except, it shall be in one continuous piece of not less than 25 yards and each roll shall not exceed 200 pounds in weight.

5.2 Packing.

5.2.1 *Level A.*—Each roll of the burlap cloth wrapped with paper as specified in 5.1.1, shall be overwrapped completely with waterproof barrier-material conforming to type B–2 of Federal Specification UU–P–271. Closure and seams shall be sealed with a continuous seam, minimum ¾ inch wide of water-resistant adhesive conforming to Military Specification MIL–A–140. Each overwrapped roll of burlap cloth shall then be completely covered with the same type burlap cloth as in the roll. The burlap cloth wrapping shall be sewn with 16-ply cotton twine, approximately one stitch to the inch with every third stitch knotted. The wrapping shall be closed at each end with two wire ties. Five inches of surplus covering shall be gathered together with the first wire tie applied as close to the roll as possible. The second wire tie shall be applied approximately 1 inch from the first wire tie. The wire ties shall be not less than six inches long, 15 gage soft iron or steel with a formed eye at each end. Alternatively, the burlap covering may be in tubing form presewn on one end, with closure effected by wire tying the open end as specified above.

5.2.2 *Level B.*—Each roll of burlap cloth, wrapped with kraft paper as specified in 5.1.1, shall be completely covered with burlap cloth as specified in 5.2.1. Wrapping with waterproof barrier-material shall not be required.

5.2.3 *Level C.*—The burlap cloth packaged as specified in 5.1.2, shall be packed in a manner acceptable to common carriers for safe transportation to point of destination specified in shipping instructions at the lowest transportation rate for such supplies.

5.3 Marking.

5.3.1 *Civilian agencies.*—Shipping containers shall be marked in accordance with Federal Specification PPP–P–31.

5.3.2 *Military agencies.*—Shipping containers shall be marked in accordance with Military Standard MIL–STD–129.

5.4 Federal Standard 102 shall be referred to for definitions and application of the various levels of packaging protection for supplies and equipment.

6. NOTES

6.1 Intended use.—Burlap covered by this specification is intended for use in equipage, covering of baled material, camouflage materials and sand bags, and overwrapping of textile products when packed for delivery.

6.2 Ordering data. — Procurement documents should specify the following:

(a) Title, number, and date of this specification.

(b) Class of cloth required (see 1.2).

(c) Width, if other than specified (see 3.2.1).

(d) Both the level of packaging and the level of packing required (see 5.1 and 5.2).

6.3 Jute and kenaf.

6.3.1 *Jute.*—Jute is defined as the bast fiber obtained from various species of Corchorus.

6.3.2 *Kenaf.*—Kenaf is defined as the bast fiber obtained from Hibiscus Cannabinus.

6.4 This specification incorporates the requirements of Military Specification MIL–B–14083 (CE) 6 June 1955.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

6.5 Nonmilitary sampling for inspection shall be conducted in accordance with table II unless otherwise stated in the invitation for bids. When nonmilitary reference is made to paragraphs under the Military heading (4.2) it shall be understood that such reference omits the inclusion of stated requirements pertaining to Military Standard MIL–STD–105 unless the Civilian Government agency has elected to use such requirements.

6.6 Transportation description.—The transportation description applicable to this item is:

Cloth, burlap, jute, not otherwise indexed by name.

Carload minimum weight 30,000 pounds.

Truckload minimum weight 30,000 pounds.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:
Army—E M Q
Navy—S Sh MC
Air Force.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.