CCC-C-482C
October 3, 1972
SUPERSEDING
Fed. Spec. CCC-C-482B
August 20, 1968

FEDERAL SPECIFICATION

CLOTH, PRESSING, NYLON

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the requirements for four types of nylon pressing cloth (see 6.1).

1.2 Classification.

1.2.1 Types. Nylon pressing cloth shall be of the following types as specified (see 6.2):

Type I - Spun warp and filling yarn.
Type II - Filament warp yarn and spun filling yarn.
Type III - Spun warp yarn and filament filling yarn.
Type IV - Filament warp and filling yarn.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specifications:

P-S-579	-	Soap, Laundry, Chip and Powdered.
UU-P-268	-	Paper, Kraft, Untreated, Wrapping.
PPP-B-636	-	Boxes, Shipping, Fiberboard.
PPP-P-1133	-	Packaging and Packing of Synthetic Fiber Fabrics.
PPP-T-45	-	Tape, Gummed, Paper, Reinforced and Plain, for Sealing and Securing.

Federal Standards:

Fed. Std. No. 4	-	Glossary of Fabric Imperfections.
Fed. Std. No. 123	-	Marking for Domestic Shipment (Civil Agencies).
Fed. Std. No. 191	-	Textile Test Methods.

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Fort Worth, Denver, San Francisco, Los Angeles, and Seattle, Washington.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standard:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Laws and Regulations:

Rules and Regulations Under the Textile Fiber Products Identification Act (16 CFR 303).

(Copies may be obtained without charge from the Federal Trade Commission, Washington, DC 20580.)

3. REQUIREMENTS

3.1 Standard sample. When a standard sample is available, the finished cloth shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.4).

3.2 Material.

3.2.1 Nylon. The yarn used in the manufacture of the cloth shall be of cut staple or multi-filament nylon as specified in 3.2.2, and shall be a polyamide prepared from hexamethylene diamine and adipic acid or its derivatives. The nylon shall have a melting point of 250°C. ± 6°C. When

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

cut staple is used, the use of any form of nylon waste is prohibited, e.g., undrawn fiber, mixtures of deniers, lusters of cross sections, and waste from any stage of fiber production; whether drawn, undrawn or mixed or garnetted fiber. Tests shall be as specified in 4.4.

3.2.2 Yarn.

3.2.2.1 Spun yarn. The yarn for the warp of types I and III cloth, and for the filling of types I and II cloth shall be nylon staple which has been drawn, spun, and twisted into 2 ply.

3.2.2.2 Filament yarn. The yarn for the warp of type II cloth, the filling of type III cloth, and the warp and filling of type IV cloth shall be bright multifilament nylon.

3.3 Color. The color of the finished cloth shall be that shade imparted by the finish, provided the individual pieces are uniform in shade and the finished cloth meets the requirements as specified in 3.5 and 3.7.

3.3.1 Colorfastness. The finished cloth shall show colorfastness to pressing equal to or better than the standard sample when tested as specified in 4.4. When no standard sample is established the cloth shall show no staining of the test cloth when tested as specified in 4.4.

3.4 Physical requirements. The finished cloth shall conform to the minimum physical requirements specified in table I, when tested as specified in 4.4.

TABLE I.- Physical requirements

Type	Weight per square yard	Yarns per inch		Breaking strength	
		Warp	Filling	Warp	Filling
	Ounces			Pounds	Pounds
I	7.0	38	36	210	220
II	5.6	66	54	280	240
III	5.6	54	60	240	280
IV	3.6	60	42	250	180

3.4.1 Weave. The weave shall be plain for types I and IV and a 2 up and 1 down right twill for types II and III.

3.4.2 Width. The width of the finished cloth shall be a minimum of 54 inches, inclusive of selvage.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

3.5 Finish. The cloth shall be heat treated at not less than 380°F. The heat treated cloth shall be given an additional resin or other type of finish to increase the heat resistant properties.

3.6 Slippage. The warp and filling yarns in the finished cloth shall show no slippage when tested as specified in 4.4.

3.7 Accelerated ageing. The finished cloth shall not lose more than 50 percent of the original breaking strength for both warp and filling when tested in accordance with breaking strength and ageing tests as specified in 4.4.

3.8 pH. The pH value of the finished cloth shall be no lower than 5.0 nor higher than 8.5 when tested as specified in 4.4.

3.9 Adherence. The finished cloth shall not adhere to a heated hand iron when tested as specified in 4.4.

3.10 Dimensional stability. The finished cloth shall not shrink nor elongate more than 3.0 percent in the warp nor more than 2.0 percent in the filling when tested as specified in 4.4.

3.11 Length and put-up.

3.11.1 Rolls (military requirements). Unless otherwise specified (see 6.2), the cloth shall be furnished in continuous lengths, each not less than 50 yards. The cloth shall be put-up on a full width roll as specified in PPP-P-1133.

3.11.2 Bolts (civil agencies). Approximately 50 continuous yards (plus or minus 5 percent) of cloth of the type specified shall be put up as flat folded pieces (bolts) in accordance with level A "put-up" of PPP-P-1133, or at the option of the supplier, the cloth may be put-up by winding on a flat chipboard or cardboard insert of not less than 1/8 inch thick by 12 ± 1/4 inches wide, by specified length.

3.12 Fiber identification. Each roll of cloth shall be labeled, ticketed, or invoiced for fiber content in accordance with the Rules and Regulations Under the Textile Fiber Products Identification Act.

3.13 Workmanship. The finished cloth shall conform to the quality established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable procurement documents.

4.2.2 Examination of the end item. Defects found during this examination shall be classified in accordance with 4.2.2.1 through 4.2.2.3.

4.2.2.1 Yard-by-yard examination. The required yardage of each roll shall be examined on one side and defects clearly noticeable at normal inspection distance (3 feet) shall be classified as listed. The defects found shall be counted regardless of their proximity to each other, except when two or more defects represent a single local condition of the cloth, only one shall be scored. A continuous defect shall be counted as one defect for each yard or fraction thereof in which it occurs. The sample unit shall be 1 yard, full width of the finished cloth. The acceptable quality level shall be 4.0 defects per 100 units (yards). The sample size shall be in accordance with inspection level I of MIL-STD-105. The lot size shall be expressed in units of one yard each. The number of rolls selected shall be in accordance with table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

Defects

Hole, cut or tear
Smash
Knot 1/
Grease or oil stain
Embedded crease or wrinkle
Area of no finish

1/ To be scored when larger than limits shown on figure 1 of Fed. Std. No. 4.

4.2.2.1.1 Overall examination. Each defect shall be counted no more than once in each roll examined. The sample unit shall be one roll. The size (number of rolls selected as sample) and the acceptance number shall be as shown in table II.

Defects

Shade not uniform.
Baggy, ridgy or wavy cloth.
Objectionable odor.
Width less than specified.
Overall uncleanness.

TABLE II

Lot size (yards)	Sample size (rolls)	Acceptance number
Up to 3200 1/	3	0
3201 up to and including 10,000	5	0
10,001 up to and including 35,000	8	0
35,001 up to and including 150,000	13	1
150,001 and over	20	2

1/ If a lot contains fewer than three rolls, each roll shall be examined.

4.2.2.2 Examination for length.

4.2.2.2.1 Individual rolls or bolts. During the yard-by-yard examination, each roll or bolt in the sample shall be examined for length. Any length found to be less than the minimum specified or more than two yards less than the length marked on the ticket shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls or bolts in the sample are defective in respect to length.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

4.2.2.2.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual lengths of rolls or bolts in the sample is less than the total of the lengths marked on the ticket.

4.2.2.3 Examination for compliance with Textile Fiber Products Identification Act. During the yard-by-yard examination, each roll or bolt in the sample shall be examined for conformance with the Textile Fiber Products Identification Act. Each roll or bolt not labeled in accordance with this act shall be a defect. The lot shall be unacceptable if two or more of these defects occur.

4.3 Examination of preparation for delivery requirements. An examination shall be made in accordance with the provisions of PPP-P-1133 to determine whether packaging, packing and marking comply with the section 5 requirements.

4.4 Testing of the end item. The methods of testing specified in Fed. Std. No. 191, wherever applicable and as listed in table IV shall be followed. The physical and chemical values specified in section 3 apply to the results of the determinations made on a sample unit for test purposes as specified in the applicable test method. The sample unit shall be 3 continuous yards full width of the finished cloth. The sample size shall be as listed in table III. The lot size shall be expressed in units of 1 yard. The lot shall be unacceptable if one or more sample units fail to meet any requirement specified. All test reports shall contain the individual values utilized in expressing the final result.

TABLE III.- Sample size

Lot size (units)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

TABLE IV.- Test methods

Characteristic	Requirement paragraph	Test method
Material identification	3.2.1	1530 1/
Melting point	3.2.1	1534 1/

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

TABLE IV.- Test methods (cont'd)

Characteristic	Requirement paragraph	Test method
Presence of any form of nylon waste	3.2.1	2/
Ply and staple yarns	3.2.2	Visual 3/
Filament	3.2.2	Visual 3/
Luster (bright)	3.2.2	1/
Colorfastness to pressing	3.3.1	4.4.1 3/
Weight	3.4	5041
Yarn per inch:		
Warp	3.4	5050
Filling	3.4	5050
Breaking strength:		
Initial:		
Warp	3.4	5100
Filling	3.4	5100
After accelerated ageing:		
Warp	3.7	5100 and 4.4.2
Filling	3.7	5100 and 4.4.2
Weave	3.4.1	Visual 3/
Finish	3.5	4/
Yarn slippage	3.6	5410 5/
pH	3.8	2811
Adherence	3.9	4.4.3 3/
Dimensional stability	3.10	4.4.4

1/ Unless otherwise specified, a certification of compliance shall be submitted and will be acceptable for the stated requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

2/ The supplier shall furnish a certificate of compliance furnished by the fiber producer that each lot of nylon staple used conforms to the requirements.

3/ One determination shall be made from each sample unit and the results reported as "Pass" or "Fail".

4/ The supplier shall submit a certificate of compliance indicating that the cloth was heat treated at not less than 380°F. and that a resin or other type finish was added to increase the heat resistance properties. The certificate shall be accompanied by actual tests, inspection or other verifiable data.

5/ The general procedure of method 5410 shall be followed except that the evaluation shall be by visual examination for evidence of yarn slippage. Any yarn slippage observed shall be considered as a test failure. Report results as "Pass or "Fail".

4.4.1 Colorfastness to pressing. The colorfastness to pressing of the finished cloth shall be determined as follows:

4.4.1.1 Specimen. The specimen shall be a strip 1 inch by 10 inches long cut from the nylon cloth.

4.4.1.2 Apparatus. A wooden block 6 inches wide by 12 inches long and 2 inches thick shall have two drilled holes (one at each end) across the width approximately 1 inch from each end to accommodate two bolts, threaded on both ends, for wing nuts. Two metal bands, 1 inch wide and 12 inches long, with holes drilled to fit the bolt positions, shall be placed on either lengthwise side. The wooden block shall be covered over the top with a cotton roving pad to simulate the buck of a press. The top of the roving pad shall be covered with the standard six-fiber repeat test cloth consisting of a warp of polyester fiber or orlon 81 and a six-fiber filling with equal bars of wool, spun nylon, spun rayon, spun silk, spun acetate and bleached cotton. The strip of nylon cloth shall be placed over the test cloth. Secure the strip by means of the metal bands and tighten the wing nuts.

4.4.1.3 Procedure. The whole apparatus shall be exposed in a circulating hot air oven at 176°C. ± 2°C. for 15 minutes and then removed. The specimen shall be covered immediately with a cotton strip cloth saturated with distilled water and pressed with a hand iron, having a temperature of 325°F. to 350°F. for 45 seconds. The water saturated cloth shall be removed and replaced with another cotton strip that has been saturated in soap solution conforming to type I of P-S-579. The stock solution of the soap may be prepared

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

by dissolving 1 pound of chip soap in 1 gallon of hot water containing 0.3 percent available chlorine. The soap saturated test cloth shall be placed over the specimen and covered with dry cotton cloth and pressed as specified above. The soap saturated cloth shall be removed and the specimen covered with a cotton cloth saturated in a 5 percent boiling starch solution having 0.3 percent available chlorine, over which a dry cotton cloth shall be placed and pressed as specified above. The apparatus shall be unclamped and the multifiber test cloth examined for stains. One determination shall be made from each sample unit. Report staining or no staining of test cloth.

4.4.2 Resistance to ageing. The test specimens of cloth for determining resistance to ageing shall be so selected that the identical warp and filling yarns are tested originally and after subjection to ageing. This shall be done by marking all the specimens required before cutting. The specimens shall be so cut and marked that specimens in each group, warp and filling, for original breaking strength and for resistance to ageing shall contain the identical yarns.

4.4.2.1 Procedure. Five warp and five filling tests shall be made. The test specimens shall be exposed in the accelerated ageing unit as specified in method 5850 of Fed. Std. No. 191. The specimens shall be exposed in the oven for 5 hours at a temperature of 176°C. ± 2°C. After removal from the oven, the specimens shall be brought to equilibrium under Standard Condition as defined in Fed. Std. No. 191. They shall then be tested for breaking strength as specified in table IV and the percent of breaking strength (B.S.) lost shall be calculated as follows:

$$\text{Percent of B.S. lost} = \frac{\text{original B.S} - \text{B.S. after ageing} \times 100}{\text{original B.S.}}$$

4.4.3 Adherence. A sample of the finished cloth 5 ± 0.5 inches square shall be placed on a flat surface. A heated hand iron, which has not been treated with any antistick agent such as wax, weighing 4 to 5 pounds and having a temperature of 325°F. to 350°F. shall be placed stationary under its own weight on the sample for 60 seconds. At the end of this period the iron is lifted and observed for adherence of material to the pressing surface of the iron. Material shall be considered as failing the adherence test if the sample adheres to the iron when the iron is lifted off the flat surface.

4.4.4 Dimensional stability. Three specimens shall be selected from the cloth sample unit as follows: One specimen from each side of the cloth to within three inches of the selvage and one specimen from the center of the cloth. No two specimens shall contain the same filling yarns. Each specimen, 20 inches square, shall be cut from the cloth and conditioned for 4 hours in

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

an atmosphere having a relative humidity of 65 ± 2 percent and a temperature of 70°F. ± 5°F. Each specimen shall have an 18 inch square mark off and then formed into a loop by stapling two opposite sides together. A glass rod 1/4 inch in diameter and 21 inches long shall be placed inside the loop at the top, and a glass rod 1/4 inch in diameter and 21 inches long weighing approximately 100 grams shall be placed inside the loop at the bottom. Each specimen shall be immersed in a tub of boiling water by attaching twine or wire to the ends of the top glass rod and allowing the specimen to hang freely in the boiling water for 15 minutes. Each specimen shall be removed and allowed to drain. After the staples are removed, each specimen shall be dried in a flat position on a horizontal screen and reconditioned as stated above. The marked square shall be measured in three places in the warp direction and three places in the filling direction and the percent of dimensional stability determined. The dimensional stability of the sample unit shall be calculated as follows and reported to the nearest 0.1 percent:

$$\text{Dimensional stability, percent} = \frac{A - B}{A} \times 100$$

A = Average of initial measurements (3 specimens)
B = Average of measurements after immersion and reconditioning (3 specimens)

The shrinkage of the sample unit in the warp direction and the filling direction shall be the average of the specimens tested from each direction respectively, and shall be reported separately to the nearest 0.1 percent. When a test result registers elongation rather than shrinkage, each elongation result shall be prefixed with a minus sign and inclosed in parenthesis.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A, B, or C as specified (see 6.2).

5.1.1 Military requirements.

5.1.1.1 Levels A and C. The cloth put up as specified, shall be packaged in accordance with the applicable requirements of PPP-P-1133.

5.1.2 Civil agencies (see 6.3).

5.1.2.1 Level B (standard pack). Cloth, put up in bolts as specified, shall be completely wrapped in a 30-pound minimum basis weight kraft paper conforming to grade B of UU-P-268. The bolt shall be so wrapped that the paper encircles the bolt twice with the width of the paper sufficient to

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

fold over and protect the ends of the bolt. The wrapping shall be secured with 2-1/2 inch minimum width gummed paper tape conforming to type III, grade C of PPP-T-45, applied over the folded ends of wrapping, centered approximately to the width of the bolt. Wrapping shall be applied in a manner which shall permit the bolt identification tag attached to selvage of material to be on the outside of the wrapped bolt.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Military requirements.

5.2.1.1 Levels A, B and C. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1133.

5.2.2 Civil agencies (see 6.3).

5.2.2.1 Level B (standard pack). Bolts of cloth packaged as specified in 5.1.2, shall be packed in fiberboard containers conforming to type CF (variety DW) or SF, class domestic, style FTC, FOL, SFF or RSC-L of PPP-B-636, except that in no event shall the gross weight of box and contents exceed 90 pounds, nor the burst test of the fiberboard be less than grade 275. Sleeve liner for RSC-L boxes shall be not less than grade 175, and the top and bottom full width by full length fiberboard pads shall test not less than grade 125. Box closure shall be in accordance with the appendix of the box specification. According to weight of wrapped bolts; 12 bolts of up to 6 pounds each, 8 bolts of up to 10 pounds each, 6 bolts of from 11 to 14 pounds each, 4 bolts of from 15 to 21 pounds each, 3 bolts of from 22 to 28 pounds each, 2 bolts of from 29 to 42 pounds each, or one bolt of over 43 pounds shall be packed per shipping container. Containers of 6 to 12 bolts shall be packed with bolts in 2 stacks side by side, 4 bolts or less shall be in a single stack within the container.

5.3 Marking.

5.3.1 Military requirements. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the applicable requirements of PPP-P-1133.

5.3.2 Civil agencies. Each bolt shall be provided with an identification tag on the outside of the wrapping. No other marking is required for the individual bolts. Each shipping container shall be marked in accordance with Fed. Std. No. 123 with the additional precautionary markings as follows:

On each side panel: "DO NOT STAND ON END" in 1-inch letters.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

For quantity contained: "....BOLTS - Total Yardage....yds." indicating total number of bolts and total yardage contained.

6. NOTES

6.1 Intended use. Nylon pressing cloth is intended for use as covers for flat bed laundry presses.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number and date of this specification.
(b) Type required (see 1.2).
(c) When verification of melting point is required (see 3.2.1 and 4.4.1).
(d) Length, if other than specified (see 3.11).
(e) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 Civil agencies. The standard pack requirements in 5.1.2 and 5.2.2 cover packaging and packing for bolts of cloth approximating 50 continuous yards in length and are intended for use in stores stock replenishments. Procuring officers should use the standard pack requirements when it is known that the cloth approximating 50 continuous yards in length will be shipped from supplier to a domestic warehouse, supply depot or intermediate storage point for temporary storage, subsequent issue or shipment to eventual user.

6.4 Standard sample. For access to standard sample, address the procuring office issuing the invitation for bids.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

MILITARY CUSTODIANS:

Army - GL
Navy - SA
Air Force - 82

Review activity:

Army - MD

User activity:

Navy - YD

Civil Agency Coordinating Activities:

GSA-FSS
USDA-AFS

Preparing activity:

Army - GL

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 15 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

CCC-C-482C - Cloth, Pressing, Nylon

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01760

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

U.S.MAIL

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRES-EQS
Natick, Massachusetts 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:30Z
Check the source to verify that this is the current version before use.