INCH-POUND
MIL-DTL-24643/29E
1 October 2009
SUPERSEDING
MIL-DTL-24643/29D
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -20 °C TO +90 °C, 300 VOLTS, TYPE LSMU (INCLUDING VARIATION LSMUS)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

This cable can be manufactured in two variations: LSMU and LSMUS (double overall shield)

Construction, Non-Watertight

First	-	Copper conductor, tin-coated, ASTM B286, Size 20 – 7strands.
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation. Minimum average wall thickness of 0.013 inch. Standard identification code applied by Method 1 on white-colored insulation.
Fourth	-	The specified number of singles (see table I) shall be cabled together in accordance with 3.4.4 of MIL-DTL-24643. Cabling sequence shall be consecutive starting with no. 1 from the center outward. Fillers may be used as necessary to form a firm well-rounded assembly.
Fifth	-	An optional binder.

Construction, Variant Type LSMU

Sixth	-	Cross-linked polyolefin jacket. Minimum average wall thickness of 0.030 inch.

Construction, Variant Type LSMUS

Sixth	-	Braided shield of tin-coated copper.
Seventh	-	Spirally wrapped 0.002-inch thick polyethylene terephthalate (polyester film) separator tape with 25 percent minimum overlap.
Eighth	-	Braided shield of tin-coated copper.
Ninth	-	An optional binder.
Tenth	-	Cross-linked polyolefin jacket. Minimum average wall thickness of 0.030 inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:04Z
Check the source to verify that this is the current version before use.

TABLE I. Details (shielded and unshielded).

Military part no. M24643/29	Type and size	Number of conductors	Overall diameter	
			min. (inch)	max. (inch)
-01UN	LSMU-14	14	0.365	0.400
-01UD	LSMUS-14	14	0.425	0.460

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic Electricals:

Conductor resistance (ohms/1000 feet at 25 °C, max.)	10.93
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	2000
Conductor to overall shield (Type LSMUS only)	1000
Overall shield to overall shield (Type LSMUS only)	200
Insulation resistance (megohms/1000 feet, min.)	
Conductor to conductor	2000
Conductor to overall shield (Type LSMUS only)	2000
Overall shield to overall shield (Type LSMUS only)	100
Conductor continuity	No failure
Shield continuity (LSMUS only)	No failure
Jacket flaws (LSMUS only)	No failure
Group A:	
Visual and dimensional	No failure
Group B:	
Cold bending cable	No failure
Thermoset proof test (percent, max.)	
Insulation	50
Jacket (when tested at 200 °C)	50
Physicals (unaged)	
Insulation (extruded)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:04Z
Check the source to verify that this is the current version before use.

Jacket (cable)	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160
Tear (lb/in thickness, min.)	35
Group C:	
Physicals (aged) air oven	
Insulation(extruded)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (insulation) (cycles, min.)	25
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Shrinkage	No failure
Surface transfer impedance (Type LSMUS only)	
Milliohms per meter (max.)	700
EMP response (dB, min.)	60
Group D:	
Flame propagation (cable)	No failure
Qualification Inspection:	
Qualification inspection shall include basic electricals, groups A, B, C, and D, plus the following:	
Aging and compatibility (cable) (125±5 °C)	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Shield insulation	2
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:04Z
Check the source to verify that this is the current version before use.

Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	45
Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LSMU-14 and LSMUS-14	2500

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2008-033)

Review Activities:
Army – AR, AV, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:04Z
Check the source to verify that this is the current version before use.