INCH-POUND
MIL-DTL-24643/32F
1 October 2009
SUPERSEDING
MIL-DTL-24643/32E
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -20 °C TO +90 °C, TYPE LS2SWAU

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction, Watertight

First	-	Copper conductor, coated or uncoated, ASTM B286, 22 AWG – 7 strands.
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation. Nominal wall thickness of 0.013 inch; wall thickness may vary from nominal as necessary, in order for the completed cable to meet the specified electrical requirements. Colored insulation, one white and one black conductor for each pair.
Fourth	-	Two conductors (one black and one white) cabled together with a nominal lay of 2.5 inches to form a pair.
Fifth	-	An optional binder.
Sixth	-	Braided shield of 34 or 36 AWG, tin-coated copper. Braid angle of 30 to 35 degrees; minimum coverage of 85 percent.
Seventh	-	Shield insulation of two polyester tapes, outer tape sealed. An alternate shield insulation may consist of one polyester tape, plus an extruded jacket of a suitable transparent material, minimum average thickness of the transparent material 0.003 inch. The standard identification code shall be applied by Method 2.
Eighth	-	The specified number of pairs (see table I) shall be cabled together in accordance with 3.4.4 of MIL-DTL-24643. Cabling sequence shall be consecutive starting with no. 1 from the center outward. Fillers may be used as necessary to form a firm well-rounded assembly.
Ninth	-	An optional binder.
Tenth	-	Cross-linked polyolefin jacket (see table I for thickness).

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:06Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/32	Type and size	Number of pairs	Cable jacket thickness min avg. (inch)	Overall diameter	
				min. (inch)	max. (inch)
-01UN	LS2SWAU-3	3	0.050	0.480	0.520
-02UN	LS2SWAU-7	7	0.050	0.610	0.660
-03UN	LS2SWAU-10	10	0.050	0.770	0.830
-04UN	LS2SWAU-14	14	0.063	0.860	0.930
-05UN	LS2SWAU-19	19	0.063	0.970	1.040
-06UN	LS2SWAU-24	24	0.063	1.120	1.210
-07UN	LS2SWAU-30	30	0.063	1.190	1.280
-08UN	LS2SWAU-37	37	0.063	1.290	1.380
-09UN	LS2SWAU-44	44	0.063	1.460	1.550
-10UN	LS2SWAU-61	61	0.075	1.660	1.740

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic Electricals:

Conductor resistance (ohms/1000 feet at 25 °C, max.)	17.37
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	2000
Conductor to shield	1000
Component shield to component shield	500
Insulation resistance (megohms/1000 feet, min.)	
Conductor to conductor	500
Conductor to shield	500
Component shield to component shield	100
Conductor continuity	No failure
Shield continuity	No failure

Group A:

Visual and dimensional	No failure
Hydrostatic (open end) (leakage at 300 lb/in^2, 2 hours, in^3, max.)	1.0
Capacitance	
Mutual capacitance, at 1 kilohertz (KHz) (pF/ft, max.)	30
Capacitance unbalance (percent max.)	8

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:06Z
Check the source to verify that this is the current version before use.

Characteristic impedance, at 1 megahertz (MHz) (ohms)	75±5
Group B:	
Cold bending cable	No failure
Thermoset proof test (percent, max.)	
Insulation	50
Jacket (when tested at 200 °C)	50
Drip (95±1 °C)	Zero
Physicals (unaged)	
Insulation (extruded)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160
Tear (pounds per inch thickness, min.)	35
Attenuation, at 3 MHz (decibel (db)/100 ft max.)	3.0
Group C:	
Physicals (aged) air oven	
Insulation (extruded)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Cable fill (sealant) removability	No failure
Shrinkage	No failure
Shield (conformance to material, construction and coverage)	No failure
Pulse response time (nanoseconds/500 ft, max.)	400
Group D:	
Flame propagation (cable)	No failure

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:06Z
Check the source to verify that this is the current version before use.

Qualification Inspection:

Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:

Aging and compatibility (cable) (125±5 °C)	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Shield insulation	2
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	45
Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No failure

UNIT ORDERING LENGTHS:

Type	Size	Feet (nominal)
LS2SWAU	3 through 30	1000
LS2SWAU	37 through 61	500

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:06Z
Check the source to verify that this is the current version before use.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2008-036)

Review Activities:
Army – AR, AV, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:06Z
Check the source to verify that this is the current version before use.