INCH-POUND
MIL-DTL-24643/34F
1 October 2009
SUPERSEDING
MIL-DTL-24643/34E
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -20 °C TO +90 °C, 300 VOLTS, TYPE LSMS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction, Non-Watertight

First	-	Copper conductor, tin-coated, 16 AWG, Class B stranding (7 by 0.0192 inches), in accordance with ASTM B8 or ASTM B 286, 16 AWG with 19 strands.
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation (black). Minimum average wall thickness of 0.013 inch. Standard identification code applied by Method 1.
Fourth	-	The specified number of singles (see table I) shall be cabled together in accordance with 3.4.4 of MIL-DTL-24643. Cabling sequence shall be consecutive starting with no. 1 from the center outward. Fillers may be used as necessary to form a firm well-rounded assembly.
Fifth	-	An optional binder.
Sixth	-	Braided shield of tin-coated copper.
Seventh	-	An optional binder.
Eighth	-	Cross-linked polyolefin jacket. Minimum average wall thickness of 0.075 inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:07Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/34	Type and size	Number of conductors	Overall diameter	
			min. (inch)	max. (inch)
-01UO	LSMS-37	37	0.740	0.800
NOTE: Weight of completed cable shall not exceed 0.060 lb/ft.				

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic Electricals:

Conductor resistance (ohms/1000 feet at 25 °C, max.)	5.1
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	2000
Conductor to shield	1000
Insulation resistance (megohms/1000 feet, min.)	
Conductor to conductor	2000
Conductor to shield	500
Conductor continuity	No failure
Shield continuity	No failure
Jacket flaws	No failure
Group A:	
Visual and dimensional	No failure
Group B:	
Thermoset proof test (percent, max.)	
Insulation	50
Jacket (when tested at 200 °C)	50
Physicals (unaged)	
Insulation (extruded)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:07Z
Check the source to verify that this is the current version before use.

Tear (lb/in thickness, min.)	35
Group C:	
Physicals (aged) air oven	
Insulation (extruded)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (insulation) (cycles, min.)	25
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Shrinkage	No failure
Surface transfer impedance (milliohms per meter, max.)	700
EMP response (dB, min.)	60
Shield (conformance to material, construction and coverage)	No failure
Group D:	
Flame propagation (cable)	No failure
Qualification Inspection:	
Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:	
Aging and compatibility (cable) (125±5 °C)	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:07Z
Check the source to verify that this is the current version before use.

Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	45
Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No Failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LSMS-37	1000

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2008-038)

Review Activities:
Army – AR, AV, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:07Z
Check the source to verify that this is the current version before use.