INCH-POUND
MIL-DTL-24643/39F
1 October 2009
SUPERSEDING
MIL-DTL-24643/39E
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -20 °C TO +90 °C, TYPE LS1S75MU

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction, Non-Watertight

First	-	Copper conductor, tin-coated, ASTM B286, 22 AWG – 7 strands.
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation. Nominal wall thickness of 0.070 inch; wall thickness may vary from nominal as necessary, in order for completed cable to meet the specified electrical requirements.
Fourth	-	Braided shield of 34 AWG, tin-coated copper. Braid angle of 30 to 35 degrees; minimum coverage of 85 percent.
Fifth	-	Shield insulation of two polyester tapes, outer tape sealed. An alternate shield insulation may consist of one polyester tape plus an extruded jacket of a suitable transparent material, minimum average thickness of the transparent material 0.003 inch. The standard identification code shall be applied by Method 2.
Sixth	-	The eight singles cabled around a center filler with a lay in accordance with 3.4.4 of MIL-DTL-24643. Cabling sequence shall be consecutive, starting with no. 1. Fillers may be used as necessary to make a firm, well-rounded assembly.
Seventh	-	An optional binder.
Eighth	-	Cross-linked polyolefin jacket. Minimum average wall thickness 0.050 inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:09Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/39	Type and size	Number of conductors	Overall diameter	
			min. (inch)	max. (inch)
-01UN	LS1S75MU-8	8	0.950	1.030

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic Electricals:	
Conductor resistance (ohms/1000 feet at 25 °C, max.)	17.37
Voltage withstand (volts, root mean square, min.)	
Conductor to shield	7000
Component shield to component shield	500
Insulation resistance (megohms/1000 feet, min.)	
Conductor to shield	500
Component shield to component shield	100
Conductor continuity	No failure
Shield continuity	No failure
Group A:	
Visual and dimensional	No failure
Characteristic impedance, at 1 megahertz (MHz) (ohms)	75±3
Group B:	
Thermoset proof test (percent, max.)	
Insulation	50
Jacket (when tested at 200 °C)	50
Attenuation, at 400 MHz (decibel (db)/100 ft max.)	9.0
Physicals (unaged)	
Insulation (extruded)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:09Z
Check the source to verify that this is the current version before use.

Tear (lb/in thickness, min.)	35
Cold bending cable	No failure
Group C:	
Physicals (aged) air oven	
Insulation (extruded)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Shrinkage	No failure
Shield (conformance to material, construction and coverage)	No failure
Group D:	
Flame propagation (cable)	No failure
Qualification Inspection:	
Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:	
Aging and compatibility (cable) (125±5 °C)	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Shield insulation	2
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:09Z
Check the source to verify that this is the current version before use.

Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	45
Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LS1S75MU-8	1000

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2008-043)

Review Activities:
Army – AR, AV, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T00:09Z
Check the source to verify that this is the current version before use.