INTERIM AMENDMENT

TO

FEDERAL SPECIFICATION

KEY, SOCKET HEAD SCREW

This interim amendment was developed by the General Services Administration, Federal Supply Service, Washington, DC 20406, based upon currently available technical information. It is recommended that Federal Agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

The General Services Administration has authorized the use of this interim amendment as a valid exception to GGG-K-275D, dated March 19, 1974.

PAGE 3

Paragraph 3.2, fourth line, change "tables IV thru XVI" to "tables IV through XII".

Paragraph 3.2.1, delete and substitute:

"3.2.1 Handles. Handles for type IV, VI, VII, and VIII keys shall be of a suitable shape and finish to provide a comfortable grip, and be free from rough edges, sharp corners, or tool marks that affect the appearance of the tool. Screwdriver type handles of type VII and VIII keys shall be made of transparent amber or yellow virgin plastic and chemically polished, and be furnished with or without a cushion grip covering. All types of handles shall not slip on the bit or shaft when subjected to the test in 4.4.2.2."

Paragraph 3.3.1, delete and substitute:

"3.3.1 Test load. All L-type keys and bits tested in accordance with 4.4.2 shall withstand the test load specified in table I, II, or III, as applicable."

Paragraph 3.4, delete and substitute:

"3.4 Hardness. Keys and bits shall be hardened all over to Rockwell C 45-52 for sizes 9/16 inch and larger, and Rockwell C 50-57 for sizes 1/16 inch to 9/16. Sizes 0.050 inch and smaller shall have a Knoop micro hardness not less than 565, nor more than 685."

Paragraph 3.6, at beginning of first sentence, add "Handles of keys, and".

PAGE 6

Paragraph 4.4.1, in both the first and second sentences, delete "0.093" and substitute "0.050".

Paragraph 4.4.2 and 4.4.2.1, delete and substitute:

"4.4.2 Torsion tests. Torsion tests shall be conducted for L-type keys and bits to determine conformance to 3.3.1. In addition, the bits of keys with handles (or case) shall be subjected to a torsion test to determine the integrity of the handle-bit or handle-shaft connection.

FSC 5120

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:38Z
Check the source to verify that this is the current version before use.

4.4.2.1 Torsion test for L-type keys, and bits. L-type keys and bits shall be tested by inserting the short arm of L-type keys or bits of equivalent length into a suitable socket and applying an initial load of 20% of the torsional moment shown in table I, II, or III for the applicable size key or bit, and then releasing the load. An angular reference line shall then be established (see figure 11). Next, the full specified torsional moment shall be applied for at least ten seconds and then released again. The permanent set resulting upon release of the torsional moment shall not exceed ten degrees. Keys or bits having a greater than ten degree permanent set, or showing cracks, rounded corners, or other defects which might affect serviceability shall be considered defective.

Keys and bits with a major diameter or maximum width across flats through 0.250 inch shall then have a torsion load applied until the key of bit fails. Unless failure occurs by a uniform shear fracture, the key or bit shall be considered defective."

PAGE 7

Paragraph 4.4.2.2, delete and substitute:

"4.4.2.2 Torsion test for handles. Keys with a handle or case shall be tested for ability to resist slippage between the handle, shaft, and bit by applying a torsion moment of 50 inch-pounds (or the torsion moment applicable to the bit, if less) to the handle while the key is inserted in the socket used for the torsion test on the bit. Keys with plastic handles shall be subjected to the test within one minute after being uniformly heated to 125 degrees Fahrenheit. Any key showing slippage between components when less than the required torque is applied shall be considered defective."

Paragraph 5.1, delete and substitute:

"5.1 Preservation, packaging, packing, labeling, and marking. The preservation, packaging, packing, labeling, and marking shall be as specified in the contract or purchase order.

PAGE 8

Table I, delete and substitute the following table:

TABLE I. Torsional Moment for Testing Hexagon Keys and Bits.

Nominal Key Size (Width across flats of hexagon in inches)	Torsional Moment (Inch-pounds)
0.028	0.94
0.035	1.80
0.050	5.25
1/16	10.25
5/64	20.00
3/32	35.00
7/64	55.00
1/8	82.00
9/64	118.00
5/32	160.00
3/16	278.00
7/32	440.00
1/4	665.00
5/16	1275.00
3/8	2200.00
7/16	3500.00
1/2	5200.00
9/16	6500.00
5/8	9000.00
3/4	15500.00
7/8	24600.00
1	28800.00

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:38Z
Check the source to verify that this is the current version before use.

PAGE 9

Table II, delete and substitute the following table:

TABLE II. Torsional Moment for Testing Spline Keys.

Nominal Key Size (Major diameter of splines in inches)	Torsional Moment (Inch-pounds)
0.033	0.8
0.048	2.4
0.060	4.5
0.069	7.0
0.072	8.0
0.076	12.0
0.096	19.0
0.111	29.0
0.133	50.0
0.145	65.0
0.168	111.0
0.183	131.0
0.216	216.0
0.251	329.0
0.291	530.0
0.372	1100.0
0.454	2000.0
0.595	4500.0

PAGE 14

Table VIII, columns Y and Z, add "±" in front of "0.063" and "0,125", respectively.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:38Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:38Z
Check the source to verify that this is the current version before use.