INCH-POUND

MIL-DTL-44477A (GL)
9 September 1996
SUPERSEDING
MIL-C-44477 (GL)
8 November 1993

DETAIL SPECIFICATION

CONTAINER, AERIAL DELIVERY, GENERAL PURPOSE, INDIVIDUAL EQUIPMENT

This specification is approved for use by the Natick Research, Development, and Engineering Center, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers one type and size of a parachutist's individual equipment container.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Drawing. The following Government drawing forms a part of this document to the extent specified herein. Unless otherwise specified, the issue is that cited in the solicitation.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, U.S. Army Natick Research, Development, and Engineering Center, Natick, Attn: SSCNC-UTE Natick, MA 01760-5017 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:09Z
Check the source to verify that this is the current version before use.

DRAWING

U.S. ARMY NATICK RESEARCH, DEVELOPMENT AND ENGINEERING CENTER

11-1-6832 - Container, Aerial Delivery, General Purpose, Individual Equipment

(Copies of drawings are available from the U.S. Army Natick Research, Development and Engineering Center, ATTN: AMSSC-S-IMI, Natick, MA 01760-501 7).

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection in accordance with 4.2.

3.2 Materials and components. Materials and components shall conform to the requirements on the applicable drawings, to subsidiary specifications and standards applicable thereto, and as specified herein.

3.2.1 Recycled, recovered, or environmentally referable materials. Recycled, recovered, or environmentally preferable materials should be used to the maximum extent possible provided the material meets or exceeds the operational requirements, and promotes economically advantageous life cycle costs.

3.3 Construction. The construction shall conform in all respects to the drawing listed in Section 2 and all subsidiary drawings pertaining thereto, and as specified herein.

3.3.1 Stitching, machine. All machine stitching shall be as specified on the applicable drawings and as specified herein.

3.3.1.1 Types 301 and 308 stitching. Ends of all type 301 stitching shall be backstitched or overstitched not less than 1/2 inch in accordance with the required stitch pattern. Ends of type 308 stitching shall be secured by crowding a minimum of three stitches (accomplished by not allowing the materials to move) at the beginning and end of the stitching. Thread tension shall be maintained so that there will be no loose stitching resulting in the puckering of the material sewn. The lock shall be embedded in the materials sewn.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:09Z
Check the source to verify that this is the current version before use.

3.3.1.1.1 Repairs of type 301 stitching. Repairs of type 301 stitching shall be as follows:

a. When thread breaks or bobbin run-outs occur during the stitching, the stitching shall be repaired by restarting the stitching a minimum of 1 inch (1/2 inch for box-x and W-W stitching) from the end of the stitching. 1/

b. Thread breaks or two or more consecutive skipped or run-off stitches noted during inspection of the item (in-process or end item) shall be repaired by overstitching. The stitching shall start a minimum of 1 inch from the defective area, (1/2 inch for box-x and W-W stitching), continue over the defective area, and continue a minimum of 1 inch (1/2 inch for box-x and W-W stitching) beyond the defective area onto the existing stitching. Loose or excessively tight stitching shall be repaired by removing the defective stitching, without damaging the materials, and restitching in the required manner. 1/

1/ When making the above repairs, the ends of the stitching are not required to be backstitched.

3.3.1 .1.2 Repairs of type 308 stitching. Repairs of type 308 stitching shall be in accordance with 3.3.1 .1.1 a and 3.3.1 .1.1 b, except that the stitching shall overstitch the defective area a minimum of three stitches onto the existing stitches.

3.3.1.2 Automatic stitching. Automatic stitching machines may be used to perform any of the required stitch patterns provided the requirements for the stitch pattern, stitches per inch, and size and type of thread are met, and at least three or more tying, overlapping, or back stitches are used to secure the ends of stitching.

3.3.2 Thread ends. All thread ends shall be trimmed to a maximum length of 1/4 inch.

3.3.3 Setting of grommets. Holes shall be prepunched to receive the grommets. Holes prepunched to receive the grommets shall be smaller than the outside diameter of the grommet barrel so that the barrel must be forced through the hole. The grommet shall be securely clinched without cutting the adjacent material.

3.3.4 Finishing of the jacketed wire rope ends. All wire rope ends shall be finished by either the melt method specified in 3.3.4.1 or by the dip method specified in 3.3.4.2, such that the ends are completely enclosed with the melted coating flush with the unmelted nylon jacket.

3.3.4.1 Melt method. Heat the wire rope end nylon jacket with a suitable electrical heating element so as to melt the nylon over the end to form a smooth round surface. Remove any melted residue on the jacket surface with a fine abrasive material such that the surface is not damaged and is finished smooth.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:09Z
Check the source to verify that this is the current version before use.

3.3.4.2 Dip method. Coat the wire rope end with a nylon II or nylon 6/6 powder. Heat the coated end for 10 seconds at 405 ± 15°F using either an induction coil (2 to 4-inch) with an automatic timer control or an electric melting pot with an automatic temperature control (see 6.3).

3.4 Replacement of defective components. During the spreading, cutting and manufacturing process, components having material defects or damages that are classified as defects in table I shall be removed from production and replaced with nondefective and properly matched components.

3.5 Repairs. Repairs such as mends, darns, patches, or splices are not permitted on the container.

3.6 Workmanship. The finished and assembled containers shall conform to the quality of the product established by this specification.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.2)
b. Conformance inspection (see 4.3)

4.2 First article inspection. When a first article inspection is required (see 3.1 and 6.2) it shall be examined in accordance with 4.3. Sampling for first article inspection shall be as specified in the contract or purchase order (see 6.2).

4.3 Conformance inspection. Conformance inspection shall include the examination of 4.3.1, 4.3.2, 4.3.3 and 4.3.4. Sampling for the inspections in 4.3.3 and 4.3.4 shall be as specified in the contract or purchase order (see 6.2).

4.3.1 Component and material inspection. Components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.3.2 In-process inspection. Inspection of subassemblies shall be made to ascertain that construction details and dimensional requirements which cannot be examined in the finished product are in accordance with specified requirements. The Government reserves the right to exclude from consideration for acceptance, any material or service for which in-process inspection has indicated nonconformance.

4.3.3 End item visual examination. The end items shall be examined for visual defects. Each noncompliance shall be scored as a defect in accordance with table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:09Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects

Examine	Defect	Classification Major	Minor
Fabric	Any hole (except drill holes), cut, or tear, weak places or broken yarns	101	
	Exposed drill holes		201
Webbing and tape	Not firmly and tightly woven; edge frayed or scalloped	102	
	Exposed end of tie-down tapes not dipped in wax as required		202
	Exposed end of nylon webbing or tape end not seared smooth as required		203
Fastener tape, hook and pile	Any hole, cut, or tear. Hooks missing or flattened; foreign matter or dirt impairing proper function	103	
Hardware	Broken or bent; corroded areas; burrs or sharp edges	104	
	Any required component not specified type or size	105	
	Any required component not functioning, improperly set or reversed	106	
Brass grommets	Clinched excessively tight, cutting adjacent material	107	
	Insecurely clinched to a degree that grommet may be detached from material	108	
	Washer installed on incorrect side of material		204
	Barrel split		205
	Loosely clinched, permitting grommet to rotate freely within the hole		206
	Washer omitted	109	
Open seams and run-offs	1/2 inch or less		207
	More than 1/2 inch	110	

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:09Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd.)

Examine	Defect	Classification Major	Minor
	NOTE: A scam shall be classified as open when one or more stitches joining a seam are broken or when two or more skipped stitches or run-offs occur. On a double stitching seam, a seam shall be considered open when either one or both sides of the scam are open.		
Binding	Improperly or loosely applied showing raw edge of fabric	111	
	End of binding not finished as specified or overlapped less than 1 inch		208
Seam and stitch type	Wıong seam or stitch type	112	
Stitch tension	Loose, resulting in a loosely exposed top or bobbin thread; tight, resulting in excessive tightness of fabric on seams	113	
Stitches per inch	One stitch less than minimum specified		209
	Two or more stitches less than minimum specified	114	
	One or two stitches in excess of maximum specified		210
	More than two stitches in excess of maximum specified	115	
	NOTE: Variation in the number of stitches per inch, caused by the operator speeding up the machine and pulling the fabric in order to sew over heavy places, heavy seams or in turning corners, shall be classified as follows: a. Within the major defect classification - minor defect b. Within the minor defect classification - no defect		

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:09Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd.)

Examine	Defect	Classification Major	Classification Minor
Stitching margins	Larger than specified by more than 3/1 6 inch for more than 2 inches		211
Thread breaks	Not overstitched as specified		212
	NOTE: Thread breaks not overstitched shall be classified as open seams.		
Stitching ends	Ends of stitching backstitched less than 1/2 inch (except where ends are turned under in a hem or held down by other stitching)		213
	Ends of stitching not backstitched	116	
Stitching	Any required row of stitching omitted (except on W-W stitching)	117	
	W-W stitching:		
	One or more rows of stitching omitted	118	
	Length of stitching less than specified by more than 1/4 inch	119	
Components and assembly	Any component or required operation omitted or not as specified (unless otherwise classified herein)	120	
	Needle chews	121	
	Mends, darns, or patches	122	
	Any turn under on stitched ends of webbing not securely caught in W-W stitching	123	
	Turn under on ends of straps, chapes, and loops less than specified by more than 1/8 inch		214
Marking and identification	Omitted, illegible, incorrect, misplaced, or size of characters not as specified		215
Clearness	Noticeable spots or stains, i.e., grease, oil, ink, dirt not removed; thread ends not trimmed to 1/4 inch or less		216

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:09Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd.)

Examine	Defect	Classification Major	Minor
Jacketed wire rope	Not specified type or size	124	
	Ends not nylon coated or wire material not completely enclosed	125	
	Surface of nylon coated end not smooth or flush with unmelted jacketed surface	126	
Swaged wire rope sleeve	Missing	127	
	Not specified type or size	128	
	Not swaged as specified	129	
	One sleeve swage omitted		217
	Two sleeve swages omitted	130	
	Swaged excessively tight, cutting wire rope material	131	
	Swaged loosely, permitting sleeve to rotate freely	132	

4.3.4 End item dimensional examination. The end items shall be examined for conformance to the dimensions specified on the drawings. Only those dimensions that can be evaluated without damaging or disassembling the end items shall be examined. Any dimension not within the specified tolerance shall be classified as a defect.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When actual packaging of materiel is to be performed by DoD personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activity within the Military Department or Defense Agency, or within the Military Department's System Command. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature which maybe helpful, but is not mandatory).

6.1 Intended use. The container assembly is used by airborne personnel during parachute operations.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:09Z
Check the source to verify that this is the current version before use.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number and date of this specification
b. When first article is required (see 3.1)
c. Sampling plan, lot size, sample size (see 4.3)
d. Packaging requirements (see 5.1)

6.3 Source of heat sealing. A source for the requirement of sealing and forming the ends of the nylon jacketed wire rope (see 3.3.4.2- induction coil dip method) is Boyd Coatings Research Co., Inc., 51 Parmenter Road, Hudson, MA 01749.

6.4 Subject term (key word) listing.

Air delivery
Carrier

6.5 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodian:
Army - GL

Review activity
Army - AV

Preparing activity:
Army - GL

(Project 1670-A855)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T02:09Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	MIL-DTL-44477A (GL)	96 09 09

3. DOCUMENT TITLE: Container, Aerial Delivery, GEneral Purpose, Individual Equipment

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial	(2) AUTOVON
U.S. Army Natick RD&E Center	508-233-5175	256-5175
c. ADDRESS (Include Zip Code) Commander, U.S. Army Natick RD&E Center ATTN: SSCNC-WEF Natick, MA 01760-5018	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

DD Form 1426, OCT 89 — Previous editions are obsolete — 198/290

Source: https://assist.dla.mil - Downloaded: 2026-10-22T02:09Z
Check the source to verify that this is the current version before use.

NATICK OPI, 1 MAR 96 NATICK OPI, JUL 91 IS OBSOLETE.