J-C-103b
MAY 2, 1960
SUPERSEDING
Int. Fed. Spec. J–C–00103a (COM–NBS)
April 6, 1956 and
Fed. Spec. J–C–103
October 23, 1941

FEDERAL SPECIFICATION

CABLE, POWER, ELECTRICAL, (RUBBER-INSULATED, BUILDING-TYPE) AND WIRE, ELECTRICAL, (RUBBER-INSULATED, BUILDING-TYPE)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—This specification covers cable and wire for building purposes which employ copper or aluminum, solid or stranded conductors, insulated with rubber or neoprene (see 6.6) for 0- to 5000-volt service. Types RU RUH, RUW, and all neoprene R insulations are limited to 600-volt service. Types RW and RHW insulations with fibrous coverings must be suitably shielded for 2000- to 5000-volt service. (See 6.7.)

1.2 Classification

1.2.1 *Types.*—Insulated wire in accordance with this specification shall be furnished in the following types, as specified in the invitation for bids:

Type designation	Insulation	Temperature Limit	
		Dry	*Wet*
		°C.	° C.
R	*Code	60	---
RW	*Moisture resistant	60	60
RH	*Heat resistant	75	---
RHW	*Heat and moisture resistant	75	75
RU	*Latex	60	---
RUH	*Latex heat resistant	75	---
RUW	*Latex moisture resistant	60	60
All Neoprene R Polymerized chloroprene		60	---

* Rubber, see 6.6.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:07Z
Check the source to verify that this is the current version before use.

1.2.1.1 Unless otherwise specified in the invitation for bids (see 1.2.2), wires and cable of the type designations in 1.2.1, with the exception of All Neoprene R, shall be furnished with a single copper conductor and a fibrous covering; All Neoprene R shall be furnished with a single copper conductor and a neoprene sheath.

1.2.1.2 The following letter suffixes indicate modifications of the type designations in 1.2.1, when specified in the invitation for bids:

(AL) designates an aluminum conductor in lieu of copper.

(D) designates a twin wire or cable having two rubber-insulated fibrous-covered conductors laid parallel under an outer fibrous covering.

(M) designates a cable having two or more rubber-insulated fibrous-covered conductors twisted together under and outer fibrous covering.

(L) designates a wire or cable having an outer covering of lead.

(N) designates a wire or cable having a neoprene covering in lieu of a fibrous covering.

For example, the combination of letters RD(AL) represents a twin wire cable having two aluminum conductors each covered with code-type insulation and a fibrous covering, laid parallel under an outer fibrous covering, and R(N) represents a single copper conductor having code-type insulation and a neoprene jacket or covering.

1.2.2 *Voltages.* — The maximum working voltages of wire and cable in accordance with this specification shall be 600, 1,000, 2,000, 3,000, 4,000, or 5,000 volts, as specified in the invitation for bids. The letter designations shown in 1.2.1 when used alone indicate conductors for use at not more than 600 volts. Wire and cable for use at higher voltages shall be indicated by adding numeral suffixes to the type letters in 1.2.1 and 1.2.1.2 as follows:

10 for use at not more than 1,000 volts.
20 for use at not more than 2,000 volts.
30 for use at not more than 3,000 volts.
40 for use at not more than 4,000 volts.
50 for use at not more than 5,000 volts.

For example, R(AL) represents a single aluminum conductor having rubber insulation of the code type and a fibrous covering designed for use at not more than 600 volts and R(AL)20 represents a single aluminum conductor having rubber insulation of the code type and a fibrous covering designed for use at not more than 2,000 volts.

1.2.3 *Sizes.*—Wire and cable in accordance with this specification shall be of the following sizes as specified in the invitation for bids:

Type	AWG or circular-mil size of conductor
R, RW, RH, and RHW	14 to 2,000,000
RU**, RUH**, and RUW**	14 to 2
All Neoprene R*	14 to 1,000,000

* 600-volt service only.

** Single conductor, 600-volt service only.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards.—The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification:

Federal Specifications:

J–C–98 — Cable and Wire, Insulated; Methods of Sampling and Testing.

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.

Fed. Std. 123 — Marking for Domestic Shipment (Civilian Agencies).

Fed. Test Method Std. No. 601—Rubber; Sampling and Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:07Z
Check the source to verify that this is the current version before use.

in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

Military Specifications:

MIL–C–12000—Cable, Cord, and Wire, Electric, Packaging and Packing of

Military Standards:

MIL–STD–105 — Sampling Procedures and Tables for Inspection by Attributes.

MIL–STD–109 — Inspection Terms and Definitions.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications.—The following document forms a part of this specification. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply:

Underwriters' Laboratories, Inc., Standards:

UL–44 — Standard for Rubber-Covered Wires and Cables.

(Copies may be obtained from the Underwriters' Laboratories, Inc., 161 Sixth Avenue, New York 13, N. Y.; 207 East Ohio Street, Chicago 11, Illinois; or 1655 Scott Lane, Santa Clara, California.)

3. REQUIREMENTS

3.1 Cable and wire furnished under this specification shall conform to the requirements of Underwriters' Laboratories, Inc., Standard No. 44 for Rubber-Covered Wires and Cables.

3.2 Wire and cable furnished under this specification shall be not more than one year old from the date of manufacture.

3.3 Fire and casualty hazards.

3.3.1 Each bidder shall submit to the contracting agency proof that the wire and cable he proposes to supply under this specification conforms to the requirements of Underwriters' Laboratories, Inc., Standard No. 44 for Rubber-Covered Wires and Cables. The label or listing of the Underwriters' Laboratories, Inc., may be accepted as evidence that the wire or cable conforms to this requirement.

3.3.2 In lieu of the label or listing, the bidder may submit independent proof satisfactory to the contracting agency that his wire or cable conforms to the applicable requirements of the published standards including methods of tests of the Underwriters' Laboratories, Inc., Standard No. 44 for Rubber-Covered Wires and Cables.

3.3.3 Compliance with the above preliminary requirements in regard to fire and casualty hazards does not absolve the bidder from complete compliance with the requirements of this specification in order to secure acceptance of his material.

4. SAMPLING, INSPECTION AND TEST PROCEDURES

4.1 Sampling, non-military.

4.1.1 *Lot.*—Unless otherwise specified in the invitation for bids, the lot shall be formed as described in paragraph 3 of section 6 of Federal Specification J–C–98.

4.1.2 *Sampling for inspection and tests.*—Unless otherwise specified in the invitation for bids, the sample shall be taken as described in paragraph 6 of section 6 of Federal Specification J–C–98.

4.2 Visual inspection, nonmilitary.

4.2.1 Each inspection unit in the sample, 4.1.2, as well as the package from which the inspection unit is taken, shall be examined visually before any tests are made. Visual inspection shall cover construction, tinning of

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:07Z
Check the source to verify that this is the current version before use.

TABLE I.—*Group A inspection*

Inspection	Requirement paragraph	Inspection paragraph	AQL	
			Major	Minor
			Percent	*Percent*
Visual and mechanical:				
General construction Tinning Splices Marking Type of conductor (diameter) Lubrication of neoprene insulation Joints Repairs	----------	----------	1.0	4.0
Electrical:	*J–C–98*			
Resistance of conductor	6021	4.4.3	1.0**	*
Insulation resistance	6031	4.4.7.2		
Dielectric strength	6111	4.4.7.1		

* All electrical defects are considered major.
** 1.0 percent unless otherwise specified.

conductors, splices, marking, type of conductor, lubrication of neoprene insulation and jacket, joints and repairs, and may be limited to that part of the package which is visible without unrolling.

4.3 General inspection, Military.

4.3.1 *Definitions.*—Military Standard MIL–STD–109 applies for definitions of inspection terms used herein.

4.3.2 *Acceptance inspection.* — Acceptance inspection shall consist of group A, group B, and group C inspection in 4.3.2.1 through 4.3.2.3.1. Group B inspection shall normally be performed on lots that have passed Group A inspection and on samples selected from units that have been subjected to and met the group A inspection. However, the order may be varied when the Government considers it more practical to select separate samples for group B or group C inspection or both.

4.3.2.1 *Group A inspection.*—Group A inspection including sampling shall be in accordance with table I and Military Standard MIL–STD–105. Group A inspection shall be performed in any order which is satisfactory to the Government inspector.

4.3.2.2 *Group B inspection.*—This inspection including sampling shall conform to table II and to Military Standard MIL–STD–105. Unless otherwise specified herein, normal inspection shall be used at the start of the contract. The reduced inspection procedure shall be R–1.

4.3.2.2.1 *Group B sampling plans.* — The group B sampling plans as listed in table II shall be as follows:

AQL	Inspection level for normal inspection	Inspection level for reduced inspection
Percent		
6.5 ----------	L–7	L–5

4.3.2.2.2 *Order of inspection within group B.*—Group B inspection shall be performed in any order which is satisfactory to the Government inspector.

4.3.2.2.3 *Procedure in the case of failure.* —If an inspection lot is rejected, the contractor shall immediately investigate the cause of failure and shall report to the Government inspector the results thereof and

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:07Z
Check the source to verify that this is the current version before use.

TABLE II.—*Group B inspection*

Inspection	Requirement paragraph	Inspection paragraph	Sampling plan
Subgroup 1:	*J–C–98*		
Average thickness of insulation	1011	4.4.3	See 4.3.2.2.1
Minimum thickness of insulation (less than nominal 3/64 inch)	1014	4.4.3	
Minimum thickness of insulation (nominal 3/64 inch and over)	1011	4.4.3	
Thickness of braid	1111	4.4.3	
Thickness of cotton tape	1121 or 1124	4.4.3	
Thickness of lead covering	1311 or 1313	4.4.3	
Thickness of neoprene sheath, average and minimum	1331	4.4.3	
Lay of pitch, lay of twist	1521	4.4.3	
Tangent of angle between braid and axis of wire cable	1611	4.4.3	
Tangent of angle between serving or wrap and axis of wire or cable	1621	4.4.3	
Picks per inch	8011	4.4.3	
Yarn size	8041	4.4.3	
Length of lay, wrap or serving	1531	4.4.3	
Carriers and ends per carrier, braids	8021	4.4.3	
Subgroup 2:	-----	4.4.4	6 specimens per 100,000 feet
Accelerated aging	4031	4.4.4.1	
Air oven test	4011	4.4.4.2	
Oxygen pressure test	4021	4.4.4.3	
Air pressure test	4223	4.4.4.4	
Change in tensile strength after oil immersion			
Subgroup 3:			
Flame resistance, fibrous covering except tapes	5211	4.4.3	6 specimens per 100,000 feet or fraction thereof
Flame resistance, neoprene insulation and sheath	5211	4.4.3	
Subgroup 4:			
Moisture resistance, fibrous coverings other than tape	8221	4.4.3	6 specimens per 100,000 feet or fraction thereof
Moisture absorption, insulation	8211	-----	

details of the corrective action taken. If the contractor and Government inspector cannot agree on the effectiveness of the corrective action, the matter shall be referred to the contracting officer for resolution.

4.3.2.3 *Group C inspection.*—This inspection shall be as listed in table III.

4.3.2.3.1 *Specimens.*—Six specimens shall be prepared and tested from each lot of 500,000 feet or fraction thereof of cable and wire. If each of the 6 specimens meet the specified requirements, accept the lot.

4.3.2.3.1.1 If 2 or more of the 6 specimens fail to meet the specified requirement, the lot shall be rejected.

4.3.2.3.1.2 If only 1 of the 6 specimens fails to meet the specified requirements, a second sample of 6 specimens shall be tested. Lot acceptance shall be permitted only if in the combined sample of 12 specimens not more than one specimen fails to meet the requirements. Failure of 2 or more specimens in the combined first and second samples shall result in lot rejection.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:07Z
Check the source to verify that this is the current version before use.

TABLE III.—*Group C inspection*

Inspection	Requirement paragraph	Inspection paragraph	Sampling plan
	J–C–98		
Recovery	3161	4.4.3	6 specimens per 500,000 feet
Tensile strength, insulation and neoprene sheath	3021	4.4.3	
Elongation, insulation and neoprene sheath	3031	4.4.3	
Specific inductive capacity	6271	----	

4.3.2.3.2 *Noncompliance.* — If a lot fails group C inspection, the contractor shall immediately investigate the cause of failure and shall report to the Government inspector the results thereof and details of the corrective action taken on the process and on all units of product which were manufactured with the same conditions, materials, processing, etc. If the Government inspector does not consider that the corrective action will enable the product to meet the specified requirement or if the contractor cannot determine the cause of failure, the matter shall be referred to the contracting officer.

4.3.3 *Disposition of nonconforming product.*—Disposition of lots and sample units rejected during group A or B inspection shall be in accordance with Military Standard MIL–STD–105. The following shall be suitably tagged or identified by equivalent means to indicate the cause of failure and means to correct the fault:

(*a*) Sample units found defective during groups A, B, or C inspection.

(*b*) Inspection lots rejected during group A or B inspection.

(*c*) Product has been reworked as a result of failure during group C inspection.

The required information shall be presented to the Government when the product is submitted and shall become the property of the Government.

4.4 **Tests.**

4.4.1 *Nonmilitary.* — The wire and cable shall be subjected to the tests in 4.4.3 through 4.4.7.3 as described in the referenced methods of Federal Specification J–C–98.

4.4.2 *Military.*—The wire and cable shall be subjected to the tests in 4.4.3 through 4.4.7.3 as described in the referenced methods of Federal Specification J–C–98, modified by the instructions in 4.3.

4.4.3 The applicable methods of tests as described in Federal Specification J–C–98 are listed in table IV.

4.4.4 *Accelerated aging.* — The insulation and neoprene sheath shall be tested for resistance to accelerated aging by the following methods. The change in tensile strength and elongation shall be used to measure the amount of deterioration due to aging. If tube specimens are used for determining the original tensile strength and elongation, tube specimens with the conductor still in the insulation shall be aged, except for oil immersion. When tube specimens are tested for the oil immersion test, the conductor shall be removed before immersing the specimen in the oil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:07Z
Check the source to verify that this is the current version before use.

TABLE IV.—*Methods of tests*

Test	Method in J–C–98
Size of conductor	1431
*Resistance of conductor	6021
Tensile strength, aluminum conductors	3211
Lay of pitch, lay of twist	1521
Average thickness of insulation	1011
Minimum thickness of insulation (less than nominal 3/64 inch)	1014
Minimum thickness of insulation (nominal 3/64 inch and over)	1011
Tensile strength, insulation and neoprene sheath	3021
Ultimate elongation of insulation and neoprene sheath	3031
Average recovery, insulation (except RH and RHW) and neoprene sheath	3161
Thickness of neoprene sheath (Modify thickness of insulation by measuring over and under the jacket)	1013
Minimum thickness of neoprene sheath (Modify thickness by adding "core assembly is removed and specimen of the jacket slipped over the pin of the micrometer)"	1014
Thickness of tape	1124
Thickness of braid	1111
Yarn size, wraps and servings	8041
Tangent of angle between braid yarns and axis of wire or cable	1611
Tangent of angle between serving or wrap yarn and axis of wire or cable	1621
Picks per inch, braid	8011
Coverage, wrap or serving	8131
Length of lay, wrap, or serving except specimen shall be 20 to 24 inches in length	1531
Number of carriers and ends per carrier, braid	8021
Flame resistance, all neoprene R insulation, neoprene sheath, and fibrous coverings except tapes	5211
Moisture resistance, fibrous coverings other than tapes	8221
Flexibility and finish, fibrous coverings	2041
Identification of neoprene insulation and sheath (chloroprene)	7251
Thickness of lead covering	1311 or 1313

* The temperature corrections in Underwriter's Standard No. 44 shall be used.

4.4.4.1 *Air oven test.* — RU, RUH, RUW, and All Neoprene R insulation and the 60° C. neoprene sheath for R, RW, RU, and RUW insulated wires shall be tested as described in method 4031 of Federal Specification J–C–98 with the following exceptions:

Type	Time of exposure	Temperature of exposure
Insulation RU and RUW	96 hrs	------
Insulation RUH	60 days	81° to 83° C. (177.8° to 181.4° F.)

4.4.4.2 *Oxygen pressure test.*—All insulation, the 60° C. neoprene sheath for R, RW, RU, and RUW insulated wires and the 75° C. neoprene sheath for RH, RHW, and RUH insulated wires shall be tested as described in method 4011 of Federal Specification J–C–98 with the following exceptions:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:07Z
Check the source to verify that this is the current version before use.

Type	Time of exposure	Temperature of exposure
Insulation RH, RHW, RUH	166 ± 1 hr	79° to 81° C. (174.2° to 177.8° F.)
75° C. neoprene sheath for RH, RHW, and RUH insulated wires	166 ± 1 hr	79° to 81° C. (174.2° to 177.8° F.)

4.4.4.3 *Air pressure test.*—RH, RHW, and RUH insulation and 75° neoprene sheath for RH, RHW, and RUH insulated wires shall be tested as described in method 4021 of Federal Specification J–C–98.

4.4.4.4 *Resistance to oil.*—All Neoprene R insulation and 65° and 75° neoprene sheath shall be tested as described in method 4223 of Federal Specification J–C–98, except that the tensile strength of the specimen shall be based on the cross-sectional area obtained before oil immersion.

4.4.4.5 *Rubber content, RU, RUH, and RUW insulation.*—A composite sample of the insulation shall be prepared from the inspection units in the sample as described in method 1211 of Federal Test Method Standard No. 601. The rubber content shall be determined as described in method 16111 of Federal Test Method Standard No. 601.

4.4.6 *Composition of lead sheath.*—A composite sample of the lead sheath shall be prepared by taking equal portions from each inspection unit in the sample and thoroughly blending the portions. The composition of the sheath shall be determined as described in method 7231 of Federal Specification J–C–98 except that two specimens from the composite sample shall be tested.

4.4.7 *Electrical tests.* — Electrical tests should be made in the plant of the manufacturers of the wire or cable under the supervision of the Government inspector. (See 6.4.)

4.4.7.1 *Dielectric strength.* — All of the wire or cable in the delivery shall be subjected to the dielectric strength test described in method 6111 of Federal Specification J–C–98 except that the capacity of the test circuit shall be not less than 5 kilovolt-amperes.

4.4.7.2 *Insulation resistance except RW insulation.*—All of the wire or cable in the delivery except class RW insulation shall be subjected to the insulation resistance test described in method 6031 of Federal Specification J–C–98 except that the test temperature, voltage, time of immersion, and temperature correction factors in Underwriters Laboratories, Inc., Standard No. 44 shall be used.

4.4.7.3 *Capacitance and stability factor for RW insulation.*—The change in capacitance of each inspection unit in the sample shall be determined as described in method 6271 of Federal Specification J–C–98 with the following exceptions: (1) The specimen shall be dried in air for 24 hours at a temperature of 70° ± 2° C. and allowed to cool to 50° C. before immersion in water. (2) The temperature of the water during immersion is 50°C. (3) A 60-cycle alternating current at an average stress of 80 volts per mil is used. (4) Three specimens shall be tested. (5) The power factor using a 60-cycle alternating current at an average stress of 80 and 40 volts per mil is determined after 1 and 14 days of immersion.

4.5 Compliance criteria, non-military.

4.5.1 *Inspection.*—If one or more of the packages, 4.1.2, fails to conform to the requirements for which inspection was made, 4.2, the lot from which the packages were taken shall be considered to have failed to meet the requirements of this specification.

4.5.2 *Tests.*—Compliance of the lot with respect to the tests enumerated in 4.4.3, 4.4.4,

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:07Z
Check the source to verify that this is the current version before use.

and 4.4.7.3 shall be based on the principles described in section 6 of Federal Specification J–C–98.

4.5.2.1 If the composite sample of insulation, 4.4.5, or lead sheath, 4.4.6, fails to conform to the requirements for rubber content or composition of the lead sheath, respectively, the lot of wire from which the sample for inspection was taken shall be considered to have failed to meet the requirements of this specification for rubber content or composition of the lead sheath.

4.5.2.2 Any reel, coil, or roll of wire or cable which shows the presence of a defect or fails to meet the requirement when subjected to the electrical tests in 4.4.7.1 or 4.4.7.2 shall be considered to have failed to meet the requirements of this specification. If after the defects are repaired and the roll, reel, or coil is again subjected to the dielectric strength and insulation resistance tests, the presence of a defect is not shown, the roll, reel, or coil shall be considered to have met the requirements of this specification for dielectric strength and insulation resistance.

4.6 Compliance criteria, Military.

4.6.1 The compliance criteria shall be as set forth in 4.3 except that for rubber content, 4.4.5, and composition of lead sheath, 4.4.6, which shall be as given in 4.5.2.1.

5. PREPARATION FOR DELIVERY

(For civil agency procurement the levels of preservation, packaging and packing protection used are defined in Federal Standard No. 102.

5.1 Nonmilitary.

5.1.1 *Packaging.*—Unless otherwise specified, level C packaging of Federal Standard No. 102 shall be used.

5.1.2 *Packing.*—Unless otherwise specified, level C packing of Federal Standard No. 102 shall be used. The material shall be packed in a manner which will insure arrival at destination in satisfactory condition and which will be acceptable to the carrier at lowest rate.

5.1.3 *Marking.*—Shipping containers shall be marked with the name of the material, conductor size, type of insulation, and quantity contained therein, as defined by the contract or order under which the shipment was made, the name of the contractor, and the number of the contract or order. In addition to any special marking in the contract or order, it shall be marked in accordance with Federal Standard No. 123.

5.2 Military.

5.2.1 *Packaging.*

5.2.1.1 *Level A.*—The cable and wire shall be preserved and packaged as specified for level A preservation and packaging in Military Specification MIL–C–12000.

5.2.1.2 *Level C.*—The cable and wire shall be preserved and packaged as specified for level C preservation and packaging in Military Specification MIL–C–12000.

5.2.2 *Packing.*

5.2.2.1 *Level A.*—The cable and wire shall be packed in accordance with Level A packing requirements of Military Specification MIL–C–12000.

5.2.2.2 *Level B.*—The cable and wire shall be packed in accordance with Level B packing requirements of Military Specification MIL–C–12000.

5.2.2.3 *Level C.*—The cable and wire shall be packed in accordance with Level C packing requirements of Military Specification MIL–C–12000.

5.2.3 *Marking.*—Cable and wire shall be marked in accordance with Military Specification MIL–C–12000.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:07Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Ordering data.—Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

(*a*) Title, symbol, and date of this specification.

(*b*) Type, (1.2.1, 1.2.1.1, 1.2.1.2), size, and service voltage.

(*c*) Level of packaging and packing required.

6.2 If laboratory tests are required, purchasing officers should order wire or cable for test purposes as required by Federal Specification J–C–98, in addition to the number of feet required for installation.

6.3 Underwriters' Laboratories, Inc., Standard No. 44 for Rubber-covered Wire and Cables referenced in 3.1 includes all bulletins and amendments to the Standard issued by Underwriters' Laboratories, Inc.

6.4 Underwriters' Laboratories, Inc., Standard No. 44 for Rubber-Covered Wire and Cable permits a substitution of the spark test in place of part of dielectric strength and insulation resistance tests for 600 volt wire and cable. Since the spark test is usually conducted as a part of the manufacturing process, the dielectric strength and insulation resistance (when required) should be specified in the invitation for bids and arrangements should be made with the manufacturer for witnessing the tests in his plant.

6.5 Transportation description.—Transportation description applicable to this item is:

Aluminum cable:

Cable, electric, aluminum, with or without steel core, insulated.

Carload minimum weight 30,000 pounds.

Truckload minimum weight 30,000 pounds.

Copper cable:

Carload minimum weight 30,000 pounds.

Truckload minimum weight 30,000 pounds.

6.6 Throughout the specification the term "rubber" is used to designate compounds employing natural rubber, polybutadiene (BR), copolymers of butadiene and styrene (SBR), or blends thereof. The term "neoprene" is used to designate the synthetic rubber "polychloroprene".

6.7 Classes RW and RHW fibrous-covered wires are recognized by Underwriters' Laboratories, Inc., for ratings greater than 2000 volts, only if provided with suitable shielding.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded, by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTEREST:
Army—O Sig E
Navy—Y S MC
Air Force.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:07Z
Check the source to verify that this is the current version before use.