INCH-POUND

MIL-R-7885D
AMENDMENT 1
31 March 1994

MILITARY SPECIFICATION

RIVETS, BLIND, STRUCTURAL, MECHANICALLY LOCKED SPINDLE AND FRICTION LOCKED SPINDLE, GENERAL SPECIFICATION FOR

This amendment forms a part of MIL-R-7885D, dated 18 April 1988, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 1

1.2: Under Type I, Style A Add:

"Class 3 - 100° Flush shear head rivets."

PAGE 9

4.6.4 and 4.6.5: Add the following sentence:

"The load rate shall not exceed 110,000 pounds per minute per square inch of fastener cross sectional area up to the approximate yield load after which it may be increased."

4.6.4: Add the following sentence:

"Rivets shall be tested at max. grip in coupons of 1/2 G thickness where G = Max. Grip. Spacers may be installed on the blind side for rivet grips greater than those listed in Table III."

PAGE 26

Table XV: Hole Dimensions - Type I. For .125 diameter (Style B), change hole diameter from ".145" to ".144".

PAGE 27

TABLE XIX: Change tolerances on listed installation hole diameters from "+.0000 - .0005" and "+.0005 -.0000" to ±.0005."

PAGE 30

Figure 3 change Note 1 to read :

"1. Material: Alloy Steel, 46 min. HRC."

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-17T09:25Z
Check the source to verify that this is the current version before use.

Type I rivets, change Note 4 to read:

"Material: Alloy steel 46 min. HRC, 2024-T3 Aluminum alloy or 7075-T6 Aluminum alloy."

Figure 5 change to read:

Delete 2 inch square dimensions from the coupons for both Type I and Type II rivets.

Add "T" dimension to indicate total coupon thickness for Type I rivets.

Add Note 5 to Type I:

"5. Size and configuration of coupon is optional, sufficient material is required to support the load."

Add Note 3 to Type II:

"3. Size and configuration of coupon is optional, sufficient material is required to support the load."

PAGE 33

Figure 6: Redraw ends of middle sheets to show they are defined by "Y" dimension.

PAGE 35

Figure 10 change to read:

Change .75 inch minimum edge distance as dimensioned on drawing to "2D min." with "3/" beneath it.

Change .75 min. for the hole spacing as dimensioned on drawing to "3D min." with "3/" beneath it.

Change Note 1 to read:

"1/ Material: Alloy steel 46 min. HRC. When testing aluminum rivets, test plates made of 2024-T3 or 7075-T6 may be used."

Add Note 2:

"2/ Number of holes and configuration of test plate is optional."

Add Note 3:

"3/ D = DIA. of rivet."

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T09:25Z
Check the source to verify that this is the current version before use.

Custodians:
Army - AR
Navy - AS
Air Force - 99

Review Activities:
Army - AV
Air Force - 82

User Activities:
Navy - MC

Preparing Activity:
DLA - IS
(Project No. 5320-0812)

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T09:25Z
Check the source to verify that this is the current version before use.