NOT MEASUREMENT SENSITIVE

MIL−L−7870B
AMENDMENT 1
20 December 1994

MILITARY SPECIFICATION

LUBRICATING OIL: GENERAL PURPOSE, LOW TEMPERATURE

This amendment forms a part of MIL−L−7870B, dated 24 July 1992, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 3

2.2: Add "ASTM D4636 Standard Test Method for Corrosiveness and Oxidation Stability of Hydraulic Oils, Aircraft Turbine Engine Lubricants, and Other Highly Refined Oils".

PAGE 9

Delete Table IV. and substitute:

"TABLE IV. Test methods for oil properties.

CHARACTERISTICS	ASTM TEST METHODS
Corrosion and oxidation stability	[1] D4636
Pour point	D97
Flash point (open cup method)	D92
Precipitation number	D91
Viscosity	D445
Color	D1500
Evaporation loss of lubricating greases and oils	D972
Acid number	D974

[1] Test shall be run for 168 hours at 135°C. Use hexane, heptane, and/or acetone to clean coupons. Use Alternate Procedure 2."

Custodians:
Army − AT
Navy − AS
Air Force − 11

Preparing activity:
Air Force − 11

(Project 9150−1142)

Review activities:
Army − MI, SM
Navy − OS, SA, SH
Air Force − 68
DLA − GS

AMSC N/A

FSC 9150

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T09:22Z
Check the source to verify that this is the current version before use.