COMMERCIAL ITEM DESCRIPTION

PRIMER COATING (GENERAL PURPOSE, AEROSOL)

The General Services Administration has authorized the use of this commercial item description in preference to TT-P-605.

This description covers an aerosol primer for general purpose interior and exterior use on metals, wood, and plastic surfaces.

Salient characteristics

The aerosol primer shall be furnished in nominal 1-pint commercial pressurized dispenser with a net content of 369g minimum. The total solids shall be at least 78g and the lead content shall not be more than 0.06 percent by weight of nonvolatiles. The contents shall be dispersible by hand shaking for 1 minute at standard conditions. The valve shall spray easily with moderate finger pressure and close immediately upon release of pressure. The spray shall be without sputtering and a smooth and uniform film shall be deposited. The can shall deliver at least 98 percent by weight of contents.

Drying time.[1/] The primer shall dry-to-touch within 10 minutes, dry-through within 2 hours, and have no aftertack after 48 hours (ASTM D 1640).

Color.[1/] The color shall be a general match to the color specified (ASTM D 1729).

Specular gloss.[1/] The 60° specular gloss shall be between 25 and 50 (ASTM D 523).

Flexibility.[1/] The primer shall bend over a 1/8 inch mandrel at 0° and 25° C without cracking or flaking (ASTM D 1737).

Lifting.[1/] After drying at standard conditions for 4 hours, the primer shall not wrinkle or lift when recoated with the same primer, and when recoated a second time with the same primer after drying for 24 hours at standard conditions.

Immersion resistance.[1/] The primer shall not blister, soften, or show other film defects after immersion in distilled water for 18 hours at 25° C. The film shall be unchanged after 24 hours of drying at standard conditions.

Knife test.[1/] The primer shall ribbon or curl and not flake or powder, and show bevelled edges at a cut made with a craftsmans knife (curved blade).

The issues of the ASTM standards in effect on the date of the solicitation shall be used to determine compliance with these requirements.

Certification. The contractor shall certify that the product offered meets the salient characteristics of this description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices, and is the same product sold in the commercial marketplace. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements. The manufacturer shall utilize recovered materials to the maximum extent practicable.

Packaging, packing, and marking. Packaging, packing, and marking shall be as specified in the contract or order.

1/ Spray two coats, each consisting of 1 horizontal and 1 vertical pass, from a distance of 175 to 225 mm to clean cold rolled steel panels (SAE steel No. 1010, dead soft, Finish A, 1/32 inch). Unless otherwise specified allow to dry for 48 hours at standard conditions.

ASTM standards are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

CIVIL AGENCY COORDINATING ACTIVITIES:

DOT - FAA
NASA - JFK

Preparing Activity:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 20261O-26T08:14Z
Check the source to verify that this is the current version before use.