OK

A-A-2112
November 1, 1982

COMMERCIAL ITEM DESCRIPTION

Costumer, Metal (Contemporary Style)

The General Services Administration has authorized the use of this Commercial Item Description in preference to Interim Federal Specification AA-C-001870.

Salient Characteristics:
The characteristics concisely describe the essential physical and functional/performance characteristics of the commercially available items.

Design. The costumer shall be contemporary style designed for heavy duty office use.

Type I - Round pole with a circular base. Knock-down construction.

Metal. Exposed metal shall be satin finish aluminum with a protective coating, satin finish anodized aluminum, satin finish stainless steel or satin finish chrome plated steel.

Pole. The pole shall be a minimum of one inch diameter capped with metal or high impact plastic.

Hooks. Costumer shall have 4 double hooks (hat and coat) thru bolted with matching bolt head and cap nut. All ends shall have plastic garment protectors. The bottom of the hooks shall be a minimum of 56" from the floor. Alternatively, the hooks may have ball ends and be attached to the pole with pop rivets.

Identification label. The label shall have the contractor's name or trademark, contract number, NSN (if specified), month and year of manufacture legibly marked with permanent dark ink. The label shall be affixed to the bottom of the base and shall not be removable by hand without defacement after being affixed for 4 hours.

Workmanship. Edges and corners shall be eased. Metal shall be free of sharp edges and burrs to prevent injury to personnel or damage to their clothing. Chromium plating shall be free of pits, blisters, stains and brush or grind marks.

Performance. Each unit shall comply with the following requirements. Failure of any costumer to comply with these requirements shall be cause for rejection.

FSC 7110

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:19Z
Check the source to verify that this is the current version before use.

Stability test. The manufacturer shall develop a device for suspending weight from the coat hook and hat hook. The device shall hold the weight within two inches from the end of hooks and not allow the weights to hang more than 15 inches below the hook. One of the top sets of hooks on one side of the costumer shall be loaded as follows: The hat hook shall be loaded with 20 pounds and the coat hook loaded 50 pounds. Any tipping, instability, deformation, or loosening of pole from base of the costumer shall be reason for rejection.

Hook test. All four hooks shall be loaded as specified as above. Any permanent set or loosening of the hooks from the pole shall be reason for rejection. In addition, any distortion of the pole or loosening of the pole from the base shall be reason for rejection.

Level test. Place unit on a level surface plate. If a 1/16 inch thick feeler guage can be easily inserted under the base at any point, the unit shall be rejected.

Chromium plating test. Plated samples shall be tested for corrosion in accordance with the 5 percent neutral salt spray at 95 degrees F in accordance with ASTM Test Method B-117. Test period shall be not less than 48 hours. After the specified exposure is completed, the specimen shall be visually examined to assure that the plating shows no evidence of peel, chip, uneven color, powder film, pits or stain. Widely scattered spots of corrosion are permitted, however, none of these spots shall exceed 1/16" along the greatest dimension.

Regulatory Requirement. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practicable.

Packaging, packing and marking. Packaging, packing and marking shall be as specified in the Solicitation.

ASTM Test Method. Copies of the ASTM Test Method B-117 are obtainable from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:19Z
Check the source to verify that this is the current version before use.