COMMERCIAL ITEM DESCRIPTION

SOAP, SCOURING (CAKE)

The General Services Administration has authorized the use of this commercial item description in lieu of Federal Specification P-S-571.

This commercial item description covers cake scouring soap intended for use in cleaning glass and porcelain surfaces.

Salient characteristics:

Appearance. The cakes shall be homogeneous in appearance and texture; firm, not crumbly and free from cracks, crushed edges and holes.

Moisture and volatile matter at 105° C. The soap cakes shall have a maximum of 5.0 percent by weight moisture and volatile matter at 105° C when tested in accordance with ASTM D 460, Section 11.

Matter insoluble in water. The soap cakes shall contain at least 85 percent water-insoluble matter using ASTM D 460, Section 19. Not more than 1 percent by weight of matter insoluble in water shall be retained on a No. 100 U.S. Standard sieve.

Total alkali. The total alkali, calculated as Na_2O shall be not more than 0.8 percent when tested as specified in ASTM D 460, Sections 21-22.

Anhydrous soap. The cake soap shall contain not less than 6.0 percent anhydrous soap using ASTM D 460, Sections 21-22.

Performance. When tested as follows the scouring soap shall remove all the test soil and not scratch the glass panel.

Make the soiling mixture by mixing the following ingredients to form a smooth paste:

Ingredient	Percent by weight
Lanolin, anhydrous	38.0
Asphalt (conforming to ASTM D 312, type II)	12.0
Turpentine	20.0
Lubricating oil, automotive, 30W, nondetergent	15.0
Lampblack (conforming to ASTM D 209)	15.0

Apply a thin, even film of the soiling mixture to one side of a clean, scratch-free 4 by 4-inch window-glass pane. Dampen a wad of clean cloth of soft material like unsized cotton and rub it on the soap cake so as to pick up approximately two grams of soap. Apply the soap to the soiled glass panel with a circular hand motion and let dry, forming a film. Wipe the dried film off the glass panel with a clean, dry cloth. The soiling mixture shall have been completely removed from the panel. There shall be no streaks or scratches on the glass panel. There shall be no fine abrasion of the glass surface which causes distortion or blurring of images seen through the glass panel.

The issues of the ASTM standards in effect on the date of the solicitation shall be used to determine compliance with these requirements.

Certification. The contractor shall certify that the product offered meets the salient characteristics of this description, and that the product conforms to the producer's own drawings, specifications, standards and quality assurance practices and is the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance prior to the first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Packaging, packing, and marking. The packaging and packing shall be in accordance with normal commercial practice and shall assure acceptance by common carrier and provide product protection against loss and damage during multiple shipments, handling and storage. The shipping container shall be in compliance with the National Motor Freight Classification and Uniform Freight Classification.

ASTM standards are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19130.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:04Z
Check the source to verify that this is the current version before use.