
MILITARY SPECIFICATION SHEET


CAPACITORS, FIXED, CERAMIC DIELECTRIC, (GENERAL PURPOSE), ESTABLISHED RELIABILITY STYLE CKR76 (FEEDTHROUGH)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the capacitors described herein shall consist of this specification and the latest issue of MIL-C-39014.




INCHES	MM	INCHES	MM
.001	.03	.078	1.98
.004	.10	.093	2.36
.005	.13	.100	2.54
.010	.25	.164	4.17
.018	.46	.187	4.75
.023	.58	.216	5.49
.025	.64	.250	6.35
.031	.79	.267	6.78
.050	1.27	.325	8.26
.051	1.30	.340	8.64
.073	1.85	.631	16.03




CASE
CIRCUIT DIAGRAM



APPROX ACTUAL SIZE



HEX NUT



LOCKWASHER
MS 35333-72

NOTES:
1. Dimensions are in inches.
2. Unless otherwise specified, tolerances are ±.031(.79 mm).
3. A nut and internal tooth lock washer shall be supplied with each capacitor.

FIGURE 1. Style CKR76 capacitors.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T17:26Z
Check the source to verify that this is the current version before use.

REQUIREMENTS:

Dimensions and configuration: See figure 1.

Case type: Feedthrough.

Capacitance value: See table I.

Capacitance tolerance: +80, -20 percent.

Operating temperature range: -55°C to +125°C.

Voltage rating: 200 volts dc at 85°C, derated linearly to 100 volts dc at 125°C (see figure 3).

Current rating: 10 amperes, maximum.

Dissipation factor: Not more than 3.0 percent.

Dielectric withstanding voltage:

Application of test voltage: Between one capacitor-element terminal and the case.

Barometric pressure:

Method 105, MIL-STD-202, condition B (50,000 feet).
Application of test voltage: Between one terminal and the case.
Test potential: 150 percent of dc rated voltage.

Insulation resistance:

Measured between one terminal and the case: Not less than the value specified in table I.

Insertion loss: Not applicable.

Seal: Not applicable.

Solderability: Method 208, MIL-STD-202, two terminals.

Voltage-temperature limits: In accordance with MIL-C-39014.

Capacitance change with reference to 25°C		For capacitance
Steps A through D of table V Bias = 0 volts	Steps E through G of table V Bias = rated voltage	
±15 percent	+15, -25 percent	Less than 1,000 pF
+22, -56 percent	+22, -66 percent	1,000 pF and greater

Immersion:

IR: Not less than 3,000 megohms.
ΔC: ±20 percent from initial measured value.

Salt spray (corrosion): In accordance with MIL-C-39014.

Terminal strength: Not applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T17:26Z
Check the source to verify that this is the current version before use.

Moisture resistance:

Application of test voltage: Between one terminal and the case.
IR: Not less than 3,000 megohms.
ΔC: ±20 percent from initial measured value.

Resistance to soldering heat:

ΔC: Less than ±20 percent from initial measured value.
Cooling time prior to measurement after test: 1 ±.1 hour.

Life:

Rated conditions: 100 percent of dc rated voltage at 85°C.

0 through 3,000 hours:

IR: At 25°C not less than 50,000 megohms.
At 125°C not less than 5,000 megohms.
ΔC: ±20 percent from initial measured value.
Dissipation factor: Not greater than 3.0 percent.

4,000 through 32,000 hours:

IR: At 25°C not less than 10,000 megohms.
At 125°C not less than 1,000 megohms.
ΔC: ±20 percent from initial measured value.
Dissipation factor: Not greater than 3.0 percent.

Accelerated conditions, 200 percent of dc rated voltage at 85°C.

0 and 250 hours:

IR: At 25°C not less than 50,000 megohms.
At 125°C not less than 5,000 megohms.
ΔC: ±20 percent from initial measured value.
Dissipation factor: Not greater than 3.0 percent.

1,000, 2,000 and 4,000 hours:

IR: At 25°C not less than 10,000 megohms.
At 125°C not less than 1,000 megohms.
ΔC: ±20 percent from initial measured value.
Dissipation factor: Not greater than 3.5 percent.

Marking: Marking shall consist of the "J" certification mark and the military part number as shown on figure 2.



FIGURE 2. Hex flats - expanded view.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T17:26Z
Check the source to verify that this is the current version before use.




FIGURE 3. Voltage derating with temperature.

Part number: M39014/18- (dash number from table I).

NOTE: Installation torque should not exceed 5 inch-pounds.

TABLE I. Electrical characteristics and dash number.

Capacitance	Insulation resistance		Dash number Failure rate level (percent per 1,000 hours)			
	25°C	125°C	1.0(M)	0.1(P)	0.01(R)	0.001(S)
pF	GΩ	GΩ				
10	0.1	0.01	0321	0341	0361	0381
22	"	"	0322	0342	0362	0382
47	"	"	0323	0343	0363	0383
100	"	"	0324	0344	0364	0384
220	"	"	0325	0345	0365	0385
470	"	"	0326	0346	0366	0386
1000	"	"	0327	0347	0367	0387
1500	"	"	0328	0348	0368	0388
5000	0.05	0.005	0329	0349	0369	0389
10000	"	"	0330	0350	0370	0390
15000	"	"	0331	0351	0371	0391
27000	"	"	0332	0352	0372	0392

Supersession data: Data numbers previously listed in this specification sheet were for capacitance values and tolerances that are not available for this style; no specific item to item replacement is recommended.

Revision letters are not used to denote changes due to the extensiveness of the changes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T17:26Z
Check the source to verify that this is the current version before use.

Custodians:
Army - ER
Navy - EC
Air Force - 11
NASA - NA

Review activities:
Navy - OS, TD
DLA - ES

User activities:
Navy - AS, SH, MC

Agent:
DLA - ES

Preparing activity:
Navy - EC

(Project 5910-1508-3)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T17:26Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY
Naval Electronic Systems Command
Washington, DC 20363

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12503 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

COMMANDER
NAVAL ELECTRONIC SYSTEMS COMMAND
DEFENSE STANDARDIZATION PROGRAM BRANCH
DEPARTMENT OF THE NAVY
WASHINGTON, DC 20363
ATTN: ELEX 8111

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T17:26Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-C-39014/18H	CAPACITORS, FIXED, CERAMIC DIELECTRIC

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

Source: https://assist.dla.mil -- Downloaded: 202610-21T17:26Z
Check the source to verify that this is the current version before use.

be used ... shall be used ... the circuit on figure 4, or equivalent, shall