MIL-C-24643/6B
3 October 1986
SUPERSEDING
MIL-C-0024643/6A(SH)
8 November 1985
MIL-C-24643/6
28 September 1984

MILITARY SPECIFICATION SHEET

CABLE, ELECTRICAL, 600 VOLTS, A.C., TYPE LSMDY

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the cable described herein shall consist of this specification and the latest issue of MIL-C-24643.

REQUIREMENTS:

Qualification required.

Construction (watertight)

First - Copper conductor, uncoated (see table I for size).
Second - Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third - Ethylene propylene rubber or cross-linked polyethylene insulation (see table I for wall thickness).
- Standard identification code applied by method 1.
Fourth - Nineteen conductors, cabled together with a lay not greater than 24 times the pitch diameter of the layer. Cabling sequence to be consecutive, starting with no. 1, from the center outward. Fillers shall be used to form a firm, well-rounded assembly.
Fifth - Binder tape applied helically with overlap.
Sixth - Cross-linked polyolefin jacket.
Seventh - Braided metal armor.
Eighth - Cross-linked polyolefin jacket (see table I for wall thickness). Cable surface marking required.

(B) denotes changes.

AMSC N/A FSC 6145
DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:55Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/6	Type and size	Conductor size AWG	Insulation thickness (min) (inch)	Inner cable jacket thickness (nominal) (inch)	Diameter over armor (nominal) (inch)	Cable jacket thickness (nominal) (inch)	Overall diameter		Conductor resistance per 1000 feet (max) (ohms)	Insulator resistance (megohms)	Cold bending mandrel (inches)
							minimum (inches)	maximum (inches)			
-01AN	LSMDY-6	12(class B)	0.028	0.050	1.000	0.060	1.120	1.190	1.715	100	15
-02AN	LSMDY-14	9(class B)	.040	.050	1.380	.060	1.500	1.570	0.859	100	21
-03AN	LSMDY-23	7(class B)	.052	.085	1.710	.075	1.880	1.960	.542	100	25
-04AN	LSMDY-40	4(class C)	.052	.065	1.960	.075	2.150	2.240	.270	90	29
-05AN	LSMDY-60	2(class D)	.052	.065	2.250	.075	2.425	2.525	.171	75	33

EXAMINATION AND TESTS:

	Requirements
Basic electrical:	
Conductor resistance - ohms/1000 feet at 25°C, maximum..	(see table I)
Voltage withstand - volts, root mean square, minimum	
Conductor to conductor.....	2500
Conductor to armor.....	2500
Armor to water.....	500
Insulation resistance - megohms/1000 feet, minimum.....	(see table I)
Conductor continuity.....	No failure
Group A:	
Visual and dimensional.....	No failure
Watertightness - see MIL-C-24643 for limits of water leakage (with outer jacket removed).....	No failure
Group B:	
Cold bending, cable - (see table I for mandrel diameter).....	No damage
Drip - 95 ± 1°C.....	Zero
Tear - pounds per inch thickness, minimum (ASTM D 470)..	35
Physicals (unaged)	
Insulation	
Ethylene propylene rubber	
Tensile strength - lb/in^2, minimum.....	700
Elongation - percent, minimum.....	250
Cross-linked polyethylene	
Tensile strength - lb/in^2, minimum.....	1800
Elongation - percent, minimum.....	250
Jacket (cable)	
Tensile strength - lb/in^2, minimum.....	1300
Elongation - percent, minimum.....	160

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:55Z
Check the source to verify that this is the current version before use.

EXAMINATION AND TESTS: (Continued)

	Requirements
Group C:	
Physicals (aged)	
Insulation	
Ethylene propylene rubber	
Air oven	
Tensile strength - percent of unaged, minimum	75
Elongation - percent of unaged, minimum	75
Cross-linked polyethylene	
Air oven	
Tensile strength - percent of unaged, minimum	80
Elongation - percent of unaged, minimum	80
Jacket (cable)	
Air oven	
Tensile strength - percent of unaged, minimum	60
Elongation - percent of unaged, minimum	60
Hot oil immersion	
Tensile strength - lb/in^2, minimum	50
Elongation - percent, minimum	50
Shrinkage	No failure
Permanence of printing (jacket) - cycles, minimum	250
Permanence of printing (conductor) - cycles, minimum	50
Cable filler removability	No failure
Heat distortion - percent of unaged, maximum	30
Armor - conformance to material construction and coverage	No failure

QUALIFICATION INSPECTION:

Qualification inspection shall include basic electrical, all of groups A, B and C, plus the following:

Aging and compatibility (cable)(125 ± 5°C)	No failure
(B) Abrasion resistance (jacket) - scrapes, minimum	75
Acid gas equivalent - percent, maximum	
Jacket	2
Fillers	2
Insulation	18
Halogen content - percent, maximum	
Jacket	0.2
Fillers	0.2
Flame propagation (cable)	No failure
Immersion (jacket)	
Tensile strength - percent of unaged, minimum	50
Elongation - percent of unaged, minimum	50

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:55Z
Check the source to verify that this is the current version before use.

QUALIFICATION INSPECTION: (Continued)

	Requirements
Smoke index, maximum	
Jacket	25
Fillers	--
(B) Insulation	45
Toxicity index, maximum	
Jacket	5
Fillers	5
Insulation	1.5
Durometer outer (jacket) - (type A) hardness, minimum	80
Weathering (jacket)	No failure

UNIT ORDERING LENGTH: 1000 feet (nominal)

NOTE: Not for Air Force use.

Custodians:
Army - MI
Navy - SH

Review activities:
Army - AV, CR, ER
Navy - EC
DLA - IS

User activities:
Army - ME, AR, AL
Navy - CG

Preparing activity:
Navy - SH
(Project 6145-1005-06)

☆U.S. GOVERNMENT PRINTING OFFICES: 1988 — 704-036/45590

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:55Z
Check the source to verify that this is the current version before use.