INCH-POUND
MIL-DTL-24643/12F
1 October 2009
SUPERSEDING
MIL-DTL-24643/12E
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -20 °C TO +90 °C, 300 VOLTS, TYPE LSTTOP

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction, Non-Watertight

First	-	Copper conductor, coated or uncoated, 20 AWG, Class K stranding.
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation. Minimum average wall thickness of 0.020 inch. Telephone identification code applied by Method 3.
Fourth	-	Two conductors shall be cabled together to form pair. The length of lay shall be determined to permit a completed cable to meet the twisting and bending endurance tests.
Fifth	-	The specified number of pairs (see table I) shall be cabled together in one or more layers, with the minimum amount of fillers necessary to obtain a firm well-rounded assembly. Cabling sequence to be consecutive, starting with no. 1, from the center outward. The length of lay shall be determined to permit a completed cable to meet the twisting and bending endurance tests. A single pair shall not be used as center for the cable core. Outer layer shall be left-hand. Inner layer(s) direction of lay shall be at the manufacturer's option.
Sixth	-	An optional binder.
Seventh	-	Cross-linked polyolefin jacket. Minimum average wall thickness of 0.060 inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:57Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/12	Type and size	Number of pairs	Overall diameter max. (inches)	Roller diameter max. (inches)
-01UN	LSTTOP-3	3	0.480	1.4
-02UN	LSTTOP-5	5	0.590	1.8
-03UN	LSTTOP-10	10	0.700	2.1
-04UN	LSTTOP-15	15	0.830	3.0

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic Electricals:	
Conductor resistance (ohms/1000 feet at 25 °C, max.)	11.53
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	2000
Insulation resistance (megohms/1000 feet, min.)	
Conductor to conductor	100
Conductor continuity	No failure
Group A:	
Visual and dimensional	No failure
Group B:	
Thermoset proof test (percent, max.)	
Insulation	50
Jacket (when tested at 200 °C)	50
Twisting and bending endurance (see table I for roller sizes)	
At 75 °C (cycles, min.)	6000
At minus 30±2 °C (cycles, min.)	2000
Physicals (unaged)	
Insulation (extruded)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:57Z
Check the source to verify that this is the current version before use.

Tear – (lb/in thickness, min.)	35
Group C:	
Physicals (aged) air oven	
Insulation (extruded)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Group D:	
Flame propagation (cable)	No failure
Qualification Inspection:	
Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:	
Aging and compatibility (cable) (125±5 °C)	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2
Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	45

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:57Z
Check the source to verify that this is the current version before use.

Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LSTTOP-3, 5, and 10	2500
LSTTOP-15	1500

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2008-016)

Review Activities:
Army – AR, AV, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:57Z
Check the source to verify that this is the current version before use.