INCH-POUND
MIL-DTL-24643/2F
1 October 2009
SUPERSEDING
MIL-DTL-24643/2E
22 August 2002

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -20 °C TO +90 °C, 300 VOLTS, TYPE LSDCOP AND LSTCOP

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction, Non-Watertight

First	-	Copper conductor, coated or uncoated (see table I for size).
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation with minimum average wall thickness of 0.015 inch. Standard identification code applied by Method 3.
Fourth	-	The specified number of conductors (see table I) shall be cabled together with a left-hand lay. The length of lay shall be as required for the completed cable to meet the twisting and bending endurance tests. A tie cord shall be laid straight as a central core in LSDCOP-1½. Fillers may be used as necessary to form a firm well-rounded assembly.
Fifth	-	An optional binder.
Sixth	-	Cross-linked polyolefin jacket. Minimum average wall thickness of 0.030 inch.

NOTE: Because of the peculiar lay-up of LSDCOP-1½ cable, the centering and circularity requirements shall not apply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:53Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/2	Type and size	Conductors		Conductor resistance (ohms)	Overall diameter	
		No.	Size AWG		min. (inch)	max. (inch)
-01UN	LSDCOP-1	2	20 (Class B)	11.42	0.235	0.250
-02UN	LSDCOP-1½	2	18 (Class K)	9.00	0.300	0.315
-03UN	LSDCOP-2	2	18 (Class K)	7.16	0.310	0.330
-04UN	LSTCOP-2	3	18 (Class K)	7.16	0.325	0.345

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic Electricals:

Conductor resistance (ohms/1000 feet at 25 °C, max.)	See table I
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	1500
Insulation resistance (megohms/1000 feet, min.)	
Conductor to conductor	100
Conductor continuity	No failure

Group A:

Visual and dimensional	No failure

Group B:

Thermoset proof test (percent, max.)	
Insulation	50
Jacket (when tested at 200 °C)	50
Twisting and bending endurance	
At 75 °C (cycles, min.)	6000
At minus 30±2 °C (cycles, min.)	2000

NOTE: Roller diameters for bending endurance test shall be as follows:

Cable type and size	Roller diameter (inch, max.)
LSDCOP-1	0.75
LSDCOP-1½	0.95
LSDCOP-2	1.00
LSTCOP-2	1.00

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:53Z
Check the source to verify that this is the current version before use.

Physicals (unaged)	
Insulation (extruded)	
Tensile strength (lb/in^2, min.)	700
Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1300
Elongation (percent, min.)	160
Tear (lb/in thickness, min.)	35
Group C:	
Physicals (aged) air oven	
Insulation (extruded)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Shrinkage	No failure
Group D:	
Flame propagation (cable)	No failure
Qualification Inspection:	
Qualification inspection shall include basic electricals; Groups A, B, C, and D; plus the following:	
Aging and compatibility (cable) (125±5 °C)	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:53Z
Check the source to verify that this is the current version before use.

Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index, max.	
Jacket	25
Fillers	45
Insulation	45
Toxicity index, max.	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) - Type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
All	500

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

Custodians:
Army – MI
Navy – SH

Preparing Activity:
Navy – SH
(Project 6145-2008-007)

Review Activities:
Army – AR, AV, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:53Z
Check the source to verify that this is the current version before use.