INCH-POUND
MIL-DTL-24643/5H
27 November 2023
SUPERSEDING
MIL-DTL-24643/5G
1 October 2009

DETAIL SPECIFICATION SHEET

CABLE, ELECTRICAL, -4 DEGREES FAHRENHEIT (-20 DEGREES CELSIUS) TO +194 DEGREES FAHRENHEIT (+90 DEGREES CELSIUS), 600 VOLTS, TYPE LSMDU

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-24643.

Construction (Watertight)

First	-	Copper conductor, coated or uncoated (see table I for size).
Second	-	Separator may be used at manufacturer's option where required to provide free-stripping insulation.
Third	-	Thermoset insulation (see table I for wall thickness). Standard identification code applied by method 1 or method 3. If identification method 1 is used, insulation color shall be black.
Fourth	-	Nineteen conductors cabled together in accordance with 3.4.4 of MIL-DTL-24643. Cabling sequence shall be consecutive, starting with pair no. 1, from the center outward. Fillers may be used as necessary to form a firm, well-rounded assembly.
Fifth	-	An optional binder.
Sixth	-	Cross-linked polyolefin jacket. See table I for thickness.

NOTE: Manufacturer's identification tape is required (see 3.4.9 of MIL-DTL-24643).

Distribution Statement A. Approved for public release: distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:54Z
Check the source to verify that this is the current version before use.

TABLE I. Details.

Military part no. M24643/5	Type and size	Conductor size (AWG)	Insulation thickness min. avg. (inch)	Cable jacket thickness min. avg. (inch)	Overall diameter max. (inches)	Conductor resistance (ohms)	Insulation resistance (megohms)
-01UN	LSMDU-6	12 (class B)	0.028	0.060	1.000	1.730	100
-02UN	LSMDU-14	9 (class B)	0.040	0.060	1.395	0.868	100
-03UN	LSMDU-23	7 (class B)	0.052	0.075	1.765	0.598	100
-04UN	LSMDU-40	4 (class C)	0.052	0.075	2.040	0.273	90
-05UN	LSMDU-60	2 (class D)	0.052	0.075	2.330	0.172	75

REQUIREMENTS:

Qualification required.

INSPECTION:

Basic electricals:

Conductor resistance (ohms/1,000 feet at 77 °F [25 °C], max.)	See table I
Voltage withstand (volts, root mean square, min.)	
Conductor to conductor	2,500
Insulation resistance (megohms/1,000 feet, min.)	
Conductor to conductor	See table I
Conductor continuity	No failure

Group A:

Visual and dimensional	No failure
Watertightness (see MIL-DTL-24643 for limits of water leakage)	No failure

Group B:

Cold bending (cable)	No failure
Thermoset proof test (percent, max.)	
Insulation	50
Jacket (when tested at 392 °F [200 °C])	50
Drip (203±1.8 °F [95±1 °C]) (see MIL-DTL-24643 for limits of drip allowance)	No failure
Physicals (unaged)	
Insulation (extruded insulation only)	
Tensile strength (lb/in^2, min.)	700

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:54Z
Check the source to verify that this is the current version before use.

Elongation (percent, min.)	150
Jacket (cable)	
Tensile strength (lb/in^2, min.)	1,300
Elongation (percent, min.)	160
Tear (lb/in thickness, min.)	35

Group C:

Physicals (aged) (air oven)	
Insulation (extruded insulation only)	
Tensile strength (percent of unaged, min.)	75
Elongation (percent of unaged, min.)	75
Jacket (cable)	
Tensile strength (percent of unaged, min.)	60
Elongation (percent of unaged, min.)	60
Permanence of printing (insulation) (cycles, min.)	25
Permanence of printing (jacket) (cycles, min.)	125
Heat distortion (percent of unaged, max.)	30
Cable fill (sealant) removability	No failure
Shrinkage	No failure

Group D:

Flame propagation (cable)	No failure

Qualification inspection:

Qualification inspection shall include basic electricals; groups A, B, C, and D; plus the following:

Aging and compatibility (cable) (257±9 °F [125±5 °C])	No failure
Abrasion resistance (jacket) (scrapes, min.)	75
Acid gas equivalent (percent, max.)	
Jacket	2
Fillers	2
Insulation	18
Halogen content (percent, max.)	
Jacket	0.2
Fillers	0.2
Insulation	0.2

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:54Z
Check the source to verify that this is the current version before use.

Immersion (jacket)	
Tensile strength (percent of unaged, min.)	50
Elongation (percent of unaged, min.)	50
Smoke index (max.)	
Jacket	25
Fillers	45
Insulation	45
Toxicity index (max.)	
Jacket	5
Fillers	5
Insulation	1.5
Durometer (jacket) − type A (hardness, min.)	80
Weathering (jacket)	No failure
Electrical moisture absorption	No failure

UNIT ORDERING LENGTHS:

Type and size	Feet (nominal)
LSMDU-6, LSMDU-14, and LSMDU-23	1,000
LSMDU-40 and LSMDU-60	500

CHANGES FROM PREVIOUS ISSUE: Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extent of the changes.

CONCLUDING MATERIAL

Custodians:
Army – MI
Navy – SH

Preparing activity:
Navy – SH
(Project 6145-2013-022)

Review activities:
Army – AR, CR
Navy – CG, EC
DLA – CC

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:54Z
Check the source to verify that this is the current version before use.