MILITARY SPECIFICATION
HMX/RESIN EXPLOSIVE COMPOSITION
LX-14-0
(For Use in Ammunition)

This Amendment forms a part of Military Specification MIL-H-48358 (AR) dated 30 September 1977.

Page 2

Table I - after MIL-P-63196 add "Type I"

Page 3

3.2.3 Granulation. Correct "compsition" to composition: and "specified-in" to "specified in".

Page 4

3.4 Foreign matter. Correct "woods" to "wood".

4.3.1 Submission. Add "The sample shall be obtained from a production lot which has been produced by the contractor using the same production processes, procedures, and equipment as will be used in fulfilling the contract. All materials shall be obtained from the same sources of supply as will be used during regular production."

4.3.3 Rejection. Add "See MIL-A-48078".

Page 9

4.5 Testing. Add "PRECAUTION - This specification covers sampling and testing of toxic and hazardous materials. Accordingly, it is emphasized that all applicable safety rules, regulations, and procedures must be followed in the handling and processing of these materials."

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Armament Research and Development Command, Attn. DRDAR-QA, Dover, New Jersey 07801 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:23Z
Check the source to verify that this is the current version before use.

4.6.3.1 HMX Content. Delete 4.6.3.1.1 and 4.6.3.1.2 in their entirety and substitute the following:

"4.6.3.1.1 Reagent. Prepare the extraction solvent by adding excess RDX and HMX to 1, 2-dichloroethane (EDC). The mixture shall be maintained for at least eight hours at the temperature (± 2°C) at which the analysis will be performed. Prior to use for extraction, the EDC solution shall be agitated for two hours and filtered.

4.6.3.1.2 Procedure. Approximately 2.5g of the dried sample shall be accurately weighed (recorded to the nearest 0.1 mg) and quantitatively transferred to a 250 ml screw cap bottle. Add 150 ml of saturated EDC solution (see 4.6.3.1.1), attach the screw cap, and place the bottle on a mechanical shaker. The bottle shall be shaken at least thirty minutes, until visual examination indicates complete dissolution of the elastomeric binder. The sample solution shall then be transferred to a tared filtering crucible attached to a vacuum flask. About 30 ml of the saturated EDC solution shall then be poured into the bottle, the screw cap replaced, the bottle shaken by hand, and the contents transferred to the filtering crucible. This procedure shall be repeated at least twice in order to remove all residue from the bottle. The bottle and cap shall then be rinsed twice with 30 ml aliquots of the EDC solution, with the washings being transferred to the filtering crucible. The crucible shall then be removed from the flask, 20 ml of the saturated EDC solution shall be added, and the crucible shall be reconnected to the flask, allowing the liquid to filter through the residue. This procedure shall be performed a total of three times. The crucible shall then be removed from the flask and the interior portions beneath the glass frit shall be carefully rinsed with the saturated EDC. After rinsing, the crucible shall again be connected to the vacuum flask and aspirated for approximately two minutes. The crucible shall then be placed in an oven (100 ± 5°C) for one hour, or until dry. After cooling to room temperature the crucible shall be accurately weighed (recorded to the nearest 0.1 mg). The HMX content of the sample shall be calculated as shown below:

Source: https://assist.dla.mil -- Downloaded: 202610-22T19:23Z
Check the source to verify that this is the currentversion before use.

$$\% \text{ HMX} = \frac{100\ (A-B)}{W}$$

A = Final weight of crucible, g

B = Tare weight of crucible, g

W = Sample weight, g

Page 11

6.2 Delete all material following "DRDAR-QA, Dover, New Jersey".

6.3 Change "5703 F1" to "5702 F1 (MIL-P-63169 Type I)" and delete "in accordance with MIL-P-63196".

Custodian:
Army-AR

Preparing Activity:
Army-AR

Project Number: 1376-A149

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:23Z
Check the source to verify that this is the current version before use.