CCC-C-417 (GSA-FSS)
8 July 1952

INTERIM FEDERAL SPECIFICATION

CLOTH; COATED (TABLE AND SHELF)

(This Interim Federal Specification has been prepared by the Federal Supply Service, General Services Administration, based upon currently available technical information, but has not been approved for promulgation as a Federal specification. It is subject to modification, and pending its promulgation as a regular specification, may be used in procurement.)

1. SCOPE AND CLASSIFICATION

1.1 Scope.- Oilcloth covered by this specification is primarily intended for table covers and shelf covers.

1.2 Classification.

1.2.1 Type.- Oilcloth covered by this specification shall be of one type as defined herein.

1.2.2 Color.- The color of the oilcloth shall be of the following, as specified:

White	Green	Red	GSA stock colors
Black	Orchid	Yellow	

1.2.3 Grade.- The oilcloth shall be of a grade known commercially as firsts.

2. APPLICABLE SPECIFICATIONS

2.1 Specifications.- The following Federal Specification, of the issue in effect on date of invitation for bids, forms a part of this specification:

CCC-T-191 Textile Tests Methods.

(Copies of Federal specifications and the Federal Specifications Index may be obtained upon application, accompanied by money order, coupon, or cash, to the Superintendent of Documents, Government Printing Office, Washington 25, D. C., or to the GSA Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, and Seattle. Prices may be obtained from the Superintendent of Documents or from the GSA Regional Offices.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

(Copies of this and other Interim Federal Specifications may be obtained upon application the to the issuing agency or to the GSA Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, and Seattle.)

2.2 Specifications and other publications applicable only to individual departments are listed in section 7.

3. REQUIREMENTS

3.1 Material.

3.1.1 Basic cloth.- The basic cloth shall be made of clean cotton yarns, the cloth weighing not less than 1 pound per 5.29 yards in the gray using 55-inch width basis. This cotton cloth is known commercially as 55-inch 5.29 sheeting, count 40 x 38.

3.1.2 Coating.- The glazed surface shall be elastic and smooth and be of either oil or synthetic resin.

3.1.3 Width.- The width of the coated cloth shall be 54 inches. A tolerance of plus or minus 1/2 inch will be permitted.

3.1.4 Strength.- The breaking strength (grab method) of the coated fabric shall be not less than 35 pounds in the warp and not less than 25 pounds in the filling.

3.1.5 Weight.- The weight per square yard of the coated fabric shall be not less than 9.4 ounces. In case of dispute the weight of the roll shall be taken and this shall be not less than 10.6 pounds per 12 yards of 54-inch material.

3.1.6 Blocking.- When tested in accordance with paragraph 4.3 there shall be no evidence of blocking. The surfaces shall be free of adhesion.

3.1.7 Cracking.- The glazed coated surface shall not crack when creased surface side out.

3.1.8 Length of roll.- The length of roll shall be 12 to 12½ yards.

3.1.9 Workmanship.- The workmanship shall be free from avoidable imperfections in manufacture and from defects or blemishes affecting the appearance or serviceability.

4. SAMPLING, INSPECTION AND TEST PROCEDURES

4.1 Sampling.- Not less than one sample shall be taken at random from each 1,000 yards or fraction thereof, except when the shipment is over 10,000 yards, in which case a sample shall be taken from each one-tenth of the shipment. Each sample shall be at least 1 yard long by the full width of the material.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

4.2 Inspection.- Inspection shall be made at the point of delivery or at the factory at the discretion of the purchasing agent.

4.3 Tests.- Unless otherwise specified, tests shall be conducted in accordance with the applicable methods described in Federal Specification CCC-T-191.

5. PREPARATION FOR DELIVERY

5.1 Packaging.- Unless otherwise specified, commercial packages will be acceptable under this specification.

5.2 Packing.- The oilcloth shall be prepared for shipment to permit acceptance by carrier for transportation at the lowest applicable rate, and to afford maximum protection for normal hazards of transportation.

5.3 Marking.- Unless otherwise specified, shipping containers shall be marked with the name and color of the material, as defined by the contract or order under which the shipment is made, the quantity contained therein, the name of the contractor, the number of the contract or order, the name and address of the consignee, and the gross weight.

6. NOTES

6.1 Purchasers should specify the color or pattern required and should exercise any desired options offered herein. (See 1.2, 5.1, and 5.3).

6.2 Patent notice.- When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever, and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

7. DEPARTMENTAL REQUIREMENTS

7.1 Army.- (To be supplied)

7.2 Navy.- (To be supplied)

7.3 Air Force.- (To be supplied)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.