CCC-C-417c
October 27, 1964

SUPERSEDING
Int. Fed. Spec. CCC-C-00417b (GSA-FSS)
December 21, 1962 and
Fed. Spec. CCC-C-417a
April 1, 1953

FEDERAL SPECIFICATION

CLOTH, COATED (TABLE AND SHELF)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. The coated cloth covered by this specification consists of a cotton base cloth coated on one side with oleoresinous or synthetic resin compound, and is primarily intended for table and shelf covers.

1.2 Classification.

1.2.1 *Type and colors.* Cloth covered by this specification shall be of one type, and unless otherwise specified shall be of the following solid colors, (see 3.2.5 and 6.1):

White
Green
Red
Yellow

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

CCC-T-191—Textile Test Methods.
PPP-P-51—Packaging, Packing and Marking of Textile Fabrics (Woolens, Worsteds, Cottons, Silks, and Synthetics).
PPP-B-636—Box, Fiberboard.
UU-P-268—Paper, Kraft, Untreated, Wrapping.
UU-T-111—Tape, Paper, Gummed (Sealing and Securing).

Federal Standard:

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, and Auburn, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

Military Standard:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards require by contractors in connection with specific

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 **Other publications.** The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids shall apply.

Color Association of the United States, Inc.:

Standard Color Card of America.

(Copies of this color card may be obtained from the Textile Color Card Association of the United States, Inc., 200 Madison Avenue, New York 16, N. Y.)

3. REQUIREMENTS

3.1 Material

3.1.1 *Base cloth.* The base cloth shall be woven from cotton yarns of which the cotton has been thoroughly cleaned, carded or combed, and evenly spun, (see 6.2).

3.1.2 *Coating compound.* The coating compound used for facing the cloth shall be oleoresinous (vegetable oil and clays) or synthetic resin, pigmented to meet the specified color requirements. A certificate of compliance shall be furnished by the contractor to the procurement officer stating the type of oil or resin utilized.

3.2 **Coated cloth.** The coated cloth shall consist of a base cloth as specified in 3.1.1 and shall be coated on one side. The coated cloth shall meet the following requirements when tested as specified in table IV.

3.2.1 *Breaking strength.* The breaking strength of the coated cloth shall be not less than 35 pounds in the warp direction and not less than 25 pounds in the filling direction when tested as specified in table IV.

3.2.2 *Weight.* The weight per square yard of the coated cloth shall be not less than 6.97 ounces when tested as specified in table IV.

3.2.3 *Blocking.* Coated cloth shall show no evidence of blocking (scale rating of 1) when tested as specified in table IV.

3.2.4 *Cracking.* Coated cloth shall show no signs of cracking or flaking when tested as specified in 4.3.1.

3.2.5 *Colors.* Colors as specified in 1.2.1 shall approximately match the following cable numbers of the Standard Color Card of America:

White—Cable No. 70001
Green—Cable No. 70167
Red—Cable No. 70042
Yellow—Cable No. 70205

3.2.5.1 *Matching.* Colors shall be matched to the cable numbers as specified in 3.2.5, or when other colors are required and a standard color referenced, under natural (north sky) daylight or artificial daylight having a color temperature of 7500° Kelvin and shall be a good approximation to the standard sample under incandescent lamplight at 2800° Kelvin.

3.2.5.2 *Colorfastness to crocking.* Coated cloth shall show no less than good colorfastness to wet and dry crocking when tested as specified in table IV.

3.2.5.3 *Colorfastness to light.* Coated cloth shall show no less than good colorfastness to light after 40 hours exposure when tested as specified in table IV, except the color red, which shall show no less than fair colorfastness to light after 40 hours exposure.

3.2.6 *Finish.* Coated cloth shall have a glazed or satin finish. Except where one of the two finishes is unacceptable for a specific end use the other finish shall be required. The finish shall be plain (void of any pattern).

3.2.7 *Width.* Coated cloth shall have a width of 54 inches, plus or minus 1/2 inch.

3.2.8 *Length.* Unless otherwise specified the length of coated cloth shall be 12-1/2 yards in one continuous piece, put-up in roll or bolt form.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

3.2.9 *Toxicity.* Coated cloth shall have no adverse effects on the health of personnel when the item is used for its intended purpose, (see 6.3).

3.3 **Workmanship.** Coated cloth shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels (AQL's).

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 **Responsibility for inspection.** Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 **Inspection for acceptance.** Inspection shall be in accordance with the provisions of MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 *Inspection of components.* In addition to the quality assurance provisions of the subsidiary specifications, components listed in table I will be accepted on the basis of a contractors certificate of compliance with the requirements specified for such characteristics.

TABLE I

Material	Characteristic	Requirement reference
Base cloth	Woven, cotton	3.1.1
Coating compound	Type of coating compound	3.1.2

4.2.2 *Examination of the end item.* The end item shall be examined for the defects listed in 4.2.2.1 and 4.2.2.2.

4.2.2.1 *Yard-by-yard examination.* The required yardage of each roll or bolt shall be inspected on the coated side for the defects listed herein. All defects shall be counted regardless of their proximity, one to another, except where two or more defects represent a single local condition of the cloth, in which case only one defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The unit of product for this examination shall be one linear yard. The sample size shall be in accordance with inspection level II of MIL-STD-105. The AQL shall be 4.0 defects per 100 units (yards). The lot size shall be expressed in units of one yard each and shall not be larger than 22,000 units. An approximate equal number of yards shall be examined from each bolt or roll selected. Not more than 5 yards shall be examined in any roll or bolt. The number of pieces from which the sample is to be selected shall be in accordance with table II.

TABLE II—*Sampling table*

Lot size in yards	Sample size in pieces	Acceptable number
Up to 1,300[1]	3	0
1,301 to 3,200	5	0
3,201 to 8,000	7	0
8,001 to 22,000	10	0

[1]If lot contains less than three pieces, each piece in the lot shall be examined.

Examine	Defect
Coated cloth for coating defects ..	Any uncoated area.
	Any thinly coated area evidenced by light area or window.
	Any separation of coating from base cloth.
	Tacky coating.
	Cracked or checked coating.
	Any blister or lump.
	Nonuniform coating.
	Any wrinkle or crease on coated surface.
Coated cloth for width	Width greater than width specified by more than ½ inch.
	Width less than width specified by more than ½ inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

Examine	Defect
Coated cloth for color and finish ..	Color not as specified or does not match standard sample within established color tolerances when applicable.
	Finish not as specified or does not match finish of standard sample within established tolerances when applicable.
Coated cloth for workmanship	Any cut, hole, tear or scratch or abrasion on coated surface.
	Curled, folded, doubled or rolled edges.

4.2.2.2 *Examination of the end item for defects in length, number of pieces in the roll or bolt.* The sample unit for this examination shall be one bolt or roll. The rolls or bolts to be used in this examination shall be the same as selected in 4.2.2.1. The lot shall be unacceptable if any of the defects listed below are found.

Examine	Defect
Roll or bolt for length	Length of roll or bolt more or less than specified, (see 3.2.8).
	Length of roll or bolt less than length indicated on roll or bolt piece ticket.
Roll or bolt for number and length of pieces	More than 1 piece in roll or bolt.
Roll or bolt for gross length	Actual gross length of rolls or bolts less than the total gross yards marked on piece ticket.

4.2.2.3 *Examination of preparation for delivery requirements.* An examination shall be made to determine that packaging, packing and marking requirements of section 5 of this specification are complied with. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be sealed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 of MIL-STD-105 and the AQL shall be 4.0 defects per hundred units.

Examine	Defect
Marking (exterior and interior).	Omitted, incorrect, illegible, or improper size, location, sequence, or method of application.
	Preshrinkage process is identified by name or trademark on container.
Materials	Any component missing.
	Any component damaged, affecting serviceability.
Workmanship	Inadequate application of components, such as incomplete closure of case liners, container flaps, loose strapping, inadequate stapling.
	Bulging or distortion of containers.
Weight	Gross or net weight exceeds requirements.

4.3 Testing of the end item. Whenever applicable, the methods of testing specified in CCC-T-191, and those listed in table IV, and herein, shall be followed. The requirements specified in section 3, except those for blocking apply to the average of the determinations made on a unit of product for test purposes as specified in applicable test method. For the characteristic "blocking" the requirement shall apply to each determination separately. The unit of product shall be one continuous yard, full width of the finished cloth. The sample size shall be in accordance with table III. The lot shall be unacceptable if one or more units fail to meet a test requirement.

TABLE III

Lot size (yards)	Sample size
800 or less	2
801 to 22,000	3

4.3.1 *Test for cracking.* Cut an 8- by 8-inch specimen of the finished coated cloth,

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

TABLE IV—*Testing*

Characteristic	Test method	Specification requirements	No. of determinations per unit of product	Results reported numerically to nearest:
Identification of cotton	1200	3.1.1	1	Pass or fail
Breaking strength	5100	3.2.1	5 (each direction)	1.0 pounds
Weight of finished cloth	5041	3.2.2	5	0.1 ounce
Blocking	5872	3.2.3	3	Whole scale rating
Colorfastness to:				
Crocking	5650	3.2.5.2	1	Excellent, good, fair or poor
Light	5660	3.2.5.3	1	Excellent, good, fair or poor

Crease the test specimen to form a crease parallel to the direction of the filling yarns of the base cloth. A 10 pound metal roller approximately 5-1/2 inches in diameter and 2 inches in width with a suitable handle shall be rolled one time over the coated cloth specimen while the specimen rests on a hard surface. It shall then be folded in the same position, but the opposite direction and the weight again applied. The specimen shall then be visually examined for cracking or flaking which, if evident, shall be cause for rejection. The results from one specimen shall be reported from each unit of product.

5. PREPARATION FOR DELIVERY

(For civil agency procurement the definitions and application of levels of packaging and packing shall be in accordance with Fed. Std. No. 102.)

5.1 **Packaging.** Packaging shall be level A, B, or C, as specified, (see 6.1 and 6.1.1).

5.1.1 *Military and civil agencies.*

5.1.1.1 *Levels A and C.* Coated cloth put up in rolls or bolts shall be packaged in accordance with the applicable requirements for class 5 fabrics of PPP-P-51.

5.1.2 *Civil agencies.*

5.1.2.1 *Level B.*

5.1.2.1.1 *Standard pack (civil agencies).* Twelve yards of coated cloth of the color specified shall be put up in bolt form by winding the length of cloth full width, without folding, on a flat chipboard or cardboard insert of not less than 1/8 inch thick by 12 ± 1/4 inches wide by 54 ± 1/4 inches long; or at the option of the manufacturer, the put-up may be in roll form on chipboard tube in accordance with requirements of PPP-P-51. Each roll shall be wrapped in accordance with method "D" of PPP-P-51. Bolts, put-up as above, shall be completely wrapped in kraft paper, 30 pounds (minimum) basis weight (24 x 36—500), conforming to grade B of UU-P-268. The bolt shall be so wrapped that the paper shall encircle the bolt twice, with width of paper sufficient to fold over and protect the ends of the bolt. Wrapping shall be secured by gummed paper tape 2-1/2 inches minimum width, conforming to UU-T-111, class 3, applied over the folded ends of wrapping, centered approximately to the width of the bolt. Wrapping shall be applied in a manner which will permit the bolt identification tag attached to edge of material to be on the outside of the wrapped bolt.

5.2 **Packing.** Packing shall be level A, B, or C, as specified (see 6.1 and 6.1.1).

5.2.1 *Military and civil agencies.*

5.2.1.1 *Levels A and C.* The coated cloth shall be packed in accordance with the applicable requirements of PPP-P-51, except that fiberboard or rigid type shipping containers shall be used. In addition, a separator pad, made of A-flute double-faced cor-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

rugated fiberboard having a minimum bursting strength of 200 p.s.i. conforming to the material requirements of PPP-B-636 and measuring one-fourth of an inch less than the inside length and width of the shipping containers, shall be placed between each layer or roll.

5.2.2 *Civil agencies.*

5.2.2.1 *Level B.*

5.2.2.1.1 *Standard pack (civil agencies).* Six rolls or bolts of coated cloth wrapped as specified in 5.1.2.1.1 shall be packed in new fiberboard containers conforming to class domestic, style FTC, FOL, SFF, or RSC-L of PPP-B-636, except that in no event shall the gross weight of box and contents exceed 90 pounds, nor the burst test of the fiberboard be less than 275 p.s.i. Sleeve liner for type RSC-L-boxes shall be of not less than 175 p.s.i., top and bottom full width by full length fiberboard pads shall test not less than 100 p.s.i. Box closure shall be in accordance with appendix to the box specification. According to weight of wrapped bolts or rolls, 12 bolts or rolls of up to 6 pounds each, 8 bolts or rolls of up to 10 pounds each, 6 bolts or rolls of from 11 to 14 pounds, 4 bolts or rolls of from 15 to 21 pounds each, 3 bolts or rolls of from 22 to 28 pounds each, 2 bolts or rolls of from 29 to 42 pounds each, or one bolt or roll of over 43 pounds shall be packed per shipping container. Containers of 6 to 12 bolts or rolls shall be packed with bolts or rolls in two stacks, side by side. Up to four bolts or rolls shall be in a single stack within the container.

5.3 **Marking.**

5.3.1 *Military.* In addition to any special marking required by the contract or order, shipments shall be marked in accordance with PPP-P-51.

5.3.2 *Civil.* In addition to any special marking required by the contract or order, each bolt or roll shall be provided with an identification tag on the outside of the wrapping. No other marking is required for the individual bolts or rolls. Each shipping container shall be marked in accordance with PPP-P-51 and with the additional precautionary markings as follows: For, quantity contained ".... BOLTS—Total yardage .... YDS. or .... "ROLLS—Total yardage .... YDS."

6. NOTES

6.1 **Ordering data.** Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

(*a*) Title, number and date of the specification.
(*b*) Colors required (1.2.1).
(*c*) Finish (3.2.6).
(*d*) Length (3.2.8).
(*e*) Selection of applicable levels of packaging and packing (5.1 and 5.2).

6.1.1 In the preparation of contracts or orders, it must be noted that various options, choices, and alternatives as indicated in PPP-P-51 may be exercised in the preparation for delivery of cloth.

6.2 **Base cloth.** The base cloth which has proved satisfactory for use in the manufacture of the coated cloth covered by this specification is made of cotton; the cloth weighing not less than 1 pound per 5.68 yards in the greige (54-inch width); and the yarns per inch being not less than 40 in the warp direction and not less than 32 in the filling direction.

6.3 **Toxicity.** Question pertaining to toxicity shall be referred by the procuring activity to the appropriate departmental authority which will act as advisor to that procuring activity.

6.4 **Transportation description.** The transportation description and minimum weights applicable to this commodity are:

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.

Rail:

Oilcloth
Carload minimum weight 30,000 pounds.

Motor:

Oilcloth
Truckload minimum weight (W) 30.6 pounds, (W) subject to Rule 115, National Motor Freight Classification.

MILITARY INTERESTS:

Army—GL

Air Force—11

Copies of this specification may be purchased

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:29Z
Check the source to verify that this is the current version before use.