CCC-C-417E
May 1, 1975
SUPERSEDING
Fed. Spec. CCC-C-417D
November 30, 1970

PROPOSED FEDERAL SPECIFICATION

CLOTH, COATED OR LAMINATED (TABLE AND SHELF)

This proposed Federal Specification draft, dated May 1, 1975, prepared by the General Services Administration, Federal Supply Service, Washington, DC 20406, has not been approved for promulgation and is subject to modification. DO NOT USE FOR PROCUREMENT PURPOSES.

1. SCOPE AND CLASSIFICATION.

1.1 Scope. The coated or laminated cloth covered by this specification shall consist of non-woven, woven, or knitted cloth composed of cotton, polyester or cotton-polyester blended yarns; and shall be coated or laminated on one side with a synthetic resin compound. The cloth is primarily intended for use as table and shelf covers.

*1.2 Classification.

1.2.1 Type and colors. Cloth covered by this specification shall be of one type, and unless otherwise specified shall be of the following solid colors, (see 3.2.5 and 6.1):

White
Green
Red
Yellow

2. APPLICABLE DOCUMENTS.

2.1 The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

Federal Specification:

PPP-P-1136 - Packaging and Packing of Coated (Plastic; Rubber) and Laminated Fabrics.

Federal Standards:

Fed. Std. No. 191 - Textile Test Methods.

(Acitivities outside the Federal Government may obtain copies of Federal Specifications, and Standards and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal specifications required by activities outside the Federal Government for bidding purposes are available without charge from the Business Service Centers at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications, Standards, drawings and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

Standard Color Card of America

(Application for copies should be addressed to the Color Association of the United States, Inc., 200 Madison Avenue, New York, NY 10016.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Base cloth. The base cloth shall be a non-woven, woven, or knitted fabric made from cotton, polyester, or cotton-polyester blended yarns (see 4.2.1 and 6.2).

3.1.2 Coating or laminating material. The coating or laminating material used for facing the cloth shall be a synthetic resin pigmented to meet the specified color requirements. A certificate shall be furnished by the contractor to the procurement officer stating the type of resin utilized and that it is nontoxic (see 4.2.1).

3.2 Coated or laminated cloth. The coated or laminated cloth shall consist of a base cloth such as specified in 3.1.1 and shall be coated or laminated on one side. There shall be no striking through of the coating or laminating to the back of the cloth. The coated or laminated cloth shall meet the following requirements when tested as specified in Table III.

3.2.1 Breaking strength. The breaking strength of the coated or laminated cloth shall average not less than 30 pounds in the warp direction and not less than 22 pounds in the filling direction when tested as specified in Table III. When non-wovens are used for backing material the breaking strength shall be 30 pounds in the machine direction and 22 pounds in the cross direction.

3.2.2 Weight. The weight per square yard of the coated or laminated cloth shall be not less than 6.0 ounces when tested as specified in Table III.

3.2.3 Blocking. Coated or laminated cloth shall show no evidence of blocking (scale rating of 1) when tested as specified in Table III.

3.2.4 Cracking. Coated or laminated cloth shall show no signs of cracking or flaking when tested as specified in 4.3.1.

3.2.5 Colors. Colors as specified in 1.2.1 shall approximately match the following cable numbers of the Standard Color Card of America:

White - Cable No. 70001
Green - Cable No. 70167
Red - Cable No. 70042
Yellow - Cable No. 70205

3.2.5.1 Matching. Colors shall be matched to the cable numbers as specified in 3.2.5, or when other colors are required shall match the standard color referenced, under natural (north sky) daylight or artificial daylight having a color temperature of 7500° Kelvin and shall be a good approximation to the standard sample under incandescent lamplight at 2800° Kelvin.

3.2.5.2 Colorfastness to crocking. Coated or laminated cloth shall show a Munsell Value for crocking not lower than 8.5 when tested as specified in Table III.

3.2.5.3 Colorfastness to light. Coated or laminated cloth shall show no less than "good" colorfastness to light after 40 hours exposure when tested as specified in Table III, except the color red, which shall show no less than "fair" colorfastness to light after 40 hours exposure.

3.2.6 Finish. Coated or laminated cloth shall have a plain or satin finish.

3.2.7 Width. Coated or laminated cloth shall have a width of 53 inches, plus or minus 1 inch.

3.2.8 Length and put-up. Unless otherwise specified the length of coated or laminated cloth shall be not less than 12 or more than 12-1/2 yards of one continuous piece, put-up in roll form.

3.3 Workmanship. Coated or laminated cloth shall conform to the quality and grade of product established by this specification. The occurence of defects shall not exceed the applicable acceptable quality level (AQL's).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements as specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except when otherwise indicated hereinafter.

4.2.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase documents. In addition to the quality assurance provisions of the subsidiary specifications, components listed in Table I will be accepted on the basis of a contractors certificate of compliance for the requirements specified for such characteristics.

TABLE I.

Material	Characteristic	Requirements reference
Base cloth	Non-woven, woven or knitted fabric	3.1.1
Coating or laminating compound	Type of coating or laminating compound	3.1.2

4.2.2 Examination of the end item. The end item shall be examined for the defects listed in 4.2.2.1 and 4.2.2.2.

4.2.2.1 Yard-by-yarn examination. The required yardage of each roll shall be inspected on the coated or laminated side for the defects listed herein. All defects shall be counted regardless of their proximity, one to another, except where two or more defects represent a single local condition of the cloth, in which case only one defect shall be counted. A continuous defect shall be counted as one defect for each warpwise yard or fraction thereof in which it occurs. The unit of product for this examination shall be one liner yard. The sample size shall be in accordance with inspection level II of MIL-STD-105. The AQL shall be 4.0 defects per 100 units (yards). The lot size shall be expressed in units of one yard each. An approximate equal number of yards shall be examined from each roll selected.

Examine	Defect
Coated or laminated cloth for coating defects	Any uncoated or unlaminated area. Any thinly coated or laminated areas evidenced by light area or window. Any separation of coating or laminating from base cloth. Tacky coating or laminating. Cracked or checked coating or lamination. Any blister or lump. Nonuniform coating or laminating. Any wrinkle or crease on coated or laminated surface.
Coated or laminated cloth for color and finish	Color not as specified or does not match standard sample within established color tolerance when applicable. Finish not as specified or does not match finish of standard sample within established tolerances when applicable.
Coated or laminated cloth for workmanship	Any cut, hole, tear or scratch or abrasion on coated or laminated surface. Curled, folded, double or rolled edges.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

4.2.2.2 Examination of the end item for defects in length, width, number of pieces in the roll. The sample unit for this examination shall be one roll. The rolls to be used in this examination shall be the same selected in 4.2.2.1. The lot shall be unacceptable if any of the defects listed below are found.

Examine	Defects
Roll for length	Length of roll more or less than specified (see 3.2.8). Length of roll less than length indicated on roll piece ticket.
Roll for number of pieces	More than 1 piece in roll.
Rolls for gross length	Actual gross length of rolls less than the total gross yards marked on piece tickets.
Roll for width	Width greater than specified by more than 1/2 inch. Width less than specified by more than 1/2 inch.

4.2.2.3 Examination of preparation for delivery requirements. An examination shall be made to determine whether packaging, packing and marking requirements of section 5 of this specification are complied with. The examination shall be conducted as specified in PPP-P-1136.

4.3 Testing of the end item. Whenever applicable the methods of testing specified in Fed. Std. No. 191, and those listed in Table III, and herein, shall be followed. The requirements specified in section 3, except those for blocking apply to the average of the determinations made on a unit of product for test purposes as specified in applicable test method. For the characteristic "blocking" the requirement shall apply to each determination separately. The unit of product shall be one continuous yard, full width of the finish cloth. The sample size (number of sample units) shall be in accordance with Table II. The lot size shall be expressed in units of 1 yard. The lot shall be unacceptable if one or more units fail to meet a test requirement.

TABLE II.

Lot size (yards)	Sample size (units)
800 or less	2
801 to 22,000	3
22,001 and over	5

4.3.1 Test for cracking. Resistance to cracking at low temperatures shall be tested in accordance with Table III except that the hydrostatic resistance shall not apply.

TABLE III. Testing

Characteristic	Test method	Specification requirements	No. of determinations per unit of product	Results reported numerically to nearest:
Identification of cotton	1200	3.1.1	1	Pass or fail
Breaking strength	5100	3.2.1	5 (each direction)	1.0 pounds
Weight of finished cloth	5041	3.2.2	5	0.1 ounce
Blocking	5872	3.2.3	3	Whole scale rating
Colorfastness to: Crocking	5651	3.2.5.2	1	Excellent, good, fair or poor
Light	5660	3.2.5.3	1	Excellent, good, fair or poor
Resistance to cracking (low temperature)	5874	3.2.4	--	Pass or fail

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Put-up, packaging, packing and marking. The put-up, packaging, packing and marking shall be in accordance with PPP-P-1136. The level of put-up shall be A or C as specified (see 6.1), the level of packaging shall be A or C as specified (see 6.1), the level of packing shall be A, B or C as specified (see 6.1) and the marking shall be Civil or Military as specified (see 6.1).

6. NOTES

6.1 Ordering data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

a. Title, number, and date of this specification.
b. Colors, required (1.2.1).
c. Finish (3.2.6).
d. Length (3.2.8).
e. Selection of applicable levels of packaging and packing (5.1).

6.2 Base cloth. The base cloth which has provided satisfactory for use in the manufacture of the coated or laminated cloth covered by this specification is made of cotton, polyester, or cotton polyester blended yarns; the cloth weighing not less than 1 pound per 7.5 yards in the greige (54-inch width); and the yarns per inch being not less than 34 in the warp direction and not less than 30 in the filling direction. Knitted or non-woven cloth of equivalent weight and texture are acceptable.

6.3 Toxicity. When required, questions pertaining to toxicity may be referred by the procuring activity to the appropriate departmental authority which will act as advisor to that procuring activity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.