CCC–C–418
15 APRIL 1953
SUPERSEDING
Int. Fed. Spec. CCC–F–21 (GSA–FSS)
10 July 1952 and
Fed. Spec. KK–L–136b
8 October 1945

FEDERAL SPECIFICATION

CLOTH, COATED, UPHOLSTERY (VINYL RESIN BASE)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—Type I, regular coated fabrics, are intended primarily for use as ordinary furniture upholstery covering. Type II, special coated fabrics, are intended for use under abnormal conditions (see 6.1).

1.2 Classification.

1.2.1 *Types, classes, and treatments.*—Coated fabrics covered by this specification shall be of the following types, classes, and treatments, as specified:

Type I.—Regular (see 6.1)
- Class 1.—15.0 ounces per square yard
- Class 2.—18.0 ounces per square yard
- Class 3.—20.0 ounces per square yard
- Class 4.—25.0 ounces per square yard
- Class 5.—29.0 ounces per square yard
- Class 6.—40.5 ounces per square yard

Type II.—Special (see 6.1)
- Class 1.—15.0 ounces per square yard
- Class 2.—18.0 ounces per square yard
- Class 3.—20.0 ounces per square yard
- Class 4.—25.0 ounces per square yard
- Class 5.—29.0 ounces per square yard
- Class 6.—40.5 ounces per square yard

Treatment a.—Flame resistance
- *a*-1.—Permanent resistance
- *a*-2.—Nonpermanent resistance

Treatment *b*.—Mildew resistance
Treatment *c*.—Cold resistance
Treatment *d*.—Oil resistance

2. APPLICABLE SPECIFICATIONS

2.1 Specifications.—The following Federal Specifications of the issues in effect on date of invitation for bids, form a part of this specification:

VV–O–526—Oil; Lubricating, Machine.
CCC–T–191—Textile Test Methods.

(Copies of Federal specifications and the Federal Specifications Index may be obtained upon application, accompanied by check, money order, cash, or Government Printing Office coupons, to the General Services Administration, Business Service Center, Region 3, Seventh and D Streets, S. W., Washington 25, D. C. This office will also honor deposit account numbers issued by the Government Printing Office. Single copies of product specifications required for bidding purposes are available without charge at the GSA Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C. Prices of additional copies may be obtained from the GSA Regional Offices.)

2.2 Specifications and other publications applicable only to individual departments are listed in section 7.

3. REQUIREMENTS

3.1 Materials.

3.1.1 *Base fabric.*—The base fabric shall conform to the requirements of table I. Class 4 is a knitted cotton fabric, all other classes are woven cotton fabrics.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

3.1.2 *Coating.*—The coating shall be plasticized and pigmented polyvinylchloride resin, or copolymer thereof.

3.2 **Physical requirements.** — The coated fabric shall conform to requirements shown in table I, when tested in accordance with the applicable requirements of paragraph 4.3.

3.2.1 *Finish.*—Color and grain shall be as specified.

3.2.2 *Width.* — The width of the finished coated fabric shall be as specified. A minus tolerance of ⅜ inch and plus tolerance of 2 inches will be allowed. (See method 5020.)

3.2.3 *Length of rolls.*—Rolls shall be from 50 to 70 yards in length and contain not more than 3 pieces, none of which shall be less than 15 yards in length. (See method 5010.)

3.2.4 *Elongation (class 4).*—Class 4 coated fabrics when tested in accordance with paragraph 4.3.3, shall have not less than the following minimum elongation at the indicated stresses:

5 pounds—0.25 inch
25 pounds—0.35 inch
50 pounds—0.45 inch

3.2.5 *Colorfastness to crocking.* — Colorfastness to crocking shall have a rating of at least good when tested in accordance with method 5650.

3.2.6 *Accelerated weathering.*—The coated surface shall be exposed to accelerated weathering in accordance with method 5804 200 hours. There shall be no appreciable fading of the color, discoloration, exudation, development of tackiness, or stiffening.

3.2.7 *Blocking.*—The coated surface shall show a rating of not more than 2 when tested in accordance with method 5872.

3.2.8 *Adhesion of coating to fabric base.*—The pull necessary to separate the coating from the fabric shall be not less than 5 pounds per inch of width when tested in accordance with method 5970.

TABLE I.—*Physical requirements*

Class	Suggested base fabric		Finished width (tolerance −⅜ in., +2 ins.)	Finished weight, minimum	Coating weight, minimum	Breaking or bursting strength, minimum		Tearing strength, minimum	
	Width	Commercial designation				Warp	Filling	Warp or wales	Filling or courses
	Inches		*Inches*	*Oz./sq. yd.*	*Oz./sq. yd.*	*Pounds*	*Pounds*	*Pounds*	*Pounds*
1	53	1.32 Sateen	50	15.0	7.0	125	100	3	3
	58	1.21 Sateen	54	15.0	7.0	125	100	3	3
2	53	1.12 Sateen	50	18.0	8.0	140	120	3	3
	58	1.02 Sateen	54	18.0	8.0	140	120	3	3
3	54	1.14 Broken twill	50	20.0	10.5	120	120	3	3
	58	1.06 do	54	20.0	10.5	120	120	3	3
4	60	6.50 Knitted	52	25.0	18.5	150 (burst)		7	5
5	60	11.65 Chafer duck	54	29.0	17.5	140	140	4	4
6	60	11.65 do	54	40.5	29.5	140	140	4	4

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

3.2.9 *Abrasion resistance.* — The surface coating shall not be abraded down to the fabric backing when subjected to 300 double rubs for class 1, 500 double rubs for classes 2 and 3, 1500 double rubs for classes 4 and 5, and 2500 double rubs for class 6 when tested in accordance with paragraph 4.3.4.

3.2.10 *Volatility.*—The loss of weight of the coated fabric shall not exceed 3 percent and there shall be no appreciable change in flexibility when tested in accordance with paragraph 4.3.5.

3.2.11 *Plasticizer extraction.* — The material shall retain substantially all of its original flexibility when tested in accordance with paragraph 4.3.6.

3.2.12 *Cold resistance.*

3.2.12.1 *Type I.* — The coating shall not crack through to the fabric base when tested in accordance with method 5874 at a temperature of minus 20 ± 2° F. for 2 hours.

3.2.12.2 *Type II.* — The coating shall not crack through to the fabric base when tested in accordance with method 5874 at a temperature of minus 40 ± 2° F. for 4 hours.

3.2.13 *Hydrostatic resistance.* — The finished material shall not leak at a pressure of 70 pounds per square inch for class I and 100 pounds for all other classes when tested in accordance with method 5512.

3.2.14 *Flame resistance (type II only).*— When flame resistant material is specified no specimen shall continue flaming for more than 2 seconds after the flame is withdrawn, the average length of char of the 10 specimens tested shall be not more than 2 inches, and the maximum length of char of any one specimen shall not exceed 3 inches, when tested in accordance with method 5902.

Treatment a-1—Permanent resistance. — The requirements of paragraph 3.2.14 shall apply to samples of coated fabric subsequent to exposure as outlined in method 5804.

Treatment a-2—Nonpermanent resistance. —The requirements of paragraph 3.2.14 shall apply to samples of coated fabric as received.

3.2.15 *Mildew resistance (type II only).*— When mildew material is specified the finished material, after exposure to the mildew resistance test described in method 5760 shall retain a breaking strength of not less than 90 percent of the applicable minimum strength for its class as specified in table I. If both fire and mildew resistance are specified, retained strength shall be not less than 75 percent of the applicable minimum.

3.2.16 *Oil resistance (type II only).* — When oil-resistant material is specified the coating shall show no indication of penetration of oil when tested in accordance with paragraph 4.3.7.

3.3 Identification of coated fabric. — For identification purposes, the fabric shall be permanently marked on the back with the manufacturer's name or trade-mark and the date of manufacture, in ½-inch-block letters approximately 8 inches in from either selvage and repeating at intervals of not more than 36 inches along the length of the fabric.

3.4 Workmanship. — The coated fabric shall be free from defects which affect its appearance or which may impair its serviceability.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Sampling.—One piece not less than 1½ yards long and the full width of each type, class, color, treatment and finish, shall be taken at random from each 1000 yards or fraction thereof as offered for delivery, except that when the shipment is over 10,000 yards one piece shall be taken at random from each one-tenth of the shipment.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

4.2 **Inspection.**—Inspection shall be made at the point of delivery or at the factory, at the discretion of the purchaser.

4.3 **Tests.**—Tests shall be conducted in accordance with the following methods of Federal Specification CCC–T–191 and as hereinafter described:

Test	Method No.
Colorfastness to crocking	5650
Weathering resistance	5804
Width	5020
Finished weight	5041
Breaking strength	5100
Tearing strength	5134
Blocking	5872
Bursting strength	5120
Cold resistance	5874
Flame resistance	5902
Mildew resistance	5760
Water resistance	5512
Adhesion of coating to fabric — the period allowed for evaporation of solvent shall be 4 hours in lieu of 2 hours	5970
Length	5010

4.3.1 *Atmospheric conditions.* — Unless otherwise specified, the atmospheric conditions surrounding the specimen prior to and during tests shall be 23° ± 1.1° C. (73.5° ± 2° F.) and 50 ± 4 percent relative humidity; the conditioning period prior to testing shall be 48 hours.

4.3.2 *Weight of coating.* — The weighings shall be made on material which is in equilibrium with an atmosphere as described in 4.3.1.

4.3.2.1 The weight of coating shall be determined by removing the coating from the fabric as follows:

Soak the back of the fabric with cyclohexanone or other suitable solvent to assist in stripping the coating from the fabric. Immerse the fabric from which the coating has been removed in hot cyclohexanone (approximately 180° F.) for 2 to 5 hours and then rinse thoroughly in methyl ethyl ketone and dry. The weight of the base fabric shall be subtracted from the total weight of finished fabric.

4.3.3 *Elongation.* — The elongation test shall be run in conjunction with the bursting strength test (method 5120). An autographic attachment shall be used to graph the bursts. Five specimens shall be graphed on the same card and the average taken at the 5-pound, 25-pound, and 50-pound points on the graph.

4.3.4 *Abrasion.* — The resistance to abrasion shall be determined as described in method 5304 of Federal Specification CCC–T–191 with the following exceptions:

a. The long dimension of the specimen shall be parallel to the warp direction of the sample.

b. The tension on the specimen shall be 6 pounds.

c. The abrader shall be silicon-carbide cloth 240 grit.

d. The wear on the coating and discoloration shall be observed after
300 double rubs for class 1 material
500 double rubs for classes 2, 3, 4, 5, and 6 materials.

e. Abradant to be changed after each observation.

f. One specimen shall be tested from each sample.

If a specimen fails because of imperfections in the weave of the fabric, disregard that test.

4.3.5 *Volatility.* — The coated fabric shall be conditioned for at least 48 hours and a 3- by 5-inch specimen cut out and weighed. The specimen shall be placed in a circulating hot-air oven and held for 5 hours at 220° ± 2° F.; cooled, conditioned, and again weighed. The loss in weight then shall be calculated and the specimen compared for flexibility with the original sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

4.3.6 *Plasticizer extraction.* — One 2- by 2-inch specimen of the finished material shall be immersed in a beaker containing 100 cc. of hexane for 24 hours, removed, shaken free of excess solvent, and reimmersed in a fresh beaker of hexane for 24 hours. No agitation shall be used in either immersion. Specimens shall be air-dried for 4 hours in standard atmospheric conditions.

4.3.7 *Oil resistance.* — An 8- by 8-inch specimen shall be placed on a wood frame. The inside dimension of the wood frame shall be 6 by 6 by 1 inch. The coated fabric shall be inserted with the coated side up. The specimen shall be forced into the frame by a wooden block 5¾ by 5¾ by ¾ inch, with rounded corners to form a basin of uniform depth. The edges of the specimen shall be tacked to the frame and the block removed. Grade 10 oil conforming to Federal Specification VV-O-526 shall be poured into the basin as rapidly as possible to a depth of ½ inch. After the oil has been in the basin for 4 hours, the bottom of the specimen forming the basin shall feel dry and there shall be no indication that the oil has permeated the coated fabric.

5. PREPARATION FOR DELIVERY

5.1 Packaging.—Commercial packages will be acceptable.

5.2 Packing.—The subject commodity shall be prepared for shipment to permit acceptance by carrier for transportation at the lowest applicable rate, and to afford maximum protection from normal hazards of transportation.

5.3 Marking.

5.3.1 *Shipping containers.*—Shipping containers shall be marked with the name, type, class, color, treatment, and grain of the material as defined by the contract or order under which the shipment is made, the quantity contained therein, the name of the contractor, the number of the contract or order, the name and address of the consignee and the gross weight.

6. NOTES

6.1 Intended use.

6.1.1 *Type I.* — Class 1 is primarily intended for applications where there is no great stress on the fabric; such as for flat upholstering (slip seats and other padded applications), wall coverings, headlining, slip covers, door panels, and miscellaneous applications in which the properties of the coating and decorative values are the principal considerations; classes 2 and 3 are intended for medium and deep spring upholstery applications; classes 4 and 5 are intended for deep spring construction; class 6 is intended for exceptionally heavy duty rugged service such as buses.

6.1.2 *Type II.* — Type II fabrics are intended for use in special installations such as extra low or high temperatures, in unusually damp climates, or where exposed to solvents and oil, etc.

6.2 Ordering data. — Purchasers should specify the type, class, treatment, finish, width, and place of inspection desired (see 1.2, 3.2.1, 3.2.2, and 4.2). Purchasers should also exercise any desired options offered herein (see 6.4).

6.3 Federal specifications do not include all types, classes, grades, finishes, etc., of the commodities indicated by the titles of the specifications or which are commercially available, but are intended to cover the types, etc., which are suitable for Federal Government requirements.

6.4 It is believed that this specification adequately describes the characteristics necessary to secure the desired material, and that normally no samples will be necessary

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

prior to award to determine compliance with this specification. If, for any particular purpose, samples with bids are necessary they should be specifically asked for in the invitation for bids, and the particular purpose to be served by the bid sample should be definitely stated, the specification to apply in all other respects.

6.5 Transportation description.

6.5.1 *Transportation description applicable to these items is:*

Cloth, cotton, synthetic resin coated.
Carload weight 30,000 pounds.

Cloth, cotton, plastic coated, not otherwise indexed.
Truckload volume weight 30,000 pounds.

Patent notice.—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

7. DEPARTMENTAL REQUIREMENTS

7.1 The following specifications and standard, of the issues in effect on date of invitation for bids, and special requirements, form a part of this specification for purchases made under this specification by the respective departments.

7.2 Air Force.

7.2.1 *Applicable specification.*

Military Specification:

MIL–P–6065—Packaging, Packing and Marking for Cloth Fabric, and Webbing.

(Copies of specifications, standards, and drawings required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

7.2.2 *Packaging, packing, and marking.*—The material shall be packaged, packed, and marked for shipment in accordance with Military Specification MIL–P–6065.

7.3 Army.

7.3.1 *Applicable specifications.*

Federal Specification:

UU–T–116—Tape; Paper, Gummed, Water-Resistant.

Military Specifications:

JAN–P–105—Packaging and Packing for Overseas Shipment—Boxes, Wood Cleated, Plywood.

JAN–P–106—Packaging and Packing for Overseas Shipment—Boxes; Wood, Nailed.

MIL–B–107—Boxes, Wood, Wirebound (Overseas Type).

JAN–P–125—Packaging and Packing for Overseas Shipment—Barrier-Materials, Waterproof, Flexible.

MIL–A–140—Adhesive, Water-Resistant, Waterproof Barrier-Material.

Military Standard:

MIL–STD–129—Marking of Shipments.

(Copies of specifications and standard required by contractors in connection with specific Army procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

7.3.2 *Qualification.*—Unless otherwise specified, the type II, class 5 coated fabrics acceptable for Army requirements under this specification shall be of a make or brand which has been tested and found to meet all the requirements of this specification.

7.3.2.1 *Samples.*—Sufficient type II, class 5 material shall be furnished by suppliers desiring qualification of their products, as required to conduct the applicable tests, includ-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

ing those for cold resistance (at — 65° F.). flame resistance (permanent), mildew resistance, and oil resistance (see 3.2.12, 3.2.14, 3.2.15, 3.2.16).

7.3.2.2 *Disqualification.* — Failure of any qualification sample to pass any prescribed test shall be cause for disqualification, and additional tests will be made only after the supplier has clearly shown that changes have been made in the product which the Government considers sufficient to warrant conducting additional tests.

7.3.2.3 *Qualified products lists.*—The Army reserves the right to reject bids on makes or brands of type II, class 5 products that have not been subjected to the required tests and found satisfactory for inclusion in a Military Qualified Products List of Fabrics, Coated, Upholstery (Vinyl Resin Base). The attention of suppliers is called to this requirement, and manufacturers are urged to have the products they propose to offer tested for qualification. Application for qualification should be made to the Commanding Officer, Detroit Arsenal, Center Line, Michigan.

7.3.3 *Tearing strength.* — In lieu of the values shown in table I of the specification, the type II, class 5 coated fabric shall have a tearing strength (warp and filling) of not less than 6 pounds.

7.3.4 *Cold resistance.*—For Army requirements the type II class 5 coated fabric shall not crack through to the fabric after being exposed for 5 hours at a temperature of — 65° F., and then bent rapidly at that temperature over ⅛-inch mandrel through an angle of 180 degrees. This performance at low temperatures shall be shown by two test specimens, 8 inches long and 2 inches wide, one cut in the warp direction and the other in the filling direction.

7.3.5 *Inspection testing.*—Inspection tests for acceptance of individual lots furnished for Army requirements shall consist of tests for all the requirements for type I coated fabrics (see 3.1.1, 3.1.2, 3.2, 3.2.2, and 3.2.4), and of such additional tests (see 3.2.12, 3.2.14, 3.2.15, and 3.2.16) as may be deemed advisable by the procuring agency.

7.3.6 *Packaging.* — The coated fabrics in the widths and lengths specified in 3.2.2 and 3.2.3, respectively, shall be wound on standard fiberboard cores and wrapped in not less than two thicknesses of waterproof material conforming to the requirements of type C-1 of Military Specification JAN–P–125. The ends of each roll shall be protected by headers of the same, or equal material securely taped or glued to the body of the outer wrapping with water-resistant tape or water-resistant adhesive conforming to the requirements of Federal Specification UU–T–116 and Military Specification MIL–A–140, respectively.

7.3.7 *Packing.*

7.3.7.1 *For domestic shipment.* — Rolls packaged as specified in 7.3.6 will not require overpacking.

7.3.7.2 *For overseas shipment.* — Rolls, packaged as specified in 7.3.6 shall be overpacked in a snug-fitting box constructed in conformance with the requirements of one of the following Military Specifications:

JAN–P–105—Style A or B, type 3 load.
JAN–P–106—Style 2, type 3 load.
MIL–B–107—Style 1 or 2, type 3 load.

The boxes shall be designed to fit the rolls in a compact manner and shall be strapped in conformance with the requirements of the appendix to the applicable box specification.

7.3.8 *Marking.*—Each roll or shipping container shall be marked in accordance with Military Standard MIL–STD–129.

7.4 **Navy.**

7.4.1 *Applicable specifications and standard.*

Federal Specifications:

NN–B–591—Boxes; Fiberboard, Wood-Cleated (for Domestic Shipment).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

NN-B-601—Boxes; Wood-Cleated-Plywood, for Domestic Shipment.
NN-B-621—Boxes; Wood, Nailed and Lock-Corner.
NN-B-631—Boxes; Wood Wirebound for Domestic Shipment.
LLL-B-631—Boxes; Fiber, Corrugated (for Domestic Shipment).
LLL-B-636—Boxes; Fiber, Solid (for Domestic Shipment).

Military Specifications:
JAN-P-103—Packaging and Packing for Overseas Shipment—Boxes, Wood-Cleated; Solid Fiberboard.
JAN-P-105—Packaging and Packing for Overseas Shipment—Boxes, Wood, Cleated, Plywood.
JAN-P-106—Packaging and Packing for Overseas Shipment—Boxes; Wood, Nailed.
MIL-B-107—Boxes, Wood, Wirebound (Overseas Type).
JAN-P-108—Packaging and Packing for Overseas Shipment—Boxes, Fiberboard (V-Board and W-Board), Exterior and Interior.
JAN-P-125—Packaging and Packing for Overseas Shipment—Barrier-Materials, Waterproof, Flexible.
JAN-P-138—Packaging and Packing for Overseas Shipment—Boxes, Wood, Fiberboard-Lined.
MIL-A-140—Adhesive, Water-Resistant, Waterproof Barrier-Material.

Navy Department Specification:
General Specifications for Inspection of Material.

Military Standard:
MIL-STD-129—Marking of Shipments.

(Copies of specifications and standard required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

7.4.2 *Inspection procedures.* — For Naval purchases the general inspection procedures shall be in accordance with the General Specifications for Inspection of Material.

7.4.3 *Packaging.*

7.4.3.1 *For domestic shipment.* — Unless otherwise specified, the cloth shall be rolled open width on a convolute or spiral-wound chipboard tube with an outer surface which is compatible with the cloth. The tube shall have a solid wall 0.062 inch thick (minimum) and the inside diameter of the tube shall be one inch minimum. The tube shall extend approximately one inch beyond each side of the maximum width of the rolled fabric. Each roll shall be individually wrapped with a terra-cotta wrapper in accordance with trade practice, suitably secured.

7.4.3.2 *For domestic shipment and storage, or overseas shipment.* — Unless otherwise specified, the cloth packaged as described in 7.4.3.1 shall be overwrapped with waterproof barrier-material conforming to Military Specification JAN-P-125, and sealed with adhesive conforming to Military Specification MIL-A-140.

7.4.4 *Packing.*

7.4.4.1 *For domestic shipment and storage.*—Unless otherwise specified the subject commodity packaged as described in 7.4.3.2 shall be packed in wood-cleated fiberboard, wood-cleated plywood, nailed wood, wirebound wood, corrugated fiber, or solid fiber boxes conforming to Federal Specifications NN-B-591, NN-B-601, NN-B-621, NN-B-631, LLL-B-631, and LLL-B-636, respectively. The gross weight of wood or wood-cleated boxes shall not exceed approximately 200 pounds except where the weight of an individual item exceeds this amount. The gross weight of fiberboard boxes shall be subject to the limitation of the box specification.

7.4.4.2 *For overseas shipment.* — When specified the subject commodity packaged as described in 7.4.3.2 shall be packed in wood-cleated solid fiberboard, cleated-plywood, nailed-wood, wirebound, fiberboard, or fiberboard-lined wood boxes conforming to Mili-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

tary Specifications JAN–P–103, JAN–P–105, JAN–P–106, MIL–B–107, JAN–P–108, and JAN–P–138, respectively. The gross weight of wood or wood-cleated boxes shall not exceed approximately 150 pounds except where the weight of an individual item exceeds this amount, and of fiberboard boxes approximately 70 pounds.

7.4.5 *Marking.*—In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with Military Standard MIL–STD–129.

7.4.6 *Ordering data.* — Procurement documents should specify whether domestic or overseas shipment is required (see 7.4.4).

NAVY INTEREST: A *MC* Sh S Y

This specification is a part of Section IV, Part 5, of the Federal Standard Stock Catalog.

Copies of this specification can be purchased ach from the , Washington 25, D. C. Single copies required for bidding purposes are available without charge at the nearest

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.