INCH-POUND

CCC-C-46D
AMENDMENT 1
June 23, 1995

FEDERAL SPECIFICATION

CLOTH, CLEANING, NONWOVEN FABRIC

The General Services Administration has authorized the use of this amendment, which forms a part of CCC-C-46D, dated September 30, 1986, by all federal agencies.

PAGE 4

3.7.1: Delete paragraph in its entirety and substitute the following:

"3.7.1 Class 1. When tested in accordance with applicable requirements of method 5508 referenced in 4.3, the Class 1 cloth shall not be seriously affected by the following organic solvents: trichloroethylene, turpentine, and stoddard solvent."

3.7.3: Delete paragraph in its entirety and substitute the following:

"3.7.3 Class 7. When Class 7 cloth is tested in accordance with 4.3.6, the average percentage of extractable matter, excluding volatiles, shall be no more than 0.20 percent using methyl ethyl ketone (MEK) and 0.20 percent using trichloroethylene."

PAGE 7

4.3.2: Delete paragraph in its entirety and substitute the following:

"4.3.2 Linting. Cut a 1/8 inch aluminum panel to 5 by 5 inches. Drill 16 holes spaced 1 inch apart and countersink (see Figure 1). Install MS24694, or equal, screws and secure with AN315-3R, or equal, nuts. Rub the surface of the panel vigorously with the cloth for one minute and examine for evidence of linting. Repeat this procedure two times with the cloth soaked in methyl ethyl ketone and water."

MILITARY INTERESTS:

Custodians:

Army - GL
Navy - AS
Air Force - 99

CIVIL AGENCY COORDINATING ACTIVITIES:

GSA-FSS

Preparing activity:
Navy - AS

(Project 7920-0268)

AMSC N/A

FSC 7920

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.