CCC-J-191
JANUARY 5, 1932
SUPERSEDING
F. S. No. 614
January 25, 1929

FEDERAL STANDARD STOCK CATALOGUE

Section IV

(Part 5)

FEDERAL SPECIFICATION

FOR

JEAN; BLEACHED

This specification was approved for promulgation by the Federal Specification Board on January 5, 1932, for the use of the departments and independent establishments of the Government in the purchase of this commodity, and shall become mandatory for all departments and independent establishments of the Government not later than June 15, 1932. It may be put into effect, however, at any earlier date, after promulgation.

A. APPLICABLE FEDERAL SPECIFICATIONS.

A–1. The following Federal specification of the issue in effect on date of invitation for bids, shall form a part of this specification: F. S. CCC–T–191. Textile Materials; General Specifications (Methods of Physical and Chemical Tests) identical with Federal Specification No. 345.

A–2. Any special requirements of the individual departments of the Government are noted in section H.

B. TYPES AND GRADES.

B–1. The material shall be of one type.

B–2. The grade shall be that known commercially as "firsts."

C. MATERIAL AND WORKMANSHIP.

C–1. *Material.*—The material shall be made of thoroughly cleaned cotton free from waste.

C–2. *Workmanship.*—It shall be free from avoidable imperfections in manufacture and from defects or blemishes affecting the appearance or serviceability.

D. GENERAL REQUIREMENTS.

D–1. See section E.

525511 O - 43

Source: https://assist.dla.mil -- Downloaded
Check the source to verify that this is the curr

E. DETAIL REQUIREMENTS.

E–1. *Weave.*—The weave shall be a 3-harness twill $\left(\frac{2}{1}\right)$

E–2. *Length of bolts or rolls.*—Any commercial length over 35 yards will be accepted.

E–3. *Finish.*—The material shall be fully bleached.

E–4. *Width.*—The width shall be 36 inches unless otherwise specified. A tolerance of plus or minus one-half inch will be permitted.

E–5. *Weight.*—The weight per square yard shall be 4.8 ounces. A tolerance of minus 2½ per cent or plus 5 per cent will be permitted. (This is 3.33 yards per pound.)

E–6. *Thread count.*—The threads per inch shall be 98 in the warp and 60 in the filling. A total minus tolerance of two threads and any plus tolerance will be permitted.

E–7. *Strength.*—The minimum breaking strength (grab method) shall be 85 pounds in the warp and 48 in the filling directions.

F. METHODS OF SAMPLING, INSPECTION, AND TESTS.

F–1. Any requirements applicable to the individual departments are noted in section H.

F–2. *Sampling.*—Not less than one sample at least 1 yard in length by the width of the material shall be taken at random from each 1,000 yards or fraction thereof, except when the shipment is over 10,000 yards, in which case a sample shall be taken from each one-tenth of the shipment.

F–3. *Testing.*—Federal Specification CCC–T–191, identical with General Specifications for Textile Materials FSB No. 345, in effect on date of invitation for bids, wherever practicable, shall be followed.

G. PACKAGING, PACKING, AND MARKING.

G–1. Any special requirements of the individual departments of the Government are noted in section H.

G–2. *Packaging.*—Unless otherwise specified, commercial packages will be acceptable under this specification.

G–3. *Packing.*—Unless otherwise specified, the material shall be packed in substantial containers, so constructed as to insure acceptance by common or other carrier, for safe transportation, at the lowest rate, to the point of delivery.

G–4. *Marking.*—Unless otherwise specified, shipping containers shall be marked with the name of the material, the size, the type, quantity contained therein, the name of the contractor, and the number of the order.

H. REQUIREMENTS APPLICABLE TO INDIVIDUAL DEPARTMENTS.

H–1. The following departmental specifications of the issue in effect on date of invitation for bids shall form a part of this specification:

H–1a. *Army.*—United States Army Specification No. 100–2.

Source: https://assist.dla.mil -- Dow
Check the source to verify that this is

H–1b. *Navy.*—Navy Department General Specification for Inspection of Material, together with Appendix III—Textiles.

Copies of this specification and appendix may be obtained without cost upon application to the Bureau of Supplies and Accounts, Navy Department, Washington, D. C.

I. NOTES.

I–1. The bleached jean is based on 39-inch unbleached jean.

I–2. It is believed that this specification adequately describes the characteristics necessary to secure the desired material, and that normally no samples will be necessary prior to award to determine compliance with this specification. If, for any particular purpose, samples with bids are necessary, they should be specifically asked for in the invitation for bids, and the particular purpose to be served by the bid sample should be definitely stated, the specification to apply in all other respects.

I–3. This specification governs all United States Government purchases of this commodity. Users are requested to retain this specification in permanent file until a revision is issued.

I–4. Interested parties are advised that an alphabetical index of Federal specifications may be purchased as noted in the paragraph next below, price to be obtained from the Superintendent of Documents.

I–5. Copies of this specification, and of F. S. CCC–T–191 may be obtained upon application, accompanied by money order or coupon or cash, to the Superintendent of Documents, Government Printing Office, Washington, D. C. Price, 5 cents.

Notice.—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility or any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Source: https://assist.dla.mil -- Dow
Check the source to verify that this is