CCC-P-86E
AMENDMENT-1
November 21, 1972

FEDERAL SPECIFICATION

PADDING, COTTON, STITCHED ROVING

This amendment, which forms part of Federal Specification CCC-P-86E, dated October 20, 1971, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 3

2.2, lines 3, 4, and 5: Delete in their entirety and substitute the following:

"(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago, Illinois 60606.)"

3.2.1 Delete and substitute the following:

"3.2.1 Roving. The roving shall be made of cleaned, natural color cotton which has been carded and drawn."

Delete table I in its entirety and substitute the following:

"TABLE I. Physical requirements

Thickness Inch	Wgt/sq. yd., ozs. (min.)	Width, inches (min.)
0.31 ± 0.06	32.0	74

"

PAGE 5

4.2.2.1, second sentence: Delete "the more serious" and substitute "one".

Table II, line 9: Delete "Strands of roving per inch not as specified."

FSC 8320

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

Delete table IV in its entirety and substitute the following:

"TABLE IV. Test methods

Characteristic	Requirement paragraph	Test method
Padding		
Cotton identification	3.2.1	1200 1/
Weight per square yard (min)	3.3	5040
Thickness	3.3	2/
Strands of roving per inch	3.2.3	5050
Rows of stitching per inch	3.2.3	5050

1/ Unless otherwise specified a certificate of compliance is required and will be acceptable for the requirements specified.

2/ Apparatus: The test apparatus shall consist of a base plate and a circular pressure plate with a bearing surface of 20 square inches, and means of applying 0.6 pounds per square inch loading on the sample. This pressure shall be evenly distributed over the 20 square inch area. The thickness measuring device shall be capable of measuring the thickness of the sample (distance between base and pressure plate) to an accuracy of 0.01 inch.

Procedure: The 0.6 pound per square inch pressure shall be applied to five test specimens and the thickness results shall be averaged and recorded to the nearest 0.01 inch."

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

6.2.1 Delete in its entirety.

Military Custodians:

Army - GL
Navy - SA
Air Force - 82

Review activity:

Army - MD

User activities:

Navy - CG, MC, MS

Preparing activity:

Army - GL

Civil Agency Coordinating Activities:

GSA-FSS
HEW

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.