application to the Bureau of Supplies and Accounts, Navy Department, Washington, D C

H-1c. *Marine Corps*—Instructions issued by the quartermaster.

NOTES

I-1. The purpose of sponge rubber cushions is to prevent dangerous slipping of rugs on polished floors and to add cushioning effect Purchasers should specify the type and style required (see paragraphs B-1, E-1c, and E-2)

I-2 Cushions should be purchased by the square yard

I-3 This specification covers only the types, classes, grades, sizes, etc, of the commodity as generally purchased by the Federal Government, and is not intended to include all of the types, etc, which are commercially available

I-4 An Index of Federal Specifications may be purchased as noted in the paragraph next below, price to be obtained from the Superintendent of Documents

I-5 Copies of this specification and of ZZ-R 601 may be obtained upon application, accompanied by money order or coupon or cash, to Superintendent of Documents, Government Printing Office, Washington, D C Price, 5 cents each

Notice—When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever, and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto

For sale by the Superintendent of Documents Washington D C - Price 5 cents

GSA-WASH DC 52-8526

ZZ-C-811

OCTOBER 20, 1938

FEDERAL STANDARD STOCK CATALOG

Section IV

(Part 5)

FEDERAL SPECIFICATION

FOR

CUSHION (UNDERLAY); CARPET AND RUG, SPONGE-RUBBER

This specification was approved on the above date by the Director of Procurement, for the use of all departments and establishments of the Government, and shall become effective not later than May 15 1939 It may be put into effect home or, at any earlier date after promulgation

A APPLICABLE SPECIFICATION

A 1 The following Federal Specification, of the issue in effect on date of invitation for bids, shall form a part of this specification

ZZ-R 601 - Rubber goods, general specifications (methods of physical tests and chemical analyses)

B TYPES, GRADE AND STYLES

B-1 The cushion shall be of a single grade in either of the two following types, and in the style of either strip form or of definite dimensions, as specified in the invitation for bids

Type I —Without woven fabric cover or insert.
Type II —With woven fabric cover or insert (as specified).

C. MATERIAL AND WORKMANSHIP

C 1 *Material*—The cushion shall be made of sponge rubber (and with commercial grade of woven fabric if type II is specified).

C 2 *Workmanship*—Cushion shall be free from defects in workmanship

D GENERAL REQUIREMENTS

D-1 The sponge rubber shall be of uniform texture, and free from objectionable odor

E DETAIL REQUIREMENTS

E-1. *Dimensions*—

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T12:28Z
Check the source to verify that this is the current version before use.

E-1a *Thickness*—The thickness of the cushion shall be 1/16, 3/32, 1/8, 3/16, 1/4, 5/16, or 3/8 inch, as specified. The thickness at any point shall be subject to the following tolerances:

3/8 inch thick and under—minus 1/64 inch, plus 1/32 inch
Over 3/8 inch—minus 1/32 inch, plus 1/16 inch

E-1b *Width*—Cushion shall be furnished in 27 inch, 36 inch, or 54-inch widths, as specified. The specified width shall be subject to a tolerance at any point of plus or minus 1/2 inch.

E-1c *Length*—Standard length rolls as stated below shall be furnished as specified. The length of any roll shall be subject to a variation of plus or minus 5 percent. Cushion 1/4 inch thick and less shall be delivered in 20- or 40-yard rolls. 20-yard rolls shall be in one piece. 40-yard rolls may be in two pieces. However, if furnished in two pieces, the shorter piece shall be not less than 5 yards long. Cushion over 1/4-inch thick shall be delivered in 20-yard rolls. These rolls may be in one or two pieces. However, if furnished in two pieces, the shorter of the two pieces shall be not less than 5 yards long.

E-2 *Dimensions, cushion of definite size*—If cushion pads of definite size are required, they shall be in one piece and of the dimensions specified. If splicing of two or more sections is necessary in forming the pad, the bond at the splice shall be firmly made. Pads may be ordered of the standard thicknesses as specified, and shall be subject to the same length, width, and thickness tolerances as roll material.

E-3 *Weight*—The weight per square yard shall be in accordance with the following table:

WEIGHT

Thickness (inch)	Maximum weight per square yard	
	Type I	Type II
	Pounds	Pounds
1/16	1 75	2 50
1/8	3 00	3 25
3/16	3 75	4 25
1/4	5 75	5 50
5/16	6 50	7 00
3/8	8 00	8 50

E-4 *Compressibility*—Type I cushion, when subjected to the test described in paragraph F-3, shall show an initial compression not less than the following:

1/8 inch and under—10 percent of original thickness
Over 1/8 inch—35 percent of original thickness

E-4a Type I cushion, after being subjected to the compression test described in paragraph F-3, shall recover to at least 94 percent of its original thickness.

E-5 *Accelerated aging*—When tested as described in paragraph F-4, the sponge rubber shall not become sticky nor shall it crack when bent sharply back upon itself, nor shall its condition have changed in any way that would be likely to impair its usefulness.

F METHODS OF SAMPLING, INSPECTION AND TESTS

F-1 *Sampling*—One sample 6 inches long and the full width of the roll shall be taken from each lot of five rolls or less. If pads are ordered, the manufacturer shall furnish 1 square foot of material from each lot of 2 000 square feet or less. This sample shall be guaranteed by the manufacturer to be identical in composition and cure with the rubber offered for delivery.

F-2 *Thickness*—Thickness shall be measured with a gage having a circular foot of 6 5 square centimeters (1 0 square inch) area under a load of 100 grams.

F-3 *Compression test*—A sample of the full thickness of the roll shall be cut 2 inches square (4 square inches), and placed under a compressive load of 10 pounds per square inch (40 pounds). The measurement of initial compressibility is then made and the decrease in thickness shall be computed as a percentage of the original thickness. The sample shall be held under this compressive load for a period of 24 hours, plus or minus 1/2 hour, at which time the load shall be removed and the sample allowed to rest for 1 hour. The thickness measurement shall then be taken and shall be expressed as a percentage of the original thickness.

F-4 *Accelerated aging test*—A piece of the sponge rubber shall be exposed to the action of oxygen (not more than 1 ounce of rubber per 170 cubic inches of oxygen) for 120 hours at a temperature of 158°, plus or minus 2° F, and a pressure of 300 pounds, plus or minus 10 pounds per square inch.

G PACKAGING, PACKING, AND MARKING FOR SHIPMENT

G-1 *Packaging*—Unless otherwise specified, commercial packages are acceptable under this specification.

G-2 *Packing*—Unless otherwise specified, the subject commodity shall be delivered in standard commercial containers, so constructed as to insure acceptance by common or other carriers, for safe transportation, at the lowest rate, to the point of delivery.

G-3 *Marking*—Unless otherwise specified, shipping containers shall be marked with the name of the material, the size, type, and the quantity contained therein, as defined by the contract or order under which the shipment is made, the name of the contractor, and the number of the contract or order.

H REQUIREMENTS APPLICABLE TO INDIVIDUAL DEPARTMENTS

H-1 The following departmental specifications of the issue in effect on date of invitation for bids shall respectively form a part of this specification:

H-1a *Army*—United States Army Specification No. 100-2, Standard Specification for Marking Shipments.

H-1b *Navy*—Navy Department General Specification for Inspection of Material, copies of which may be obtained without cost upon

Source: https://assist.dla.mil -- Downloaded: 20260-26T12:28Z
Check the source to verify that this is the current version before use.