ZZ-F-1299A
October 21, 1975
SUPERSEDING
Int. Fed. Spec. ZZ-F-001299(DSA-DM)
March 31, 1971

FEDERAL SPECIFICATION

FINGER COT, SURGICAL, DISPOSABLE

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers disposable natural latex rubber finger cots suitable for use as a covering for the protection of lesions of the finger and as an aid to the maintenance of aseptic conditions in the performance of examinations by finger.

1.2 Classification.

1.2.1 Sizes. The finger cots covered by this specification shall be of the following sizes:

Size A - Medium
Size B - Large

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

PPP-B-566 - Boxes, Folding, Paperboard.
PPP-B-585 - Boxes, Wood, Wirebound.
PPP-B-601 - Boxes, Wood, Cleated-Plywood.
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-B-676 - Boxes, Set-Up.

Federal Standards:

Fed. Std. No. 123 - Marking for Shipment (Civil Agencies).
Fed. Test Method Std. No. 601 - Rubber; Sampling and Testing.

FSC 6515

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers, at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Fort Worth, Denver, San Francisco, Los Angeles and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standard:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.

(Copies of Military Specifications and Standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless a specific issue is identified, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM) Standard:

D 412 - Tension Testing of Vulcanized Rubber

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Material. The finger cots shall be fabricated from natural latex rubber and shall be free from coloring and fillers. The finger cots shall be powdered with a material to facilitate ease of application.

3.2 Size, design and dimensions. The finger cots shall be rolled to allow easy application to the finger and shall possess a firm ring or bead. The finger cots shall be dry heat cured. The dimensions of the finger cots shall be as specified in table I for the appropriate size. The thickness, length, and inside diameter of the finger cots shall be tested in accordance with 4.4.

TABLE I. Dimensions (in inches).

Size	Inside diameter at open end	Length	Thickness
A	3/4 ± 1/32	2-3/4 ± 1/8	.0035 to .0040
B	7/8 ± 1/32	2-3/4 ± 1/8	.0035 to .0040

3.3 Tensile strength. The minimum tensile strength of the natural latex rubber in the unaged condition shall be 3400 pounds per square inch (psi) when tested in accordance with 4.4.

3.4 Ultimate elongation. The minimum ultimate elongation of the natural latex rubber in the unaged condition shall be 825 percent when tested in accordance with 4.4.

3.5 Resistance to aging. The tensile strength and ultimate elongation of the natural latex rubber shall not decrease more than 25 percent of the value before aging, when tested in accordance with 4.4. The resistance to aging shall be measured by the change in tensile strength and ultimate elongation.

3.6 Finish. The finger cots shall have a uniform smooth finish free from holes, visible surface or embedded particles, tackiness, bloom, strings, and other imperfections.

3.7 Workmanship. Workmanship shall be first class throughout. The finger cots shall be free from defects which detract from their appearance or impair their serviceability.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105, and as indicated in table II. Unit of product for examination purposes shall be one finger cot.

TABLE II. Sampling criteria for examination.

Type defect	Inspection level	AQL (percent defective)
Major	II	1.0
Minor	II	2.5

4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105, and as indicated in table III. Unit of product for test purposes shall be one finger cot.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

TABLE III. Sampling criteria for tests.

Component	Characteristic	Requirement	Test procedure	Inspection level	AQL*
Finger cot	Thickness	3.2	4.4	S-2	1.5
	Length	3.2	4.4	S-4	1.5
	Inside diameter	3.2	4.4	S-2	1.5
	Tensile strength	3.2	4.4	S-1	1.5
	Ultimate elongation	3.4	4.4	S-1	1.5
	Resistance to aging	3.5	4.4	S-1	1.5

* percent defective

4.2.3 Sample unit usage. Where feasible, the same sample unit shall be used for the determination of two or more test characteristics.

4.3 Examination.

4.3.1 Of finger cot. The finger cots shall be examined to determine compliance with all the requirements contained in this specification. Examination shall be conducted in accordance with tables II and IV. Examination, however, shall not be restricted to defects listed in table IV. Any finger cot in the sample containing one or more defects shall be rejected and if the number of defective finger cots in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected.

TABLE IV. Classification of defects.

Categories	Defects
Critical	None defined.
Major	
101	Cots not of size specified.
102	Cots possess tears, holes, blisters, tackiness, or embedded particles.
103	Finish of cots not smooth, or uniform.
104	Cots not powdered.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of defects. (cont'd)

Categories	Defects
105	Cots not rolled.
106	Ring or bead of cot not firm or not uniform.
107	Cots adhering to each other in unit package.
108	Cots not free from foreign matter.
109	Cots not easily applied to finger.
Minor	
201	Cots excessively powdered.

4.3.2 Preparation for delivery. An examination shall be made to determine whether the packaging, packing, and marking comply with the requirements of section 5. Defects shall be scored as specified in table V. Sampling shall be in accordance with MIL-STD-105. The sample unit shall be one container fully prepared for delivery. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 and the acceptable quality level shall be 4.0 expressed in units of percent defective.

TABLE V. Examination of preparation for delivery.

Examination	Defect
Containers Quantity	Not as specified. Quantity in interior packages and shipping containers not as specified.
Packaging and packing materials	Any component missing or damaged.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, tape improperly applied, or containers distorted.
Markings	Omitted, incorrect, illegible, improper size, location, sequence, or method of application.

4.3.2.1 Examination of closure, waterproofing and banding of container. When the shipping container is required to comply with PPP-B-636, the examination for defects in closure, waterproofing or banding shall be in accordance with the appendix of the box specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

4.4 Tests. Tests shall be conducted in accordance with FED-STD-601 and table VI. All samples or specimens shall be unaged natural latex rubber. Samples or tests specimens intended for accelerated aging tests shall be protected from any excessive exposure to strong light prior to aging. The samples and specimens shall be kept in light-tight containers until ready for inspection.

TABLE VI. Test methods

Characteristic	FED-STD-601 Test Methods
Thickness	2011 or 2031
Length	2411
Inside diameter	2341
Tensile strength	4111
Ultimate elongation	ASTM D 412
Air Heat, Test	7221 or 7231

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Unit of issue. One package containing 144 finger cots of size A or size B as specified, constitutes one unit of issue.

5.1.1.1 Level A.

5.1.1.1.1 Unit package. Each unit of issue 144 finger cots) shall be packaged in a box of appropriate size constructed in accordance with PPP-B-566 or PPP-B-676. Closure shall be adequate to prevent accidental opening.

5.1.1.1.2 Intermediate package. Twelve 12 units of issue shall be packaged in a box of appropriate size constructed in accordance with PPP-B-636, type CF, class domestic. Closure shall be adequate to prevent accidental opening.

5.1.1.2 Level C. Each unit of issue shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:28Z
Check the source to verify that this is the currentversion before use.

DAL SUPPLIES AND INSPECTIONS ARE DEEMED NECESSARY TO ASSURE

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Level A. Twenty four units of issue shall be packed in an exterior container designed for a type 2 load and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2, or PPP-B-636, class weather resistant, grade V3c. Closure and strapping shall be as specified in the appendix of the applicable box specification.

5.2.1.1 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes. Fiberboard box shall be waterproof in accordance with the appendix of PPP-B-636.

5.2.2 Level B. Twenty four units of issue shall be packed in an exterior container designed for a type 2 load and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, type CF, class domestic. Closure shall be as specified in the appendix of the applicable box specification.

5.2.3 Level C. Finger cots shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, constructed so as to insure acceptance and safe delivery by common or other carriers, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Civil agencies. Marking for shipment shall be in accordance with FED-STD-123.

5.3.2 Military activities. Each unit, intermediate and exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The finger cots are intended for medical examinations by finger.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents.

(a) Title, number, and date of this specification.
(b) Size of finger cot (see 1.2.1).
(c) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(d) National Stock Number (NSN).

6.3 This specification is intended to cover the following items:

National stock number	Item identification
6515-00-935-1193	FINGER COT, SURGICAL, Disposable, Medium, 144s
6515-00-935-1194	FINGER COT, SURGICAL, Disposable, Large, 144s

Military Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
DSA-DM

Civil Agency Coordinating Activity
GSA-FSS

Project No. 6515-1951

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE
ZZ-F-1299A FINGER COT, SURGICAL DISPOSABLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?
   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

FOLD

DEFENSE PERSONNEL SUPPORT CENTER
2800 South 20th Street
Philadelphia, PA. 19101

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY
DoD - 304

U.S.MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.