INTERIM FEDERAL SPECIFICATION

MATTING FLOOR, RUBBER, APERTURE SURFACE

This Interim Federal Specification was developed by General Services Administration, Federal Supply Service, Standardization Division, Washington, D. C., 20406, based upon currently available technical information. It is recommended that Federal agencies use it in procurement and forward recommendations for changes to the preparing activity at the address shown above.

1. SCOPE AND CLASSIFICATION

1.1 This specification covers nonskid rubber matting.

1.2 Classification. The matting shall consist of two types and three widths as follows (see 6.2):

Type I Regular
Type II Oil and grease resistant.

1.2.1 Widths. The matting shall be furnished in the following widths (see 6.2):

24 inches
30 inches
36 inches
48 inches

2. APPLICABLE DOCUMENTS.

2.1 The following specifications and standards of the issues in effect on the date of invitation for bids or request for proposal form a part of this specification to the extent specified herein:

Federal Specifications

UU-P-268	Paper, Kraft, Untreated, Wrapping
UU-T-111	Tape, Paper, Gummed (Sealing and Securing)
PPP-B-591	Boxes, Fiberboard, Wood-Cleated
PPP-B-601	Boxes, Wood, Cleated-Plywood
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner
PPP-B-640	Boxes, Corrugated, Triple Wall, 350 pound maximum weight

Federal Standards:

Fed. Std. No 102 Preservation, Packaging and Packing Levels
Fed. Std. No. 123 Marking for Domestic Shipment (Civilian agencies).
Int. Fed. Test Method Std. No. 00501 - Floor Coverings, Resilient, Non-textile, Sampling and Testing.
Fed. Test Method Std. No. 601 - Rubber, Sampling and Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C., 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

Military Specifications:

MIL-L-10547 - Liners, Case, Waterproof

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS.

3.1 Material. The matting shall be a rubber compound consisting of natural or synthetic rubber or a mixture thereof with or without textile cord reinforcement. The rubber compound used for Type II matting shall be oil and grease resistant. Matting material shall conform to the physical properties specified in Table I when tested as specified in Table V.

3.2 Form. The matting shall be supplied in rolls scored every 12 + 1/2 inches. The area between score marks shall constitute one section. Each section shall have widthwise corrugations on the top surface and diagonal corrugations on the bottom surface. The section shall be a combination of open and solid areas with approximately 20 percent being open and arranged in a regular geometric repeat pattern. The solid areas shall have a taper from top to bottom surface of approximately 3/32 inch measured along one edge.

3.3 Dimensions

3.3.1 Thickness. The thickness of the matting shall be not less than 5/16 inch.

3.3.2 Width. The matting shall be supplied in the following widths as specified (See 6.2) 24 inch, 30 inch, 36 inch, and 48 inch. A minus tolerance of 1/8 inch will be permitted.

Table I - Physical properties of matting

CHARACTERISTIC	REQUIREMENT
Tensile strength,	
original lbs. per sq. in. min.	1300
after aging (percent of original min.)	20
Elongation, percent min.	
original	300
after aging	225
Adhesion, pounds per inch of width min.	4
Swelling after water immersion,	
percent, max.	8
Hardness, durometer	65±5
Resistance to organic materials (Type II)	Pass

3.3.3 Length. The length of the matting rolls for various widths shall be as follows:

24 inch - 60 sections
30 and 36 inch - 40 sections
48 inch - 30 sections

3.4 Color. The color of the matting shall be black.

3.5 Flexibility. The matting shall not crack or break when tested as specified in Table V.

3.6 Workmanship. The corrugations on the top and bottom surfaces of the matting and the edges of the solid areas shall be sharp and clean. The solid areas shall be free from blisters, cracks, protruding particles and embedded matter. Score marks shall be well defined. The occurrence of defects shall not exceed the acceptable quality level (AQL) specified herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS.

4.1 Inspection responsibility. The supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government Inspection records of the examination and tests shall be kept complete and available to the Government as specified in the contract or order. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Examination for acceptance. Examination shall be in accordance with the provisions of MIL-STD-105 except as otherwise indicated.

4.3 Inspection of the end item.

4.3.1 Visual examination of the end item. The lot size shall be expressed in units of sections of matting. The inspection level shall be S-1 of MIL-STD-105 The unit of product shall be one section of matting. The defects found during examination shall be classified in accordance with Table II. The acceptable quality level shall be 4.0 defects per hundred units.

TABLE II. - End item defects

EXAMINE	DEFECTS
Material	Not regular geometric pattern.
	Open area less than 20 percent of total surface.
	Solid area edges not tapered from top to bottom surface
	Score marks not well defined.
	Corrugations missing or malformed.
	Cracks, blisters, lumps or embedded matter in surface of matting.
	Edges not clean cut.
	Not black.

4.3.2 Dimensional examination. The matting shall be examined for dimensional defects giver in Table III. The lot size shall be expressed in units of rolls of matting The inspection level shall be S-1 of MIL-STD-105. The unit of the product shall be one roll of matting The acceptable quality level shall be 4.0 defects per hundred units.

TABLE III. - Dimensional defects

EXAMINE	DEFECT
Length of section	Not within 12 ± 1/2 inch range
Length of roll	Less than number of sections specified
Width of roll	Less than specified
Thickness of matting	Less than 5/16 inch

4.3.3 Inspection of preparation for delivery requirements. An examination shall be made to determine that markings, materials, workmanship, contents and weights comply with the requirements of Section 5 of this specification. Defects shall be scored in accordance with the classification given in Table IV. The sample unit shall be one shipping container, fully packed, selected just prior to the closing operation. Closed shipping containers shall be examined for closure defects. The lot size shall be expressed in number of shipping containers. The inspection level shall be S-2 of MIL-STD-105 and the acceptable quality level shall be 4.0 defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

Table IV. - Preparation for delivery defects

EXAMINE	DEFECT
Markings (exterior and interior)	Incorrect, incomplete, illegible, omitted; of improper size, location, sequence, or method application.
Materials	Any nonconforming component, component missing, damaged, or otherwise defective
Workmanship	Inadequate application of components such as incomplete closure of case liners, container flaps, loose or inadequate sealing, strapping or stapling, bulged or distorted containers.
Weights	Gross or net weight exceeds requirements.

4.4 Testing of the end item. Testing shall be performed in accordance with Table V for the characteristics listed therein. The physical and chemical values specified apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test method. The lot size shall be expressed in units of rolls of matting. The sample unit shall be one section (12 inch length). The sample size (number of sample units) shall be selected in accordance with level S-2 of MIL-STD-105 Failure of a sample unit to conform to the requirement for any of the characteristics tested shall be cause for rejection of the lot.

Table V. - End item testing

CHARACTERISTIC	REQUIREMENT REFERENCE	TEST REFERENCE	REQUIREMENT APPLICABLE TO: SAMPLE UNIT	REQUIREMENT APPLICABLE TO: LOT AVERAGE	RESULTS REPORTED AS
Tensile strength	Table I	4111		X	nearest pound
Elongation	Table I	4121		X	1.0 percent
Adhesion	Table I	7211		X	0.1 lb
Swelling		6211*			nearest 0.5 percent
Hardness	Table I	3021*		X	nearest whole number.
Flexibility	3.5	3121	X		pass or fail
Resistance to organic materials	Table I	6311**	X		pass or fail

NOTE All test references except as otherwise noted refer to Interim Federal Test Method Standard No. 00501

* Refers to Federal Test Method Standard No. 601.

** Lubricating oil, tallow and olive oil shall be used Scraper test shall be omitted, but samples shall be examined for evidence of swelling, softening or other deterioration.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:28Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

(Fed. Std. No. 102 should be referred to for definitions and application of the various levels of packaging and packing for civilian procurements).

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A. Matting shall be evenly rolled with the pattern or design on the outside and wrapped with two thicknesses of 60-pound minimum basis weight kraft paper conforming to grade B of UU-P-268. The wrap shall be sealed with 2-inch-minimum-width gummed paper tape conforming to class 2 of UU-T-111.

5.1.2 Level C. Matting shall be packaged in accordance with the industry's practice

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A. Matting of one type and width, only, packaged as specified in 5.1, shall be packed in a snug-fitting shipping container conforming to overseas type 3 load of PPP-B-601, or class 2, style 2 or 4, type 3 load of PPP-B-621. Each shipping container shall be provided with a type I or II, grade B or C, class 2 sealed case liner conforming to MIL-L-10547. Each shipping container shall be closed and reinforced with flat steel strapping in accordance with the appendix of the applicable container specification. When the weight of contents per shipping container is 200 pounds or more, the shipping container shall be modified by the addition of not less than two 2-by-4 inch wood skids as specified in PPP-B-621.

5.2.2 Level B. Matting of one type and width, only, packaged as specified in 5.1, shall be packed in a snug-fitting shipping container conforming to domestic type, style 1 or 2 of PPP-B-601, or PPP-B-591, class 1, style A or C of PPP-B-640 or class 1, style 2 or 4, type 3 load of PPP-B-621. When the weight of contents per shipping container is 200 pounds or more, the shipping container shall be modified by the addition of not less than two 2-by-4 inch wood skids as specified in PPP-B-621.

5.2.3 Level C. Matting, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with rules and regulations of carriers applicable to the mode of transportation.

5.3 MARKING.

5.3.1 Civil agencies. In addition to any special marking required by the contract or order, interior packages and shipping containers shall be marked in accordance with FED STD NO 123

6. NOTES.

6.1 Intended use. This matting is intended to provide a resilient, nonslip walking surface in institutional work areas. The Type II matting should be used where oil and grease contamination of the walking surface is present to a considerable extent

6.2 Ordering data. Purchasers should exercise any desired options herein and procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Type required (see 1.2).
(c) Width required (see 1.2.1 and 3.3.2).
(d) When other than commercial packaging is required (see 5.1)

Source: https://assist.dla.mil -- Downloaded: 20261O-26T12:28Z
Check the source to verify that this is the current version before use.