MIL-T-37237A
28 February 1977
SUPERSEDING
MIL-T-37237
20 May 1975

MILITARY SPECIFICATION

TUBE, DRAINAGE, SURGICAL, THORACIC, PLASTIC, RADIOPAQUE, STRAIGHT, WITH TROCAR

This specification is approved for use by all the Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a sterile, 28 Fr, disposable radiopaque, thoracic surgical drain tube and trocar suitable for closed intercostal drainage.

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids or request for proposals, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

MMM-A-250	- Adhesive, Water-Resistant, (For Sealing Fiberboard Boxes).
PPP-B-585	- Boxes, Wood, Wirebound.
PPP-B-601	- Boxes, Wood, Cleated-plywood.
PPP-B-621	- Boxes, Wood, Nailed and Lock-corner.
PPP-B-636	- Boxes, Shipping, Fiberboard.
PPP-B-676	- Boxes, Set-up.
PPP-T-76	- Tape, Pressure-sensitive Adhesive Paper, Water-Resistant, (For Carton Sealing).

MILITARY

MIL-S-36586	- Sterilization Strip Test, Bacterial Spore.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Headquarters, Defense Personnel Support Center, ATTN: Directorate of Medical Materiel, Code ATT, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 6515

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:15Z
Check the source to verify that this is the current version before use.

STANDARDS

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	- Marking for Shipment and Storage.

(Copies of specifications, standards, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply:

UNITED STATES PHARMACOPEIAL CONVENTION, INCORPORATED (USP)

Pharmacopeia of the United States

(Application for copies should be addressed to the Mack Publishing Company, Easton, PA 18042).

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 638 Method of Test for Tensile Properties of Plastic.

(Application for copies should be addressed to ASTM, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.

3. REQUIREMENTS

3.1 Material.

3.1.1 Plastic. The drainage tube shall be made of medical grade, transparent, clear, pliant polyvinylchloride (PVC) plastic. The drainage tube shall meet United States Pharmacopeia (USP) Classification IV for Plastic Containers as indicated in 4.5.1 and the requirements for Transfusion and Infusion Assemblies as shown in 4.5.5. The drainage tube shall not contain more than 5 parts per million (ppm) of lead when tested as specified in 4.5.7.

3.1.2 Aluminum. The trocar shall be of an aluminum alloy suitable for the purpose intended.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:15Z
Check the source to verify that this is the current version before use.

3.2 Style, design and dimensions.

3.2.1 Assembly. The drainage tube and trocar assembly shall consist of an outer plastic catheter and an inner aluminum trocar that fits inside the catheter, seating occurring at the distal ends. The overall length shall be approximately 17 inches. The assembly shall be suitable for closed intercostal drainage. Catheter interior and exterior walls shall be smooth, permitting unrestricted passage of fluids and be free from foreign substances. A radiopaque stripe shall be present in the catheter. The units offered for delivery shall have the tube and trocar assembled.

3.2.1.1 Catheter.

3.2.1.1.1 Distal end of catheter. The distal end of the catheter shall be chamfered to blend with the conical trocar point. The catheter shall be smoothly finished and have a shoulder to permit positive seating with the undercut part of the trocar. The eyes shall be located at the distal end within 1-5/8 inch from tip. The two eyes shall be parallel to the long axis of the catheter and on opposite sides but at different levels. The more proximal eye shall be aligned with the radiopaque stripe.

3.2.1.1.2 Proximal end of catheter. The proximal end is enlarged to form an integral funnel for readily attaching a tapered connector. The funnel shall begin approximately 1-1/2 inches from the proximal tip and have an inner diameter of 3/8 inch.

3.2.1.1.3 Dimensions. The catheter shall be 15 $\pm$ 5/8 inches long, have a wall thickness of 0.048 $\pm$ 0.005 inch and outer diameter of 0.367 $\pm$ 0.013 inch.

3.2.1.1.4 Eyes. The two eyes shall each measure 0.348 $\pm$ 0.015 inch X 0.155 $\pm$ 0.015 inch for major and minor diameters, respectively.

3.2.1.1.5 Radiopaque stripe dimensions. The radiopaque stripe shall extend for the entire length of the catheter and have a minimum depth of 50 percent of the wall thickness with a width of 0.015 to 0.060 inch.

3.2.1.2 Trocar. The aluminum trocar shall be fitted with a suitable ball handle and fit smoothly within the catheter. There may be a full length capillary groove suitable for aspiration and confirming entry into the pleural cavity. The trocar point shall be sharp and conical with an included angle of approximately 60°.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:15Z
Check the source to verify that this is the current version before use.

3.3 Physical properties of tube.

3.3.1 Breaking strength. The minimum breaking strength shall be 95 pounds when tested as specified in 4.5.2.

3.3.2 Elongation. The minimum elongation shall be 225 percent when tested as specified in 4.5.3.

3.4 Sterility. The tubes shall be sterile when tested with a biological indicator as specified in 4.5.4.

3.4.1 Certificate of sterility. A certificate stating that samples from each sterilizer lot have been biologically tested and found to be sterile shall be submitted to the procuring activity. The certificate shall include:

a. Item identification.
b. National stock number.
c. Contract or purchase order number.
d. Sterility lot or control number.
e. Date of sterilization.
f. Quantity of product in sterilizer lot.
g. Type of sterilization (gas, radiation, heat, steam, etc.).
h. Form of biological indicator (i.e., inoculated paper spore strip or carrier, inoculated product, or inoculated simulated product).
i. Test organism(s) and population density used.
j. Test medium, incubation temperature, incubation time, and dates of tests.
k. Number of test units.
l. Statement that samples comply with sterility tests.
m. Signature of head of laboratory or a designated qualified alternate.

When inspection is made at destination, the certificate shall be submitted by the contractor to the Directorate of Medical Materiel, ATTN: DPSC-ATQ, Defense Personnel Support Center, 2800 South 20th Street, Philadelphia, PA 19101, and a copy forwarded with each shipment to the consignee. When inspection is made at source, certificate of sterility shall be furnished to the cognizant Government Quality Assurance Representative for submission to the procuring activity.

3.4.2 Sterility lot. A sterility lot is that single quantity of product subjected to the same manufacturing operation and simultaneously sterilized in the same sterilizer chamber. Each immediate, unit and intermediate package shall be clearly marked with a sterility lot (control) number and date of sterilization as specified in 5.3.1 and 5.3.2. Each sterility lot shall be traceable to the pertinent manufacturing lot(s).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:15Z
Check the source to verify that this is the current version before use.

3.5 Freedom from pyrogens. When tested as specified in 4.5.5 the tube shall comply with the pyrogen test requirements of the USP.

3.6 Safety (non-toxicity). When tested as specified in 4.5.5 the tube shall comply with the safety test requirements of the USP.

3.7 Certificates. For destination inspection only, certificates of freedom from pyrogens, and safety, as specified below, shall be submitted by the contractor to Defense Personnel Support Center, Directorate of Medical Materiel, ATTN: DPSC-ATQ, 2800 South 20th Street, Philadelphia, PA 19101, and one copy of each shall be forwarded with each shipment to the consignee.

3.7.1 Certificates of safety (non-toxicity). A certificate of safety, listing all lot or control numbers, shall state that samples from each lot or control have been tested for safety as specified in 3.7 and 4.5.5 and were found to comply with such requirements. The certificate shall reference the method used in determining safety.

3.7.2 Certificate of freedom from pyrogens. A certificate of freedom from pyrogens, listing all lot or control numbers, shall state that samples from each lot or control have been tested for pyrogens as specified in 3.7 and 4.5.5, and were found to comply with such requirements. The certificate shall reference the method used in determining freedom from pyrogens.

3.8 Radiopacity. The tubing shall have a white radiopaque stripe that shows as a definite, uniform shadow when covered by a 5/8 inch thickness of aluminum and tested as specified in 4.5.6.

3.9 Manufacturer's record. The manufacturer shall place a code or lot number on the paper label, which can be verified against the manufacturer's records of all tests made on sterile, pyrogen-free catheters. These records shall be made available for inspection by any duly authorized Government representative. No shipment shall be made until all tests have been completed, verified, and recorded in the permanent records of the manufacturer.

3.10 Workmanship. Workmanship shall be first class throughout. The catheter and trocar assemblies shall be free from defects which detract from their appearance or impair their serviceability. All surfaces shall be smooth, free from pits, burrs, scale, corrosion, dirt or other foreign matter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:15Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specifications where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examination and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificates of quality. Certificates of quality supplied by the manufacturer of the plastic and metal may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the NSN, the item identification, the name of the component/material, the lot number, the lot size, the sample size, the date of testing, the test method, the individual test results, and the specifications requirements.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105. The inspection levels and acceptable quality levels shall be as indicated in table I.

TABLE I. Sampling criteria for examination.

Type of defect	Inspection level	AQL (Percent defective)
Major	S-3	2.5
Minor	S-2	4.0

Source: https://assist.dla.mil -- Downloaded: 202610-21T10:15Z
Check the source to verify that this is the current version before use.

4.2.2 For tests.

4.2.2.1 Physical tests. Sampling for physical tests shall be in accordance with MIL-STD-105 and as indicated in table II.

TABLE II. Sampling criteria for tests.

Component	Characteristic	Requirement	Test	Inspection level	AQL (percent defective)
Catheter	USP Class IV Breaking strength	3.1.1 3.3.1	4.5.1 4.5.2	S-1 S-2	1.5 1.5
	Elongation	3.3.2	4.5.3	S-2	1.5
	Sterility	3.4	4.5.4	S-2	1.0
	Freedom from pyrogens	3.5	4.5.5	S-1	1.5
	Safety	3.6	4.5.5	S-1	1.5
	Radiopacity	3.8	4.5.6	S-1	2.5
	Lead	3.1.1	4.5.7	S-1	2.5

4.2.3 Test samples. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

4.3 Examination.

4.3.1 Examination of assemblies. The assemblies shall be examined to determine compliance with all specification requirements. Examination shall be conducted in accordance with MIL-STD-105 and table III. Examination shall include but not be limited to the defects listed in table III.

TABLE III. Classification of defects.

Categories	Defects
Major	
101	Distal end of catheter not properly chamfered to blend with conical trocar point.
102	Two eyes are not at different levels.
103	Distal end of catheter to be inserted is not free from burrs, feathers, or roughness.
104	Radiopaque line is not an integral part of wall.
105	Not in accordance with dimensional requirements.
Minor	
201	Interior of catheter not smooth.
202	Catheter not free from foreign matter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:15Z
Check the source to verify that this is the current version before use.

4.4 Packaging inspection. The inspection of the unit and intermediate package, packing and marking for shipment and storage shall be in accordance with quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129.

4.5 Tests. Tests shall be conducted, as necessary, to determine compliance with all requirements contained in this specification.

4.5.1 Plastic USP class IV. Catheters shall be tested in accordance with USP requirements for class IV plastics. Samples of the drainage tubes shall be tested in accordance with the method given in the USP for the Implantation Test, except that the implant shall be allowed to remain in the living animal for a period not exceeding 144 hours and the tissues surrounding the implants shall be examined both grossly and microscopically by a pathologist certified by the American Board of Pathology or the American College of Veterinary Pathologists.

4.5.2 Breaking strength. Catheters shall be tested for breaking strength in accordance with ASTM D 638 Method of Test for Tensile Properties of Plastic.

4.5.3 Elongation. Catheters shall be tested for elongation in accordance with ASTM D 638 Method of Test for Tensile Properties of Plastics.

4.5.4 Sterility test. The drainage tube shall be tested for sterility in accordance with the method specified in the USP using inoculated product, inoculated simulated product, or paper spore strip (carrier). Product containing a biological indicator shall be marked or labeled so that it clearly differentiates from product intended for distribution. The incubation medium and minimum time in each case shall be soybean casein digest for 7 days for inoculated product, inoculated simulated product, or paper spore strip (carrier). The incubation temperature shall be as indicated in paragrapb 4.5.4.1. The minimum number of test units, regardless of lot size, shall be 10, except for inoculated carrier which shall be 20 for Type I Sterilization and 30 for Type II Sterilization including inoculated carrier and product test units. The inspection level shall be as indicated in table II, Sampling criteria for tests.

4.5.4.1 Inoculated product or simulated product. For each type of sterilization, the organism used shall be as listed below:

Type of Sterilization	Organism	Incubation Temperature
Steam	B. stearothermophilus	55° - 65°C
Dry Heat	B. stearothermophilus, or	55° - 65°C
	B. subtilis var.niger (or globigii)	30° - 35°C
Gas	B. subtilis var. niger (or globigii)	30° - 35°C
Radiation	B. pumilus	30° - 35°C

The number of viable cells shall be sufficient to provide assurance that the product has been sterilized.

Source: https://assist.dla.mil -- Downloaded: 202640-21T10:15Z
Check the source to verify that this is the currentversion before use.

4.5.4.2 Inoculated carrier. Inoculated carriers (paper spore strips) if used shall be in accordance with MIL-S-36586. Other paper carriers shall be inoculated to be of equivalent resistance. The method of incubation and number of tests units shall be as indicated in 4.5.4 Sterility test and 4.5.4.1 Inoculated product or simulated product. The method of sterilization will control the one organism in the spore strip to be tested for as shown in 4.5.4.1. NOTE: When an inoculated carrier is chosen, product samples must also be tested as required by the USP.

4.5.4.3 Alternate method. Suppliers conducting sterility tests or designating lots in a manner other than that indicated herein shall submit proof that the alternate method provides equal assurance concerning the sterility of the product. However, all sterility tests shall be conducted using biological indicators. Requests for approval of any alternate method of testing for sterility shall be made to the Contracting Officer, and approval obtained before employment of the alternate method on a government contract.

4.5.4.4 Product testing. Testing for sterility of the product after receipt by the government shall be without a biological indicator and in accordance with the USP.

4.5.5 Safety and freedom from pyrogens. Assemblies shall be tested for safety and freedom from pyrogens in accordance with the USP for Transfusion and Infusion assemblies. A minimum of five samples shall be used to prepare the safety extract. Where more samples are indicated by table II, they shall be in multiples of five to prepare a single extract. A minimum of 10 samples shall be used to prepare the freedom from pyrogen extract. Where more samples are indicated by table II, they shall be in multiples of 10 to prepare a single extract.

4.5.6 X-Ray Opacity test. The plastic catheters shall be placed on an unexposed X-ray plate and covered wth an aluminum ladder ranging in thickness from at least 1/8" to 3/4" in steps of 1/8". Using an appropriate exposure such that the steps of at least 1/4", 3/8", 1/2" and 5/8" are clearly delineated from each other, the insert appearance shall be noted.

4.5.7 Test for lead. Ten grams of plastic shall be taken, ignited to char and then further ignited in a muffler at 700 degrees Centigrade (° C.) to a white ash. The ash shall be boiled in 15 milliliters (ml.) of 10 percent nitric acid filtered into a volumetric flask and made up to 100 ml. An aliquot portion, equivalent to one gram of sample, shall be taken and placed in a separator. The dithizone test for lead, as given in the current USP, shall be applied using a control of 4 ppm or 12 ppm of lead solution as given in ı in the USP test. If the sample solution is darker than the limit, smaller aliquots shall be used until the color of the control is matched by the sample solution and the concentration of lead in ppm is determined.

Source: https://assist.dla.mil -- Downloaded: 20260-21T10:15Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. Packaging shall be levels A or C, as specified (see 6.1).

5.1.1 Unit of issue. One package containing ten drainage tubes, as specified, constitutes one unit of issue.

5.1.3 Level A.

5.1.3.1 Immediate package. Each drainage tube shall be packaged straight (not coiled) in a rigid waterproof tube capable of maintaining sterility of contents unless container is damaged or opened. The tube shall contain sufficient cushioning material to prevent damage to the trocar point and to prevent the point from puncturing the container. Each tube shall be sealed with a tamper proof closure.

5.1.3.2 Unit package. Ten immediate containers shall be packaged in a snug fitting box constructed in accordance with PPP-B-676. Closure shall be adequate to prevent spilling of contents.

5.1.3.3 Intermediate package. Twelve unit packages shall be packaged in a box of appropriate size and design constructed in accordance with PPP-B-636, type CF, class weather-resistant. Boxes shall be closed by taping the top and bottom flaps with 2 inch wide tape conforming to PPP-T-76. Closing of bottom flaps with adhesive conforming to MMM-A-250 or metal stitches is permitted.

5.1.4 Level C. Ten individually packaged sterile tubes shall be packaged in a manner that will afford adequate protection against deterioration and physical damage during shipment from the supply source to the first receiving activity.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.1).

5.2.1 Level A. Two intermediate packages (twenty-four units) shall be packed in an exterior container designed for a type 2 load and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, class weather-resistant. Closure and strapping shall be as specified in the appendix of the applicable box specification.

5.2.2 Level B. Two intermediate packages (twenty four units) shall be packed in an exterior container designed for a type 2 load and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; PPP-B-636, class domestic. Closure shall be as specified in the appendix of the applicable box specification.

Source: https://assist.dla.mil -- Downloaded: 202640-21T10:15Z
Check the source to verify that this is the current version before use.

5.2.3 Level C. The packaged tubes shall be packed in shipping containers that will afford adequate protection against damage during direct shipment from the supply source to the first receiving activity. These packs shall conform to the applicable carrier's rules and regulations.

5.3 Marking.

5.3.1 Immediate package. Each immediate package shall be marked with item identification, size (French and nominal length) of unit, sterility lot (control) number, requirements of the Federal Food, Drug and Cosmetics Act and the legend:

"STERILITY GUARANTEED UNLESS PACKAGE IS DAMAGED OR OPENED".

5.3.2 Unit and intermediate package. Each unit and each intermediate package shall be marked in accordance with MIL-STD-129. Sterility lot control number, contract or purchase order number and name of contractor shall be shown. In addition, the method of sterilization (G-Gas, R-Radiation, C-Cold, S-Steam, D-Dry Heat Sterilization) shall be shown following the level of packaging and date of packaging. Example "A-9/76-G." Final sterilization shall be on or after indicated packaging date.

5.3.3 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129. Sterility lot control number and the date and method of sterilization as specified in 5.3.2 shall be shown.

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(c) National Stock Number.

6.2 National Stock No. coverage. This specification covers the following item appearing in the Federal Supply Catalog:

National Stock No.	Item Identification
6515-00-891-7593	TUBE, DRAINAGE, SURGICAL, Thoracic, Plastic, Radiopaque, Straight, with Trocar

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing Activity:
Defense Logistic Agency - DM

Project No. 6515-2006

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:15Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:15Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE: MIL-T-37237A - TUBE, DRAINAGE, SURGICAL, THORACIC, PLASTIC, RADIOPAQUE, STRAIGHT, WITH TROCAR

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:15Z
Check the source to verify that this is the current version before use.

FOLD

DEFENSE PERSONNEL SUPPORT CENTER
2800 South 20th Street
Philadelphia, PA 19101

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY
DoD - 304

U.S.MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:15Z
Check the source to verify that this is the current version before use.