MILITARY SPECIFICATION

PITCH, COAL TAR

This amendment forms a part of MIL-P-87124A (USAF), dated 6 March 1979, and is approved for use within the Department of the Air Force and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

2.1, delete the following document:

"ASTM-D-2317 – Benzene Insoluble (BI) Content of Tar and Pitch"

Add the following documents:

"ASTM D 2569 – Test Method of Distillation of Pitch

ASTM D 4072 – Test Method for Toluene – Insoluble (TI) Content of Tar and Pitch"

PAGE 2

3.1.1, under Properties, line 2: Delete "Benzene" and substitute "Toluene".

Add the following entry:

"Properties	Limits	Test Method
Distillation, to 360 °C, percent	5.5 maximum	4.3.9"

Distribution Statement A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:50Z
Check the source to verify that this is the current version before use.

PAGE 3

4.3.2, delete and substitute:

"4.3.2 Toluene insolubles. The toluene insolubles determination shall be conducted in accordance with ASTM D 4072. Verify conformance with 3.1.1."

PAGE 4

4.3.9, add the following paragraph:

"4.3.9 Distillation. The distillation to a temperature of 360 °C shall be in accordance with ASTM D 2569. Verify conformance with 3.1.1."

Custodian:
Air Force - 20

Preparing Activity:
Air Force – 20

(Project No. 5610-F465)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:50Z
Check the source to verify that this is the current version before use.