INCH-POUND

MIL-C-70462C (AR)
AMENDMENT 2
28 April 1989
SUPERSEDING
AMENDMENT 1
23 July 1986

MILITARY SPECIFICATION

CHARGE, PROPELLING, 155MM, M203A1
LOADING, ASSEMBLING AND PACKING

This Amendment forms a part of Military Specification MIL-C-70462C (AR) dated 4 April 1986, and is approved for use within the US Army Armament Munitions and Chemical Command and is available for use by all Departments and Agencies of Department of Defense.

PAGE 3

3.5 Delete in its entirety and substitute new paragraph 3.5:

"3.5 Moisture content of black powder. The moisture content of the black powder at the igniter loading station at the time of loading shall not exceed 0.7%. The moisture content of the black powder in the basepad of the propelling charge shall be determined in accordance with 4.5.5."

* 3.6 Delete entire paragraph.

* 3.8 Delete heading "Avg Press Max (PSI)" and all entries under the same heading.

PAGE 7

* 4.4.1d Delete in its entirety and substitute the following new paragraphs:

"4.4.1d Case bodies from not more than one interfix number from one manufacturer.

4.4.1e Igniter containers and rear caps from not more than one interfix number from one manufacturer."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:29Z
Check the source to verify that this is the current version before use.

PAGE 23

* 4.5.6 Delete entire paragraph.

* 4.5.9 Delete in its entirety and substitute new paragraph 4.5.9:

"4.5.9 Proving ground assessments. These tests shall be conducted at a Government proving ground in accordance with the applicable acceptance test procedure using M549, RA or PXR-6325 projectiles inert loaded within 0.1 pound of an as fired weight of 96.0 pounds using primer, M82 and fired from M198 Howitzer with cannon M199 with 75 percent (minimum) remaining life. Firing shall be conducted with a spindle to charge base stand-off of 1 inch (plus or minus 1/4 inch). Prior to firing, all charges shall be temperature conditioned in a large conditioning box with adequate air circulation at the required temperature for a minimum of 24 hours and assurance will be made that when fired, the charges are at the conditioning temperature. The following tolerance shall apply to all 145°F and 70°F conditioning: 145°F from 140°F to 145°F; 70°F from 68°F to 72°F. Copper crusher gages (2) shall be used to measure the maximum chamber pressure of each charge. One rear piezo gage shall be used to measure the maximum chamber pressure of each charge for information and ignition delay of each charge. Velocity coils will be used to measure the muzzle velocity of each charge. Temperature indicator (thermometer) strips shall be placed on the side of all charges or on the side of the metal containers, as applicable. If any indicator strip shows the charge has been exposed to a temperature greater than 145°F, that charge will not be fired."

PAGE 24

* 4.5.9.3.2 Delete entire paragraph.

PAGE 26

* 6.8 Delete heading "Avg Press Max" and all entries under the same heading.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:29Z
Check the source to verify that this is the current version before use.

NOTE: The margins of this amendment are marked with an asterisk or vertical lines to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1320-A999)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:29Z
Check the source to verify that this is the current version before use.