MIL-P-17303D(SH)
4 January 1984
SUPERSEDING
MIL-P-17303C(NAVY)
14 October 1955
(See 6.6)

MILITARY SPECIFICATION

PACKING MATERIALS, PLASTIC METALLIC AND PLASTIC NONMETALLIC

This specification is approved for use by the Naval Sea Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers plastic metallic packings and plastic nonmetallic packings for high and low pressure valve stems and reciprocating rods handling saturated and superheated steam service and for rotary and reciprocating pumps handling water, gasoline and oil on naval ships (see 6.2.1).

1.2 Classification. The packing shall be of the following classes and types as specified (see 6.2.1 and 6.5.1):

Class I - Plastic metallic, lead base:
- Type B - Continuous strip, with or without cotton jacket, symbol 1433.
- Type C - Continuous strip, metal foil jacket, symbol 1434.
- Type D - Continuous strip, braided metal jacket, symbol 1432.
- Type E - Continuous strip, with or without cotton jacket, symbol 1437.

Class II - Plastic nonmetallic:
- Type C - Continuous strip, braided asbestos yarn with nickel-copper wire insert jacket, symbol 1108.
- Type D - Continuous strip, with or without cotton jacket, symbol 1109.
- Type E - Continuous strip, braided asbestos yarn with nickel-chromium-iron alloy insert wire jacket, symbol 1111.
- Type F - Continuous strip, braided metal jacket, symbol 1112.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, Naval Sea Systems Command, SEA 55Z3, Department of the Navy, Washington, DC 20362 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 5330

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:56Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards and drawing. Unless otherwise specified, the following specifications, standards and drawing of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

PPP-C-96 - Cans, Metal, 28 Gage and Lighter.
PPP-B-566 - Boxes, Folding, Paperboard.
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-B-640 - Boxes, Fiberboard, Corrugated, Triple-Wall.
PPP-B-676 - Boxes, Setup.

MILITARY

MIL-G-5572 - Gasoline, Aviation: Grades 80/87, 100/130, 115/145.

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

DRAWING

MILITARY

803-5184193 - Steel Globe Valves, 1/4 to 2 NTS, 1500 Class.

(Copies of specifications, standards and drawing required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. The issues of the documents which are indicated as DoD adopted shall be the issue listed in the current DoDISS and the supplement thereto, if applicable.

ASTM

D 471 - Rubber Property - Effect of Liquids. (DoD adopted)

(Application for copies should be addressed to the ASTM, 1916 Race Street, Philadelphia, PA 19103.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:56Z
Check the source to verify that this is the current version before use.

DEPARTMENT OF LABOR

Code of Federal Regulations, Title 29.
Part 1910 - Occupational Safety and Health Standards.

(Application for copies should be addressed to the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.)

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT
National Motor Freight Classification

(Application for copies should be addressed to the National Motor Freight Traffic Association, Inc., ATA TRAFFIC Dept., 1616 "P" Street, NW, Washington, DC 20036.)

UNIFORM CLASSIFICATION COMMITTEE AGENT
Uniform Freight Classification Ratings, Rules and Regulations

(Application for copies should be addressed to the Uniform Classification Committee Agent, Tariff Publication Officer, Room 1106, 222 South Riverside Plaza, Chicago, IL 60606.)

(Industry association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence.

3. REQUIREMENTS

3.1 Qualification. Packing materials furnished under this specification shall be products which are qualified for listing on the applicable qualified products list (QPL) at the time set for opening of the bids (see 4.3 and 6.3).

3.2 Material and construction. The material and construction shall conform to that of the sample submitted for qualification (see 4.3 and 6.3). The plastic core shall consist of carefully selected long fiber asbestos, binding material and lubricant. The binding material shall be metallic for class I and nonmetallic for class II packing. The binder shall be thoroughly mixed in the core and shall hold the core together to prevent separation of the various parts. The binder shall meet the temperature requirement in accordance with 3.2.1.

3.2.1 Class I, plastic metallic, lead base. The metal used for lead base packing shall not melt nor disintegrate at or below a temperature of 550 degrees Fahrenheit (°F) (see 4.6.4).

3.2.1.1 Type B, symbol 1433. The packing shall be continuous strips of approximately uniform cross section, partially compressed to prevent disintegration during application. It may be enclosed in a latticed cotton thread or knit cotton covering or may be furnished without a covering.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:56Z
Check the source to verify that this is the current version before use.

3.2.1.2 Type C, symbol 1434. The packing shall be continuous strips of uniform cross section, completely enclosed in a metal covering consisting of not less than two ribbons. The metal ribbon shall be not less than 0.0023 inch thick.

3.2.1.3 Type D, symbol 1432. The packing shall be continuous strips of uniform cross section, extruded into a braided wire jacket. The jacket shall be of copper wire not more than 0.008 inch in diameter.

3.2.1.4 Type E, symbol 1437. The packing shall be continuous strips of approximately uniform cross section, partially compressed to prevent disintegration during application. It may be enclosed in a latticed cotton thread or knit cotton covering or may be furnished without a covering.

3.2.2 Class II, plastic nonmetallic.

3.2.2.1 Type C, symbol 1108. The packing shall be continuous strips of uniform cross section, completely enclosed in a braided jacket composed of asbestos yarn with nickel-copper wire insert. The packing shall contain a corrosion inhibitor. The packing shall not corrode the 13-percent chrome steel valve stem when tested as specified in 4.6.5.

3.2.2.2 Type D, symbol 1109. The packing shall be continuous strips of approximately uniform cross section, partially compressed to prevent disintegration during application. It may be enclosed in a latticed cotton thread or knit cotton covering or may be furnished without a covering.

3.2.2.3 Type E, symbol 1111. The packing shall be continuous strips of uniform cross section, completely enclosed in a braided jacket composed of asbestos yarn with nickel-chromium-iron alloy wire insert. The core of the packing shall contain not more than 20 percent, by weight, of corrosion inhibitor. The packing shall not corrode the 13-percent chrome steel valve stem when tested as specified in 4.6.5.

3.2.2.4 Type F, symbol 1112. The packing shall be continuous strips of approximately uniform cross section, completely enclosed in a braided copper wire jacket.

3.2.3 Recovered materials. Unless otherwise specified herein, all material and articles incorporated in the products covered by this specification shall be new and shall be fabricated using materials produced from recovered materials to the maximum extent practicable without jeopardizing the intended use. The term "recovered materials" means materials which have been collected or recovered from solid waste and reprocessed to become a source of raw materials, as opposed to virgin raw materials. None of the above shall be interpreted to mean that the use of used or rebuilt products is allowed under this specification unless otherwise specifically specified.

3.3 Performance characteristics.

3.3.1 Flexibility. The packing shall be flexible to be readily formed into coils to fit a rod of the diameter specified in table I.

Source: https://assist.dla.mil -- Downloaded: 202640-18T09:56Z
Check the source to verify that this is the current version before use.

TABLE I. Size of coils.

Size of packing (inches)	Rod diameter (inches)
1/8 to 1/4	2
5/16 to 5/8	3
11/16 to 13/16	4
7/8 to 1	8
1-1/8	9
1-1/4	10

3.3.2 Simulated performance. The packing, under initial conditions and during the progress of the simulated performance tests specified in 4.6.3, shall respond readily to gland adjustment for the control of leakage from the stuffing box. There shall be no uncontrollable leakage for the duration of the test. At test completion, valve stems shall show no excessive wear.

3.3.2.1 Pressure and temperature. When class II, type E, symbol 1111 packing is installed in a stuffing box and tested as specified in 4.6.6 there shall be no leakage from the stuffing box. The packing and the valve stem shall be in satisfactory condition upon conclusion of the tests.

3.4 Size. Packing shall be furnished in the size specified (see 6.2.1).

3.5 Form. Packing shall be furnished in the form of spools, coils or spirals as specified (see 6.2.1).

3.6 Workmanship. The packing shall be free from extraneous material and visible defects, which may affect its serviceability (see 4.5.1).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Inspection system. The contractor shall prepare and maintain an inspection system acceptable to the Government for supplies and services covered by this specification. The inspection system shall be as specified in the contract (see 6.2.2).

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

Source: https://assist.dla.mil -- Downloaded: 202640-18T09:56Z
Check the source to verify that this is the current version before use.

(a) Qualification inspection (see 4.3).
(b) Quality conformance inspection (see 4.4).

4.3 Qualification inspection. Qualification inspection shall be conducted at a laboratory satisfactory to the Naval Sea Systems Command (NAVSEA). Qualification inspection shall consist of examinations and tests specified in 4.5.1 and 4.6. Application for qualification tests shall be made in accordance with "Provisions Governing Qualification SD-6" (see 6.3 and 6.3.1).

4.4 Quality conformance inspection.

4.4.1 Quality conformance inspection sampling.

4.4.1.1 Inspection lot. An inspection lot shall consist of all finished packing of one class, type and size produced under the same conditions and offered for inspection at one time.

4.4.1.2 Sampling plan. Representative lengths of packing material shall be selected from each lot offered for inspection in accordance with MIL-STD-105 at general inspection level I. The acceptable quality level (AQL) shall be 2.5 percent defective. Each sample shall be subjected to the visual examination in accordance with 4.5.1, flexibility test in accordance with 4.6.2 and the heat resistance test in accordance with 4.6.4 (as applicable). Failure of the samples to meet the AQL shall be cause for rejection of the lot represented by the samples.

4.4.2 Test reports. The contractor shall prepare test reports in accordance with data ordering document specified (see 6.2.2).

4.5 Quality conformance tests.

4.5.1 Visual examination. A visual examination shall be conducted to detect defects in workmanship and dimensions. For each length of packing material major defects such as a rip, tear, hole, void, crease, crimp, gouge or extraneous particulate matter on the surface, shall be cause for rejection of that length. Minor surface defects not affecting the serviceability of the packing material shall not be cause for rejection.

4.5.1.1 Comparison tests. The sample specimens selected in accordance with 4.4.1.2 shall be subjected to those tests which will establish the identity of the inspection samples with that given qualification and to the tests specified in 4.5.1 through 4.6.6, respectively.

4.5.1.1.1 Action in case of failure. Acceptance of the first lot under a contract or order shall be withheld until a satisfactory report is received on the comparison test sample. Except as hereinafter specified, acceptance and rejection of lots shall normally be on the basis of the lot acceptance examination and tests specified in 4.5.1. Lot acceptance shall then not be with-held pending receipt of a test report on the subsequent production sample. However, upon receipt of an unsatisfactory test report on a comparison test sample, additional samples shall be selected from every subsequent lot offered for delivery. The sample so selected shall be submitted to a laboratory satisfactory to NAVSEA and shall there be subjected to the comparison tests specified in 4.5.1.1. Lots shall then be accepted only upon receipt of a satisfactory

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:56Z
Check the source to verify that this is the current version before use.

test report on the samples so selected. Additional testing shall be discontinued and lot acceptance returned to the normal basis when four successive lots have been accepted.

4.6 Test procedures.

4.6.1 Chemical analysis. A chemical analysis shall be made using standardized procedures. The analysis shall consist of tests to identify the material components of the packing. The packing material shall conform to the requirements of 3.2.

4.6.2 Flexibility. Packing shall be coiled by hand around a rod of a diameter as shown in table I (see 3.3.1). Only sufficient packing to make one complete turn around the rod shall be used.

4.6.3 Simulated performance. Performance tests shall comply with the requirements of 3.3.2 when tested under simulated operating conditions in a machine designed for the purpose.

4.6.3.1 Class I, type B, symbol 1433 and class II, type F, symbol 1112. The packing shall be tested for the following service:

(a) Reciprocating rod service with saturated steam at 300 pounds per square inch (lb/in^2) and a rod speed of 100 feet per minute (ft/min). The test shall be concluded after 3000 hours of operation.
(b) Rotary rod service with feed water at 100 lb/in^2 (stuffing box pressure) and 250°F, with a rod speed of 4,000 ft/min. The test shall be concluded after 3000 hours of operation.

4.6.3.2 Class I, type C, symbol 1434. The packing shall be tested for rotary rod service with feed water at 100 lb/in^2 (stuffing box pressure) and 250°F, with a rod speed of 4,000 ft/min. The test shall be concluded after 3000 hours of operation.

4.6.3.3 Class I, type D, symbol 1432. The packing shall be tested for reciprocating rod service with steam at 300 lb/in^2 and 720°F with a rod speed of 170 ft/min. The test shall be concluded after 1500 hours of operation.

4.6.3.4 Class I, type E, symbol 1437 and class II, type D, symbol 1109. The packing shall be tested for rotary rod service with a sequence of fluids at 50 lb/in^2 and a rod speed of 1,375 ft/min. The sequence of the fluids shall be as follows:

(a) ASTM reference oil number 3 (test method ASTM D 471) for 200 hours.
(b) Aviation gasoline (MIL-G-5572, grade 115 or 145) for 200 hours.
(c) Sea water for 200 hours (test method ASTM D 471).
(d) ASTM reference oil number 3 for 200 hours.

4.6.3.5 Class II, type C, symbol 1108. The packing shall be tested for valve stem service with steam at 600 lb/in^2 and 750°F. The test shall be concluded after 3500 hours of operation.

Source: https://assist.dla.mil -- Downloaded: 202610-18T09:56Z
Check the source to verify that this is the current version before use.

4.6.3.6 Class II, type E, symbol 1111. The packing shall be tested for valve stem service with steam at 600 lb/in^2 and 750°F. During the test, there shall be a protracted series of simulated valve openings and closings. The tests shall be concluded after 2000 hours of operation.

4.6.4 Heat resistance test. Specimens cut from each sample of class I packing shall be subjected for 2 hours to temperatures specified in 3.2.1 (for class I).

4.6.5 Corrosion resistance test, class II, type C, symbol 1108 and class II, type E, symbol 1111. The packing shall be installed in the stuffing box of a 1-inch size, 600 lb/in^2 valve, equipped with a 13-percent chrome steel valve stem. The packing gland shall be adjusted to allow slight leakage from an applied water pressure of 300 lb/in^2. The condition shall be maintained for 24 hours to ensure the wetting of the packing. The valve shall then be drained and stored at ambient temperature. The valve stem shall be inspected after 6 and 12 months of storage.

4.6.6 Pressure and temperature test. Class II, type E, symbol 1111 packing shall be installed in the stuffing box of a 1-inch size, 1500 series valve in accordance with Drawing 803-5184193, equipped with a 13-percent chrome steel valve stem, and subjected successively to the following conditions:

(a) Superheated steam at 600 lb/in^2 and 750°F for 24 hours.
(b) Air pressure of 2000 lb/in^2.
(c) Temperature of 1100°F for 6 hours.
(d) Air pressure of 2000 lb/in^2.

4.7 Inspection of packaging. Sample packages and packs, and the inspection of the preservation-packaging, packing and marking for shipment and storage shall be in accordance with the requirements of section 5 and the documents specified therein.

5. PACKAGING

(The preparation for delivery requirements specified herein apply only for direct Government acquisition. For the extent of applicability of the preparation for delivery requirements of referenced documents listed in section 2, see 6.4.)

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.2.1).

5.1.1 Packing material containing asbestos. Packing material containing asbestos wrapped as specified in 5.1.2.1 or protected as specified in 5.1.3 shall be packaged in sealed dust and sift proof packages. Packages containing asbestos packing material shall be marked as specified in 5.3.1.

5.1.2 Level A.

5.1.2.1 Preservation-packaging. Packing material, furnished in the form of spools as specified in 3.5, shall be protected by placing a wrap of grease-proof barrier material over the packing material and between the flanges of the spool. The wrap shall be secured, utilizing pressure-sensitive tape. Packing material, furnished in the form other than on spools, shall be completely

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:56Z
Check the source to verify that this is the current version before use.

wrapped in barrier material and secured with tape as specified herein. The greaseproof barrier herein is not required when the unit container selected (see 5.1.2.1.1) is treated for greaseproofness or is inherently greaseproof.

5.1.2.1.1 Unit containers. Each package shall be placed in a fiberboard or paper box, or a metal can, at the contractor's option. The unit container selected shall conform to the following applicable specifications:

Specification	Container
PPP-B-566	Boxes, Folding, Paperboard
PPP-B-636	Boxes, Shipping, Fiberboard
PPP-B-676	Boxes, Setup
PPP-C-96	Cans, Metal, 28 Gage and Lighter.

Sealing and closure, as applicable, of the unit container shall conform to the applicable container specification or appendix thereto, with method I closure applicable to domestic, and method V closure applicable to weather-resistant containers of PPP-B-636. The net weight of packings in paperboard boxes shall not exceed 10 pounds. The net weight of packings in fiberboard boxes shall not exceed 50 pounds.

5.1.3 Level C. Preservation-packaging of packing material shall afford protection against deterioration and physical damage during shipment, from the supply source to the first receiving activity, for immediate use. The contractor's normal retail or wholesale preservation-packaging methods may be utilized when such meets the requirements of this level.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2.1).

5.2.1 Level A. Packing material, preserved-packaged as specified (see 6.2.1), shall be packed in containers conforming to any one of the following specifications at the contractor's option.

Specification	Container	Type or class
PPP-B-636	Fiberboard	Weatherboard-resistant
PPP-B-640	Boxes, fiberboard, corrugated, triple-wall	Class 2

Containers shall be closed, waterproofed and reinforced with tape or nonmetallic banding, as specified in the appendix to the applicable specification, with method V closure applicable to PPP-B-636 containers. Containers shall not exceed the weight limitations of the applicable container specification.

5.2.2 Level B. Packing material, preserved-packaged as specified (see 6.2.1), shall be packed in containers specified in 5.2.1, except that the containers shall be of the domestic class or type. Containers shall be closed

Source: https://assist.dla.mil -- Downloaded: 202640-18T09:56Z
Check the source to verify that this is the current version before use.

in accordance with the applicable container specification or appendix thereto, with method I closure applicable to PPP-B-636 containers, using pressure-sensitive tape.

5.2.3 Level C. Packing material, packaged as specified (see 6.2.1), shall be packed in containers acceptable to the common carrier which will ensure safe delivery to the destination in a satisfactory condition at the lowest applicable rate. Containers, packing or method of shipment shall be complete with Uniform Freight Classification ratings, rules and regulations or National Motor Freight classification rules or regulations, or other carrier rules, as applicable, to the mode of transportation.

5.3 Marking. In addition to any special marking required (see 6.2.1), and herein, interior packages and effective shipping containers shall be marked for shipment in accordance with MIL-STD-129.

5.3.1 Special marking. An asbestos caution label shall be affixed to each interior (unit and intermediate) package and shipping container. The caution label shall be in accordance with Code of Regulations, Title 29, Part 1910. The caution label shall state the following:

"CAUTION

CONTAINS ASBESTOS FIBERS
AVOID CREATING DUST
BREATHING ASBESTOS DUST MAY
CAUSE SERIOUS BODILY HARM."

6. NOTES

6.1 Intended use. Packing is primarily intended for general shipboard service in centrifugal pumps, valve stems, reciprocating rods and stems, expansion joints, pistons handling hot and cold water, saturated and superheated steam, fuel oil, lubricating oil, diesel fuel and gasoline, refrigerant, air and gases.

6.2 Ordering data.

6.2.1 Acquisition requirements. Acquisition documents should specify the following:

(a) Title, number and date of this specification.
(b) Class, type, size and form required (see 1.2, 3.4, and 3.5).
(c) Applicable levels of preservation-packaging and packing required (see 5.1 and 5.2).
(d) Special marking required (see 5.3).

6.2.2 Data requirements. When this specification is used in an acquisition which incorporates a DD Form 1423, Contract Data Requirements List (CDRL), the data requirements identified below shall be developed as specified by an approved Data Item Description (DD Form 1664) and delivered in accordance with the approved CDRL incorporated into the contract. When the provisions of DAR 7-104.9 (n)(2) are invoked and the DD Form 1423 is not used, the data specified

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:56Z
Check the source to verify that this is the current version before use.

below shall be delivered by the contractor in accordance with the contract or purchase order requirements. Deliverable data required by this specification is cited in the following paragraph.

Paragraph no.	Data requirements title	Applicable DID no.	Option
4.1.1	Inspection system plan	DI-R-4803	----
4.2.2, 4.5.1.1.1	Reports, test	DI-T-2072	----

(Data item descriptions related to this specification, and identified in section 6 will be approved and listed as such in DoD 5000.19L., Vol. II, AMSDL. Copies of data item descriptions required by the contractors in connection with specific acquisition functions should be obtained from the Naval Publications and Forms Center or as directed by the contracting officer.)

6.2.2.1 The data requirements of 6.2.2 and any task in section 3, 4 or 5 of this specification required to be performed to meet a data requirement may be waived by the contracting/acquisition activity upon certification by the offeror that identical data were submitted by the offeror and accepted by the Government under a previous contract for identical item acquired to this specification. This does not apply to specific data which may be required for each contract regardless of whether an identical item has been supplied previously (for example, test reports).

6.3 With respect to products requiring qualification, awards will be made only for products which are, at the time set for opening of bids, qualified for inclusion in Qualified Products List QPL-17303 whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or orders for the products covered by this specification. The activity responsible for the Qualified Products List is the Naval Sea Systems Command, SEA 55Z3, Department of the Navy, Washington, DC 20362 and information pertaining to qualification of products may be obtained from that activity. Application for qualification tests shall be made in accordance with "Provisions Governing Qualification SD-6" (see 6.3.1).

6.3.1 Copies of "Provisions Governing Qualification SD-6" may be obtained upon application to Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

6.4 Sub-contracted material and parts. The packaging requirements of referenced documents listed in section 2 do not apply when material and parts are acquired by the contractor for incorporation into the equipment and lose their separate identity when the equipment is shipped.

6.5 Supersession. Class I plastic metallic, lead base: type F has been superseded by this issue of the specification. Where this type is specified, substitute class I, type B.

Source: https://assist.dla.mil -- Downloaded: 202610-18T09:56Z
Check the source to verify that this is the current version before use.

6.5.1 Packing cross-reference. The packing classes and types in this specification and the corresponding classes and types in MIL-P-17303C(SH) and MIL-P-17303B(SH) are specified in table II:

TABLE II. Packing classes and types cross-reference.

MIL-P-17303D(SH)	MIL-P-17303C(SH)	MIL-P-17303B(SH)
Class I Type B Type C Type D Type E	Class I Type A Type B Type C Type D Type E Type F	Class I Type A Type B Type C Type D Type E
Class II Type C Type D Type E Type F	Class II Type C Type D Type E Type F	Class II Type B Type C Type D
	Class III Type B	Class III Type B

6.6 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue, due to the extensiveness of the changes.

Preparing activity:
Navy - SH
(Project 5330-N067)

☆U.S. GOVERNMENT PRINTING OFFICE: 1984—705-040/A0707

Source: https://assist.dla.mil -- Downloaded: 202640-18T09:56Z
Check the source to verify that this is the current version before use.