MIL-C-60982B (AR)
AMENDMENT 6
21 October 1993
SUPERSEDING
AMENDMENT 5
10 November 1992

MILITARY SPECIFICATION

CASE, CARTRIDGE, 40MM, M169

This amendment forms a part of MIL-C-60982B (AR), dated 17 November 1980, and is approved for use by the US Army Armament, Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.3: Delete 3.3 and substitute:

"3.3 Hardness. The hardness of the area near the mouth shall be 62 + 12 on the Rockwell 30T scale. The hardness of the base of the cartridge case shall be 64 + 10 on the Rockwell 30T scale."

Add new paragraph 3.6.1 as follows:

"3.6.1 ultrasonic inspection of barstock. The aluminum bar shall be inspected ultrasonically for internal defects such as pipe, inclusions and laminations."

PAGE 5

TABLE I: Under No. of sample units, Delete: "*"

NOTES: Delete: "* The 25 cartridge cases shall be sectioned and the diameter of each vent hole shall be measured."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:07Z
Check the source to verify that this is the current version before use.

4.4.2.1: Major 107, Delete: "Concentricity of flange diameter with second largest outside diameter. See 4.5.1" and substitute "concentricity of flange diameter with second largest diameter. See 4.5.1, 0.40%, 3.2, Gage."

* Delete: Major 115 in its entirety and substitute:

"115.	Parallelism of open end to base	0.40%	3.2	Gage (see 6.6)"

Delete: defect characteristic "Major 127" in its entirety.

Add new paragraph 4.4.3.2 as follows:

"4.4.3.2 ultrasonic inspection of barstock The material shall be examined 100% for conformance with the criteria defined in 3.6.1. The test shall be conducted in accordance with 4.5.7. The standard shall be established jointly by representatives of the barstock supplier and the contractor."

PAGE 9

* 4.5.2: Delete in its entirety and substitute:

"4.5.2 Hardness. The cartridge case shall be subjected to a Rockwell Hardness Test in accordance with ASTM E 18-67. Three (3) readings shall be taken approximately 120° apart. The average of these readings shall meet the requirement of paragraph 3.3. If any individual reading at the mouth of the case is below 60 that case shall be considered a reject. This test is a non-destructive test. Parts so tested may be returned to the lot."

PAGE 10

4.5.3: Delete "and base plug"
Delete "240" and substitute "Level B"
Delete "Level B" and substitute "72"

* 4.5.5: Delete "...1/4 inch in from the mouth..." and substitute ". ..1/8 to 1/4 inch in from the mouth. .."
Delete the lase sentence and substitute:

"Each specimen must exhibit a minimum tensile strength of 50,000 psi and a yield strength of 45,000 psi to 55,000 psi."

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:07Z
Check the source to verify that this is the current version before use.

Add new paragraph 4.5.7 as follows:

"4.5.7 Ultrasonic inspection of barstock. The test procedures, acceptance/rejection criteria and equipment design shall be submitted for approval in accordance with paragraph 6.3."

5.1.1: Delete "Level C" and substitute "Level B".

PAGE 11

5.2.1: Delete "Level C" and substitute "Level B".

6.3: Delete "AMSMC-QAF-S(D), ARDC" and substitute "AMSMC-QAF-I((D), ARDEC."

The margins of this amendment are marked with an asterisk or vertical lines to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1390-A547)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T01:07Z
Check the source to verify that this is the current version before use.