INCH-POUND

MIL-C-3880E
28 September 1990
SUPERSEDING
MIL-C-3880D
2 December 1982

MILITARY SPECIFICATION

CLUB, POLICEMAN'S

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers one type of policeman's wood club with leather thong.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be used in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8465

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:52Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

KK-L-201	- Leather, Cattlehide, Lace, and Cut Laces
TT-F-336	- Filler, Wood, Paste
TT-L-58	- Lacquer; Spraying, Clear and Pigmented (General Interior Use)
TT-S-190	- Sealer, Sanding, Lacquer-Type (For Wood Furniture)
PPP-B-636	- Boxes, Shipping, Fiberboard

MILITARY

MIL-L-35078	- Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification For

STANDARDS

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	- Marking for Shipment and Storage
MIL-STD-147	- Palletized Unit Loads
MIL-STD-731	- Quality of Wood Members For Containers and Pallets

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Standardization Documents Order Desk, Bldg. 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

1-8-38	- Club, Policeman's, M-1944

(Copies of drawings required by contractors are available from the U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:52Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3951 - Standard Practice For Commercial Packaging

D 4442 - Test Methods for Direct Moisture Content Measurement of Wood and Wood-Base Materials

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.3.

3.2 Materials and components. Materials and components shall be as specified herein and on the applicable drawings. Materials and components not definitely specified shall be of the quality normally used by the manufacturer provided the completed item complies with all provisions of this specification. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.2.1 Wood. Wood shall be any of the following species:

Ash (white)
Beech
Birch (sweet or yellow)
Elm (rock)
Pecan
Hickory
Locust
Maple (sugar)
Oak (red or white)

3.2.2 Leather. Leather shall conform to type I, type II or type III, class 2, treatment B, color natural of KK-L-201, except that the dimensions shall be as specified on Drawing 1-8-38.

3.2.3 Lacquer. Lacquer shall conform to type II, class 1 of TT-L-58. The color shall be black.

3.2.4 Sealer. The sealer shall conform to TT-S-190.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:52Z
Check the source to verify that this is the current version before use.

3.2.5 Wood filler. Filler when used shall conform to TT-F-336.

3.3 Design and construction. The design and construction of the club shall be as specified herein and as shown on Drawing 1-8-38.

3.3.1 Club. The club shall be turned from wood specified in 3.2.1. The moisture content of the wood blanks, at time of turning, shall be not less than 8 nor more than 12 percent when tested as specified in 4.4.1.1. The turned club shall be free from knots, shake, splits, checks, wane, decay, larvae channels and holes, except a hole not larger than 3/32 inch diameter by 1/2 inch deep located not less than 1/2 inch from the edge at the unstamped end of club will be permitted for holding club during lacquer operations. The slope of the grain shall not exceed 1 inch in 15 inches, measured parallel to the axis of the club blank when tested as specified in 4.4.1.1. All surfaces of the turned club shall be sanded smooth and shall be free of machine marks, chipped or torn grain, and spur.

3.3.2 Thong. Each club shall be furnished with a thong made from leather specified in 3.2.2. The finished thong shall not be pieced or spliced and shall be free of cut, hole, tear, or crack; boney, stiff, loose or pipey areas; soft spots; and discoloration or mildew. The thong shall be centered and tied around the finished club in the thong groove provided. The ends of the thong shall not be tied or knotted together. In lieu of the plus tolerance shown on Drawing 1-8-38, the thong may be supplied up to 32 inches in length.

3.4 Finish. All wood surfaces shall be sanded smooth and free from dust. One coat of sealer specified in 3.2.4, and a minimum of two coats of lacquer specified in 3.2.3 shall be applied to the entire surface of the club. The finish coat shall level out to produce a smooth and uniform appearance on the finished club without brush marks, orange peel, runs, wrinkles, drops, streaks, blushing, area of thin or no film, or wet or tacky finish. There shall be no trace of grit or coarse particles. Wood filler, as specified in 3.2.5, may be used and slight irregularity of surface of film over the open grain wood will be acceptable. However, the finish shall be free of non-uniformity of gloss due to variance in the absorption quality of the wood.

3.5 Marking for identification. The letters US shall be legibly indented on the club as shown on Drawing 1-8-38.

3.6 Workmanship. All surfaces shall be smooth and clean and shall be free of machine gouges.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:52Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for ensuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to ensure compliance with all dimensional requirements.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.4.3 and 4.4.4. Any nonconformance shall be cause for the rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:52Z
Check the source to verify that this is the current version before use.

4.4.1.1 Component and material testing. In addition to the quality assurance provisions of the subsidiary specifications and drawings, testing shall be performed on the wood for the test characteristics specified in table I. The lot size shall be expressed in units of 100 blanks of wood. The sample unit shall be one piece of wood prior to turning. The inspection level shall be S-1 and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 4.0.

TABLE I. Material tests

Material	Characteristic	Requirement paragraph	Test method	Number of determinations per sample unit	Results reported as
Wood	Moisture content	3.3.1	ASTM D 4442	3	Average of 3 determinations to nearest 0.5 percent
	Slope of grain	3.3.1	4.5.1	1	Pass or fail

4.4.2 In-process inspection. Inspection of components shall be made to ascertain that construction details which cannot be examined in the finished product are in accordance with specified requirements. The Government reserves the right to exclude from consideration for acceptance any material or service for which in-process inspection has indicated nonconformance.

4.4.2.1 Visual examination of clubs prior to finishing. Prior to application of lacquer (or filler, when used), the turned club shall be examined for defects listed in table II. The lot size shall be expressed in units of turned clubs. The sample unit shall be one turned club. The inspection level shall be I and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:52Z
Check the source to verify that this is the current version before use.

TABLE II. Unfinished club defects

Examine	Defect	Classification Major	Classification Minor
Club	Knot, wane, or hole	101	
	NOTE: A hole not larger than 3/32 inch in diameter by 1/2 inch deep located not less than 1/2 inch from edge at unstamped end of club is allowed.		
	Decay or larva channel	102	
	Shake, split, surface check, or machine marks	103	
	Spur		201
	Chipped or torn grain	104	

4.4.2.2 Finish in-process examination. Examination shall be made to determine compliance with finish requirements in 3.4. Whenever nonconformance is noted, correction shall be made to affected items and to the lot in process.

4.4.3 End item visual examination. The end items shall be examined for the defects listed in table III. The lot size shall be expressed in units of one club. The sample unit shall be one club. The inspection level shall be II and the AQL, expressed in terms of defects per hundred units, shall be 4.0 for major defects and 10.0 for total (major and minor combined) defects.

TABLE III. End item visual defects

Examine	Defect	Classification Major	Classification Minor
Club	Groove missing, misplaced, or not continuous		201
	Not finished or finish is not black	101	
	Discoloration such as streak or blushing		202

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:52Z
Check the source to verify that this is the current version before use.

TABLE III. End item visual defects (cont'd)

Examine	Defect	Classification Major	Minor
Club (cont'd)	Area of no film:		
	Bare wood showing in area of 1 square inch or more	102	
	Bare wood showing in area of less than 1 square inch		203
	Area of thin film (i.e., appears starved as if one coat was used in lieu of two coats)		204
	Wet or tacky finish		205
	Irregularity of gloss due to absorption of wood or area of rough wood		206
	Coating not smooth and uniform (e.g., brush marks, run, wrinkle, or drop)		207
	Grit or coarse particles		208
	Orange peel		209
	Evidence of spur, wane, chipped or split wood		210
Leather thong	Missing	103	
	Cut, hole, tear, crack, boney, stiff, loose, pipey, soft spot, discoloration or mildew		211
	Pieced or spliced	104	
	Not attached as specified		212
Marking	Missing, incomplete, incorrect, illegible, misplaced, not specified size, or not affixed in specified manner		213

4.4.4 End item dimensional examination. The end item shall be examined for conformance to the dimensions specified on the drawings. Only those dimensions that can be evaluated without damaging or disassembling the end items shall be examined. Any dimension deviating from the specified requirements or any taper that is not constant, for example, contains high or low spots, shall be classified as a defect. The lot size shall be expressed in units of clubs. The sample unit shall be one club. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 4.0.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:52Z
Check the source to verify that this is the current version before use.

4.4.5 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as incomplete sealing or closure of flap, improper taping, loose strapping, or inadequate stapling Bulged or distorted container
Content	Number per container is more or less than required

4.4.6 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Load not bonded as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

4.5 Methods of inspection.

4.5.1 Slope of wood grain. The slope of the wood grain may be determined by combining the grain direction of two adjacent faces of a square or rectangular piece. When one of these faces is straight grained, the true

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:52Z
Check the source to verify that this is the current version before use.

slope of grain is shown on the other face. When there is a slope on both faces, the true or combined slope is greater than the slope on either face. Slope of grain is shown on edge grained faces by the summerwood bands, and on flat grained faces by the direction in which a free flowing ink or dye spreads or by the course taken by a narrow strip lifted by a knife point and torn out. Direction of fiber may also be measured by a slope of grain detector.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial, as specified (see 6.2).

5.1.1 Level A. The thong shall be neatly coiled around the tapered portion below the handle, and the ends passed under the last coil and drawn tight.

5.1.2 Commercial. Clubs shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial, as specified (see 6.2).

5.2.1 Level A packing. Fifty clubs, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, grade V2s of PPP-B-636. Inside dimensions of the box shall be approximately 22-1/2 inches in length, 14 inches in width, and 7 inches in depth. Each shipping container shall be closed, waterproofed, and reinforced in accordance with the appendix of PPP-B-636. Boxes shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). When unit loads are strapped, strapping shall be limited to nonmetallic strapping except for type II, class F loads.

5.2.2 Level B packing. Fifty clubs, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. Inside dimensions of the box shall be approximately 22-1/2 inches in length, 14 inches in width, and 7 inches in depth. Each box shall be closed in accordance with method III as specified in the appendix of PPP-B-636.

5.2.2.1 Weather-resistant shipping container. When specified (see 6.2), the shipping container shall be a grade V3c, V2s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of PPP-B-636.

5.2.3 Commercial packing. Clubs, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:52Z
Check the source to verify that this is the current version before use.

5.3 Palletization. When specified (see 6.2), clubs, packed as specified in 5.2.2 or 5.2.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet type shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means C and D or film bonding means F or G. Pallet pattern shall be number 3 in accordance with the appendix of MIL-STD-147.

5.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The club is intended for use by personnel involved in police activities.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number, and date of this specification.
b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
c. When first article is required (see 3.1, 4.3, and 6.3).
d. Levels of preservation and packing required (see 5.1 and 5.2).
e. Type and class of unit load (see 5.2.1).
f. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
g. When palletization is required (see 5.3).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for selection, inspection, and approval of the first article.

6.4 Subject term (key word) listing.

Weapon
Wood

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:52Z
Check the source to verify that this is the current version before use.

6.5 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Review activity:

Air Force - 82

User activities:

Navy - MC
Air Force - 45

Preparing activity:

Army - GL

(Project 8465-0037)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:52Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	MIL-C-3880E	1990 September 28

3. DOCUMENT TITLE

Club, Policemen's

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code)	
U.S. Army Natick RD&E Center	(1) Commercial 508-651-5221	(2) AUTOVON 256-5221
c. ADDRESS (Include Zip Code) Commander, U.S. Army Natick RD&E Center ATTN: STRNC-ES Natick, MA 01760-5014	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

Source: https://assist.dla.mil -- Downloaded: 2026-03-16 14:14:57
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:52Z
Check the source to verify that this is the current version before use.