MILITARY SPECIFICATION

HOSE ASSEMBLIES, NON-METALLIC: GREASE GUN HIGH AND LOW PRESSURE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers hose assemblies (hose and fittings) for use with high and low pressure lubricant dispensing equipment.

1.2 Classification. The hose assemblies shall be the following types, styles and grades as specified (see 1.3, 3.8, and 6.2 b).

Type I - High pressure.
Type II - Low pressure.
Style 1 - Male fitting on each end.
Style 2 - Female fitting on each end.
Style 3 - One male and one female fitting.
Grade A - For use at temperatures down to -50° F.
Grade B - For use at temperatures down to -40° F.

1.3 Specification part number. The military specification part numbers for the hose assemblies shall be as follows:

M3868 - XX X X

- Grade (see 1.2)
- Style (see 1.2)
- Type (see 1.2, 3.4.1, 6.1.1, 6.1.2)

Example: M3868I2A

A high pressure hose assembly with female fitting on each end for use at temperatures down to -50° F (-45.5° C).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: USA Belvoir Research and Development Center, ATTN: STRBE-TSE, Fort Belvoir, VA 22060-5606 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 4720
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

QQ-B-626	- Brass, Leaded and Nonleaded: Rod, Shapes, Forgings, and Flat Products with Finished Edges (Bar and Strip).
VV-L-825	- Lubricating Oil, Refrigerant Compressor.

MILITARY

MIL-P-775	- Packaging of Hose, Hose Assemblies; Rubber, Plastic, Fabric, or Metal (Including Tubing); and Fittings, Nozzles, and Strainers.
MIL-H-5606	- Hydraulic Fluid, Petroleum Base, Aircraft, Missile, and Ordnance.
MIL-G-20241	- Gasket Material, Wool Felt, Impregnated, Adhesive, Pressure-Sensitive.
MIL-S-81733	- Sealing and Coating Compound, Corrosion Inhibitive.

STANDARDS

FEDERAL

FED-STD-H28	- Screw-Thread Standards for Federal Services.
FED-STD-601	- Rubber: Sampling and Testing.

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	- Marking for shipment and storage.
MIL-STD-130	- Identification Marking of US Military Property.
MIL-STD-889	- Dissimilar Metals.

(Copies of specifications and standards required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. The issues of the documents which are indicated as DoD adopted shall be the issue listed in the current DoDISS and the supplement thereto, if applicable.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

A 108 - Carbon Steel Bars, Carbon, Cold-Finished, Standard Quality.
B 117 - Salt Spray (Fog Testing).
B 633 - Electrodeposited Coating of Zinc on Iron and Steel.
D 297 - Rubber Product - Chemical Analysis.
D 380 - Standard Methods of Testing Rubber Hose.
D 412 - Rubber Properties in Tension.
D 413 - Rubber Property - Adhesion to Flexible Substrate.
D 471 - Rubber Property Effect of Liquids.
D 3951 - Standard Practice for Commercial Packaging.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103).

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, (except for associated detail specifications, specifications sheets or MS standards), the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Description. The hose assembly shall consist of a reinforced synthetic rubber hose with a fitting attached to each end as specified herein.

3.2 First article. Unless otherwise specified (see 6.2), a sample shall be subjected to first article inspection (see 4.3 and 6.3). Any changes or deviations of the hose assemblies from the approved first article during production will be subject to the approval of the contracting officer. Approval of the first article will not relieve the contractor of his obligation to furnish hose assemblies conforming to this specification.

3.3 Material. Material shall be as specified herein. Materials not specified shall be selected by the contractor and shall be subject to all provisions of this specification.

3.3.1 Material deterioration and control. The hose assemblies shall be fabricated from compatible materials, inherently corrosion and deterioration

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.

resistant or treated to provide protection against the various forms of corrosion and deterioration that may be encountered in any of the applicable storage and operating environments to which the hose assemblies may be exposed.

3.3.1.1 Dissimilar metals. Dissimilar metals, as defined in MIL-STD-889, shall be electrically insulated from one another to minimize or prevent galvanic corrosion. Insulation may be provided by an insulating barrier such as a corrosion inhibiting sealant conforming to MIL-S-81733 or chromate tape conforming to MIL-G-20241. Protection against corrosion could also be obtained by exclusion of the electrolyte if feasible.

3.3.1.2 Identification of materials and finishes. The contractor shall identify the specific material, material finish or treatment for use with components and sub-components, and shall make information available, upon request, to the contracting officer or designated representative.

3.3.1.3 Steel. Steel shall conform to ASTM A108.

3.3.1.4 Brass. Brass shall conform to QQ-B-626, half hard temper.

3.3.1.5 Recovered materials. For the purpose of this requirement, recovered materials are those materials which have been collected from solid waste and reprocessed to become a source of raw materials, as distinguished from virgin raw materials. The components, pieces and parts incorporated in the hose assemblies may be newly fabricated from recovered materials to the maximum extent practicable, provided the hose assemblies produced meet all other requirements of this specification. Used, rebuilt or remanufactured components, pieces and parts shall not be incorporated in the hose assemblies.

3.4 Construction.

3.4.1 Hose. The hose shall consist of an inner tube, wire reinforcement, and an outer cover. The inside and outside hose and wire braid diameters shall be as shown in table I.

TABLE I. Inside and outside hose and wire braid diameters.

Hose type	Inside diameter (inches)			Wire braid diameter (inches)		Outside diameter (inches)	
	Nom.	Min.	Max.	Min.	Max.	Min.	Max.
I	0.1875	0.179	0.210	0.414	0.461	0.594	0.656
I	0.250	0.242	0.273	0.477	0.523	0.656	0.719
I	0.375	0.367	0.398	0.633	0.680	0.813	0.875
I	0.500	0.485	0.531	0.750	0.813	0.937	1.000
II	0.1875	0.179	0.210	0.351	0.398	0.468	0.531
II	0.375	0.367	0.398	0.570	0.617	0.750	0.812
II	0.500	0.485	0.531	0.688	0.750	0.875	0.937
II	0.750	0.735	0.781	0.969	1.031	1.156	1.219

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.

3.4.1.1 Inner tube. The inner tube shall be seamless construction with a smooth bore. Walls shall be uniform in thickness, free of pitting or other defects. The tube may be encased in a fabric backing.

3.4.1.2 Reinforcement. The reinforcement for hose used for the type I hose assemblies shall consist of steel double-wire braid or equivalent spiral layers of wire combinations. The reinforcement for hose used for type II hose assemblies shall consist of a single wire braid. The steel wire shall be cushioned in rubber to prevent wear caused by the wire braids rubbing against each other. The steel wire shall in cross section be free from lumps, kinks, and corroded surfaces, and shall be braided under tension. Bonding material shall be used adjacent to the wire reinforcement to join the plies to the inner tube and to the outer cover.

3.4.1.3 Outer cover. The outer cover shall be a polychloroprene compound and resistant to the effects of abrasion, sunlight, and ozone. It shall be uniform in thickness, and free of pitting, cracking, or other defects when tested in accordance with 4.6.2.1.

3.4.2 Fittings. The end fittings for hose assemblies shall be steel or brass as specified in 3.3.1.3 or 3.3.1.4. The end fittings shall be permanent or reusable type as specified (see 6.2), and shall be style 1, 2, or 3, rigid or swivel units as specified (see 6.2). The end fitting size shall be as specified (see 6.2).

3.4.2.1 Finish. Steel end fittings shall be zinc coated in accordance with ASTM B 633, type and class optional, except salt spray requirements shall be tested as specified in 4.6.2.9.

3.4.2.2 Threads. Unless otherwise specified (see 6.2), threads of end fittings shall be American Standard taper pipe thread (NPTF), inch system, conforming to FED-STD-H28 section on Dryseal American Standard Pipe Threads.

3.5 Physical properties. The hose, hose tube, hose cover, and fittings shall conform to the physical properties specified in table II.

TABLE II. Physical properties - type I and II hose assemblies and components.

Physical property	Requirements	Test paragraph
Tensile strength, minimum, psi.		4.6.2.2
Hose tube and cover type I and II.	1250	
Ultimate elongation, minimum, percent.		4.6.2.2
Hose inner tube, type I and II.	100	
Hose outer cover, type I and II.	200	
Volume increase, maximum, percent		4.6.2.3
Hose inner tube, type I and II.	35	
Hose outer cover, type I and II.	75	

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.

TABLE II. Physical properties - type I and II hose assemblies and components. (continued)

Physical property	Requirements	Test paragraph
Adhesion, minimum, pounds.		4.6.2.4
Hose cover to reinforcement.	8	
Flexibility, low temperature, degrees F.		4.6.2.5
Hose, type I and II, all styles, (grade A).	-50	
Hose, type I and II, all styles, (grade B).	-40	
Length change, maximum, percent, all sizes.		4.6.2.6
Elongation.	2	
Contraction.	4	
Heat resistant (aging) 158 ±2° F, 24 hours, hose assembly, type I.	No evidence of damage, leaking, cracking or permanent deformation.	4.6.2.8
Corrosion resistance, salt spray, 48 hours, hose fittings, type I and II.	No evidence of damage, corrosion, cracking or permanent deformation.	4.5.2.9

3.6 Hydrostatic pressure. The hose assembly shall withstand the applicable pressures shown in table III without any evidence of leakage, cracking, rupture, separation of hose fittings from the hose, or other defects.

TABLE III. Pressure requirements.

Type hose	Nominal ID (inch)	Proof pressure (psi)	Burst pressure (min. psi)	High-low-high pressure (psi)
I	0.1875	10,000	20,000	14,000-3,330-14,000
I	0.250	10,000	20,000	14,000-3,330-14,000
I	0.375	8,000	16,000	10,500-2,500-10,500
I	0.500	7,000	14,000	8,400-2,000-8,400
II	0.1875	6,000	12,000	
II	0.375	4,500	9,000	
II	0.500	4,000	8,000	
II	0.750	2,500	5,000	

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.

3.7 Dimensions. The hose assemblies shall be in lengths as specified (see 6.2). The nominal inside diameter sizes of hose assemblies shown in table I shall be as specified (see 6.2). The hose inside diameter, wire braid diameter, and outside diameter, for each respective nominal size and type hose assembly shall be as shown in table I.

3.8 Identification marking. Each hose assembly shall be marked with the manufacturer's name or trade mark, manufacturer's part number, specification part number, grade and year of manufacture in accordance with MIL-STD-130.

3.9 Workmanship. The finished hose assemblies shall conform to the quality and grade of product established by this specification. There shall be no evidence of bulges, warpage, dirt, fins, sprues, scale, flux, burrs, scratches, cuts, pits, sharp edges, rust defective connections, or loose, damaged, or missing parts.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.4).
b. Quality conformance inspection (see 4.5).
c. Inspection of packaging (see 4.7).

4.3 Inspection conditions. Unless otherwise specified all inspections shall be performed in accordance with the test conditions specified in 4.6.2.3, 4.6.2.5, 4.6.2.7, 4.6.2.8, and 4.6.2.9.

4.4 First article inspection.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.

4.4.1 Examination. The first article hose assembly shall be examined as specified in 4.6.1. Presence of one or more defects shall be cause for rejection.

4.4.2 Tests. The first article hose assembly shall be tested as specified in 4.6.2.1 through 4.6.2.10. Failure of any test shall be cause for rejection.

4.5 Quality conformance inspection.

4.5.1 Lot. All hose assemblies of the same type, style and grade offered for inspection at one time shall constitute a lot.

4.5.2 Sampling. Sampling for examination and tests shall be in accordance with MIL-STD-105, except where otherwise indicated herein. A sample unit shall be one complete hose assembly.

4.5.3 Examination.

4.5.3.1 Samples.

4.5.3.1.1 Visual. Visual examination of the completely assembled end item shall be as specified in 4.6.1. The inspection level shall be level II. AQL shall be 2.5 for major defects.

4.5.3.1.2 Dimensional. Dimensional examination shall be made for compliance with dimensions specified in 3.7 and table I. Any deviation therefrom shall constitute a defect. The inspection level shall be level II. AQL shall be 4.0, expressed in terms of defects per hundred units.

4.5.4 Tests. Samples selected in accordance with 4.5.2 shall be tested as specified in 4.6.2.7.3. The inspection level shall be level S-3. AQL shall be 2.5, expressed in terms of defects per hundred units.

4.6 Inspection procedure.

4.6.1 Examination. The hose assemblies shall be examined as specified herein for the following defects:

Major

101. Type, style, or grade not as specified.
102. Materials not as specified.
103. Components missing or not as specified.
104. Steel fitting finish not as specified.
105. Threads not as specified.
106. Construction not as specified.
107. Physical properties not as specified.
108. Dimensions not as specified.
109. Identification marking missing, incomplete, illegible, or not as specified.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.

110. Workmanship not as specified.
111. Materials are not resistant to corrosion and deterioration or treated to be resistant to corrosion and deterioration for the applicable and operating environments.
112. Dissimilar metals as defined in MIL-STD-889 are not effectively insulated from each other.
113. Contractor does not have documentation available for identification of material, material finishes, or treatment.
114. Used, rebuilt, or remanufactured components, pieces or parts incorporated in the hose assembly.

4.6.2 Tests.

4.6.2.1 Outer cover. The outer cover of the hose shall be tested in accordance with ASTM D 297. Nonconformance to 3.4.1.3 shall constitute failure of this test.

4.6.2.2 Tensile strength and ultimate elongation. The contractor shall furnish press cured sheets made from the same compound and with equivalent cure to be used to determine the tensile strength and elongation for the tube and cover on the 0.1875-inch size hose, and for the tube on the 0.25-inch size hose. Test specimens for other hose sizes shall be cut from the hose in accordance with ASTM D 412. The tensile strength and ultimate elongation of the hose tube and cover shall be determined in accordance with ASTM D 412. Nonconformance to table II shall constitute failure of this test.

4.6.2.3 Volume increase. After fluid immersion, the volume increase of the hose tube and cover shall be determined in accordance with ASTM D 471. The immersion fluid shall be reference oil No. 3 of ASTM D 471. Test specimens shall be immersed for 70 hours at 212° F (100° C). Nonconformance to table II shall constitute failure of this test.

4.6.2.4 Adhesion (friction). From hose specified for type II hose assemblies, prepare a closed ring type specimen. The adhesion of the hose cover to reinforcement shall be determined in accordance with ASTM D 413. Nonconformance to table II shall constitute failure of this test.

4.6.2.5 Flexibility (low temperature). A straight test specimen (hose approximately 18 inches long) shall be placed in a coldbox and subjected for 24 hours to a temperature of -50° F (-45.5° C) for grade A hose; or of -40° F (-40° C) for grade B hose. At the end of the 24-hour period, and while still held at the specified low temperature, the specimen shall be bent around a mandrel having a diameter equal to 10 times the outside diameter of the specimen. Alternatively, the specimen may be first bent around such a mandrel, then subjected to the specified low temperature for 24 hours, and bent back into a straight position. Following the bending (or straightening) the tube and cover of the specimen shall be examined. Evidence of leakage, cracking, rupture, or separation of the fittings shall constitute failure of this test.

4.6.2.6 Length changes. The test specimen shall be a hose assembly complete with end fittings. After its initial length, in straight condition without

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.

tension, has been determined, the specimen shall be brought up to a hydrostatic pressure equal to 25 percent of burst pressure (see table III), in accordance with ASTM D 380, except the measurement shall be taken after final pressure has been held not less than 1 minute. With the pressure held constant, the final length of the specimen shall be recorded and the change (elongation or contraction) calculated as a percentage of the initial length. Nonconformance to table II, as applicable, shall constitute failure of this test.

4.6.2.7 Hydrostatic pressure.

4.6.2.7.1 Burst pressure. The hose assembly shall be subjected to the applicable hydrostatic burst pressure specified in table III, in accordance with ASTM D 380. Nonconformance to 3.6 or table III shall constitute failure of this test.

4.6.2.7.2 High-low-high pressure. The hose assembly (type I only) shall be filled with test fluid conforming to VV-L-825, type I or MIL-H-5606 and subjected to the applicable high-low-high pressures specified in table III. The pressure shall be increased in accordance with ASTM D 380, to the high value, and then held for 5 minutes. The pressure shall then be reduced to the low value for 5 minutes, and increased to the previous high value for a final 5 minute period. During the final period, the hose assembly shall be carefully observed. Nonconformance to 3.6 or table III shall constitute failure of this test.

4.6.2.7.3 Proof pressure. The hose assembly shall be subjected to the applicable proof pressure specified in table III, in accordance with ASTM D 380, sections 12, 13, 15.1, and 15.3, with such pressure applied for 3 minutes. While under pressure the hose assembly shall be examined. Nonconformance to 3.6 or table III shall constitute failure of this test.

4.6.2.8 Heat-aging resistance. The hose assembly (type I only) shall be placed in a covered, vented container, arranged so that test fluid conforming to VV-L-825, type I, or MIL-H-5606 will completely fill the container and cover the hose assembly. The container with its fluid and hose assembly, shall then be placed in an air oven, and maintained there at a temperature of 158° F ±2° F for 24 hours. At the end of this heating period, the hose assembly shall be removed, drained of test fluid, cooled to room temperature, and wiped dry on the exterior. It shall then be subjected to the proof-pressure test specified in 4.6.2.7.3 for 4 to 6 minutes. While under pressure the hose assembly shall be observed. Nonconformance to 3.6 or table III shall constitute failure of this test.

4.6.2.9 Salt spray. Unless otherwise specified (see 6.2), one set of zinc coated steel fittings for a type I or II hose assembly shall be subjected to the salt spray test in accordance with ASTM B 117. At the end of this period the fittings shall be washed free of salt particles, air dried to remove surface moisture, and examined. Nonconformance to table II shall constitute failure of this test.

4.6.2.10 Measurement. The length requirements of the hose assemblies shall be measured in accordance with FED-STD-601, method 2411. The inside diameter measurements shall be taken at least 1 inch from the end of the hose with an

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.

expanding ball or telescoping gage; the outside diameter shall be measured at least 1 inch from the end of the hose with steel caliper or micrometer gages graduated in not more than 0.015-inch; at least two readings 90 degrees apartshall be taken and the measurements averaged. Nonconformance to 3.7 or table I, as applicable, shall constitute failure of this test.

4.7 Inspection of packaging. The preservation, packing and marking for level A or B shall be examined in accordance with the quality assurance provisions of MIL-P-775, and for compliance with ASTM D 3951 for commercial packaging.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or commercial as specified (see 6.2).

5.1.1 Level A. Hose assemblies shall be preserved in accordance with the level A preservation and packaging requirements of MIL-P-775.

5.1.2 Commercial. Hose assemblies shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or commercial as specified (see 6.2).

5.2.1 Level A. Hose assemblies shall be packed in accordance with the level A packing requirements of MIL-P-775.

5.2.2 Level B. Hose assemblies shall be packed in accordance with the level B packing requirements of MIL-P-775.

5.2.3 Commercial. Hose assemblies shall be packed in accordance with ASTM D 3951.

5.3 Marking.

5.3.1 Military. Marking for military levels of protection (level A or B) shall be in accordance with MIL-STD-129.

5.3.2 Commercial. Commercial marking shall be in accordance with ASTM D 3951; in addition, the shipping weight and cube shall be marked on the shipping container.

6. NOTES

6.1 Intended use. The hose assemblies covered by this specification are intended for use in dispensing grease as follows.

6.1.1 Type I. With high-pressure, hand-operated or power-operated lubricating guns, buckets, or other dispensing equipment.

6.1.2 Type II. With low-pressure, hand-operated lubricating guns, buckets, or similar dispensing equipment.

Source: https://assist.dla.mil - Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this specification.
b. Type, style, and grade required (see 1.2).
c. When a first article is required for inspection and approval and number of units required (see 3.2, 4.4, and 6.3).
d. Whether permanent or reusable fittings are required (see 3.4.2).
e. Whether rigid or swivel type fittings are required (see 3.4.2).
f. Size of end fittings required (see 3.4.2).
g. Threads of end fittings, if other than specified (see 3.4.2.2).
h. Hose assembly length required (see 3.7).
i. Hose nominal diameter (size) required (see 3.7).
j. When salt spray test is not required (see 4.6.2.9).
k. Degree of preservation and degree of packing required (see 5.1 and 5.2).

6.3 First article. When a first article inspection is required, the items should be preproduction models. The first article should consist of 10 units. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examinations, tests, and approval of the first article test results and disposition of the document's first article.

6.4 Changes from previous issue. Asterisks (or vertical lines) are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodians:
Army - ME
Navy - YD
Air Force - 99

Preparing activity:
Army - ME

Project 4720-0683

Review activity:
DLA - CS
Air Force - 82

User activities:
Army - AT
Navy - CG, MC, AS, SH

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Belvoir R&D Center
ATTN: STRBE-TSE
Fort Belvoir, VA 22060-5606

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-H-3868F	Hose Assemblies, Non-Metallic; Grease Gun High and Low Pressure

3a. NAME OF SUBMITTING ORGANIZATION

b. ADDRESS *(Street, City, State, ZIP Code)*

4. TYPE OF ORGANIZATION *(Mark one)*

- ☐ VENDOR
- ☐ USER
- ☐ MANUFACTURER
- ☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T21:51Z
Check the source to verify that this is the current version before use.