GGG T-563a
AMENDMENT—4
April 2, 1964

SUPERSEDING
Interim Amendment—3(DOD)
September 26, 1963 and
Amendment—2
April 9, 1963

FEDERAL SPECIFICATION

TOOLS, BLACKSMITHS'; CHISELS, FLATTERS, FULLERS, SET HAMMERS, HARDIES, BOLT HEADING TOOLS, PUNCHES, AND SWAGES

This amendment, which forms a part of Federal Specification GGG-T-563a, dated June 9, 1958, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

Page 2, paragraph 2.1: Add the following in proper sequence: "Fed. Test Method Std. No. 151—Metals; Test Methods."

Page 2, paragraph 2.1: Under "Military Specifications" delete MIL-P-15424 in its entirety and substitute:

"MIL-H-15424—Hand Tools, Packaging of."

Page 2, paragraph 3.2: Delete and substitute:

3.2 Material. The tools, except for type I, class 1, and type VII, classes 1, 2, and 3 shall be forged from a good quality alloy steel or carbon steel of not less than 0.50 carbon. Type I, class 1, and type VII, classes 1, 2, and 3 shall be forged from a good quality alloy steel. The forgings shall be of uniform quality, free from burrs and flash marks.

Page 3, paragraph 3.4, line 9: Delete "and facilitate a comfortable handgrip."

Page 3, paragraph 3.8.2: Delete and substitute:

3.8.2 *Hardness.* When tested as specified in 4.4.1, the chisel shall show a hardness value of Rockwell C52 to C58 on the cutting end and Rockwell C28 to C43 on the striking end.

Page 4, table II: Delete the second column and substitute:

Size of cutting edge C	
Min.	Max.
Inches	*Inches*
1-15/32	1-23/32
1-27/32	2-3/32
2-3/32	2-11/32

Page 5, paragraph 3.10.1, second sentence: Delete and substitute: "The square shank shall be 2-3/8 inches plus or minus 1/2 inch in length, and unless otherwise specified, one inch square plus 0, minus 1/8 inch."

Page 8, paragraph 3.12.1, lines 2 and 3: Delete "not less than 52 nor more than 58" and substitute: "not less than 49 nor more than 54".

Pages 9 and 10, paragraph 3.14.1: Delete and substitute:

3.14.1 *Hardness.* When tested as specified in 4.4.1, the alloy steel punch shall show a hardness value of Rockwell C50 to C54 on the punch end and Rockwell C40 to C43 on the striking end.

Page 10, table IX, columns 9 and 10, third item: Delete "3/4" and "1", and substitute

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:40Z
Check the source to verify that this is the current version before use.

"5/8" and "7/8" respectively, as the minimum and maximum dimensions of the eye size for the 1/2-inch nominal size punch.

Page 12, paragraph 3.15, sixth line: Delete the letter "A" and substitute "R".

Page 12, paragraph 3.15.1, second sentence: Delete and substitute: "The square shank shall be 2-3/8 inches plus or minus 1/2 inch in length and, unless otherwise specified, 1-inch square plus 0, minus 1/8 inch."

Paragraphs 4 through 4.3: Delete and substitute:

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 Sampling for inspection and acceptance. Sampling for inspection and acceptance shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated herein.

4.2.1 *Inspection of materials and components.* In accordance with 4.1 above, the supplier is responsible for insuring that materials and components used were manufactured, tested, and inspected in accordance with the requirements of referenced subsidiary specifications and standards to the extent specified herein, or, if none, in accordance with this specification.

4.2.2 *Testing of the intermediate item.* Testing shall be performed on each sample unit of type I, chisel; type V, hardy; and type VII punch, prior to finishing or the application of coating, to determine compliance with the Rockwell hardness requirements of 3.8.2, 3.12.1, and 3.14.1, respectively. A minimum of three determinations shall be made on each tool and no individual reading may exceed the specified requirement. The inspection level shall be S-3 with an acceptable quality level (AQL) of 1.5 defects, expressed in terms of defects per hundred units.

4.2.3 *Inspection of the end item.*

4.2.3.1 *Examination of the end item.* Examination of the tool, such as chisel, flatter, fuller, set hammer, hardy, bolt heading tool, punch, or swage, as applicable, shall be in accordance with the classification of defects as set forth below. The lot size shall be expressed in units of one type, class and size of tool for the purpose of determining the sample size in accordance with MIL-STD-105. The sample unit shall be one completely fabricated tool. The inspection level shall be level II with an AQL of 2.5 for major defects and an AQL of 6.5 defects, expressed in terms of defects per hundred units.

Examine	Defect	Classification	
		Major	Minor
Design	Not type specified	X	
	Not similar to referenced figure	X	
Finish	Type of finish not as specified (see 3.6)	X	
	Indication of rust		X
	Handles not finished as required		X
Construction and Workmanship	Malformed, split, fractured, or otherwise impaired	X	
	Sharp burr or sliver on surfaces to be handled	X	
	Not free from sharp corners or rough edges	X	
	Striking faces not chamfered or slightly rounded		X
	Eyes not of size or shape as specified		X
	Handles not straight-grained or free from imperfections (see 3.4)	X	
Marking	Missing, incomplete, not legible		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:40Z
Check the source to verify that this is the current version before use.

4.2.3.2 *Dimensional examination.* Inspection shall be made for compliance with dimensions specified in applicable paragraphs and tables. Any deviation therefrom shall constitute a defect. The inspection level shall be level S-3 with an AQL of 2.5 defects, expressed in terms of defects per hundred units.

4.2.3.3 *Testing of end item.* Testing shall be performed on each sample unit in accordance with section 4.4.2. The inspection level shall be S-2 with an AQL of 4.0 defects, expressed in defects per hundred units.

4.2.4 *Inspection of preparation for delivery.* Unless otherwise specified, inspection to determine compliance with the preparation for delivery requirements shall be accomplished in accordance with MIL-H-15424.

Page 15, paragraph 4.4.1. Delete and substitute:

4.4.1 *Hardness test.* The hardness test shall be in accordance with the applicable requirements of method 243.1 of Fed. Test Method Std. No. 151 and the value thus obtained shall comply with the requirements of 3.8.2, 3.12.1, and 3.14.1. Unless otherwise specified, impressions shall be taken 1/4 inch from the cutting or striking edge.

Page 15, paragraph 4.4.2.4: Delete.

Page 15, paragraph 4.5: Delete.

Pages 15 and 16, paragraphs 5.1.1, 5.1.2, and 5.2.2: Delete "MIL-P-15424" and substitute "MIL-H-15424".

Page 16, paragraph 6.1: Add the following option:

"(e) Specify the size of square shank, if different (see 3.10.1 and 3.15.1)."

Page 16: Insert paragraph 6.4 as follows:

6.4 Transportation description. Transportation description and minimum weight applicable to this commodity are:

Rail:

Blacksmiths' anvil tools.
Carload minimum weight 36,000 pounds.

Motor:

Blacksmiths' anvil tools.
Truckload minimum weight (W) 36.2 (W), subject to Rule 115, National Motor Freight Classification.

MILITARY CUSTODIANS:

Army—GL

Navy—Ships

Air Force—MOA

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:40Z
Check the source to verify that this is the current version before use.