NOT MEASUREMENT SENSITIVE
MIL-P-85856/41
7 December 1988

MILITARY SPECIFICATION SHEET

POWDER MATERIALS FOR FLAME AND PLASMA SPRAYED COATINGS, TUNGSTEN CARBIDE PLUS NICKEL ALUMINUM COMPOSITE, SELF-FLUXING ALLOY, TYPE III, COMPOSITION L

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the powder described herein shall consist of this document and the latest issue of MIL-P-85856.

Chemical Composition

Percent by Weight		Components
Min.	Max.	
48.0	52.0	Type II, Composition J, Class 2
14.0	16.0	Type I, Composition H, Class 2 - or - Type I, Composition G, Class 2
Remainder		Type I, Composition N, Class 1

Sprayed Coating Properties

Bond Strength	41.4 MPa (6000 psi) min.
Hardness	Rockwell 15N, 83 min.
Microstructure	See paragraph 4.5.4.1.2 Porosity - 15% max. Unmelted Particles - 15% max.

Deposit Efficiency and Deposition Rate

55% min for N_2/H_2 @ 15.0 lb/hr
45% min for A/H_2 @ 6.0 lb/hr

AMSC N/A FSC 3439

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:33Z
Check the source to verify that this is the current version before use.

Comparable Documents

Powder which meets the requirements specified is qualified under the following specifications.

General Electric Company	B50TF30, Class A
Pratt & Whitney Aircraft	PWA 1322

Custodians:
Air Force - 20
Navy - AS
Army - MR

Review activities:
Air Force - 99, 71
Navy - SH

Preparing activity:
Navy - AS
(Project No. 3439-0663/41)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:33Z
Check the source to verify that this is the current version before use.