MIL-P-19152A(OS)
20 December 1974
SUPERSEDING
MIL-P-19152(NOrd)
Amendment 1
26 June 1957

MILITARY SPECIFICATION

PACKINGS, HYDRAULIC, HIGH PRESSURE (FOR HYDROPNEUMATIC SYSTEMS)

This specification has been approved for use by all departments and agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers high pressure hydraulic packings used for sealing the counter-recoil plungers and the differential cylinder pistons and rods of hydropneumatic systems. All packings shall be the modified "U" type and the size called for on the applicable drawings (see 6.2).

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or requests for proposal form a part of this specification to the extent specified herein.

SPECIFICATIONS

Federal

QQ-B-613	Brass, Leaded and Non-Leaded, Flat Products Plate, Bar, Sheet and Strip
QQ-B-637	Brass, Naval, Rod, Wire, Shapes, Forgings and Flat Products
QQ-C-450	Copper-Alum Alloy, Alum Bronze Plate, Sheet, Strip and Bar Copper Alloy Numbers 606, 612, 613, 614 and 628

FSC 5330

Source: https://assist.dla.mil -- Downloaded: 202610-18T12:19Z
Check the source to verify that this is the current version before use.

QQ-S-698	Steel, Sheet and Strip, Low Carbon
QQ-S-766	Steel Plate, Sheet and Strip-Corrosion Resisting
PPP-B-566	Box, Folding, Paperboard
PPP-B-576	Box, Wood, Cleated, Veneer, Paper Overlaid
PPP-B-585	Box, Wood, Wirebound
PPP-B-591	Box, Fiberboard, Wood-Cleated
PPP-B-601	Box, Wood, Cleated-Plywood
PPP-B-621	Box, Wood, Nailed and Lock-Corner
PPP-B-636	Box, Fiberboard
PPP-B-640	Box, Fiberboard, Corrugated, Triple-Wall
PPP-B-665	Box, Fiberboard, Metal Stayed
PPP-B-676	Box, Set Up

Military

MIL-P-116	Preservation, Methods of
MIL-L-10547	Liners, Case, and Sheet, Overwrap, Water-Vaporproof or Waterproof, Flexible
MIL-L-17672	Lubricating Oil, Hydraulic and Light Turbine, Non-Corrosive

STANDARDS

Federal

FED-STD-601	Rubber: Sampling and Testing

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	Marking for Shipment and Storage

Source: https://assist.dla.mil -- Downloaded: 202640-18T12:19Z
Check the source to verify that this is the current version before use.

DRAWINGS

Naval Sea Systems Command (Code Ident 10001)

BUORD	165347 Pc. 2 (LF100134)
BUORD	165347 Pc. 3 (LF100134)
NAVORDSYSCOM	180961 Pc. 6 (DF102127)

Others

BUSANDA	N155-5330-2-5
BUSANDA	N155-5330-2-24
BUSANDA	N155-5330-2-26
BUSANDA	N155-5330-2-8
GSSO PD	5330-244-3
GSSO PD	5330-235-5

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 First article. Packing furnished under this specification shall be a product which has been tested and passed the tests specified in 4.5.1 through 4.5.4. Any change in product will necessitate retesting (see 6.3).

3.2 Material. The packing material shall conform to applicable drawings, be dense, grainless, nonporous, resilient, oil resistant, nonabrasive, shall have a low coefficient of friction and expansion, and shall be suitable for operation in contact with oil conforming to MIL-L-17672, Military Symbol 2075.

3.3 Shape and size. The shape of the packing (in cross-section) shall be the modified "U" type. The packing shall be capable of assembling without having to resort to special or complicated fixtures,

Source: https://assist.dla.mil -- Downloaded: 202640-18T12:19Z
Check the source to verify that this is the current version before use.

and shall seal against the inside and outside containing walls of metal parts of standard dimensions shown on the applicable drawings for the particular hydropneumatic system. Unless otherwise specified on the applicable drawings, the tolerance on dimensions of the height of the packing ring shall be plus 0.02 inch, minus 0.00 inch. The packings shall conform to applicable drawings listed in 2.1.

3.4 Effect on oil. The packing shall not cause the formation of sludge or the discoloration or thickening of the oil in the differential system (see 4.5.1.2).

3.5 Reaction with metals. The packing shall not cause corrosion or pitting of the metals with which it is in contact. Slight discoloration of the metals shall not be cause for rejecting the packing (see 4.5.1.3).

3.6 Adherence to metals. The packing shall not adhere or stick to the metals of the counter-recoil system with which it is in contact. The packing shall be considered as adhering or sticking to the metals if particles or pieces of the packing remain in contact with the metallic surfaces either through operation of the metallic parts in the packing or upon removal of the packing from the assembly (see 4.5.1.3).

3.7 Hardness. Packings shall show a Durometer "A" hardness of 90 ± 5 when tested as required in 4.5.1.1.

3.8 Oil absorption. The packing when in contact with oil or immersed in oil of a type used in the system, shall not show an increase in volume exceeding 7.0 percent or a volume decrease exceeding 1.0 percent. Upon exposure to oil the packing shall not break down, soften or roughen, particularly the sealing edges or lips.

3.9 Temperature requirements. The packing shall function properly throughout the range of ambient temperatures at which the hydropneumatic system may be operated or stored. The temperature requirements shall be a minimum of -20° Fahrenheit (F) and a maximum of 160° F. The packing shall also be capable of passing the cold temperature cycling test of 4.5.4.

3.10 Packing friction. Packing friction on the counter-recoil plunger and differential piston and rod of the cycling test set of 4.5.3.1 shall be a minimum consistent with proper sealing. The counter-recoil plunger

Source: https://assist.dla.mil -- Downloaded: 20260-18T12:19Z
Check the source to verify that this is the current version before use.

packing friction shall not prevent the proper return of the recoiling parts to battery within the time prescribed in the firing cycle for a particular gun or system. The packing friction shall not prevent smooth and continuous motion of the recoiling parts during their return to battery. The packing shall not alternately grab and release the counter-recoil plunger causing a jerky and uneven movement of the recoiling parts during their return to battery. Packing friction on the differential piston and rod shall not prevent the piston and rod from immediately responding to the differential pressure in the system, nor shall packing friction prevent the proper protrusion of the piston rod.

3.10.1 Heating. During operation of the system the allowable temperature of the counter-recoil plunger, due to packing friction, shall not exceed 130° F. Temperature rise of the differential piston and rod due to packing friction shall not be considered, since during operation of the system the piston and rod may not move at all or its movement may be negligibly small.

3.11 Scoring. The packing shall at no time cause scoring, scratching, or wearing away of metal from the plunger and the differential piston and rod.

3.12 Leakage. The plunger packing shall be capable of holding the air pressure in the air chamber as specified in the contract or order (see 6.2) during periods of operation, idleness, or storage of the system. The differential piston and rod packing shall be capable of holding the oil in the differential system during periods of operation, idleness, or storage of the system.

3.13 Storage. Packing when properly packaged and packed shall be capable of being stored for 5 years without showing evidence of any deterioration that would in any way impair its serviceability. Upon removal from storage the packing shall meet all the requirements as set forth herein.

3.14 Identification. Packing furnished under this specification shall not be identification marked on the packing itself. Identification shall be made by marking the packing container or by attaching a tag to individual packing rings or groups of rings. The date of manufacturing shall be shown, with type and size noted.

Source: https://assist.dla.mil -- Downloaded: 202640-18T12:19Z
Check the source to verify that this is the current version before use.

3.15 Performance. Packings furnished under this specification shall be only those products which have met stipulated requirements and have been subjected to and passed the first article tests as specified herein. The following tests comprise the parameters of performance.

a. 4.5.1 - Physical properties tests
b. 4.5.2 - Friction evaluation test
c. 4.5.3 - Five thousand cycle endurance test
d. 4.5.4 - Cold temperature cycling test.

3.16 Workmanship. Workmanship shall be of such quality as to produce a uniform product in accordance with the detailed requirements of the applicable drawings and this specification.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3 and 6.3)
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. The first article inspection of the packings shall consist of all the tests and examinations of this specification.

4.3.1 First article inspection samples. First article inspection samples shall be submitted as specified by the contracting officer or agency. The acceptable quality level (AQL) for first article inspection shall be 1.5 percent defective. If the AQL falls below 1.5 percent in any phase of the tests, the packing shall fail to qualify.

Source: https://assist.dla.mil -- Downloaded: 202640-18T12:19Z
Check the source to verify that this is the currentversion before use.

4.4 Quality conformance inspection (end item testing). The examination and tests comprising quality conformance inspection shall consist of the examination of 4.4.2, and tests 4.5.1.1, 4.5.1.2, and 4.5.1.3.

4.4.1 Sampling.

4.4.1.1 Inspection lot. A lot shall consist of finished packings of the same material, type, style, and size produced under essentially like conditions, fabricated by the same process, and produced as one continuous run or order, or part thereof, and submitted for quality conformance inspection at the same time. Presentation of lots shall be in accordance with MIL-STD-105.

4.4.1.2 Sampling for quality conformance inspection tests (see 4.5). Samples of packings, all sizes included, shall be taken from a single production lot for testing in accordance with MIL-STD-105 at Inspection Level II. The AQL shall be 1.5 percent defective.

4.4.1.3 Sampling for visual and dimensional examination (see 4.4.2). A random sample of packings shall be taken from each lot in accordance with MIL-STD-105, Inspection Level S-1. The AQL shall be 2.5 percent defective.

4.4.1.4 Examination of preparation for delivery. An examination shall be made to determine that packaging and packing requirements comply with section 5 of this specification. The inspection shall be Inspection Level S-2 and the AQL shall be 2.5 defects per hundred units in accordance with MIL-STD-105.

4.4.2 Examination for visual and dimensional defects. Each packing taken at random as specified in 4.3.1 or 4.4.1.3 as applicable, shall be examined to verify conformance to requirements of this specification. Examination shall be conducted in accordance with table I. Packings having one or more defects shall be rejected.

4.5 Test methods.

4.5.1 Physical properties tests.

4.5.1.1 Durometer hardness test. The packing shall be subjected to a hardness test to determine compliance with the requirement of 3.7. The Durometer "A" hardness shall be determined in accordance with method 3021 as specified in FED-STD-601.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:19Z
Check the source to verify that this is the current version before use.

Table I

CLASSIFICATION OF DEFECTS FOR VISUAL AND DIMENSIONAL EXAMINATION OF THE END ITEM

Categories	Defects	Inspection method
Critical	None defined	-
Major	AQL = 1.5 percent	-
101	Shape not in accordance with applicable drawings	SIE & Visual[1]
102	Dimensions of the height exceeds tolerance of plus 0.02 inch, or minus 0.00 inch	SIE

[1]SIE – Standard Inspection Equipment.

4.5.1.2 Oil absorption test. The packing shall be tested for its oil absorption properties to determine compliance with the requirements of 3.8. The water displacement method of measuring the change of volume of the packing shall be used. The packing specimen shall first be accurately weighed in air to the nearest milligram. This first weight shall be called W_1. The specimen shall then be weighed to the nearest milligram in distilled water at 25° centigrade (C) by suspending it in the water with a fine wire. The weight of the wire must be deducted from the total weight. This second weight shall be called W_2. When weighing in water care must be taken that the specimen is free from adhering air bubbles, and, if necessary, it may be first wetted by dipping into 95 percent alcohol or a 0.2 percent solution of aerosol OT in water and rinsed with distilled water. After this second weighing the specimen must be blotted dry with filter paper. The specimen shall then be completely immersed in a container of ASTM Oil No. 3 of method 6001, FED-STD-601, and allowed to remain in the oil for a period of 70 hours ± 1 hour at 150° ± 2° F. The container shall conform to 3.9.2 of method 6001, FED-STD-601. At the end of this oil immersion period the specimen shall be removed and cleaned by rapidly rinsing it with petroleum ether (boiling point 30° C to 60° C). The specimen shall then be weighed in air to the nearest milligram. This third weight shall be called W_3. The specimen shall then be weighed in water as described above. This fourth weight shall be called W_4. Percent volume change of the specimen is equal to

Source: https://assist.dla.mil -- Downloaded: 202640-18T12:19Z
Check the source to verify that this is the currentversion before use.

$$\frac{(W_3 - W_4) - (W_1 - W_2)}{(W_1 - W_2)} \times 100.$$

A positive answer represents an increase in volume of the packing.

4.5.1.3 Corrosion and adhesion tests. The packing shall be tested for the corrosion or adhesion to brass, copper, corrosion resistant steel (CRES) and steel to determine compliance with the requirements of 3.5 and 3.6. The device for conducting these tests shall be a compression device. This compression device shall consist of a base plate provided with two stud bolts on which polished plates (to 32 micro-inch finish) of brass QQ-B-613 or QQ-B-637, copper QQ-C-450, CRES Steel QQ-S-766, and mild steel QQ-S-698 are successively placed. These plates used in this device shall measure 3 by 1 by 1/8 inches. Two compression springs, which together are capable of imposing a load of 25 pounds per square inch (psi), are placed over the studs and secured by a nut on top of each stud. The nuts also serve to adjust the spring loads so as to obtain the specified load on the packing specimen. The total surface area of the packing specimen shall be one square inch. One or more strips of packing may be used to make up this area. Before running the test the test strips of brass, copper, CRES Steel, and steel shall be cleaned with reagent grade benzene. A strip of one of the above metals and a packing specimen are placed in the device and the stud nuts are adjusted so that the springs impose a load of 25 psi on the packing. The device assembly shall then be placed in an oven at 158° ± 2° F for a period of 168 hours (one week). At the end of this period the test assembly shall be removed from the oven and disassembled. The packing contact surface of the metal test plate shall be carefully examined for corrosion and pitting. A slight discoloration of the metal shall not be considered as corrosion. The packing specimens shall be considered as adhering if particles or pieces of the packing remain in contact with the metal surface. This test shall be conducted for each kind of metal noted above.

4.5.2 Friction evaluation test. The friction evaluation test shall be performed on the packings before the 5000 cycle endurance test of 4.5.3 to determine compliance with 3.10. The friction evaluation test on the differential piston and rod packing shall be as follows: The air chamber shall be charged to a pressure of 1550 psi and the amount of oil in the differential system shall be such as to bring the end of the differential piston rod flush with the outside face of the gland nut. Pressure gages shall be installed in the air chamber and the differential oil chamber. Oil shall then be bled from the differential system causing a drop in oil pressure which in turn causes the differential piston rod to move outward. When slow and continuous movement of the differential piston rod is first

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:19Z
Check the source to verify that this is the current version before use.

observed, simultaneous readings of the air and oil pressure gages shall be noted and recorded. These pressure gage readings will give information necessary for calculating the frictional load of the differential piston and rod packing. This test shall be repeated for air pressures of 1200, 900, 600, and 300 psi. The frictional load shall not exceed 1500 pounds. In each instance the end of the differential piston rod shall be flush with the outside face of the gland nut at the beginning of the test. This test is run at the lower air pressures in order to determine whether or not the differential packing possesses uniform frictional characteristics or seizure tendencies which would result in an improper relation between the air and oil pressures. In the reduced air pressure tests it shall be ascertained before each test that the oil pressure exceeds the air pressure in the 1550 to 900 psi range in order to prevent leakage of the air into the oil cylinder. The friction evaluation test on the counter-recoil plunger packing shall be as follows: With no air pressure in the air chamber and the counter-recoil plunger retracted into the air chamber the differential system shall be charged with oil to a pressure of 2000 psi in order to properly expand the counter-recoil plunger packing. The differential piston and rod will be bottomed at the beginning of this test and the subsequent positions of the rod will have no significance in this test. Before the test is run it should be ascertained that the differential packing is capable of holding the 2000 psi oil pressure. The 2000 psi oil pressure shall be maintained throughout the test in order to keep the counter-recoil packing properly expanded during the test. The air chamber is now slowly charged with air so as to gradually build up a pressure behind the counter-recoil plunger. When the plunger starts to move a reading of the air pressure gage shall be noted and recorded. This air pressure gage reading will give information necessary for calculating the frictional load of the counter-recoil plunger packing. This load shall not exceed 1200 pounds.

4.5.3 Five thousand cycle endurance test. First article test samples shall be assembled in the test set of 4.5.3.1 on the counter-recoil plunger and the differential piston and rod. An oil pressure of 3000 psi, using oil, MIL-L-17672, Military Symbol 2075, shall be applied in order to set the packing rings. After setting the packing the air chamber shall be charged to a pressure of 1550 psi. The amount of oil in the differential system shall be such as to bring the end of the differential piston rod flush with the outside face of the gland nut. The counter-recoil plunger shall then be cycled 5000 times at the rate of 10 cycles per minute on a 12 to 14 inch stroke of the plunger. Air leakage shall be recorded at 10 minute intervals and the protrusion of the differential piston rod measured every 100 cycles. During the cycling test, the maximum acceptable outward movement of the differential piston rod shall be an average of 0.002 inch per cycle measured every 100 cycles. The counter-recoil plunger packing shall not permit oil leakage to exceed 1 drop per 10 cycles during

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:19Z
Check the source to verify that this is the current version before use.

the test. Temperature readings of the counter-recoil plunger shall be taken and recorded at regular intervals. The temperature of the counter-recoil plunger, due to packing friction, shall not exceed 130° F.

4.5.3.1 Cycling test set. The cycling test set consists essentially of a stripped 5-inch, 38-caliber housing, but containing all of the components of the counter-recoil system. Hydraulic equipment is provided on the test stand by which the counter-recoil plunger is cycled so as to simulate the action of actual gun fire. A cycling counter, suitable gages, and load measuring devices are provided to obtain the required data.

4.5.4 Cold temperature cycling test. A suitable cold temperature test box shall be constructed around the housings in the vicinity of the enclosure containing the counter-recoil plunger packing and the differential piston and rod packings. The box shall be so constructed and located that it will be capable of holding sufficient quantities of dry ice against the packing enclosures. Provision shall be made for determining the temperature of the packing enclosures at all times. The air chamber shall be charged to a pressure of 1550 psi. The amount of oil in the differential system shall be such as to bring the end of the differential piston rod flush with the outside face of the gland nut. Dry ice shall then be placed in the temperature boxes and immediately micrometer readings of the protrusions of the differential piston rod and temperature readings of the packing enclosures shall be taken and recorded. These micrometer and temperature readings shall be taken at 15 minute intervals for a period of time that is required to bring the temperature of the packing enclosures down to -20° F as specified in 3.9. It should be noted that if the packings do not contract and leak there will be no protrusion of the differential piston rod. If the packing has not leaked excessively the counter-recoil plunger shall be cycled as described in 4.5.3 for 100 cycles while maintaining the cold condition of the packing enclosures. Air and oil pressure readings shall be taken and recorded in order to determine the leakage behavior of the packings. The packing enclosures shall now be allowed to return to room temperature. If necessary the air and oil chambers shall be recharged to the initial condition of the test. The counter-recoil plunger shall now be cycled as described in 4.5.3 for 200 cycles. If the packings have leaked or shown tendencies to fail under the cold tests, the additional 200 cycles at room temperature will serve to determine the recovery characteristics of the packings.

Source: https://assist.dla.mil -- Downloaded: 202610-18T12:19Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A. Unless otherwise specified, a nesting of five packings of the same size shall be packaged in accordance with method IC-1 or IC-3 of MIL-P-116.

5.1.2 Level C. Packaging shall be sufficient to afford physical protection against damage during shipment from the supply source to the first receiving activity for immediate use. This level may conform to the supplier's commercial practice when such meets the requirement of this level.

5.2 Intermediate packaging.

5.2.1 Level A. When specified, packages shall be further packaged in quantities not to exceed 10 pounds, in paperboard or fiberboard boxes conforming to PPP-B-566, PPP-B-636, PPP-B-665, or PPP-B-676.

5.2.2 Level C. Unless otherwise specified, intermediate packaging will not be required.

5.3 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.3.1 Level A. Packings, packaged as specified, shall be packed in containers conforming to PPP-B-576 (class 2), PPP-B-585 (class 2 or 3), PPP-B-591 (class II), PPP-B-601 (overseas type), PPP-B-621 (class 2), PPP-B-636 (weather-resistant class), or PPP-B-640 (class 2). Shipping containers shall be closed, strapped, or banded in accordance with the applicable box specification. Gross weight of wood, wood-cleated, and triple-wall boxes shall not exceed 200 pounds; fiberboard boxes shall not exceed the weight limitations of box specification. Containers shall be provided with a case liner conforming to MIL-L-10547 and shall be sealed in accordance with the appendix thereto. The case liner will not be required when the unit, intermediate or exterior container is weather-resistant or class 2 or 3 fiberboard.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:19Z
Check the source to verify that this is the current version before use.

5.3.2 Level B. Packings, packaged as specified, shall be packed for shipment in containers conforming to those specified for level A, except that the containers shall be of domestic grade, class, type, or style where applicable. Box closure and strapping shall be in accordance with the applicable container specification or appendix thereto.

5.3.3 Level C. Packings, packaged as specified, shall be packed in a manner to insure carrier acceptance and safe delivery at destinations. Containers shall conform to the rules and regulations applicable to the mode of transportation.

5.4 Marking. In addition to any special marking(s) specified, marking for shipment shall be in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The packings covered by this specification are for use in the counter-recoil systems of gun mounts, hydropneumatic systems of missiles, aircraft components, rockets, and torpedoes.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this specification

b. Applicable lists of drawings and standards (see 2.1)

c. Air pressure in counter-recoil system air chamber or component system (see 3.12)

d. Where lot acceptance tests will be performed if different from 4.1

e. Selection of applicable levels of packaging and packing (see 5.1, 5.2, and 5.3).

6.2.1 Contracts or orders should specify the following provisions for first article inspection.

6.2.1.1 Whether first article inspection is required. When a supplier is in continuous production from contract to contract, consideration should be given to waive the first article inspection. If first article inspection is required, indicate:

Source: https://assist.dla.mil -- Downloaded: 202610-18T12:19Z
Check the source to verify that this is the current version before use.

a. Where the first article inspection is to be conducted (at the supplier's plant or at a Government plant).

b. That approval of first article samples or the waiving of the first article inspection shall not relieve the supplier of his obligation to fulfill all other requirements of this specification and contract.

Custodian:
Navy - OS

Preparing activity:
Navy - OS
(Project No. 5330-N046)

Source: https://assist.dla.mil -- Downloaded: 202610-18T12:19Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE: MIL-P-19152A(OS), Packings, Hydraulic, High Pressure (For Hydropneumatic Systems)

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO (If "Yes", in what way?)

4. REMARKS

SUBMITTED BY (Printed or typed name and address - Optional)

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426

REPLACES EDITION OF 1 JAN 68 WHICH MAY BE USED

S/N 0102-314-1802

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T12:19Z
Check the source to verify that this is the current version before use.