METRIC

DOD-P-24631/2A(SH)
16 October 1987
SUPERSEDING
DOD-P-24631/2(SH)
13 April 1984

MILITARY SPECIFICATION SHEET

PAINT, EPOXY, DARK GREY, NAVY FORMULA 185, TYPE II (METRIC)

This specification is approved for use within the Naval Sea Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the paint described herein shall consist of this specification and the latest issue of DOD-P-24631(SH).

Formula: This formula covers dark grey epoxy paint designated Navy formula 185 for exterior use. The paint shall consist of the ingredients specified in the quantities specified.

AMSC N/A FSC 8010

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:34Z
Check the source to verify that this is the current version before use.

TABLE I. Navy formula 185 - component A.

	Component A	Pounds	Kilograms	Gallons 1/	Liters 1/
Curing agent	Scotch Weld 2216A (clear amber), 3M Company	1398.2	634.2	170.97	647.1
Carbon black	Raven 1255 beads, Columbian Carbon	13.7	6.2	0.91	3.4
Titanium dioxide	ASTM D 476, type III or IV	33.5	15.2	1.00	3.8
Magnesium silicate	MIL-P-15173, type A	726.4	329.5	32.24	122.0
Aromatic solvent	HI SOL 10, Ashland	127.1	57.7	17.41	65.9
n-Butyl alcohol	ASTM D 304	1052.7	477.5	155.55	588.8
Ethylene glycol mono ethyl ether	TT-E-781	542.7	246.2	69.85	264.4
Ethylene glycol mono butyl ether	TT-E-776	90.7	41.1	12.05	45.6
Thickener	Bentone 38, NL Ind.	27.0	12.2	1.90	7.2
Thickener activator	Propylene carbonate, Jefferson Chemical	9.5	4.3	0.96	3.6
Dispersant	Tenlo 70, Diamond Shamrock	1.9	0.9	.23	0.9
		4023.4	1825.0	463.07	1752.7

1/ Provided for guidance only - actual values are dependent on variation in raw materials.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:34Z
Check the source to verify that this is the current version before use.

TABLE II. Navy formula 185 - component B.

	Component B	Pounds	Kilograms	Gallons 1/	Liters 1/
Epoxy resin	Scotch Weld 2216B Clear, 3M Company	1117.0	506.7	116.39	440.5
Carbon black	Raven 1255 Beads, Columbian Carbon	17.0	7.7	1.13	4.3
Titanium dioxide	ASTM D 476, type III or IV	41.5	18.8	1.24	4.7
Magnesium silicate	MIL-P-15173, type A	899.7	408.1	39.93	151.1
Aromatic solvent	HI SOL 10, Ashland	157.4	71.4	21.56	81.6
n-Butyl acetate	TT-B-838	1303.6	591.3	176.91	669.6
Ethylene glycol mono ethyl ether	TT-E-781	672.1	304.9	86.51	327.4
Ethylene glycol mono butyl ether	TT-E-776	112.3	50.9	14.92	56.5
Thickener	Bentone 38, NL Ind.	33.5	15.2	2.36	8.9
Thickener activator	Propylene Carbonate, Jefferson Chemical	11.8	5.4	1.19	4.5
Dispersant	Tenlo 70, Diamond Shamrock	2.4	1.1	0.29	1.1
		4368.3	1981.5	462.43	1750.2

1/ Provided for guidance only - actual values are dependent on variation in raw materials.

NOTES:

1. The curing agent shall be Scotch Weld 2216A (transparent) available from 3M Company, 3M Center, 2501 Hudson Road, St. Paul, MN, or equivalent (see figure 1 of this specification sheet).
2. The carbon black shall be "Raven 1255 beads" available from Columbian Carbon, Akron, OH, or equivalent.
3. The solvent shall be any 97-99 percent aromatic with a flash point of 100-110 degrees Fahrenheit (°F) (38-43 degrees Celsius (°C)).
4. The thickener shall be "Bentone 38" available from N.L. Industries, Inc., Hightstown, NJ, or equivalent.
5. The thickener activator shall be "propylene carbonate" available from Jefferson Chemical, Shaker Heights, OH, or equivalent.
6. The dispersant shall be "Tenlo 70" available from Diamond Shamrock, Morristown, NJ, or equivalent.
7. The epoxy resin shall be Scotch Weld 2216B (clear amber) available from 3M Company, 3M Center, 2501 Hudson Road, St. Paul, MN, or equivalent (see figure 2 of this specification sheet).
8. The magnesium silicate shall be used in accordance with MIL-P-15173, type A and shall be asbestos-free.

Use of alternative ingredients in this formula shall have prior approval by the Naval Sea Systems Command. Approval will be based on review of data showing equivalent physical and chemical characteristics to the specified ingredient. It will be necessary to demonstrate that the paint compound made using the alternative ingredient will conform to all requirements of this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:34Z
Check the source to verify that this is the current version before use.

TABLE III. Quantitative requirements.

Requirements	Component A		Component B		Mixed component	
	Min	Max	Min	Max	Min	Max
Pigment:						
Percent by mass of paint	17.2	21.2	19.9	23.9		
Percent by volume of paint	5.6	9.6	7.2	11.2		
Volatiles:						
Percent by mass of paint	43.3	47.3	49.7	53.7		
Percent by volume of paint	53.2	57.2	64.3	68.3		
Nonvolatiles:						
Percent by mass of paint	33.5	37.5	24.4	28.4		
Percent by volume of paint	35.2	39.2	22.5	26.5		
Consistency, Krebs units					60.0	----
Mass per unit volume:						
lbs/gallon	8.44	8.94	9.20	9.70	8.82	9.32
Kg/L	1.011	1.071	1.102	1.162	1.057	1.116
Fineness of grind (Hegman)					6.0	----
Flash point, Pensky-Martens						
°C					27.0	----
°F					80.0	----
Wet reflectance color (Rw), percent					1.74	2.06
Set-to-touch time:						
hours at 23°C (73°F)					6.0	8.0
Dry-hard hours at 23°C (73°F)					---	24.0
Titanium dioxide, percent of pigment	3.5	----	3.5	----		
Pot life, hours at 23°C (73°F)					6.0	----
Gloss, 16°C (60°F) specular, percent					---	10.0
Contrast ratio					0.9	

Preparing activity:
Navy - SH
(Project 8010-N313)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:34Z
Check the source to verify that this is the current version before use.




FIGURE 1. Infrared spectrogram of Scotch Weld 2216A (aliphatic amine).

SH 12141

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:34Z
Check the source to verify that this is the current version before use.




FIGURE 2. Infrared spectrogram of Scotch Weld 2216B (epoxy resin).

SH 12142

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:34Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY

COMMANDER
NAVAL SEA SYSTEMS COMMAND (SEA 55Z3)
DEPARTMENT OF THE NAVY
WASHINGTON, DC 20362-5101

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12503 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

COMMANDER
NAVAL SEA SYSTEMS COMMAND (SEA 55Z3)
DEPARTMENT OF THE NAVY
WASHINGTON, DC 20362-5101

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T23:34Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
DOD-P-24631/2A(SH)	PAINT, EPOXY, DARK GREY, NAVY FORMULA 185, TYPE II (METRIC)

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*:

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

Source: https://assist.dla.mil -- Downloaded: 20260-19T23:34Z
Check the source to verify that this is the current version before use.